

Symmetry of boundary conditions of the Dirac equation for electrons in carbon nanotubes

Edward McCann and Vladimir I. Fal'ko

Department of Physics, Lancaster University, Lancaster, LA1 4YB, United Kingdom

We consider the effective mass model of spinless electrons in single wall carbon nanotubes that is equivalent to the Dirac equation for massless fermions. Within this framework we derive all possible energy independent hard wall boundary conditions that are applicable to metallic tubes. The boundary conditions are classified in terms of their symmetry properties and we demonstrate that the use of different boundary conditions will result in varying degrees of valley degeneracy breaking of the single particle energy spectrum.

INTRODUCTION

Carbon nanotubes are the subject of intense research, motivated by the desire to use their unique physical and electronic properties in the development of nanoscale electrical devices [1, 2]. The electronic properties of nanotubes follow from the band structure of graphene – a two-dimensional (2D) sheet of graphite – which is a semimetal, having a vanishing energy gap at the six corners, K -points, of the hexagonal first Brillouin zone. A single-wall nanotube may be thought of as a graphene sheet rolled up to form a nanometre-diameter cylinder. Periodicity around the circumference results in quantized transverse wavevectors leading to metallic or semiconducting behaviour depending on whether the K -point wavevector K is an allowed wavevector.

While the energy spectrum of an infinitely long tube will be continuous, a finite tube should possess discrete energy levels corresponding to standing waves typical of a confined quantum particle. Evidence of discrete levels was seen in transport measurements [3, 4] a few years ago, followed by the direct observation of sinusoidal standing wave patterns by scanning tunneling microscopy [5, 6]. The measured wavelength of the standing waves 0.75 nm, about three times larger than the lattice constant $a = 0.25$ nm, corresponded to wavevectors near the K -point K . More recently, Coulomb blockade measurements on carbon nanotube quantum dots [7, 8, 9] have found evidence for fourfold periodicity of the spectra that is in agreement with expectations based on spin and K -point degeneracy, although the experiments appeared to show varying degrees of degeneracy breaking. A number of authors [10, 11, 12, 13, 14] have modelled finite-length nanotubes in order to describe the atomic scale variation of standing waves patterns and the opening of an energy gap displaying an oscillating dependence on the tube length. Rather than concentrating on one particular model of a boundary, we aim to describe all possible energy independent hard wall boundary conditions for metallic single wall nanotubes. We will classify the boundary conditions in terms of their symmetry properties and show how different boundary conditions produce varying degrees of K -point degeneracy breaking.

In the scanning tunneling microscopy measurements of Ref. 6 an additional slow spatial modulation of the standing waves was observed. It was interpreted as being a beating envelope function with wavevector q , $\hbar q = \hbar K$ resulting from the interference of left and right moving waves with slightly different total wavevectors $K \pm q$. Theoretically, the effective mass model [15, 16, 17, 18] provides a reliable analytical description of the electronic structure near the K -point where the total wavevector is $k = K + q$ and the dispersion relation is linear $E = \hbar v q$, v is the Fermi velocity and $s = \pm 1$ for the conduction and valence band, respectively. For spinless electrons, the envelope wavefunction $\psi(q; r)$ has four components corresponding to two inequivalent atomic sites in the hexagonal graphite lattice (A and B) and to two inequivalent K -points in the hexagonal first Brillouin zone. The resulting eigenvalue equation for ψ is the massless Dirac equation,

$$\begin{aligned} \text{iv} \cdot \mathbf{r} \psi &= E \psi; \quad \psi = \begin{pmatrix} 0 \\ 0 \end{pmatrix}; \quad (1) \\ &= e^{i z/2} \begin{pmatrix} x \\ y \end{pmatrix} e^{-i z/2} \end{aligned}$$

where the role of spin ("pseudo-spin") is assumed by the relative amplitudes on the A and B atomic sites: ψ is a vector in the $(x; y)$ plane rotated by the chiral angle of the tube. Also, $v = \hbar/3a$ is the Fermi velocity, a is the lattice constant of graphite and \hbar is the nearest neighbour transfer integral.

In this paper we consider the effective boundary conditions for the envelope function in a finite size carbon nanotube. Since the effective mass model for ψ corresponds to the Dirac equation, we begin by deriving all possible energy independent hard wall boundary conditions for the Dirac equation. We write them in terms of a small number of arbitrary parameters, mixing angles, that describe mixing between boundary conditions with different discrete symmetries. Then, in order to illustrate the meaning of the general boundary conditions, we evaluate the resulting energy level spectra for non-interacting electrons in finite-length metallic nanotubes and the corresponding standing wave envelope functions. To anticipate a little, we find that energy independent hard wall

boundary conditions for the Dirac equation may be expressed in general terms as

$$M = M^\dagger; \quad M^2 = 1; \quad n_B : M g = 0; \quad (2)$$

where M is an Hermitian, unitary 4×4 matrix $M^2 = 1$ with the constraint that it anticommutes with the operator $n_B :$, proportional to the component of the current operator normal to the interface, n_B is the unit vector normal to the interface. As explained in the Appendix, we find four possible linear combinations of matrices satisfying these constraints on M , which, assuming n_B is a vector confined to the $(x;y)$ plane, may be written in terms of a small number of arbitrary parameters:

$$M_1 = \cos(\theta_1 : n_1) + \sin(\theta_2 : n_2); \quad (3)$$

$$M_2 = \cos(\theta_1 : I) + \sin(\theta_2 : n_B); \quad (4)$$

$$M_3 = \cos(\theta_2 : n_B) + \sin(\theta_1 : n_1); \quad (5)$$

$$M_4 = \cos(\theta_1 : I) + \sin(\theta_2 : n_2); \quad (6)$$

where the angles θ_1, θ_2 and θ_3 are arbitrary, n_1 and n_2 are three-dimensional space-like vectors satisfying the constraints $n_1 \cdot n_B = n_2 \cdot n_B = n_1 \cdot n_2 = 0$, and θ_1 and θ_2 are two-dimensional (confined to the $(x;y)$ plane) space-like vectors satisfying the constraint $\theta_1 : \theta_2 = 0$. Here we have adopted a matrix direct product notation to highlight the separate K -point space and AB space structure, using the notation $f_{x;y;z}; I g$ for 2×2 Pauli matrices and the unit matrix that operate within a block (AB space) and $f_{x;y;z}; I g$ for 2×2 Pauli matrices and the unit matrix that operate in K -point space. For example, the operator M may be written as a direct product $M = \theta_z$. Note that the boundary conditions of the Hadron bag model [19], in which elementary particles are confined by a scalar (mass) term at the boundary, are described by $M = \theta_z : n_B$. Berry and Mondragon [20] considered "neutrino billiards" with a two component Dirac equation confined by a term proportional to θ_z , corresponding to $M = I \theta_1$ or $M = \theta_z \theta_2$ with either n_1 or n_2 lying in the $(x;y)$ plane.

There are two non-equivalent K -points that we label as K and K' . The Dirac equation is diagonal in K -point space, so that, in the absence of boundary conditions, there are two right moving (R_K) and ($R_{K'}$) and two left moving (L_K) and ($L_{K'}$) plane wave solutions near the Fermi surface of a metallic tube. The solutions R_K and $L_{K'}$ are eigenvectors of the pseudo-spin component along the tube axis n_B with eigenvalue $+s$, whereas the solutions $R_{K'}$ and L_K have eigenvalue $-s$, where $s = \pm 1$ for the conduction and valence band, respectively. Also, the solutions R_K and $L_{K'}$ are eigenvectors of pseudo-helicity $i \sigma \cdot \hat{r} = \hat{r} \cdot \hat{p}$ with eigenvalue $+s$, whereas the solutions $R_{K'}$ and L_K have eigenvalue $-s$. There are different ways of combining the right and left moving waves in order to create standing waves. The first possibility

is that waves at the same K -point combine, namely $R_K^{(R)}$ and $L_{K'}^{(L)}$ form a standing wave with helicity eigenvalue $+s$, and $R_{K'}^{(R)}$ and $L_K^{(L)}$ form a standing wave with helicity eigenvalue $-s$. This situation is realised by the matrix M_1 , Eq.(3), because it is diagonal in K -point space. A second possibility is that waves from opposite K -points combine, namely $R_K^{(R)}$ and $L_K^{(L)}$ form a standing wave with spin component eigenvalue $+s$, and $R_{K'}^{(R)}$ and $L_{K'}^{(L)}$ form a standing wave with spin component eigenvalue $-s$. This situation is realised by the matrix M_2 , Eq.(4), because it is off-diagonal in K -point space. A third possibility is a combination of the previous two, with waves scattered back at the boundary into a mixture of both of the K -points. This situation is realised by the matrices M_3 , Eq.(5), and M_4 , Eq.(6), because they have both diagonal and off-diagonal in K -point space parts.

EFFECTIVE MASS MODEL

In the effective mass model of two-dimensional graphite [15], the total wavefunction ψ_{tot} is written as a linear combination of four components $m = f1;2;3;4g$ corresponding to two K -points $K = f1;2g$ and s -type atomic orbitals $\phi_j(r - R_j)$ on two non-equivalent atomic sites $j = fA;Bg$ in the unit cell,

$$\psi_{tot}(r) = \sum_{m=1}^4 \sum_n X_n^{(m)} \psi_m^{(0)}(r) G_m(r) \sigma + \dots \psi_m(r); \quad (7)$$

where

$$\psi_m^{(0)}(r) = \frac{1}{\sqrt{N}} \sum_{R_j} X_n^{(m)} e^{iK \cdot R_j} \phi_j(r - R_j); \quad (8)$$

$$G_m(r) = \frac{1}{\sqrt{N}} \sum_{R_j} X_n^{(m)} e^{iK \cdot R_j} \phi_j(r - R_j) \phi_j(r - R_j); \quad (9)$$

are Bloch type functions constructed from the atomic orbitals, R_j is the position of an atom in real space and the summation is over the number of unit cells $N \gg 1$. The functions $\psi_m(r)$ are components of the envelope function $\psi(r)$. Substituting this expression for ψ_{tot} into the Schrodinger equation and integrating with respect to fast degrees of freedom that vary on the scale of the unit cell leads to the Dirac equation Eq.(2) for the envelope function where the K -points are taken as $K = (\pm 4/3a; 0)$ and the components of ψ are written in the order K_A, K_B, K'_B, K'_A . The appearance of the chiral angle of the tube in the Dirac equation shows that the axes of the $(x;y)$ coordinate system have been rotated to be transverse and parallel to the tube axis. Applying periodic boundary conditions to the wavefunction ψ_{tot} , Eq.(7), in the direction transverse to the nanotube axis produces a

condition for the envelope function that leads to metallic or semiconducting behaviour depending on whether the transverse component of wavevector q is allowed to be zero [16, 17].

BOUNDARY CONDITIONS FOR THE EFFECTIVE MASS MODEL

In order to obtain hard wall boundary conditions for the Dirac equation, we place an additional confinement potential at the boundary $r = r_B$,

$$h \nabla_{\perp} \psi + c \tilde{M} \psi(r = r_B) = E \psi; \quad (10)$$

where c is a real constant and \tilde{M} is an arbitrary 4×4 Hermitian, unitary matrix, $\tilde{M}^2 = 1$. The orientation of the boundary is defined by a unit vector n_B normal to it, and we assume that the wavefunction is zero outside the confined region, but non-zero inside it. Then, we integrate across an infinitesimal width of the boundary, giving

$$in_B : \psi = c \tilde{M} \psi; \quad (11)$$

Substituting this equation back into itself, we find the requirements that $\tilde{M}^2 = 1$ (thus we set $c = 1$) and $n_B : \tilde{M} = 0$. The boundary condition can be written as $\psi = M \psi$ where $M = in_B : \tilde{M}$, $M^2 = 1$ and $fn_B : M = 0$, giving the result quoted in the introduction Eq.(2).

If, in the graphite coordinate system, we define the normal to the boundary as $n_B = (\sin \theta; \cos \theta; 0)$, where θ is the chiral angle of the tube, then we may choose two mutually orthogonal 3D vectors as $n_1 = (\cos \theta \sin \theta; \sin \theta \sin \theta; \cos \theta)$ and $n_2 = (\cos \theta \cos \theta; \sin \theta \cos \theta; \sin \theta)$, and two additional orthogonal 2D vectors as $\hat{e}_1 = (\cos \theta; \sin \theta; 0)$ and $\hat{e}_2 = (-\sin \theta; \cos \theta; 0)$. This introduces two new mixing angles, ϕ and ψ : the arbitrary parameters contained within the boundary conditions describe the amount of mixing between different discrete symmetries. First, we note that the pseudo-spin of a 2D graphite sheet does not transform in the same way as the spin of relativistic fermions, because certain transformations result in a swapping of the orientation of A and B atoms. This additional operation is described by a "pseudo-spin- $\frac{1}{2}$ " operator $\sigma_z = \sigma_x \sigma_z$ that corresponds to a reflection in the $(x; y)$ plane of relativistic fermions. For example, an active rotation of the 2D graphite sheet anticlockwise by $\phi = 3$ about the perpendicular z axis, $\psi(0) = C_6 \psi(r)$, is described by $C_6 = \sigma_z R(\phi = 3) = \sigma_x \exp(i 2 \phi \sigma_z)$ where $R(\phi) = I \exp(i \phi \sigma_z)$ is a continuous rotation operator.

Table 1 shows a summary of the discrete symmetries of the boundary conditions in terms of the orientation

of the vectors n_1, n_2, \hat{e}_1 and \hat{e}_2 . In addition to σ_z we consider parity $P = \sigma_x I$, corresponding to a rotation by π about the z axis ($x \rightarrow -x$ and $y \rightarrow -y$), and charge conjugation (C) and time reversal symmetry (T) that involve the complex conjugation operator combined with $C = i \sigma_y \sigma_z$ and $T = I \sigma_y$, respectively. The angles ϕ and ψ mix terms with different symmetry with respect to σ_z : $\phi = 0$ and $\psi = 0$ correspond to evenness with respect to σ_z whereas $\phi = \pi/2$ and $\psi = \pi/2$ correspond to oddness. Since spin and/or helicity label different states at the same energy, values of ϕ and ψ not equal to multiples of $\pi/2$ will lead to broken degeneracy. The angles ϕ, ψ , and mix different symmetries with respect to combinations of P, C and σ_z .

| M | | | σ_z | P | C | T |
|---------------|---------|-------------------------|---------------------|----|----|----|
| I | $n_1 :$ | $n_1 = n_{(x;y)}$ | $u = \frac{\pi}{2}$ | 1 | 1 | 1 |
| | | $n_1 = n_z$ | $u = 0$ | +1 | +1 | +1 |
| σ_z | $n_2 :$ | $n_2 = n_{(x;y)}$ | $u = 0$ | +1 | 1 | 1 |
| | | $n_2 = n_z$ | $u = \frac{\pi}{2}$ | 1 | 1 | 1 |
| $\hat{e}_1 :$ | I | $\hat{e}_1 = \hat{e}_1$ | $u = 0$ | +1 | +1 | +1 |
| | | $\hat{e}_1 = \hat{e}_2$ | $u = \frac{\pi}{2}$ | 1 | 1 | 1 |
| $\hat{e}_2 :$ | $n_B :$ | $\hat{e}_2 = \hat{e}_2$ | $u = \frac{\pi}{2}$ | 1 | +1 | 1 |
| | | $\hat{e}_2 = \hat{e}_1$ | $u = 0$ | +1 | 1 | +1 |

Discrete symmetries of the boundary conditions

SINGLE PARTICLE ENERGY SPECTRUM

In order to illustrate the meaning of the general boundary conditions, we calculate the form of non-interacting single particle standing waves created by the boundary conditions and the corresponding energy spectrum. For simplicity, we will consider only metallic nanotubes with arbitrary chiral angle θ . We suppose that the x axis is perpendicular to the tube axis and we consider only the zero momentum transverse mode so that $\mathbf{k} = j \frac{2\pi}{C_h} \hat{e}_1$ where C_h is the circumference. The Dirac equation is diagonal in K -point space, so that, in the absence of boundary conditions, there are two right moving ($\psi_K^{(R)}$ and $\psi_K^{(L)}$) and two left moving ($\psi_K^{(L)}$ and $\psi_K^{(R)}$) plane wave solutions:

$$\begin{aligned} \psi_K^{(R)} &= A e^{i q y} \begin{pmatrix} B \\ B \\ B \\ 0 \end{pmatrix} e^{i \phi} \begin{pmatrix} C \\ C \\ C \\ A \end{pmatrix}; \quad \psi_K^{(L)} = B e^{-i q y} \begin{pmatrix} B \\ B \\ B \\ 0 \end{pmatrix} e^{i \psi} \begin{pmatrix} C \\ C \\ C \\ A \end{pmatrix}; \\ \psi_K^{(R)} &= C e^{i q y} \begin{pmatrix} B \\ B \\ B \\ 1 \end{pmatrix} e^{i \phi} \begin{pmatrix} C \\ C \\ C \\ A \end{pmatrix}; \quad \psi_K^{(L)} = D e^{-i q y} \begin{pmatrix} B \\ B \\ B \\ 1 \end{pmatrix} e^{i \psi} \begin{pmatrix} C \\ C \\ C \\ A \end{pmatrix}; \end{aligned}$$

where A, B, C and D are arbitrary constants, q is the wavevector along the tube and we consider $q \neq 0$ and $E = \text{svq}$, $s = \pm 1$. The solutions $\begin{pmatrix} R \\ K \end{pmatrix}$ and $\begin{pmatrix} L \\ K \end{pmatrix}$ are eigenvectors of pseudo-spin component $\hat{\sigma}_y = I \begin{pmatrix} e^{iz/2} & 0 \\ 0 & e^{-iz/2} \end{pmatrix}$ with eigenvalue $+s$, whereas the solutions $\begin{pmatrix} R \\ F \end{pmatrix}$ and $\begin{pmatrix} L \\ K \end{pmatrix}$ have eigenvalue $-s$. Also, the solutions $\begin{pmatrix} R \\ K \end{pmatrix}$ and $\begin{pmatrix} L \\ K \end{pmatrix}$ are eigenvectors of pseudo-helicity $\hat{h} = \hat{\sigma}_y \hat{\sigma}_x = \hat{\sigma}_x I \begin{pmatrix} e^{iz/2} & 0 \\ 0 & e^{-iz/2} \end{pmatrix}$ with eigenvalue $+s$, whereas the solutions $\begin{pmatrix} R \\ F \end{pmatrix}$ and $\begin{pmatrix} L \\ F \end{pmatrix}$ have eigenvalue $-s$. In the following we consider each of the four linear combinations M_1 to M_4 separately, and we consider a system with the same type of boundary condition on the right (at $y = +L=2$) and on the left (at $y = -L=2$). We introduce an index $u = \text{RF;LG} = 1$ to label the right and left hand side so that the normal to the boundary, defined with respect to the graphite coordinate system, is $n_B = u(\sin \theta; \cos \theta; 0)$, and we take into account the possibility of different mixing angles, $\theta_R, \theta_L, \theta_u$ and θ_v , and vectors $n_1 = (u \cos \theta \sin \theta_u; u \sin \theta \sin \theta_u; \cos \theta_u)$, $n_2 = (u \cos \theta \cos \theta_u; u \sin \theta \cos \theta_u; \sin \theta_u)$, $n_1 \cdot n_2 = (\cos \theta_u; \sin \theta_u; 0)$ and $n_2 \cdot n_1 = (-\sin \theta_u; \cos \theta_u; 0)$.

M 1: diagonal boundary conditions

With the above definitions of the mixing angles, the boundary condition M_1 produces the following relations between the components of the wavefunction at the interface:

$$\begin{aligned} u \sin(\theta_u + \theta_v) e^{i\theta_u} A_K &= [1 + \cos(\theta_u + \theta_v)] B_K = 0; \\ u \sin(\theta_u - \theta_v) e^{i\theta_u} A_F &= [1 - \cos(\theta_u - \theta_v)] B_F = 0; \end{aligned}$$

The equations are diagonal in K -point space so do not describe intervalley scattering. With these boundary conditions on the right (at $y = +L=2$) and on the left (at $y = -L=2$), standing waves at K are created from combining $\begin{pmatrix} R \\ K \end{pmatrix}$ and $\begin{pmatrix} L \\ K \end{pmatrix}$ and are labelled by helicity $= +s$, and those at F are created from $\begin{pmatrix} R \\ F \end{pmatrix}$ and $\begin{pmatrix} L \\ F \end{pmatrix}$ and have label $= -s$. We find that

$$\begin{aligned} B &= (-1)^{p_1} A \exp[i s (\theta_R - \theta_L) = 2 + i s (\theta_R + \theta_L) = 2]; \\ D &= (-1)^{p_2} C \exp[-i s (\theta_R - \theta_L) = 2 + i s (\theta_R + \theta_L) = 2]; \end{aligned}$$

and the corresponding wavevectors are

$$\begin{aligned} q^{(+s)} &= \frac{s(\theta_R + \theta_L)}{2L} - \frac{s(\theta_R - \theta_L)}{2L} + \frac{p_1}{L}; \\ q^{(-s)} &= + \frac{s(\theta_R + \theta_L)}{2L} - \frac{s(\theta_R - \theta_L)}{2L} + \frac{p_2}{L}; \end{aligned}$$

where p_1, p_2 are integers such that $q \neq 0$. Using $E = \text{svq}$ shows that the mixing angles θ_R and θ_L break K -point degeneracy whereas θ_R and θ_L break electron-hole symmetry.

M 2: off-diagonal boundary conditions

The boundary condition M_2 is equivalent to the following relations between the components of the enveloped wavefunction at the interface:

$$\begin{aligned} A_K + u \sin \theta_u e^{i\theta_u} A_F &= \cos \theta_u e^{i\theta_u} B_F = 0; \\ B_K - u \sin \theta_u e^{i\theta_u} B_F &= \cos \theta_u e^{i\theta_u} A_F = 0; \end{aligned}$$

The equations are off-diagonal in K space so describe intervalley scattering. Standing waves are created from combining $\begin{pmatrix} R \\ K \end{pmatrix}$ and $\begin{pmatrix} L \\ F \end{pmatrix}$, with spin eigenvalue $= +s$, and $\begin{pmatrix} R \\ F \end{pmatrix}$ and $\begin{pmatrix} L \\ K \end{pmatrix}$, with spin eigenvalue $= -s$. We find that

$$\begin{aligned} D &= (-1)^{p_1} A \exp[i s (\theta_R - \theta_L) = 2 + i s (\theta_R + \theta_L) = 2]; \\ B &= (-1)^{p_2} C \exp[-i s (\theta_R - \theta_L) = 2 - i s (\theta_R + \theta_L) = 2]; \end{aligned}$$

and the corresponding wavevectors are

$$\begin{aligned} q^{(+s)} &= \frac{s(\theta_R + \theta_L)}{2L} - \frac{(\theta_R - \theta_L)}{2L} + \frac{p_1}{L}; \\ q^{(-s)} &= \frac{s(\theta_R + \theta_L)}{2L} + \frac{(\theta_R - \theta_L)}{2L} + \frac{p_2}{L}; \end{aligned}$$

where p_1, p_2 are integers such that $q \neq 0$. The angles θ_R and θ_L break degeneracy whereas θ_R and θ_L break electron-hole symmetry.

M 3: mixed boundary conditions (i)

The boundary condition M_3 produces the following relations between the components of the wavefunction at the interface:

$$\begin{aligned} A_K (1 - \sin \theta_u \cos \theta_v) + u \cos \theta_u e^{i\theta_u} A_F &= 0; \\ u \sin \theta_u \sin \theta_v e^{i\theta_u} B_K &= 0; \\ B_K (1 + \sin \theta_u \cos \theta_v) - u \cos \theta_u e^{i\theta_u} B_F &= 0; \\ u \sin \theta_u \sin \theta_v e^{i\theta_u} A_K &= 0; \end{aligned}$$

The matrix M_3 has both diagonal and off-diagonal in K -point space parts. Standing waves are created from linear combinations of all $\begin{pmatrix} R \\ K \end{pmatrix}$, $\begin{pmatrix} L \\ F \end{pmatrix}$, $\begin{pmatrix} R \\ F \end{pmatrix}$ and $\begin{pmatrix} L \\ K \end{pmatrix}$. We find that

$$\begin{aligned} B &= \sin \theta_u e^{i s \theta_u} A e^{i u q L} + i s u \cos \theta_u e^{i\theta_u} C e^{i u q L}; \\ D &= \sin \theta_u e^{i s \theta_u} C e^{i u q L} + i s u \cos \theta_u e^{i\theta_u} A e^{i u q L}; \end{aligned}$$

and the corresponding wavevectors are given by

$$\begin{aligned} \cos(2qL) &= \cos \theta; \\ \cos \theta &= \sin \theta_R \sin \theta_L \cos(\theta_R + \theta_L) \\ &\quad \cos \theta_R \cos \theta_L \cos(\theta_R - \theta_L); \end{aligned}$$

where $q = 0$ and $0 < q < \frac{\pi}{2L}$. The energy levels are

$$E = \pm v_F \sqrt{\frac{n^2}{4L^2} + \frac{n^2}{4L^2}}; \quad (12)$$

where $n = \pm 1, 2, 3, \dots$ are integers. The spectrum always has positive-negative energy symmetry, but broken degeneracy for $q \neq 0$; g .

M 4: mixed boundary conditions (ii)

The boundary condition $\psi = M_4 \psi$ produces the following relations between the components of the wavefunction at the interface:

$$\begin{aligned} A_K (1 + \sin \theta_u \sin \theta_u) - u \sin \theta_u \cos \theta_u e^{+i\theta_u} B_K \\ \cos \theta_u e^{i\theta_u} B_R = 0; \\ B_K (1 - \sin \theta_u \sin \theta_u) - u \sin \theta_u \cos \theta_u e^{-i\theta_u} A_K \\ \cos \theta_u e^{-i\theta_u} A_R = 0; \end{aligned}$$

The matrix M_4 has both diagonal and off-diagonal in K space parts. Standing waves are created from linear combinations of all $\begin{pmatrix} R \\ K \end{pmatrix}$, $\begin{pmatrix} L \\ R \end{pmatrix}$, $\begin{pmatrix} R \\ R \end{pmatrix}$ and $\begin{pmatrix} L \\ K \end{pmatrix}$. We find that

$$\begin{aligned} B &= i u \sin \theta_u e^{i\theta_u} A e^{i\theta_u L} + \cos \theta_u e^{-i\theta_u} C e^{i\theta_u L}; \\ D &= i u \sin \theta_u e^{-i\theta_u} C e^{i\theta_u L} + \cos \theta_u e^{+i\theta_u} A e^{i\theta_u L}; \end{aligned}$$

and the corresponding wavevectors are given by

$$\begin{aligned} \cos(2qL) &= \cos \theta_u; \\ \cos \theta_u &= \cos \theta_R \cos \theta_L \cos(\theta_R - \theta_L) \\ \sin \theta_R \sin \theta_L \cos(\theta_R + \theta_L); \end{aligned}$$

where $q = 0$ and $0 < q < \frac{\pi}{2L}$. The energy levels are

$$E = \pm v_F \sqrt{\frac{n^2}{4L^2} + \frac{n^2}{4L^2}}; \quad (13)$$

where $n = \pm 1, 2, 3, \dots$ are integers. The spectrum always has positive-negative energy symmetry, but broken degeneracy for $q \neq 0$; g .

DISCUSSION

In this paper, we considered the effective mass model of spinless electrons in single wall carbon nanotubes that describes slowly varying spatial envelope wavefunctions $\psi(\mathbf{r})$ with small wavevectors q in the region of linear dispersion $E = v_F |q|$ near the K points. Taking into account the two inequivalent K points, the envelope wavefunctions obey the Dirac equation for massless fermions, written in terms of four component spinors, with the role of spin assumed by the relative amplitude of the wave function on the sublattice atoms (A and B).

We found that energy independent hard wall boundary conditions for the Dirac equation may be written as $\psi = M \psi$ where M is an Hermitian, unitary 4×4 matrix $M^2 = 1$ with the additional constraint that it anticommutes with the component of the current operator normal to the boundary. All possible linear combinations of matrices M obeying these constraints were expressed in terms of a small number of arbitrary parameters, mixing angles, that describe mixing between boundary conditions with different discrete symmetries. Then, in order to illustrate how the presence of non-zero mixing angles breaks K -point degeneracy and electron-hole symmetry, we evaluated the resulting energy level spectra for non-interacting electrons in finite-length metallic nanotubes and the corresponding standing wave envelope functions.

The intention of this paper was to classify all possible boundary conditions for the spatially long-range envelope functions of a closed nanotube with length much greater than its circumference $L \gg L_c$. The analysis was restricted to energy independent boundary conditions, although in principle they could be generalised by performing a gradient expansion. We focused on arm chair tubes and did not consider the possibility of edge states that may exist in zigzag graphite edges [21, 22, 23]. Rather than modelling the microscopic details of a boundary, such as shape or roughness, the nature of the boundary is characterised by mixing angles that describe the degree of symmetry breaking. In practice, the correct choice of a particular set of boundary conditions and values of symmetry mixing angles needed to describe a given nanotube will depend on experimental details and may not be known beforehand. To illustrate this, we compare our results to the idealised microscopic models of a capped arm chair nanotube and a model of a boundary obtained by setting the wavefunction to zero along a straight line of atoms. We find that the description of a capped nanotube considered in Ref. [13] corresponds to our off-diagonal boundary conditions M_2 , $M_2 = M_2$, with $\theta_u = 0$ or π so that the component A_K of the wavefunction is related to B_R at the boundary. A model of a boundary obtained by setting the wavefunction to zero, which is equivalent to a particle-in-a-box model [14], also corresponds to our off-diagonal boundary conditions M_2 , $M_2 = M_2$, but with $\theta_u = \pi/2$ so that the component A_K of the wavefunction is related to A_R at the boundary. Although the two models are described by a different mixing angle, they both correspond to the off-diagonal boundary conditions, introduce inter-valley scattering at the boundary and, in general, they break K -point degeneracy with the mixing angle θ_u dependent on the length of the nanotube.

The authors thank J T Chalker and C J Lambert for discussions, and EPSRC for financial support.

APPENDIX

In this appendix, we briefly describe the method of finding linear combinations of matrices that satisfy the constraints on M described by the boundary conditions, Eq. (2). Any 4×4 matrix may be written as a linear combination of the matrices I , I , I (n_1), I (n_2), I , and I (n_1), where n_1 and n_2 are arbitrary three-dimensional space-like vectors. The first step is to find all the linear combinations that produce the unit matrix I when squared:

$$M_a = I - I;$$

$$M_b = \cos(I \cdot n_1) + \sin(I \cdot n_1);$$

$$M_c = \cos(I \cdot n_2) + \sin(I \cdot n_2);$$

where the vectors are unit vectors with additional constraints $n_1 \cdot n_2 = 0$, $n_1 \cdot n_2 = 0$ that ensure no cross-terms survive. The next step is to find the conditions under which the matrices M_a , M_b , and M_c anticommute with the operator n_B : that is proportional to the component of the current operator normal to the interface. Clearly, M_a does not anticommute, so it is discarded. The matrix M_b anticommutes if $n_1 \cdot n_B = 0$, $n_2 \cdot n_B = 0$, and $n_1 = \hat{k}$ (M1), or if $n_1 \cdot n_B = 0$, $n_2 = n_B$, and n_1 is confined to the (x ; y) plane (M3). The matrix M_c anticommutes if n_1 and n_2 are confined to the (x ; y) plane and $n_2 = n_B$ (M2), or if n_1 is confined to the (x ; y) plane, $n_2 = \hat{k}$, and $n_2 \cdot n_B = 0$ (M4).

[1] Saito R, Dresselhaus G and Dresselhaus M S 1988 Physical properties of carbon nanotubes (Imperial College Press: London).

[2] Dekker C 1999 Physics Today 52 (5) 22.

- [3] Bockrath M, Cobden D H, McEuen P L, Chopra N G, Zettl A, Thess A and Smalley R E 1997 Science 275 1922.
- [4] Tans S J, Devoret M H, Dai H, Thess A, Smalley R E, Geerlings L J and Dekker C 1997 Nature 386 474.
- [5] Venema L C, Winkler J W G, Janssen J W, Tans S J, Temmink Tuinstra H L J, Kouwenhoven L P and Dekker C 1999 Science 283 52.
- [6] Lemay S G, Janssen J W, van den Hout M, Mooij M, Bronikowski M J, Willis P A, Smalley R E, Kouwenhoven L P and Dekker C 2001 Nature 412 617.
- [7] Liang W, Bockrath M and Park H 2002 Phys. Rev. Lett. 88 126801.
- [8] Buitelaar M, Bachtold A, Nussbaumer T, Iqbal M and Schonenberger C 2002 Phys. Rev. Lett. 88 156801.
- [9] Cobden D H and Nygard J 2002 Phys. Rev. Lett. 89 046803.
- [10] Rubio A, Sanchez-Portal D, Artacho E, Ordejón P and Soler J M 1999 Phys. Rev. Lett. 82 3520.
- [11] Rochefort A, Salahub D R and Avoiris P 1999 J. Phys. Chem. B 103 641.
- [12] Wu J, Duan W, Gu B-L, Yu J-Z and Kawazoe Y 2000 Appl. Phys. Lett. 77 2554.
- [13] Yaguchi T and Ando T 2001 J. Phys. Soc. Japan 70 1327; Yaguchi T and Ando T 2001 J. Phys. Soc. Japan 70 3641.
- [14] Jiang J, Dong J and Xing D Y 2002 Phys. Rev. B 65 245418.
- [15] DiVincenzo D P and Mele E J 1984 Phys. Rev. B 29 1685.
- [16] Ajiki H and Ando T 1993 J. Phys. Soc. Japan 62 1255.
- [17] Kane C L and Mele E J 1997 Phys. Rev. Lett. 78 1932.
- [18] McEuen P L, Bockrath M, Cobden D H, Yoon Y-G and Louie S G 1999 Phys. Rev. Lett. 83 5098.
- [19] Chodos A, Jaeger L, Johnson K, Thom C B and Weiskopf V F 1974 Phys. Rev. D 9 3471.
- [20] Berry M V and Mondragon R J 1987 Proc. R. Soc. Lond. A 412 53.
- [21] Klein, D J 1994 Chem. Phys. Lett. 217 261.
- [22] Fujita M, Wakabayashi K, Nakada K and Kusakabe K 1996 J. Phys. Soc. Japan 65 1920.
- [23] Ryu S and Hatsugai Y 2002 Phys. Rev. Lett. 89 077002.