

Pomeranchuk effect in unstable *Ytterbium* systems

Mucio A. Continentino and André S. Ferreira
*Instituto de Física, Universidade Federal Fluminense,
 Campus da Praia Vermelha,
 Niterói, RJ, 24.210-340, Brazil.**
 (Dated: March 22, 2022)

$YbInCu_4$ and its alloys present discontinuous, first order iso-structural transitions at pressure dependent temperatures $T_V(P)$, where a local moment phase coexist with a renormalized Fermi liquid phase. We show that along the coexistence line $T_V(P)$ the entropy of the large volume renormalized Fermi liquid phase is smaller than that of the higher density, local moment phase. This implies the existence of a Pomeranchuk effect in these Kondo lattice materials in analogy with 3He . The theoretical possibility of using these systems as cooling machines is discussed.

PACS numbers: 71.28.+d; 71.27.+a; 65.50.+m; 64.10.+h

The system 3He presents the unusual feature that along its melting line, where the solid and liquid phases coexist, the entropy of the liquid is smaller than that of the solid^{1,2}. This occurs for a range of temperature $T < T_N = 0.32K$, where the melting pressure versus temperature curve has a minimum, but for $T > T_N$, the temperature of magnetic ordering of the solid. This feature is the basis of the cooling technique known as the Pomeranchuk effect¹ which had an important practical application as a cooling mechanism to reach very low temperatures in this system. It is believed to be a unique property of quantum 3He and is a direct consequence that in its liquid phase this is a renormalized Fermi liquid, with a linear temperature dependent entropy ($S_L/Nk_B = 3.0T$) while in the solid phase for the temperature range above, it may be seen as a collection of weakly interacting spin-1/2 local moments with¹ $S_S/Nk_B \approx \ln 2$. Also for the low temperatures associated with this behavior of 3He , elastic excitations (the phonons) are quenched and the relevant degrees of freedom are the magnetic ones due the spin-1/2 nuclei.

The Kondo lattice system $YbInCu_4$ presents isostructural transitions, which for the pure system at ambient pressure ($P \approx 1$ bar) occurs at a temperature $T_V = 42K$ ^{3,4}. This is a discontinuous, first order transition which is accompanied by large changes in transport properties and in magnetic behavior. In Fig. 1 we show the temperature dependent magnetic susceptibility of $YbInCu_4$ in the range of the isostructural transition. Above T_V , the susceptibility is of the Curie-Weiss type characteristic of a system of weakly interacting local moments ($\Theta \approx -7.2 K$)⁴. Below the transition, the susceptibility is nearly temperature independent, i.e., Pauli like as in a Fermi liquid. The value of χ_0 indicates a renormalized value consistent with the coefficient of the linear term in the specific heat, $\gamma = 50$ mJ/molK²⁴. This leads us to consider $YbInCu_4$ in its low temperature phase as a moderate heavy fermion system.

This picture of $YbInCu_4$ at T_V as a renormalized Fermi liquid phase coexisting with a local moment phase at a line of first order transitions $T_V(P)$ brings out a powerful analogy with 3He .




FIG. 1: Susceptibility curve for $YbInCu_4$ (schematic). At $T_V \approx 42K$ ($P = 0$) there is a discontinuous, first order iso-structural transition with a volume increase in the low temperature phase. At T_V a local moment phase coexists with a renormalized Fermi liquid phase⁴.

Along the melting line $T_m(P)$ of 3He and the line $T_V(P)$ of the present system, we find coexistence of a renormalized Fermi liquid phase and a phase of local moments (in 3He the liquid and solid phases, respectively).

The nature of the coexisting phases in $YbInCu_4$ leads us to expect that as in 3He , the Fermi liquid phase of this material has a smaller entropy that of the local moment phase for some range of temperatures where these phases coexist.

The Clausius-Clapeyron equation², as applied to the $YbInCu_4$ system can be written as,

$$\left(\frac{dP}{dT}\right)_{T_V(P)} = \frac{S_{FL} - S_{LM}}{V_{FL} - V_{LM}} \quad (1)$$

where the derivative is obtained at the volume instability curve $T_V(P)$. The entropy of the local moment phase and of the renormalized Fermi liquid phase are given by S_{LM} and S_{FL} , respectively. Notice that, since both phases are truly solid and the change in volume is small (see Table I), the difference ($S_{FL} - S_{LM}$) is mostly due to the magnetic degrees of freedom. In 3He the derivative

in Eq. 1 is calculated at the melting curve where the solid and liquid coexist. In this system, the melting pressure as a function of temperature passes through a minimum at T_\times , where $S_{solid} = S_{liquid}$ and presents a negative (dP/dT) for $T < T_\times$, consistent with $S_{solid} > S_{liquid}$ in this range, since the molar volume of the liquid V_L is larger than that of the solid, V_S .^{1,2}




FIG. 2: Pressure of the volume instabilities in $YbInCu_4$ as a function of temperature, obtained from resistivity measurements⁴.

A plot of the instability temperature for $YbInCu_4$ as a function of pressure $T_V(P)$ (or $P(T_V)$), obtained from resistivity measurements⁴ is shown in Fig. 2. From the Clausius-Clapeyron equation, the experimental negative sign of (dP/dT) at T_V and the fact that the molar volume in the Fermi liquid phase of $YbInCu_4$ (V_{FL}) is larger than that of the local moment phase V_{LM} , we can conclude that the entropy of the former (S_{FL}) at the coexistence line $P(T_V)$ is smaller than that of the local moment phase, for this range of temperatures, just as in 3He for $T < T_\times$. As pointed out before, the features $S_{FL} < S_{LM}$, $V_{FL} > V_{LM}$ are at the root of the Pomeranchuk effect in 3He which, as we have just shown, also occurs in the Kondo lattice system $YbInCu_4$.

In Table I we list for comparison some thermodynamic parameters of $YbInCu_4$ and 3He . Notice that for the former material, (T_\times, P_\times) are obtained from a crude extrapolation of the Fermi liquid entropy⁴ $S_{FL}/Nk_B = 6.0 \times 10^{-3}T$ up to that of independent local moments⁵ $S_{LM}/Nk_B = \ln(2J + 1) = \ln 8$.

In the case of 3He the Pomeranchuk effect is the basis for the construction of a practical apparatus which has provided the means for attaining very low temperatures in this system and eventually discovering its superfluid phases¹. The results above show the theoretical possibility of constructing a Pomeranchuk cooling machine based on the Kondo lattice system $YbInCu_4$. An estimation of the cooling efficiency of such machine is given by the

	3He	$YbInCu_4$
Large Volume Phase (V_L)	Liquid	Fermi Liquid
Small Volume Phase (V_S)	Solid	Local Moment
$(V_L - V_S)/V_L$	0.05	0.005
$(dP/dT)(kbar/K)$	- 0.016	- 0.5
(W/Q)	> 13	0.08 ($T = 40K$)
(T_\times, P_\times) (K, kbar)	(0.32, 0.029)	(346, -151)

TABLE I: Thermodynamic parameters for 3He , Ref. ² and $YbInCu_4$, Ref. ⁴. (T_\times, P_\times) for $YbInCu_4$ were obtained extrapolating the Fermi liquid entropy to reach to non-interacting local moment value.

ratio (W/Q) , where $W = P_V(V_{FL} - V_{LM})$ is the compressional work to squeeze the Fermi liquid into the local moment phase. The quantity $Q = T(S_{LM} - S_{FL})$ is the latent heat which represents the maximum amount of heat which can be removed by converting the Fermi liquid into the local moment phase. The ratio $W/Q = -(P_V/T)(dP_V/dT)^{-1}$ attains for 3He its lowest value, $(W/Q) = 13$, at $T = 0.14K^2$. For $YbInCu_4$ this can be much smaller, for example, $(W/Q) = 0.08$ at $T = 40K$ using the value of (dP_V/dT) obtained from Fig. 2 (see Table I).




FIG. 3: Schematic temperature variation of the entropy of the Fermi liquid and local moment phases at the instability field H_V . Cooling can be achieved by isentropically increasing the magnetic field to bring the FL phase into the LM phase as in a process from A to B.

Notice however that instead of adiabatically squeezing $YbInCu_4$ to transform the Fermi liquid into the local moment phase and reduce the temperature, it is easier to play with the magnetic field^{4,5} which strongly affects the volume transition at T_V . In Fig. 3 we show schematically the temperature dependence of the entropy $S(H_V, T)$ of the Fermi liquid and local moment phases at the instability field H_V . A similar curve is obtained for $S(P_V, T)$. Cooling can be achieved by isentropically increasing the magnetic field to bring the Fermi liquid into the local moment phase, as in the process $A \rightarrow B$ illustrated in the figure. We point out that $T_V(H)$ is a universal decreasing function⁴ of H_V . Then, the magnetic field can

be used as the *compressing agent* which is simpler than actually squeezing the Fermi liquid.

In this Letter we have shown the existence of a Pomeranchuk effect in $YbInCu_4$ and its alloys, which opens the theoretical possibility of using these materials as cooling machines. Our approach suggests to view the transition at T_V in $YbInCu_4$ as the melting of a Kondo lattice.

Acknowledgments

We would like to thank Conselho Nacional de Desenvolvimento Científico e Tecnológico-CNPq-Brasil

(PRONEX98/MCT-CNPq-0364.00/00), Fundação de Amparo a Pesquisa do Estado do Rio de Janeiro-FAPERJ for partial financial support. We thank J. C. Fernandes and E. Miranda for useful suggestions and discussions.

* Electronic address: mucio@if.uff.br

¹ I. Pomeranchuk, Zh. Eksp. i Teor. Fiz. (USSR) **20**, 919 (1950); R. C. Richardson, Rev. Mod. Phys. **69**, 683 (1997).

² D. S. Betts, *Refrigeration and Thermometry below One Kelvin*, Sussex University Press, 1976.

³ I. Felner and I. Nowik, Phys. Rev. **B33**, 617 (1986).

⁴ J. L. Sarrao, Physica **B259-261**, 128 (1999) and references therein.

⁵ M.O. Dzero, L.P. Gorkov and A.K. Zvezdin, J.Phys.-Cond.Mat. **12**, L711 (2000).