The magnetopolaron effect in light reflection and absorption by a wide quantum

I. G. Lang, L. I. Korovin

A. F. Ioffe Physical-Technical Institute, Russian Academy of Sciences, 194021 St. Petersburg, Russia

S. T. Pavlov^{†‡}

†Facultad de Fisica de la UAZ, Apartado Postal C-580, 98060 Zacatecas, Zac., Mexico

[‡]P. N. Lebedev Physical Institute, Russian Academy of Sciences, 119991 Moscow, Russia

(March 22, 2022)

Light reflection and absorption spectra by a semiconductor quantum well (QW), which width is comparable to a light wave length of stimulating radiation, are calculated. A resonance with two close located exited levels is considered. These levels can arise due to splitting of an energy level of an electron-hole pair (EHP) due to magnetopolaron effect, if the QW is in a quantizing magnetic field directed perpendicularly to the QW plane. It is shown that unlike a case of narrow QWs light reflection and absorption depend on a QW width d. The theory is applicable at any ratio of radiative and non-radiative broadenings of electronic excitations. PACS numbers: 78.47. + p, 78.66.-w

At passage of light through a semiconductor quantum well (QW) in reflected and transmitted light waves characteristic occur, on which it is possible to judge features of electronic processes proceeding in a QW. The most interesting results turn out when energy levels of an electronic system are discrete. It takes place in a quantizing magnetic field directed perpendicularly to a QW plane or in case of a resonance of the stimulating light frequency ω_{ℓ} with an excitonic state in a zero magnetic field.

Two close located energy levels of excitation arise in a case of a magneto-phonon resonance [1], when the condition

$$\omega_{LO} = j\Omega \tag{1}$$

is satisfied, where ωLO is the longitudinal optical (LO) phonon frequency, $\Omega = |e|H/cm_{e(h)}$ is the cyclotron frequency, $m_{e(h)}$ is the electron (hole) effective mass. Integers j correspond to ordinary polarons, fractional j correspond to so-called "weak" polarons [2]. Weak polarons arise in crossing points of two terms characterized by values $\Delta N \geq 2$, where ΔN is the difference of LO phonons numbers for these two terms. Real direct transitions between such terms with emitting of one phonon are impossible. But as the terms are crossed, their splitting is inevitable. To calculate the splitting value it is necessary to take into account transitions between crossed terms through virtual intermediate states or to take into account in the operator of the electron-phonon interaction small two-phonon contributions. We obtain that splitting $\Delta E weak$ for weak polarons should be essentially less, than for usual polarons at integer j. Contributions of transitions through intermediate states in ΔE_{weak} are of higher order on the Fröhlich electron-phonon coupling constant α [3], than $\alpha^{1/2}$.

Light scattering and absorption by narrow QWs are theoretically investigated in conditions of a magnetophonon resonance, when a light wave length is much greater than a QW width d, in [4] - at a pulse irradiation, in [5] - at a monochromatic irradiation. It was shown that especially interesting results may be obtained for weak polarons. Monochromatic light reflection, absorption and transmission are theoretically investigated for wide QW, when the interaction of light with two close located energy levels (for instance, two energy levels of an usual or weak polaron) is essential. A condition of a wide QW is as follows

 $\kappa d \geq 1$,

where κ is the wave vector module of a light wave. The normal incidence of light on a semiconductor QW surface in a plane xy is considered. The QW may be in a quantizing magnetic field, perpendicular to the QW surface. For calculation of light reflection and absorption the technique developed in [6] and applicable to any low-dimensional semiconductor objects (QWs, quantum wires and dots) is used at monochromatic and at pulse irradiation at any light pulse form. For dimensionless light reflection \mathcal{R} and absorption \mathcal{A} in case of two close located excitation energy levels $\hbar\omega_1$ and $\hbar\omega_2$ following results are obtained:

$$\mathcal{R} = \frac{1}{4Z} \{ [\tilde{\gamma}_{r1}(\omega_{\ell} - \omega_2) + \tilde{\gamma}_{r2}(\omega_{\ell} - \omega_1)]^2 + \frac{1}{4} (tilde\gamma - r1\gamma_2 + \tilde{\gamma} - r2\gamma_1)^2 \}$$
(2)

$$\mathcal{A} = \frac{1}{2Z} \{ \tilde{\gamma}_{r1} \gamma_1 [(\omega_{\ell} - \omega_2)^2 + \gamma_2^2 / 4] \\ + \tilde{\gamma}_{r2} \gamma_2 [(\omega_{\ell} - \omega_1)^2 + \gamma_1^2 / 4] \\ - (\Delta_1 \tilde{\gamma}_{r2} - \Delta_2 \tilde{\gamma}_{r1}) [(\omega_{\ell} - \omega_2) \gamma_1 - (\omega_{\ell} - \omega_1) \gamma_2] \}, \quad (3)$$

$$Z = \{ (\omega_{\ell} - \omega_{1})(\omega_{\ell} - \omega_{2}) - \frac{\tilde{\gamma}_{r1}\gamma_{2} + \tilde{\gamma}_{r2}\gamma_{1} + \gamma_{1}\gamma_{2}}{4} -\Delta_{1}(\omega_{\ell} - \omega_{2}) - \Delta_{2}(\omega_{\ell} - \omega_{1}) \}^{2} + \frac{1}{4} \{ (\omega_{\ell} - \omega_{2})(\tilde{\gamma}_{r1} + \gamma_{1}) + (\omega_{\ell} - \omega_{1})(\tilde{\gamma}_{r2} + \gamma_{2}) -\Delta_{1}\gamma_{2} - \Delta_{2}\gamma_{1} \}^{2}, \quad (4)$$

where $\tilde{\gamma}_{r1(2)}$ is the radiative broadening of the states 1(2), $\gamma_{1(2)}$ is the non-radiative broadening of the same states, $\Delta_{1(2)}$ is the radiative energy shift of states. The formulas (2) - (4) are fair, if excitations 1 and 2 are characterized by the same wave function dependent on coordinates z. The last is carried out for usual polarons (but not for combined polarons [7,8]). For wide QWs $\tilde{\gamma}_{r1(2)}$ are determined by expressions

$$\tilde{\gamma}_{r1(2)} = \gamma_{r1(2)} |R(\omega_{\ell}\nu/c)|^2,$$
(5)

where

$$R(\kappa) = \int_{-d/2}^{d/2} dz \exp(-i\kappa z)\Phi(z), \qquad (6)$$

 ν is the light refraction factor, which for simplicity is considered as identical for a QW and barrier, $\Phi(z)$ is the wave function of excitation at $z_e = z_h = z$, where $z_{e(h)}$ is the electron (hole) coordinate. The factor $|R(\omega_\ell \nu/c)|^2$ determines the dependence of $\tilde{\gamma}r1l(2)$ on the QW width. The radiative energy shifts $\Delta_{1(2)}$ also depend on QW width d and aspires to zero at $\kappa d \to 0$.

In a limiting case $\tilde{\gamma}_{1(2)} \ll \gamma_{1(2)}$, $\Delta_{1(2)} \ll \gamma_{1(2)}$ the perturbation theory on interaction of light with electronic system is applicable. Thus, $\mathcal{R} \ll 1$, $\mathcal{A} \ll 1$ and $\mathcal{R} \ll \mathcal{A}$. If radiative and non-radiative damping are comparable, \mathcal{R} and \mathcal{A} achieve as much as possible allowable values about unit. Most interesting results turn out under conditions

$$\gamma_{rl(2)} \gg \gamma_{1(2)}, \quad \Delta_{1(2)} \gg \gamma_{1(2)}.$$
 (7)

If $\gamma_l = \gamma_2 = 0$, light absorption $\mathcal{A} = O$, and for light reflection \mathcal{R} from (2) we have

$$\mathcal{R} = \frac{[(\tilde{\gamma}_{r1} + \tilde{\gamma}_{r2})/2]^2(\omega_{\ell} - \Omega_0)}{(\omega_{\ell} - \omega_{d1})^2(\omega_{\ell} - \omega_{d2})^2 + [(\tilde{\gamma}_{r1} + \gamma_{r2})/2]^2(\omega_{\ell} - \Omega_0)^2}$$
(8)

where

$$\Omega_0 = (\omega_1 \tilde{\gamma}_{r2} + \omega_2 \tilde{\gamma}_{r1}) / (\tilde{\gamma}_{r1} + \tilde{\gamma}_{r2}),$$
$$\omega_{d1(2)} = (1/2) [\omega_1 + \Delta_1 + \omega_2 + \Delta_2$$
$$\pm \sqrt{(\omega_1 + \Delta_1 - \omega_2 - \Delta_2)^2 + 4\Delta_1 \Delta_2}].$$

It follows from (8) that at $\omega \ell = \Omega 0$ $\mathcal{R} = O$, i. e. there is a total transmission point of light through a QW. At $\omega_{\ell} = \omega_{dl}$ or $\omega_{\ell} = \omega_{d2}$ $\mathcal{R} = l$, i. e. light is totally reflected. The position of points of total reflection depends on the QW width d.




FIG. 1. Dimensionless reflection \mathcal{R} as function of light frequency ω_{ℓ} in case of two excitation energy levels in a wide QW under condition $\gamma_r \gg \gamma$. Continuous and dashed lines are the permitted transitions, dot-and-dash lines are the forbidden transitions. $\gamma_r(\gamma)$ is the radiative (non- radiative) broadening of an exited state.




FIG. 2. Same, that in Fig.1 for dimensionless absorption \mathcal{A} .

Represented in Fig. 1 and 2 frequency dependencies \mathcal{R} and \mathcal{A} correspond to inequalities (7). These figures may

concern and to weak polarons, when ΔE_{weak} and $\tilde{\gamma}_{rl(2)}$ may be comparable.

So, it is possible to make following conclusions. First, it is shown that if a light wave length is comparable to a QW width, height and form of peaks on curves $\mathcal{R}(\omega_{\ell})$ and $\mathcal{A}(\omega_{\ell})$ depend on a QW width.

Secondly, it is established that in case of a wide QW the interaction of light with excitations, which are characterized by different numbers $\ell_e \neq \ell_h$ of size of quantization numbers of electrons and holes appears. Dependence of \mathcal{R} and \mathcal{A} on a QW width d is various for cases $\ell_e = \ell_h$ and $\ell_e \neq \ell_h$.

Thirdly, it is shown that for wide QWs is kept original behavior of \mathcal{R} depending on frequency ω_{ℓ} (i. e. existence of two points of total reflection and one point of total transmission if the non-radiative damping is much less than radiative one.

- E. J. Johnson, D. M. Larsen. Phys. Rev. Letters, 16, 15, 655 (1966).
- [2] L. I. Korovin, I. G. Lang, S. T. Pavlov, Magnetopolaron states involving confined phonons in a semiconductor quantum well. Spatial correlation of electron and hole, Zh. Eksp. Teor. Fiz., 1999, **115**, N 1, p. 187-204 (JETP, 1999, **88**, N 1, p. 105-113).
- [3] H. Fröhlich. Adv. Phys. **3**, 2, 325 (1954).
- [4] D. A. Contreras-Solorio, S. T. Pavlov, L. I. Korovin, I. G. Lang. Phys. Rev. B,62, 24, 16815 (2000); condmat/0002229.
- [5] I. G. Lang, L. I. Korovin, A. Contreras-Solorio, S. T. Pavlov, Magnetopolaron effects in light reflection and absorption of a three-level system in a quantum well, Fiz. Tverd.Tela, 2002, 44, N 11, pp. 2084-2096 (Physics of the Solid State (St. Petersburg), 2002, 44, N 44, pp. 2181-2195)); cond-mat/ 0001248.
- [6] I. G. Lang, L. I. Korovin, S. T. Pavlov. cond-mat/0311180.
- [7] L. I. Korovin, I. G. Lang, S. T. Pavlov. Pisma Zh. Eksperim. i Teor.Fiz., 65, 7, 511 (1997).
- [8] L. I. Korovin, I. G. Lang, S. T. Pavlov, Combined Polaron States in Magnetooptical Effects in a Quantum Well, Zh. Eksp. Teor. Fiz., 1999, 116, N 4(10), p. 1419-1439

(JETP, 1999, **89**, N 4, p. 764-784).