arXiv:cond-mat/0405127v1 [cond-mat.str-el] 6 May 2004

Theory of the Metal-Insulator Transition in $PrRu_4P_{12}$ and $PrFe_4P_{12}$

S. H. Curnoe[1,2*], H. Harima[3], K. Takegahara[4] and K. Ueda[1,5]

[1] *Institute for Solid State Physics, University of Tokyo, Kashiwanoha 5-1-5, Kashiwa, Chiba 277-8581, Japan*
[2] *Department of Physics and Physical Oceanography, Memorial University of Newfoundland, St. John's NL, A1B 3X7, Canada*
[3] *Institute of Scientific and Industrial Research, Osaka University, Ibaraki, Osaka 567-0047, Japan*
[4] *Department of Materials Science and Technology, Hirosaki University, Hirosaki, Aomori 036-8561, Japan*
[5] *Advanced Science Research Center, Japan Atomic Energy Research Institute, Tokai, Ibaraki 319-1195, Japan*

(Dated: March 22, 2022)

All symmetry allowed couplings between the $4f^2$-electron ground state doublet of trivalent praseodymium in $PrRu_4P_{12}$ and $PrFe_4P_{12}$ and displacements of the phosphorus, iron or ruthenium ions are considered. Two types of displacements can change the crystal lattice from body-centred cubic to simple orthorhombic or to simple cubic. The first type lowers the point group symmetry from tetrahedral to orthorhombic, while the second type leaves it unchanged, with corresponding space group reductions $Im\bar{3} \rightarrow Pmmm$ and $Im\bar{3} \rightarrow Pm\bar{3}$ respectively. In former case, the lower point-group symmetry splits the degeneracy of the $4f^2$ doublet into states with opposite quadrupole moment, which then leads to anti-quadrupolar ordering, as in $PrFe_4P_{12}$. Either kind of displacement may conspire with nesting of the Fermi surface to cause the metal-insulator or partial metal-insulator transition observed in $PrFe_4P_{12}$and $PrRu_4P_{12}$. We investigate this scenario using band-structure calculations, and it is found that displacements of the phosphorus ions in $PrRu_4P_{12}$(with space group reduction $Im\bar{3} \rightarrow Pm\bar{3}$) open a gap everywhere on the Fermi surface.

PACS numbers: 71.27.+a 61.50.Ks 71.15.Mb 71.70.Ej

I. INTRODUCTION

The rare earth-filled skutterudites (RT_4Pn_{12}; R=rare earth; T = Fe, Ru or Os; Pn = P, As or Sb) exhibit a wide range of phenomena, including superconductivity in nearly all of the La-compounds[1,2,3], as well as $PrRu_4As_{12}$[2] and $PrRu_4Sb_{12}$[3], heavy fermion superconductivity in $PrOs_4Sb_{12}$[4], semiconducting or semimetallic behaviour in the Ce-compounds[5] and ferromagnetism in several of the Nd- and Eu-compounds[1,3,5,6] and UFe_4P_{12}.[7] $PrRu_4P_{12}$ undergoes a metal-insulator (M-I) transition at approximately $T_{MI} = 60$K,[8,9] while in $PrFe_4P_{12}$ there is a partial M-I transition at a much lower temperature, seen as a sharp upturn in the resistivity at $T_{MI} = 6.7$K,[10,11] which then tends to zero at low temperatures. In both cases, the M-I transition is accompanied by a structural phase transition which doubles the volume of the primitive cell.[12,13]

In $PrFe_4P_{12}$, a peak in the magnetic susceptibility is observed at T_{MI},[1] and T_{MI} is field-dependent, but there is no magnetic ordering.[14] However, in-field neutron diffraction experiments found direct evidence of anti-quadrupolar ordering below T_{MI}.[15] In contrast, T_{MI} of $PrRu_4P_{12}$ is not field dependent (as seen in the specific heat[16] and thermal expansion[17]) and no peak is observed in the susceptibility either,[8] which suggests that there is no ordering of any kind at T_{MI}. An upturn in the susceptibility at very low temperatures hints that there may be some kind of ordering below $T = 0.35$K,[1] and is likely related to the low-temperature magnetic field dependent peaks found in the thermal expansion and specific heat, whose positions decrease in temperature with decreasing field.[16,17]

Nesting of the Fermi surface may be the common feature of the M-I transition in both of these materials. Band-structure calculations for $LaFe_4P_{12}$,[18] $PrFe_4P_{12}$ and $PrRu_4P_{12}$[19] found an approximately cubed-shaped hole-like Fermi surface, with nesting wavevector $q = (1, 0, 0)$ (due to the 48th band in $LaFe_4P_{12}$ and the 49th band in $PrFe_4P_{12}$ and $PrRu_4P_{12}$). The band itself has a roughly flat dispersion, which means that slight differences can cause substantially different Fermi surface topologies. Thus, in $PrRu_4Sb_{12}$ and $LaRu_4Sb_{12}$ the resulting FS does not have the nesting property.[19,20] $LaFe_4P_{12}$ and $PrFe_4P_{12}$ possess an additional smaller hole-like spherical Fermi surface, so that the M-I transition in $PrFe_4P_{12}$ is incomplete, and it remains a metal at low temperatures. It has been suggested that a nested Fermi surface is also a possible cause of the resistivity upturns seen in $NdFe_4P_{12}$, $SmRu_4P_{12}$, $GdRu_4P_{12}$ and $TbRu_4P_{12}$.[21]

If nesting is a prerequisite for the M-I transition, then so is a cell-doubling structural instability, which halves the Brillouin zone (BZ) at the nesting wave vector. All of the rare earth-filled skutterudites crystallise in the body-centred cubic (bcc) lattice with space group $Im\bar{3}$ (#204), except for the low-temperature phases of $PrFe_4P_{12}$ and $PrRu_4P_{12}$. In these cases, superlattice reflections are a clear indication of doubling of the primitive cell.[12,13] The change in structure appears to be due to a displacement of Fe ions in $PrFe_4P_{12}$ and both of Ru and P ions in $PrRu_4P_{12}$, with space groups Pmmm (#47) and $Pm\bar{3}$

(#200) respectively.

In Section II, all symmetry allowed couplings of Pr^{3+} $4f^2$ electrons to the lattice are considered. It is shown that anti-quadrupolar ordering of the $4f^2$ electrons follows when the point group symmetry at the Pr site is lowered from tetrahedral to orthorhombic (as is the case in the $Im\bar{3} \rightarrow Pmmm$ transition). In Section III we present band structure calculations which show that a gap opens everywhere at the Fermi energy when P ion displacements (with space group reduction $Im\bar{3} \rightarrow Pm\bar{3}$) are considered in $PrRu_4P_{12}$.[22] We summarise our results in Section IV.

II. STRUCTURAL PHASE TRANSITION AND ANTI-QUADRUPOLAR ORDERING

According to XANES studies on $PrRu_4P_{12}$[23] and susceptibility measurements on $PrFe_4P_{12}$,[10] the valency of the Pr ion is +3, ie, a $4f^2$ configuration with total angular momentum $J = 4$. The Ru/Fe ions form a crystal field with O_h symmetry with respect to the Pr ions, but the P ions lower the symmetry to T_h. Under O_h symmetry, the $J = 4$ state splits into a singlet, a doublet and two triplets, corresponding to the representations $\Gamma_1 \oplus \Gamma_3 \oplus \Gamma_4 \oplus \Gamma_5$ of O respectively. Under the actual symmetry T_h, the Γ_3 doublet is split into states related by time reversal symmetry (complex conjugates). Crystal field splitting alone cannot determine the ground state, but specific heat measurements on $PrFe_4P_{12}$[24] and $PrRu_4P_{12}$[16] favour the doublet, which is

$$|\Gamma_3^+\rangle = \sqrt{7/24}|4\rangle - \sqrt{5/12}|0\rangle + \sqrt{7/24}|-4\rangle \quad (1)$$

$$|\Gamma_3^-\rangle = \sqrt{1/2}|2\rangle + \sqrt{1/2}|-2\rangle. \quad (2)$$

These states carry quadrupole moment $\langle\Gamma_3^\pm|3J_z^2 - J^2|\Gamma_3^\pm\rangle = \pm 8\hbar^2$.

On the other hand, a singlet ground state,

$$|\Gamma_1\rangle = \sqrt{5/24}|4\rangle - \sqrt{7/12}|0\rangle + \sqrt{5/24}|-4\rangle \quad (3)$$

with a low lying triplet first excited state has not been conclusively ruled out. The exact form of the triplets is unknown in T_h, because in general they are linear combinations of

$$|\Gamma_4^x\rangle = [|3\rangle + |-3\rangle + \sqrt{7}(|1\rangle + |-1\rangle)]/4 \quad (4)$$

$$|\Gamma_4^y\rangle = i[-|3\rangle + |-3\rangle + \sqrt{7}(|1\rangle - |-1\rangle)]/4 \quad (5)$$

$$|\Gamma_4^z\rangle = (|4\rangle - |-4\rangle)/\sqrt{2} \quad (6)$$

and

$$|\Gamma_5^{yz}\rangle = [\sqrt{7}(-|3\rangle + |-3\rangle) - |1\rangle + |-1\rangle]/4 \quad (7)$$

$$|\Gamma_5^{xz}\rangle = i[-\sqrt{7}(|3\rangle + |-3\rangle) + |1\rangle + |-1\rangle]/4 \quad (8)$$

$$|\Gamma_5^{xy}\rangle = (|2\rangle - |-2\rangle)/\sqrt{2}. \quad (9)$$

In the following discussion, we often refer to the representations of O_h, but since the actual crystal symmetry is T_h, we should use the following correspondences between the representations of O and T:

Dimension	O	T
1	Γ_1	Γ_a
1	Γ_2	Γ_a
2	Γ_3	$\Gamma_b \oplus \Gamma_c$
3	Γ_4	Γ_d
3	Γ_5	Γ_d

We use the representations of O_h for convenience, especially in the discussion of the displacement modes of the Fe/Ru ions, since by themselves they form a crystal field with O_h symmetry. However, the above table should always be used to reduce the representations of O_h to those of T_h.

Now we consider all possible modes of the displacements. There are eight Fe/Ru ions within the bcc conventional cell, which are found half-way between neighbouring Pr ions (the centres of the hexagonal faces of the bcc Wigner-Seitz (primative) cell). They form corner-sharing cubes about each Pr ion. There are 24 displacement modes, which transform according to the representations $\Gamma_1 \oplus \Gamma_2' \oplus \Gamma_3 \oplus \Gamma_3' \oplus \Gamma_4 \oplus 2\Gamma_4' \oplus 2\Gamma_5 \oplus \Gamma_5'$ of O_h, where the primes indicate the odd (*ungerade*) representations.

Twelve P ions are found *inside* the bcc primitive cell (note that the bcc primitive cell is half the volume of the bcc conventional cell). The 36 modes of the P ion displacements transform according to the representations $2(\Gamma_a \oplus \Gamma_b \oplus \Gamma_c) \oplus 4\Gamma_d \oplus \Gamma_a' \oplus \Gamma_b' \oplus \Gamma_c' \oplus 5\Gamma_d'$ of T_h. Each of the 36 modes on a single site can be either in-phase or anti-phase with the modes on the nearest neighbours, for a total of 72 modes in the bcc conventional cell. However, only the anti-phase modes will cause a cell-doubling; the in-phase modes may lower the point group symmetry but the lattice structure will remain body-centred.

Next, we consider all symmetry allowed couplings between the $4f^2$ angular momentum and the lattice. The angular momentum cannot couple to the odd representations, and since $f^\dagger f$ transforms as $\Gamma_3 \otimes \Gamma_3 = \Gamma_1 \oplus \Gamma_2 \oplus \Gamma_3$ we find that only the Fe/Ru lattice distortions which can couple to the $4f^2$ Γ_3 doublet are the Γ_1 and Γ_3 modes. The Γ_1 mode is a dilatation of the cube with the eight Fe/Ru ions on each corner and is represented by the displacement vector $v = (1, 1, 1)$. v is shorthand notation for the 24-component vector of the positions for each of the eight ions. The Γ_1 mode does not lower the point group symmetry, but it does double the primitive cell and change the lattice from bcc to simple cubic (sc). The two-dimensional Γ_3 mode is represented by the vectors $v = (1, 1, -2)$ and $v = (1, -1, 0)$. Again, this is shorthand notation for the distortion of the cube with eight Fe/Ru ions on the corners into a solid rectangle. Such a distortion also changes the lattice, and lowers the point group symmetry from O_h to D_{4h} or D_{2h} respectively. Under O_h crystal field symmetry, there is only one coupling for each of the Γ_1 and Γ_3 modes, since the identity (Γ_1) only appears once in the decompositions $\Gamma_1 \otimes \Gamma_3 \otimes \Gamma_3 = \Gamma_1 \oplus \Gamma_2 \oplus \Gamma_3$ and $\Gamma_3 \otimes \Gamma_3 \otimes \Gamma_3 = \Gamma_1 \oplus \Gamma_2 \oplus 3\Gamma_3$. Under the actual symmetry T_h, Γ_2 reduces to Γ_a, and there are two couplings

for each mode instead of one.

There are more choices of coupling to the P ion displacements. There are two different Γ_a modes, represented by $v = (1,1,1)$, and each of these has two couplings to the $4f^2$ doublet. Also there are two kinds of $\Gamma_b \oplus \Gamma_c$ modes, represented by $v = (1,1,-2)$ and $v = (1,-1,0)$, which altogether have four different couplings to the $4f^2$ doublet.

Although any of the above couplings might lead to a M-I transition via coupling to the conduction electrons, there is a significantly different consequence for those distortions which lower the point group symmetry (namely the Γ_3 or $\Gamma_b \oplus \Gamma_c$ modes) compared to those which do not (the Γ_1 or Γ_a modes). When the point group symmetry is lowered by the Γ_3 or $\Gamma_b \oplus \Gamma_c$ modes, the degeneracy of the $4f^2$ doublet is lifted, and as we shall show next, the result is anti-quadrupolar ordering.

We consider first the Γ_3 or $\Gamma_a \oplus \Gamma_b$ modes. The general form of the Hamiltonian which describes the coupling between Fe/Ru ion or P ion displacements and the $4f^2$ doublet in the bcc conventional cell is

$$\begin{aligned} H &= \epsilon(f^\dagger f + f^{*\dagger} f^* + f'^\dagger f' + f^{*\dagger} f^*) \\ &\quad + \frac{1}{2}[T(f^\dagger f^* A^* - f'^\dagger f'^* A^*) + \text{h.c.}] + \frac{\omega}{2}|A|^2 \\ &\quad + \frac{B}{4}|A|^4 + \frac{C_1}{6}|A|^6 + \frac{C_2}{12}(A^6 + A^{*6}) \\ &\quad + \frac{C_3}{12}(A^6 - A^{*6}). \end{aligned} \tag{10}$$

The operators $f^\dagger$ and $f'^\dagger$ act on the two neighbouring Pr sites and correspond to the complex wavefunctions $|f\rangle = (|\Gamma_3^+\rangle - i|\Gamma_3^-\rangle)/\sqrt{2}$ and $|f^*\rangle = (|\Gamma_3^+\rangle + i|\Gamma_3^-\rangle)/\sqrt{2}$. A is the complex amplitude of the displacement $\vec{v} = \vec{v}_3 + \chi\vec{v}_2 + \chi^2\vec{v}_1$ of either eight Fe/Ru ions or 24 P ions, where $\chi = \exp\left(\frac{i2\pi}{3}\right)$ and the displacement vectors are $\vec{v}_3 = (-1,-1,2)$, $\vec{v}_2 = (-1,2,-1)$ and $\vec{v}_1 = (2,-1,-1)$. The actual displacement is then $2\text{Re}A\vec{v}$. A corresponds to the anti-phase mode as described above, therefore it changes sign under the bcc lattice translation $t = (\frac{a}{2}, \frac{a}{2}, \frac{a}{2})$, hence odd order in A terms do not appear in H. (Note that under the same translation $f \to f'$). All of the coupling constants are real, except for T, which is real in O_h, but complex in T_h (therefore, there are twice as many coupling constants under T_h, as noted above). The C_3 term is prohibited in O_h, but allowed in T_h. C_1 should be greater than C_2 and C_3 for stability.

We begin by diagonalising H with respect to f. Writing $A = ae^{i\alpha}$ and $T = te^{i\tau}$, the eigenvalues are $\epsilon \pm ta$ with eigenvectors $e^{i(-\alpha+\tau)}|f\rangle \pm |f^*\rangle$. Then the ground state projection of H is

$$H_{eff} = -ta + \frac{\omega}{2}a^2 + \frac{B}{4}a^4 + \frac{C_1}{6}a^6 + \frac{C_2}{6}a^6\cos 6\alpha + \frac{C_3}{6}a^6 \sin 6\alpha. \tag{11}$$

We will assume for the moment that $\tau = 0$ and $C_3 = 0$ (as in O_h symmetry). Then, for $C_2 < 0$, H_{eff} has minima at $\alpha = 0, \pi/3, 2\pi/3, \pi, 4\pi/3, 5\pi/3$. The corresponding displacements are proportional to $\pm(-1,-1,2)$, $\pm(-1,2,-1)$ and $\pm(2,-1,-1)$. These displacements reduce the crystal field symmetry from O_h to D_{4h}, thereby splitting the $4f^2$ doublet, so that now the ground state is non-degenerate. For example, for the $(-1,-1,2)$ displacement ($\alpha = 0$), the $4f^2$ ground state is $|\Gamma_3^-\rangle$. The $4f^2$ ground state on the neighbouring site is orthogonal to this (because of the change of sign on T), therefore the $4f^2$ ground state alternates between $|\Gamma_3^+\rangle$ and $|\Gamma_3^-\rangle$ from site to site. Since the states $|\Gamma_3^\pm\rangle$ carry opposite quadrupole moments, it follows that the ground state will have anti-quadrupolar ordering. The displacement doubles the primitive cell and changes the structure from bcc to simple orthorhombic ($\text{Im}\bar{3}$ to Pmmm).

When $C_2 > 0$, H_{eff} has minima at $\alpha = \pi/6, \pi/2, 5\pi/6, 7\pi/6, 3\pi/2, 11\pi/6$. This leads to domains with displacements of the form $\pm(1,-1,0)$, $\pm(1,0,-1)$ and $\pm(0,1,-1)$ The corresponding $4f^2$ ground states carry quadrupole moments $J_x^2 - J_y^2$ *etc.* which alternate sign from site to site in the same way as for $C_2 < 0$. The space group reduction is also the same: $\text{Im}\bar{3}$ to Pmmm.

When the coupling constant T is complex and C_3 is non-zero (as they are in general in T_h symmetry), the angle τ is non-zero and the angle α is no longer fixed. The ground state can be a mixture of $|\Gamma_3^+\rangle$ and $|\Gamma_3^-\rangle$ and the displacements are a mixture of $(2,1,1)$ and $(1,-1,0)$ modes. However, for the case when the $4f^2$ doublet is more strongly coupled to the Fe/Ru displacements, the O_h symmetry is broken only by the presence of the P ions, which interact indirectly through their contribution to the crystal field. Therefore, in this case, it may be appropriate to take the $O_h \to T_h$ symmetry lowering as a perturbative effect, and then the resulting anti-quadrupole moment should be close to the maximum value which is found under O_h symmetry.

Now we consider the Γ_1 or Γ_a modes. The Hamiltonian is

$$\begin{aligned} H &= \epsilon(f^\dagger f + f'^\dagger f' + f^{*\dagger} f^* + f'^{*\dagger} f'^*) \\ &\quad + TA(f^\dagger f - f'^\dagger f' + \text{h.c.}) + \omega A^2 \\ &\quad + \frac{B}{4}A^4 + \frac{C}{6}A^6, \end{aligned} \tag{12}$$

where A is now the operator for the displacement $v = (1,1,1)$ and all of the coupling constants are real. In this case, the $4f^2$ ground state remains degenerate and there is no lattice distortion. Therefore, in order for this type of distortion to occur, the source of the instability must be something else, such as coupling to conduction electrons, as we show in Section III.

The assumption that the doublet is the ground state of the Pr^{3+} ion is not a strict requirement. In the alternate scenario of a singlet ground state and low-lying triplet excited state, Kiss and Fazekas[25] showed how to couple the Γ_3 lattice distortion mode to the quadrupole moment of the triplet. In this case, the Hamiltonian takes the same form as in (10) except that the operator f corresponds to the wavefunction $|f\rangle = (|\Gamma_4^z\rangle + \chi|\Gamma_4^y\rangle + \chi^2|\Gamma_4^x\rangle)/\sqrt{3}$. Diagonalising H breaks the degeneracy of the triplet; the

energy of one state is lowered by TA, and another is raised by the same amount. If TA is large enough then the state $e^{i(-\alpha+\tau)}|f\rangle - |f^*\rangle$ is the ground state of the system. Note that this state carries no magnetic moment, but in general has a quadrupole moment. Anti-quadrupolar ordering follows as before.

Thus, beginning with all possible couplings between the Pr^{3+} $4f^2$ doublet and the lattice, we find that there are only two types of lattice distortions that are consistent with a cell-doubling structural phase transition. In the first case (Γ_3), the point group symmetry is lowered from T_h to D_{2h}, and the doublet is split into states carrying opposite quadrupole moment. Anti-quadrupolar ordering is a consequence of the lower point group symmetry and doubling of the primitive cell. For the second kind of cell-doubling distortion (Γ_1), the point group symmetry remains T_h, and there is no quadrupole ordering. Experimental evidence suggests that the first scenario applies to $PrFe_4P_{12}$ and while the second one applies to $PrRu_4P_{12}$.

III. BAND STRUCTURE CALCULATIONS

Band structure calculations were performed using the FLAPW-LDA+U method[26] to investigate the origin of the M-I transition in $PrRu_4P_{12}$. The LDA+U method has described the non-magnetic localized f electron system.[19]

Various Γ_1-type lattice distortions involving P ion displacements were considered. The space group is lowered from $Im\bar{3}$ to $Pm\bar{3}$ as the primitive cell is doubled. In $Im\bar{3}$, we used the observed lattice parameters, i.e. the lattice constant $a = 8.0424$Å and the internal parameters $u = 0.3576$ and $v = 0.1444$ for P positions.[27] In $Pm\bar{3}$, the positions of Ru ions are equivalent as $8i$, $(1/2+\delta_T, 1/2+\delta_T, 1/2+\delta_T)$. While the P ions occupy the inequivalent positions $12j$, $(0, u+\delta_u^A, v+\delta_v^A)$ and $12k$, $(1/2, 1/2+u+\delta_u^B, 1/2+v+\delta_v^B)$. When $\delta_T = 0$, $\delta_u^A = \delta_u^B$ and $\delta_v^A = \delta_v^B$, the space group has the higher symmetry $Im\bar{3}$ with the smaller primitive cell. The site of Pr ions is split to two sites ($1a$ (0,0,0) and $1b$ (1/2,1/2,1/2)) in $Pm\bar{3}$ due to the inequivalent surroundings. However, since the local symmetry $m\bar{3}$ for the both sites is unchanged, any kind of lifting the degeneracy of the localized $4f^2$ state is not expected in $Pm\bar{3}$. Here the singlet Γ_1 states for $4f^2$ electrons as the starting state were assumed and found after the self-consistent steps.

Although Ru ions are experimentally distorted to minimize the total energy, the position of Ru ions does not affect the Fermi surface, because the Fermi surface of $PrRu_4P_{12}$ consists of mainly P-p band. Therefore $\delta_T = 0$ is assumed in the calculations. Moreover, the anti-phase distortion of P ions are considered. Several values of the two parameters $\delta_u = \delta_u^A = -\delta_u^B$ and $\delta_v = \delta_v^A = -\delta_v^B$ with $\delta_u\delta_v < 0$ were considered in the calculations, and are listed in Table I.

Optimal results were obtained for $\delta_u = 0.003a$ and $\delta_v = -0.004a$. This distortion produced a gap across the entire Fermi surface, as shown in Fig. 1. Fig. 2 shows the density of states in the vicinity of the Fermi level both for $Pm\bar{3}$ and $Im\bar{3}$ corresponding to Fig 1.

TABLE I: The calculated band gaps Δ_E in eV with distortions. The minus sign means that the valence and conduction bands are overlapped. The asterix indicates that a self-consistent solution was not obtained.

$\delta_v \backslash \delta_u$	0.000	0.001	0.002	0.003	0.004	0.005	0.006
-0.010	0.4	–	–	–	–	–	-
-0.005	-3.2	-3.1	0.8	1.8	2.0	1.9	–
-0.004	-4.4	-2.0	-0.3	1.1	1.6	1.6	–
-0.003	-5.5	-3,2	-1.5	-0.1	1.0	1.2	–
-0.002	-6.6	-4.4	-2.6	-1.2	-0.1	0.6	–
-0.001	-7.8	-6.3	-3.8	-2.3	-1.2	*	–
0.000	–	-6.9	-4.9	-3.5	-2.4	-1.7	-1.2
0.001	-7.8	-7.5	-6.1	-4.3	-3.6	-2.8	–




FIG. 1: Insulating band structure for $PrRu_4P_{12}$ obtained with $\delta_u = 0.003a$ and $\delta_v = -0.004a$.




FIG. 2: The density of states for $PrRu_4P_{12}$ for (a) $Im\bar{3}$ and (b) $Pm\bar{3}$ with $\delta_u = 0.003a$ and $\delta_v = -0.004a$. Solid line, dotted line and dashed line indicates total, Ru-d component and P-p component, respectively. Note that there are two P-p components in (b).

IV. DISCUSSION AND SUMMARY

There are significant differences in the nature of the transition between $PrFe_4P_{12}$ and $PrRu_4P_{12}$. The M-I transition temperatures differ by an order of magnitude, with $T_{MI} = 6.7$K for $PrFe_4P_{12}$[11] versus $T_{MI} = 60$K for $PrRu_4P_{12}$[8]. In addition, T_{MI} of the Fe-compound decreases in temperature with increasing magnetic fields[24,28], while the Ru-compound shows *no* magnetic field dependence of T_{MI} (seen as a jump in the specific heat)[16], and no anomaly in the magnetic susceptibility at T_{MI}[8] either. This suggests that, in spite of the similarities in the shape of the Fermi surface and in the structural phase transition, the lattice instability may be of a quite different character between the two materials.

The observation of anti-quadrupolar ordering below T_{MI} in $PrFe_4P_{12}$ is strong evidence that the structural phase transition in $PrFe_4P_{12}$ involves lattice distortion modes which lower the point group symmetry from T_h to D_{2h} (the Γ_3 modes). Moreover, the experiments indicate that it is the Fe ions which are displaced in this mode.[13] As for $PrRu_4P_{12}$, the absence of magnetic anomalies mentioned at the beginning of this section, as well as Raman studies[29] and electron diffraction[12], indicate that the structural phase transition at T_{MI} does not change the local Pr site symmetry and is not accompanied by quadrupole ordering, hence it involves those modes which do not lower the point group symmetry (the Γ_1 modes). Our band structure calculations favour P ion displacements over Ru ion displacements since the former are shown to be a source of the M-I transition.

The low temperature upturn in the susceptibility and the magnetic field dependence of the thermal expansion and specific heat in $PrRu_4P_{12}$ at low temperatures suggest that there may be an ordering at a lower temperature. It could be due to a second structural phase transition which lowers the point group and lifts the degeneracy of the doublet, but so far there are no experimental clues about the type of deformation involved. There are two possibilities, either in-phase or anti-phase modes of the Γ_3 type distortions described in detail above. In-phase modes were excluded as a source of the M-I transition because they do not double the primitive cell. Since the cell is already doubled below the first transition, exclusion of the in-phase modes is no longer necessary. Then the space group is lowered through the sequence $Im\bar{3} \rightarrow Pm\bar{3} \rightarrow$Pmmm, but now the $4f^2$ state has quadrupolar ordering below the second transition. Only the P-ions participate in the in-phase modes, but the anti-phase modes may involve either P ions or Fe/Ru ions. The anti-phase modes lead to anti-quadrupolar ordering and lower the space group through the same sequence $Im\bar{3} \rightarrow Pm\bar{3} \rightarrow$Pmmm. Given the similarities between the transition temperatures and the magnetic field dependences of structural phase transition in $PrFe_4P_{12}$ and the proposed second transition in $PrRu_4P_{12}$, it seems more likely that the second transition in $PrRu_4P_{12}$ would be due to displacements of the Ru ions, rather than either in-phase or anti-phase modes of P ions.

To summarise, we have studied structural phase transitions coupled to localised $4f^2$ states and to band electrons in $PrFe_4P_{12}$ and $PrRu_4P_{12}$. In both cases the source of the structural instability is identified, but the mechanisms are quite different. In $PrFe_4P_{12}$, a Jahn-Teller type mechanism occurs, as coupling between Γ_3-type displacements and the $4f^2$ electrons lifts the degeneracy and lowers the energy of the ground state of the $4f^2$ electrons. The space group is reduced from $Im\bar{3}$ to Pmmm. Coupling to the band electrons removes part of the Fermi surface. In $PrRu_4P_{12}$, our bandstructure calculations show that coupling between lattice displacements and band electrons will remove the Fermi surface everywhere and produce a metal-insulator transition. The space group is lowered from $Im\bar{3}$ to $Pm\bar{3}$. This produces no change in symmetry at the Pr sites, hence no orbital ordering occurs.

Acknowledgments

S. C. was supported by the Japan Society for the Promotion of Science. We thank Y. Aoki, K. Matsuhira, C. Sekine and I. Sergienko for valuable discussions.

* Electronic address: curnoe@physics.mun.ca
[1] G. P. Meisner, Physica **108B**, 763 (1981).
[2] I. Shirotani, T. Uchiumi, K. Ohno, C. Sekine, Y. Nakazawa, K. Kanoda, S. Todo and T. Yagi, Phys. Rev. B **56**, 7866 (1997).
[3] N. Takeda and M. Ishikawa, *J. Phys. Soc. Jpn.* **69**, 868 (2000).
[4] E. D. Bauer, N. A. Frederick, P.-C. Ho, V. S. Zapf and M. B. Maple, *Phys. Rev. B* **65**, 100506 (2002).
[5] F. Grandjean, A. Gérard, D. J. Braun and W. Jeitschko, *J. Phys. Chem. Solids* **45**, 877 (1984).
[6] C. Sekine, M. Inoue, T. Inaba and I. Shirotani, *Physica B* **281&282**, 308 (2000).
[7] G. P. Meisner, M. S. Torikachvili, K. N. Yang, M. B. Maple and R. P. Guertin, J. Appl. Phys. **57**, 3073 (1985).
[8] C. Sekine, T. Uchiumi, I. Shirotani and T. Yagi, *Phys. Rev. Lett.* **79**, 3218 (1997).
[9] T. Nanba, M. Hayashi, I. Shirotani and C. Sekine, *Physica B* **259-261**, 853 (1999).
[10] M. S. Torikachvili, J. W. Chen, Y. Dalichaouch, R. P. Guertin, M. W. McElfresh, C. Rossel, M. B. Maple and G. P. Meisner, *Phys. Rev. B* **36**, 8660 (1987).
[11] H. Sato, Y. Abe, H. Okada, T. D. Matsuda, K. Abe, H. Sugawara and Y. Aoki, *Phys. Rev. B* **62**, 15125 (2000).
[12] C. H. Lee, H. Matsuhata, A. Yamamoto, T. Ohta, H. Takazawa, K. Ueno, C. Sekine, I. Shirotani and T. Hirayama, *J. Phys.: Condens. Matter* **13**, L45 (2001).
[13] K. Iwasa, Y. Watanabe, K. Kuwahara, M. Kohgi, H. Sugawara, T. D. Matsuda, Y. Aoki and H. Sato, *Physica B* **312-313**, 834 (2002).
[14] L. Keller, P. Fischer, T. Herrmannsdörfer, A. Dönni, H. Sugawara, T. D. Matsuda, K. Abe, Y. Aoki and H. Sato, *J. Alloys and Compounds* **323-324**, 516-519 (2001).
[15] L. Hao, K. Iwasa, M. Nakajima, D. Kawana, K. Kuwahara, M. Kohgi, H. Sugawara, T.D. Matsuda, Y. Aoki, H. Sato, *Acta Phyica Polonica B***34**, 1113 (2003).
[16] C. Sekine, T. Inaba, I. Shirotani, M. Yokoyama, H. Amitsuka and T. Sakakibara, *Physica B* **281&282**, 303 (2000).
[17] K. Matsuhira, T. Takikawa, T. Sakakibara, C. Sekine and I. Shirotani, *Physica B*, **281 & 282**, 298 (2000).
[18] H. Sugawara, Y. Abe, Y. Aoki, H. Sato, M. Hedo, R. Settai, Y. Onuki and H. Harima, *J. Phys. Soc. Jpn.* **69**, 2938 (2000).
[19] H. Harima and K. Takegahara, *Physica B* **312-313**, 843 (2002).
[20] T. D. Matsuda, K. Abe, F. Watanuki, H. Sugawara, Y. Aoki, H. Sato, Y. Inada, R. Settai and Y. Onuki, *Physica B* **312-313**, 832 (2002).
[21] K. Matsuhira, Y. Hinatsu, C. Sekine, T. Togashi, H. Maki, I. Shirotani, H. Kitazawa, T. Takamasu and G. Kido, *J. Phys. Soc. Jpn. Suppl.* **71**, 237 (2002).
[22] Some preliminary results related to this article have appeared in conference proceedings: S. H. Curnoe, H. Harima, K. Takegahara and K. Ueda, *Physica B* **312-313**, 837 (2002); S. H. Curnoe, K. Ueda, H. Harima and K. Takegahara, *J. Phys. Chem. Sol.* **63**, 1207 (2002); H. Harima, K. Takegahara, S. H. Curnoe and K. Ueda, *J. Phys. Soc. Jpn. Suppl.* **71**, 70-73 (2002); H. Harima, K. Takegahara, K. Ueda and S. H. Curnoe, *Acta Physica Polonica B***34**, 1189 (2003).
[23] C. H. Lee, H. Oyanagi, C. Sekine, I. Shirotani and M. Ishii, *Phys. Rev. B* **60**, 13253 (1999).
[24] Y. Aoki, T. Namiki, T. D. Matsuda, K. Abe, H. Sugawara and H. Sato, *Phys. Rev. B* **65**, 064446 (2002).
[25] A. Kiss and P. Fazekas, *J. Phys.: Condens. Matter* **15**, S2109 (2003).
[26] H. Harima, *J. Magn. Magn. Mater.* **226-230**, 83 (2001).
[27] C. Sekine, private communications.
[28] T. D. Matsuda, H. Okada, H. Sugawara, Y. Aoki, H. Sato, A. V. Andreev, Y. Shiokawa, V. Sechovsky, T. Honma, E. Yamamoto and Y. Onuki, *Physica B* **281&282**, 220 (2000).
[29] C. Sekine, H. Saito, A. Sakai and I. Shirotani, *Solid State Commun.* **109**, 449 (1999).