arXiv:cond-mat/0405495v1 [cond-mat.supr-con] 20 May 2004

Anisotropy and internal field distribution of MgB_2 in the mixed state at low temperatures

M. Angst,[1,2,*] D. Di Castro,[1] D. G. Eshchenko,[1,3] R. Khasanov,[3,4,1] S. Kohout,[1] I. M. Savic,[5] A. Shengelaya,[1] S. L. Bud'ko,[2] P. C. Canfield,[2] J. Jun,[6] J. Karpinski,[6] S. M. Kazakov,[6] R. A. Ribeiro,[2] and H. Keller[1]

[1] *Physik-Institut der Universität Zürich, CH-8057 Zürich, Switzerland*
[2] *Ames Laboratory and Department of Physics and Astronomy, Iowa State University,Ames,IA 50011,USA*
[3] *Paul Scherrer Institute, CH-5232 Villigen PSI, Switzerland*
[4] *DPMC, Université de Genève, 24 Quai Ernest-Ansermet, CH-1211 Genève, Switzerland*
[5] *Faculty of Physics, University of Belgrade, 11001 Belgrade, Yugoslavia*
[6] *Solid State Physics Laboratory, ETH, CH-8093 Zürich, Switzerland*

(Dated: March 22, 2022)

Magnetization and muon spin relaxation on MgB_2 were measured as a function of field at 2 K. Both indicate an inverse-squared penetration depth strongly decreasing with increasing field H below about 1 T. Magnetization also suggests the anisotropy of the penetration depth to increase with increasing H, interpolating between a low H_{c1} and a high H_{c2} anisotropy. Torque vs angle measurements are in agreement with this finding, while also ruling out drastic differences between the mixed state anisotropies of the two basic length scales penetration depth and coherence length.

PACS numbers: 74.25.Op, 74.20.De, 74.25.Ha, 74.70.Ad

The understanding of the physical properties of the recently discovered 39 K superconductor[1] MgB_2 has made rapid progress in the last 3 years.[2] A central issue of research has been the involvement in superconductivity of two sets of bands with different dimensionality and pairing strength.[3,4,5] This "two-band superconductivity" leads to an array of unusual superconducting properties such as specific heat,[4] particularly also to a very unusual behavior of the superconducting anisotropies.[6]

For example, a pronounced temperature T dependence of the anisotropy γ_H of the upper critical field H_{c2}, directly related to the coherence length ξ, was observed[7,8] and calculated based on the two-band model.[9,10] Strikingly, calculations of the low field penetration depth anisotropy γ_λ, predicted a much lower anisotropy of this quantity, with a T dependence opposite to the one of H_{c2}.[11] This was experimentally confirmed as well, based on measurements, e.g., of H_{c1},[12,13] by small angle neutron scattering (SANS)[14,15] and scanning tunneling spectroscopy (STS).[16] However, e.g. the experiment of Ref. 15 indicates that whereas in the limit of very low fields H γ_λ is indeed close to 1, it is rising with increasing H, as deduced earlier more indirectly.[7]

The behavior of the anisotropies of the length scales in the mixed state $H_{c1} < H < H_{c2}$ still needs to be clarified. One point of view[17] surmises constant (with respect to H) anisotropies of the penetration depth γ_λ and the coherence length γ_H, which are, however, different from each other. This difference was predicted to lead to a sign reversal in the angle dependent torque.[17] Another point of view is that these anisotropies are not drastically different from each other, but both increase with increasing field, interpolating from the H_{c1} anisotropy in low fields to the H_{c2} anisotropy in high fields.[18]

Here, we support the latter point of view by analyzing SQUID (superconducting quantum interference device) and torque magnetization data measured on a MgB_2 single crystal with very low pinning, and muon spin relaxation (μSR) data measured on randomly aligned MgB_2 powder. In the absence of a more elaborate model of the mixed state of a two-band superconductor,[18] we base the analysis on the London model, allowing however for a H dependent penetration depth, which is obtained from the H or angle θ dependence of the bulk magnetization (SQUID/torque) as well as from the average variation of the internal field (μSR). From SQUID and μSR we find a rapid decrease of the inverse-squared penetration depth $1/\lambda^2$ ("superfluid density") with $\mu_\circ H$ increasing below about 1 T, and SQUID and torque data agree on the anisotropy γ_λ increasing strongly with H. The analysis of the torque data further suggests that γ_H is not very different from γ_λ.

Single crystals of MgB_2 were grown with a high pressure cubic anvil technique,[19] and a crystal with particularly low pinning was selected for measurements with a Quantum Design MPMS-XL SQUID magnetometer and a noncommercial torque magnetometer.[20] The crystal has a wedge shape, with one of the faces parallel to the ab planes. The μSR experiment on poly-crystalline MgB_2 was similar to the one of Ref. 21.

The magnetization of the single crystal was measured as a function of H; as can be seen in Fig. 1, the irreversibility is very low above about 0.15 T. Larger irreversibility in lower fields may be due to geometrical barriers, which is why we did not attempt to directly extract H_{c1}. The curves shown are not corrected for demagnetizing effects (the exact demagnetizing factor is difficult to estimate due to the sample shape), but we verified that any reasonable demagnetization correction does not noticeably affect above 0.2 T the results discussed below.

Within the London model of a standard superconductor, the magnetization is proportional to the logarithm of the applied field, not too close to either H_{c1} or H_{c2}. Keeping to an analysis within the London approach,




FIG. 1: Magnetization M vs field $\mu_\circ H$ at 2 K on a MgB_2 single crystal with $H\|c$ and $H\|ab$.




FIG. 2: Comparison of $1/\lambda^2$ vs H obtained from $\mathrm{d}M/\mathrm{d}\ln H$ of Fig. 1, and from the muon spin depolarization rate measured on unaligned powder (circles). The shaded box indicates fields close to or lower than H_{c1} (see text).

but dropping the requirement of a constant penetration depth λ, we have $1/\lambda^2 \propto \mathrm{d}M_{\mathrm{rev}}/\mathrm{d}\ln H$. The so obtained $1/\lambda^2$ is plotted in Fig. 2. To avoid overloading the graph, only curves assuming $M_{\mathrm{rev}} = (M_{H\uparrow} + M_{H\downarrow})/2$ are shown; except in the lowest H using instead $M_{H\uparrow}$ or $M_{H\downarrow}$ leads to very similar results. The curves for both H directions were normalized by the same constant factor. The shaded box indicates the low H region, where we are uncertain about the obtained penetration depth because of i) irreversibility, ii) demagnetizing effects, and iii) deviations from the London model due to the vicinity of H_{c1} (see below).

Also plotted in Fig. 2 is $1/\lambda^2$ obtained from the muon spin depolarization rate σ measured on randomly aligned powder at the same temperature. The depolarization rate σ is a measure of the average variation of the internal field within a superconductor, and in the mixed state (again not too close to one of the critical fields) is directly proportional to $1/\lambda^2$, since λ is the fundamental length scale of the variation of the field in a superconductor (cf. Ref. 21). An issue to be aware of when deducing λ in this way is the possible influence of pinning, which can lead to an extrinsic increase in σ. In a previous μSR experiment on MgB_2, the whole H dependence of σ was indeed ascribed to pinning.[22] To check for the possible influence of pinning on σ (as opposed to the magnetization), we performed time-dependent measurements of σ in several fields: After reaching 2 K (field cooled), statistics was gathered for 10 min, then stopped and restarted (repeated 5 to 10 times). Except for 0.1 T, changes of σ with time are well below error bars, and no clear trend discernible. This suggests that for higher H even at 2 K, pinning is not influencing σ much, and the H dependence of σ indeed intrinsic. That we observed a very similar H dependence of σ in samples from two sources synthesized slightly different supports this; an intrinsic $\sigma(H)$ dependence was also proposed in Ref. 23.

Concerning the $\mathrm{d}M/\mathrm{d}(\ln H)$ curves, it may be argued that the low field behavior is not unexpected even for a normal superconductor, since in the limit $H \to H_{c1}$ it is expected[24] $\mathrm{d}M/\mathrm{d}(\ln H) \propto H/(H - H_{c1})$. However, $\mathrm{d}M/\mathrm{d}(\ln H)$ should reach values close to the normal London slope rather quickly (within $2-3\,H_{c1}$) and the variation presented in Fig. 2 is spread over a considerably larger field range. Furthermore, the influence of the vicinity of H_{c1} on σ is opposite. The close similarity of the H dependence of the penetration depth obtained from rather different quantities (bulk magnetization from SQUID and internal field variation from μSR) strongly suggests that all curves in Fig. 2 indeed show the $\lambda(H)$ dependence, outside of the shaded box indicating vicinity of H_{c1}. A similar strong depression of $1/\lambda^2$ with H was deduced previously (for $H\|c$) from an analysis of SANS form factors.[15] The SQUID curves additionally indicate that above 10 kOe $1/\lambda^2$ no longer varies strongly.

The SQUID measurements in the two field configurations also yield the anisotropy of λ. For $H\|c$ the screening currents flow within the ab plane, giving $1/\lambda_{ab}^2$. For $H\|ab$ the currents flow also perpendicular to the planes, giving $1/(\lambda_{ab}\lambda_c)$. The ratio of the $\mathrm{d}M/\mathrm{d}\ln H$ curves for the two field configurations thus corresponds to γ_λ. Considering the curves in Fig. 2, we can see that i) in low H the anisotropy is very small, ii) in high H γ_λ is of the order of about 6 or even 7, and iii) the variation with H of γ_λ is most pronounced in low H. We stress the fact that when considering the high field region alone the standard London model with constant λ and ξ and a constant common anisotropy γ describes the data reasonably well. This indicates that at low T in high H MgB_2 is close to a "standard superconductor" with high anisotropy. Corresponding to this is the absence of an unusual $H_{c2}(\theta)$ dependence at low T, in contrast to the situation closer to T_c[10,25,26] [of course the γ_λ analysis breaks down as $\mu_\circ H \to \mu_\circ H_{c2}^{\|c}$ ($\simeq 2.8$ T for this crystal)].

An alternative method to determine the penetration depth anisotropy is to analyze the angular θ dependence of the torque τ in fixed H. We previously used this method at much higher T, finding also indications of an anisotropy increasing with H.[7] However, thermal fluc-




FIG. 3: Angle θ dependence of torque τ in 0.2 T at 8 K (symbols). Dashed line: theoretical description[17] assuming $\gamma_\lambda \ll \gamma_H$; full line: description with $\gamma_\lambda = \gamma_H$.




FIG. 4: Anisotropy determined from an analysis of the torque data (Fig. 3) with Eq. (18) of Ref. 17, at various low temperatures, as a function of field H. Also shown is the anisotropy determined from Fig. 2 (○) and the anisotropy very close to T_c (dotted line, see text).

tuations and additional intermixture of the two sets of bands by thermally excited quasiparticles, complicate the analysis there. To provide a direct comparison with the SQUID results and give a quantitative estimate of γ_λ we measured $\tau(\theta)$ at low temperature.

Due to increased irreversibility at lower T, it is important not only to use a crystal with low pinning, but also employ the "shaking technique" developed by Willemin *et al.*[27] Since the magnetometer equipped with this technique cannot reach 2 K measurements were conducted at 8, 11 and 15 K. These temperatures should be low enough to avoid too strong an influence of thermal fluctuations/excitations, as well as to probe the low temperature limit of the calculated[9,11] anisotropies.

The data were analyzed with Eq. (18) of Ref. 17, allowing for a difference in the anisotropies of the penetration depth and the coherence length. Such a difference was, however, not found in any of the curves analyzed, and a sign reversal of the torque, a key prediction of Ref. 17 for $\gamma_\lambda \ll \gamma_H$, was never observed [for an example see Fig. 3]. A preliminary report on this issue is given in Ref. 25. The best descriptions with Eq. (18) of Ref. 17 of the data were rather achieved for $\gamma_\lambda \approx \gamma_H$. The large number of parameters involved and the numerical condition of the fit formula result in extended error bars though, so that *small* differences between γ_λ and γ_H cannot be completely ruled out (but large differences[17] as calculated with H independent anisotropies *can*).

The resulting field dependence of the anisotropy $\gamma \equiv \gamma_\lambda \approx \gamma_H$ is shown in Fig. 4. The anisotropy is monotonically increasing with increasing field, up to 1.5 T (the maximum attainable by the magnetometer used). In the lowest fields, this rise seems to be much steeper than above 0.5 T. However, as a cautionary note, even with "shaking", the irreversibility cannot be said to be negligible below 0.1 T and it should also be kept in mind that we are approaching H_{c1} (see Fig. 1).

A report by another group of torque vs angle measurements performed at 10 K claimed a field-independent anisotropy of the order of $\gamma \simeq 4.3$.[28] However, analyzing the same data, a different conclusion of an anisotropy that *does* increase with H, in not too large fields, may also be reached.[29] The results of Ref. 28, as well as Ref. 30 (not finding a field-dependence as well) may be reconciled with the ones of Ref. 7 and the present results by assuming a tendency of γ to saturate in higher fields.

For comparison, a rough estimate of $\gamma(H)$ from SQUID magnetometry in fields along the principal axes [Fig. 2] is plotted in Fig. 4 as well. Qualitatively ($\gamma(H)$ being an increasing function) this is consistent with the torque results. We attribute the numerical discrepancy to the large scattering as visible in Fig. 2 and the corresponding uncertainty in the estimation of γ. The low T behavior of $\gamma(H)$ is in strong contrast to the one very close to T_c, where between H_{c1} and H_{c2} $\gamma \simeq 2$ is constant,[31] as indicated by the dotted line in Fig. 4.

A field dependent anisotropy at low T (2 K) had been deduced based on different experiments as well. Bouquet *et al.*[32] reported a H dependent effective anisotropy based on specific heat measurements. Since these are sensitive mainly to the coherence length, the experiment suggests the anisotropy γ_H to be H dependent. Cubitt *et al.*[15] observed the anisotropy of the vortex lattice γ_{VL} to increase strongly with increasing H, from less than 1.5 in 0.2 T to about 3.8 in 0.5 T, $\gamma_{VL}(H)$ being more steep in higher H. Keeping to the London model, the anisotropy of the vortex lattice should be equal to the penetration depth anisotropy γ_λ.[33] Our results extend to higher H and agree qualitatively with those of Cubitt *et al.*, but we do not find a particularly steep $\gamma(H)$ around 0.5 T, but rather a slower field dependence. Very recently, Lyard *et al.*[12] proposed a similar H dependence of anisotropies, based on a London analysis of magnetization data measured at much higher T.

The strong field dependence at low T of all anisotropies obtained from the measurements presented here, as well as by other groups, are readily explained qualitatively by

a faster suppression with H of superconductivity in the more isotropic π bands, increasing the relative contribution of the highly anisotropic σ bands. Such a suppression, consistent with the overall decrease of $1/\lambda^2$ (Fig. 2), was also observed, e.g., by spectroscopic means,[5] and is not unexpected due to the smaller gap in the π bands. Corresponding larger vortex cores and a lower "H_{c2}^{π}" have been conjectured from STS and specific heat measurements.[32,34] If π and σ bands were independent, a real upper critical field $\mu_\circ H_{c2}^{\pi} \approx 0.5\,\mathrm{T}$ would mark the destruction of superconductivity in the π bands due to vortex core overlap. Since, however, the bands are coupled together even at zero T, "H_{c2}^{π}" degenerates into a broad crossover (completely blurred for $T \to T_c$). Our results indicate that this crossover region is very broad, extending down to almost zero field. In high H superconductivity in the π bands is still induced from the σ bands likely up to the bulk H_{c2}, but with a much depressed order parameter. It should be noted that within this picture, there would in principle be two different coherence lengths to consider,[23] and that in the H region of interest, the vortex cores in the π band overlap[34] enough to seriously question the applicability of a London analysis. This may explain the remaining discrepancies between the anisotropies obtained from different measurements and calls for further theoretical work, although in a qualitative way the London analysis works out remarkably well, particularly in high H at low T, in terms of a "standard anisotropic" σ band only superconductor.

In conclusion, μSR and magnetization data show the "superfluid density" $1/\lambda^2$ in MgB_2 at 2 K to strongly decrease with increasing field below about 1 T. In parallel, the penetration depth anisotropy increases, and is not drastically smaller than the coherence length anisotropy (in the same field). This behavior is due to the fast suppression of the contribution to superconductivity of the more isotropic π bands with weaker superconductivity.

Work partly performed at the Swiss Muon Source (SμS) at the Paul Scherrer Institute (Villigen, Switzerland). We thank D. Herlach and A. Amato for technical assistance during the μSR experiments and V. G. Kogan and A. Gurevich for discussions. This work was supported by the Swiss National Science Foundation (SNSF) and by the NCCR program MaNEP sponsored by the SNSF. Ames Lab is operated for the U.S. Department of Energy by Iowa State Univ. under Contract W-7405-Eng-82. The work at Ames was supported by the Director of Energy Research, Office of Basic Energy Sciences.

* Email: angst@ameslab.gov

1. J. Nagamatsu, N. Nakagawa, T. Muranaka, Y. Zenitani, and J. Akimitsu, Nature **410**, 63 (2001).
2. P. C. Canfield and S. L. Bud'ko, Physics World **15**, 29 (2002).
3. A. Y. Liu, I. I. Mazin, and J. Kortus, Phys. Rev. Lett. **87**, 087005 (2001); H. J. Choi, D. Roundy, H. Sun, M. L. Cohen, and S. G. Louie, Nature **418**, 758 (2002).
4. See, e.g., F. Bouquet, R. A. Fisher, N. E. Phillips, D. G. Hinks, and J. D. Jorgensen, Phys. Rev. Lett. **87**, 047001 (2001).
5. See, e.g., R. S. Gonnelli *et al.*, Phys. Rev. Lett. **89**, 247004 (2002).
6. M. Angst and R. Puzniak, in *Focus on Superconductivity Research 2003*, B. P. Martines (Ed.) (Nova Publishers, New York, 2004), pp. 1−49; cond-mat/0305048.
7. M. Angst *et al.*, Phys. Rev. Lett. **88**, 167004 (2002).
8. See, e.g., A. V. Sologubenko, J. Jun, S. M. Kazakov, J. Karpinski, and H. R. Ott, Phys. Rev. B **65**, 180505(R) (2002); S. L. Bud'ko and P. C. Canfield, *ibid.* **65**, 212501 (2002); Y. Eltsev *et al.*, *ibid.* **65**, 140501(R) (2002); L. Lyard *et al.*, *ibid.* **66**, 180502(R) (2002).
9. P. Miranović, K. Machida, and V. G. Kogan, J. Phys. Soc. Jpn. **72**, 221 (2003); T. Dahm and N. Schopohl, Phys. Rev. Lett. **91**, 017001 (2003); A. Gurevich, Phys. Rev. B **67**, 184515 (2003).
10. A. A. Golubov and A. E. Koshelev, Phys. Rev. B **68**, 104503 (2003).
11. V. G. Kogan, Phys. Rev. B **66**, 020509 (2002); A. A. Golubov, A. Brinkman, O. V. Dolgov, J. Kortus, and O. Jepsen, *ibid.* **66**, 054524 (2002).
12. L. Lyard *et al.*, Phys. Rev. Lett. **92**, 057001 (2004).
13. H.-J. Kim *et al.*, cond-mat/0403198.
14. R. Cubitt, S. Levett, S. L. Bud'ko, N. E. Anderson, and P. C. Canfield, Phys. Rev. Lett. **90**, 157002 (2003).
15. R. Cubitt *et al.*, Phys. Rev. Lett. **91**, 047002 (2003).
16. M. R. Eskildsen *et al.*, Phys. Rev. B **68**, 100508(R) (2003).
17. V. G. Kogan, Phys. Rev. Lett. **89**, 237005 (2002).
18. We should note at this point that, due to the two-band nature of MgB_2, in any case we are dealing with effective length scales, derived from the natural length scales within the σ and the π bands according to the relative contributions of the two sets of bands. An analysis of μSR data more directly related to different intrinsic σ and π length scales was recently proposed in Ref. 23.
19. J. Karpinski *et al.*, Supercond. Sci. Technol. **16**, 221 (2003).
20. M. Willemin *et al.*, J. Appl. Phys. **83**, 1163 (1998).
21. D. Di Castro *et al.*, cond-mat/0307330v2.
22. C. Niedermayer, C. Bernhard, T. Holden, R. K. Kremer, and K. Ahn, Phys. Rev. B **65**, 094512 (2002).
23. S. Serventi *et al.*, cond-mat/0401454.
24. A. L. Fetter and P. C. Hohenberg, in *Superconductivity*, edited by R. D. Parks (Marcel Dekker inc., New York, 1969), p. 838.
25. M. Angst *et al.*, cond-mat/0304400.
26. A. Rydh *et al.*, cond-mat/0308319.
27. M. Willemin *et al.*, Phys. Rev. B **58**, R5940 (1998).
28. K. Takahashi *et al.*, Phys. Rev. B **66**, 012501 (2002).
29. M. Angst *et al.*, cond-mat/0206407.
30. M. Zehetmayer *et al.*, Phys. Rev. B **66**, 052505 (2002).
31. S. Kohout, unpublished. See also Ref. 25.
32. F. Bouquet *et al.*, Phys. Rev. Lett. **89**, 257001 (2002).
33. L. J. Campbell, M. M. Doria, and V. G. Kogan, Phys. Rev. B **38**, 2439 (1988).
34. M. R. Eskildsen *et al.*, Phys. Rev. Lett. **89**, 187003 (2002).