

ARPES kink is a "smoking gun" for the theory of high- T_c superconductors: dominance of the electron-phonon interaction with forward scattering peak

¹M. L. Kulić and ²O. V. Dolgov

¹Johann Wolfgang Goethe-Universität Frankfurt am Main,

Theoretische Physik, Robert-Mayer-Str.8, 60054 Frankfurt/Main, Germany

²Max-Planck-Institut für Festkörperlphysik, Heisenbergstr.1, 70569 Stuttgart, Germany

(dated: March 22, 2024)

The ARPES spectra in high- T_c superconductors (HTSC) show four distinctive features in the quasiparticle self-energy $\Sigma(k; \omega)$. All of them can be explained consistently by the theory in which the electron-phonon interaction (EPI) with the forward scattering peak (FSP) dominates over the Coulomb scattering. In particular, this theory explains why there is no shift of the nodal kink at 70 meV in the superconducting state, contrary to the clear shift of the anti-nodal singularity at 40 meV. The theory predicts a "knee"-like structure of $\text{Im} \Sigma(\omega) \mp \text{Im} \Sigma_{ph}(\omega) + \text{Im} \Sigma^C(\omega)$ which is phonon dominated, $\text{Im} \Sigma(\omega_{ph}) \mp \text{Im} \Sigma_{ph}(\omega_{ph}) \mp \text{Im} \Sigma^C(\omega_{ph}) = 2$, for $\omega_{ph} = \omega_{ph}^{(70)}$, and shows linear behavior $\text{Im} \Sigma(\omega) \mp \text{Im} \Sigma_{ph}(\omega_{ph}) \mp \text{Im} \Sigma^C(\omega_{ph}) = 2$ for $\omega > \omega_{ph}^{(70)}$ - due to the Coulomb scattering. ARPES spectra give $\gamma_{ph} > 1$ - which is obtained from $\text{Re} \Sigma$, and $\gamma_C < 0.4$ - obtained from $\text{Im} \Sigma$, i.e. $\gamma_{ph} > \gamma_C$. The dip-hump structure in the spectral function $A(k_F; \omega)$ comes out naturally from the proposed theory.

PACS numbers:

Introduction - The pairing mechanism in high-temperature superconductors (HTSC) is under intensive debate [1], [2]. In that respect ARPES experiments play a central role for theory, since they give information on the quasiparticle spectrum, lifetime effects and indirectly the pairing potential. Recent ARPES experiments on various HTSC families, such as $\text{La}_{2-x}\text{Sr}_x\text{CuO}_4$ and Bi_2SeO [3], [4], [5], [6], show four distinctive features in the quasiparticle self-energy $\Sigma(k; \omega)$: (I) There is a kink in the normal state quasiparticle spectrum, $\Sigma(k)$, in the nodal direction $(0;0)$ (k) at the energy $\omega_{\text{kink}}^{(70)} \approx 70$ meV, which is a characteristic oxygen vibration energy $\omega_{ph}^{(70)}$. However, the kink is not shifted in the superconducting state, contrary to the prediction of the standard Eliashberg theory [7]. The latter contains integration over the whole Fermi surface and over the energy giving that singularities in $\Sigma(k)$ (along all directions) must be shifted in the superconducting state by the maximal gap value Δ_0 ; (II) In the anti-nodal region, near $(\pi;0)$ (or $(0;\pi)$), there is a singularity in $\Sigma(k)$ in the normal state at $\omega_{\text{sing}}^{(40)} \approx 40$ meV - which is also a characteristic oxygen vibration energy $\omega_{ph}^{(40)}$. This singularity is shifted in the superconducting state (at $T \ll T_c$) to $\omega_{\text{sing}}^{(40)} \approx 60$ meV ($= \omega_{ph}^{(40)} + \Delta_0$), where $\Delta_0 \approx 20$ meV) is the maximal superconducting gap at the anti-nodal point. The experimental slopes of $\text{Re} \Sigma(k; \omega)$ at the kink (and singularity) give the EPI coupling constant $\gamma_{ph} > 1$. The different shifts of $\omega_{\text{kink}}^{(70)}$ and $\omega_{\text{sing}}^{(40)}$ in the superconducting state we call the ARPES non-shift puzzle; (III) There is a "knee"-like structure of $\text{Im} \Sigma(\omega) \mp \text{Im} \Sigma_{ph}(\omega) + \text{Im} \Sigma^C(\omega)$ which is phonon dominated $\text{Im} \Sigma(\omega) \mp \text{Im} \Sigma_{ph}(\omega_{ph}) \mp \text{Im} \Sigma^C(\omega_{ph}) = 2$ with $\gamma_{ph} > 1$ (obtained from $\text{Re} \Sigma$) for $\omega = \omega_{ph}^{(70)}$, and for $\omega > \omega_{ph}^{(70)}$ there is a pronounced linear behavior of

$\text{Im} \Sigma(\omega) \mp \text{Im} \Sigma_{ph}(\omega_{ph}) \mp \text{Im} \Sigma^C(\omega_{ph}) = 2$ and $\gamma_C < 0.4$ (obtained from $\text{Im} \Sigma$) - due to the Coulomb scattering. It turns out that $\gamma_{ph} > \gamma_C$; (IV) There is a dip-hump structure in the spectral function $A(k_F; \omega)$ with the quasiparticle peak sharpening in the superconducting state near the anti-nodal point.

Before explaining these distinctive features by the phonon-type theory we stress, that the ARPES spectra especially the non-shift puzzle and "knee"-like structure, can not be explained by the spin-fluctuation interaction (SFI) due to the following reasons: (i) the intensity of the SFI spectrum ($\text{Im} \Sigma(Q; \omega)$) - the spin susceptibility at $Q = (\pi; \pi)$, although pronounced in slightly underdoped materials, is strongly suppressed (even below the experimental resolution) in the normal state of the optimally doped HTSC oxides [10], although their critical temperatures differ only slightly ($T_c \approx 1$ K!). Such a huge reconstruction of the SFI spectrum around the optimal doping but with small effect on T_c gives strong evidence for the ineffectiveness of the SFI in pairing. (ii) The SFI theory [8] assumes unrealistically large coupling $g_{sf} \approx 0.65$ eV, (with the coupling constant $\lambda_{sf} \approx 2.5$), while the ARPES [3], [4], [6], resistivity [1] and magnetic [9] measurements give much smaller $g_{sf} \approx 0.1$ eV, i.e. $\lambda_{sf} < 0.2 < \gamma_C \approx 0.4$. Such a small λ_{sf} gives small T_c ; (iii) if the kink at 70 meV in the normal state would be due to the magnetic spectrum, then it would be strongly rearranged in the superconducting state, contrary to the ARPES results. On the other hand, the phonon energies are only slightly ($\approx 5\%$) changed in the superconducting state; (iv) the magnetic resonance mode at 41 meV, which appears only in the superconducting state [8], can not cause the kink, since the latter is present in $\text{La}_{2-x}\text{Sr}_x\text{CuO}_4$, where there is no magnetic resonance mode at all [3]; (v) The non-shift puzzle and "knee"-like structure of the ARPES spectra are related

to phonon features, which definitely disqualify the SFI and favor the electron-phonon interaction (EPI) as the pairing mechanism. The four distinctive features in the ARPES spectra can be explained by the theory in which the electron-phonon interaction (EPI) with the forward scattering peak (FSP) dominates over the Coulomb interaction – the EPI-FSP model.

The EPI-FSP model – The central question for the EPI theory is – why is the anti-nodal singularity $\epsilon_{\text{sing}}^{(40)}$ shifted in the superconducting state, but the nodal kink $\epsilon_{\text{kink}}^{(70)}$ is not? We show that in order to solve the ARPES non-shift puzzle one should go, as it is said before, beyond the standard Eliashberg theory for the EPI [7]. To remind the reader, the standard Eliashberg theory implies that $\epsilon_{\text{sing}}^{(40)}$ and $\epsilon_{\text{kink}}^{(70)}$ should be shifted in the superconducting state to $\epsilon_{\text{sing}}^{(40)} = \epsilon_{\text{ph}}^{(40)} + \epsilon_0$ and $\epsilon_{\text{kink}}^{(70)} = \epsilon_{\text{ph}}^{(70)} + \epsilon_0$, respectively. Here we show that the ARPES non-shift puzzle can be explained by the EPI-FSP model which contains the following basic ingredients: (1) The EPI is dominant in HTSC and its spectral function $^2F(k; k^0; \omega)$, which enters the Eliashberg equations below, has a pronounced FSP at $k = k^0$, due to strong correlations. Its width is very narrow $\Delta k = k^0 \pm k_F$ even for overdoped systems [11], [1]. Near the Fermi surface one expects that $^2_{\text{ph}}F(k; k^0; \omega) \approx ^2_{\text{ph}}F(\omega; \omega^0; \omega)$ [13], and in strongly correlated systems one has $^2_{\text{ph}}F(\omega; \omega^0; \omega) \approx \frac{2}{c}(\omega - \omega^0)$, where the charge vertex $c(\omega - \omega^0)$ is strongly peaked at $\omega - \omega^0 = 0$ with the width ω_w [11], [1]. Thereby, one can put in leading order $^2_{\text{ph}}F(\omega; \omega^0; \omega) \approx ^2_{\text{ph}}F(\omega; \omega) (\omega - \omega^0)$, which picks up the main physics whenever $\omega_w \ll \omega$ [1]. The EPI-FSP model, which results from the tight-j model with the electron-phonon interaction [11], [1] predicts the following important results: (a) the strength of pairing is due to the EPI, while the residual Coulomb interaction (including spin fluctuations) triggers the pairing to d-wave one; (b) the transport coupling constant κ_{tr} entering the resistivity, $\rho \propto \kappa_{\text{tr}} T$ is much smaller than the pairing one κ_{ph} , i.e. $\kappa_{\text{tr}} < \kappa_{\text{ph}} = 3$. We stress that the FSP in the EPI of strongly correlated systems is a general effect by a direct electronic coupling to all phonons. This is an important result, since for some phonons (for instance the half-breathing modes of O ions) the bare coupling constant $g_0^2(q)$ is peaked at large $q \approx 2k_F$ and therefore detrimental for d-wave pairing, while the one renormalized by strong correlations $g_{\text{ren}}^2(q) = g_0^2(q) \frac{2}{c}(q)$ is peaked at much smaller q , thus contributing constructively to d-wave pairing. The Monte Carlo calculations on the Hubbard model with the EPI and finite repulsion [12], confirm the existence of the FSP in the EPI – previously found analytically in [11]; (2) the dynamical part (beyond the Hartree-Fock) of the Coulomb interaction is characterized by the spectral function $S_C(k; k^0; \omega)$. The ARPES non-shift puzzle implies that S_C is either peaked at small transfer momenta $\Delta k = k^0 \pm k_F$, or it is so small that the shift is weakly affected and below the ex-

perimental resolution of ARPES. Since the ARPES data give also that the Coulomb coupling constant $c < 0.4$ is much smaller than $\kappa_{\text{ph}} > 1$, then the kink is practically insensitive to the k -dependence of S_C . Due to simplicity we assume the former case – see also discussion after Eq.(4); (3) The scattering potential due to non-magnetic impurities has pronounced forward scattering peak – due to strong correlations [11], [1], thus making d-wave pairing robust in the presence of impurities – see more below.

Eliashberg equations for the EPI-FSP model – The Matsubara Green's function is defined by $G(k) = G(k; i\omega_n)$

$$G_k = \frac{1}{i\omega_k - \epsilon_k} = \frac{i\epsilon_k + \frac{k}{k}}{\epsilon_k^2 + \frac{k^2}{k} + \tilde{\epsilon}_k^2}; \quad (1)$$

where ϵ_k , ϵ_k and $\tilde{\epsilon}_k$ are the bare quasiparticle energy, renormalized frequency and gap, respectively [13]. The 2D Fermi surface of HTSC is parameterized by $k = (k_F + k_\perp; k_F')$, where k_F (k_F') is the Fermi momentum and k_F' is the tangent to the Fermi surface [13]. In that case $k_\perp = \epsilon_k - \epsilon_F$ and $d^2k = d\epsilon_k d\epsilon_F' = \epsilon_F' d\epsilon_F' = \epsilon_F' d\epsilon_F'$. After the integration the Eliashberg equations in the FSP model read

$$\epsilon_{n,\omega'} = \epsilon_n + T \sum_m \frac{1}{\epsilon_{m,\omega'}^2 + \tilde{\epsilon}_{m,\omega'}^2} \epsilon_{m,\omega'} + \frac{c}{\epsilon_{n,\omega'}}; \quad (2)$$

$$\tilde{\epsilon}_{n,\omega'} = T \sum_m \frac{2}{\epsilon_{m,\omega'}^2 + \tilde{\epsilon}_{m,\omega'}^2} \tilde{\epsilon}_{m,\omega'} + \tilde{c}_{n,\omega'}; \quad (3)$$

where $\epsilon_{1(2),\omega'}(n-m) = \epsilon_{\text{ph},\omega'}(n-m) + \epsilon_{m,n-1(2),\omega'}$ with the electron-phonon coupling function $\epsilon_{\text{ph},\omega'}(n)$

$$\epsilon_{\text{ph},\omega'}(n) = 2 \sum_0^Z \frac{1}{d} \frac{^2_{\text{ph},\omega'}F(\omega)}{2 + \epsilon_n^2}; \quad (4)$$

Note, that Eqs.(2-3) have a local form as a function of the angle ω' , i.e. the energies at different points on the Fermi surface are decoupled. Just this (decoupling) property of the Eliashberg equations in the EPI-FSP model, is crucial for solving the ARPES non-shift puzzle. The term $\tilde{c}_{n,\omega'}$ is due to the dynamical Coulomb effects and its calculation is the most difficult part of the problem.

\tilde{c} is proportional to the charge vertex $c(\omega - \omega^0)$ and, as we said in (2), we assume that it is also almost "local" on the Fermi surface, although this assumption is not crucial at all, since $c \approx \kappa_{\text{ph}}$. After the integration it reaches the same form as the second term in Eq.(2), where $\epsilon_{1,\omega'}(n-m)$ is replaced by the Coulomb coupling function $c_{\omega'}(n-m)$. The latter has the same form as Eq.(4) but $^2_{\text{ph},\omega'}F(\omega)$ is replaced by $S_C(\omega)$. ARPES spectra give evidence that $\text{Im } \tilde{c}(\omega) \approx c_{\omega'} \approx 2$ at $T < T_c < c$ which we reproduce by taking $S_C(\omega) = A_{c,\omega'}(j! - j! T) (c - j! j)$, where $A_{c,\omega'}$ is normalized to obtain $c_{\omega'} \approx 0.4$. The contribution of the Coulomb

interaction to the gap, $\tilde{c}_{n,\zeta}^C$, in Eq.(2) includes the following effects: (i) of the Hartree-Fock pseudopotential – which maximizes T_c when $\langle \tilde{c}_{n,\zeta}^C \rangle_F = 0$ and favors unconventional (d-wave) pairing; (ii) of the dynamical part of the Coulomb interaction which is unknown and an approximation for \tilde{c}^C is needed. The SFI approach assumes that $\tilde{c}^C(k; \zeta)$ depends on the dynamical spin susceptibility χ_s . Since $\text{Im} \chi_s(q; \zeta)$ is peaked at $Q = (\pi, \pi)$ this term is repulsive and favors d-wave pairing. Although $\tilde{c}_{n,\zeta}^C$ contributes little to $\tilde{c}_{n,\zeta}$, it is important to trigger superconductivity from s-wave to d-wave pairing [1], [11].

In Eqs.(1–2) non-magnetic impurities are included. Strong correlations induce the FSP in the impurity scattering matrix, being $t(\zeta; Q; \zeta) = \frac{2}{c}(\zeta^0, \zeta^0)$ [1]. In leading order one has $t(\zeta; Q; \zeta) = (\zeta^0, \zeta^0)$, thereby not affecting any pairing. In reality impurities are pair-breaking for d-wave pairing and the next to leading term is necessary. This term is controlled by two scattering rates, $\gamma_{1,\zeta}$ and $\gamma_{2,\zeta}$, where $\gamma_{1,\zeta} = \gamma_{2,\zeta} = 0$. The case $\gamma_{1,\zeta} = \gamma_{2,\zeta}$ leads to the extreme forward scattering – not affecting T_c , while $\gamma_{2,\zeta} = 0$ means an isotropic and strong pair-breaking scattering [1].

Quasiparticle renormalization – The quasiparticle energy $\epsilon(k)$ is the pole of the retarded Green's function. For numerical calculations we take for simplicity the Lorentzian shape for $\gamma_{ph,\zeta}^2$, $F(\zeta)$ centered at ϵ_{ph} . Since our aim is a qualitative explanation of the ARPES non-shift puzzle, we perform calculations only for moderate coupling constants $\gamma_{ph,\zeta} = \gamma_{ph} = 1$, $c = 0.3$ in both, the nodal and anti-nodal direction. In fact they can take larger values, i.e. $\gamma_{ph} \sim 2$ especially in the anti-nodal region. It is apparent from Eqs.(1–2) that the quasiparticle renormalization is local (angle-decoupled) on the Fermi surface. This behavior is expected to be realized in a more realistic model with the finite width γ_w when $\gamma_w \ll \gamma_{ph}$ [1].

(I) Kink in the spectrum in the nodal direction – The kink at $\epsilon_{kink}^{(70)} = 70$ meV in $\epsilon(k)$ means that the quasiparticles moving along the nodal direction ($\zeta = \pi/4$) interact with phonons with frequencies up to 70 meV [14], i.e. $\gamma_{ph,\zeta=\pi/4}^2 F(\zeta) \neq 0$ for $0 < \zeta < \pi/4$. Since $\gamma_{\pi/4}(\zeta) = 0$ then the "local" form of Eq.(2) implies that the spectrum $\epsilon(k)$ is not shifted in the superconducting state. Numerical calculations in Fig.1a confirm this analytical result what is in agreement with ARPES results [3]. It is expected that for a realistic phonon spectrum the theoretical singularity in $\epsilon(k)$ (shown in Fig.1a) will be smeared having also an additional structure due to other phonons which contribute to $\gamma^2 F(\zeta)$.

(II) Singularity in the anti-nodal direction – The singularity (not the kink) in $\epsilon(k)$ at $\epsilon_{sing}^{(40)}$ in the anti-nodal direction ($\zeta = \pi/2$) is observed in ARPES in the normal and superconducting state of $\text{La}_{2-x}\text{Sr}_x\text{CuO}_4$ and BISCO [6]. This means that the quasiparticles moving in the anti-nodal direction interact with a narrower phonon spectrum centered around $\epsilon_{ph}^{(40)} = 40$ meV.




FIG. 1: (a) The quasiparticle spectrum $\epsilon(k)$ and (b) the imaginary self-energy $\text{Im} \Sigma(E)$ in the nodal direction ($\zeta = \pi/4$) in the superconducting ($T = 0.2$ meV) and normal ($T = 6$ meV) state. $\Omega_c = 400$ meV is the cutoff in S_c .

Since $j_{\pi/2}(\zeta) \neq 0$, then Eq.(1) gives that in the normal state $\epsilon(k)$ is singular at $\epsilon_{sing} = \epsilon_{ph}^{(40)}$, while in the superconducting state the singularity is shifted to $\epsilon_{sing}^{(40)} = (\epsilon_{ph}^{(40)} + \epsilon_0)$. This is confirmed by numerical calculations in Fig.2a for $\epsilon(k)$, and in Fig.2b for $\text{Im} \Sigma(\zeta; \zeta)$, for $\gamma_{ph} = 1$ and $c = 0.3$. ARPES spectra give $\gamma_{ph} > 1$ in the anti-nodal region. [6].

Note, that the theoretical singularity in Fig.1a is stronger than in Fig.2a, because the calculations are performed for the same temperature, and since $\epsilon_{ph}^{(70)} > \epsilon_{ph}^{(40)}$ the latter singularity is smeared by temperature effects more than the former. The real shape of these singularities depends on microscopic details, such as for instance the presence of the van Hove singularity slightly below the Fermi surface in the anti-nodal region, etc. This will be studied elsewhere.

(III) The "knee"-like shape of $\text{Im} \Sigma(E)$ – The "knee" is shown in Fig.1b for the nodal kink (at $\epsilon_{ph} = 70$ meV) and in Fig.2b for the anti-nodal singularity (at $\epsilon_{ph} = 40$ meV). In both cases there is a clear "knee"-like structure for ϵ near ϵ_{ph} , what is in accordance with the recent ARPES results in various HTSC families [3], [4], [5], [6]. From Fig.1b it is seen that for energies $\epsilon_{ph}^{(70)} < \epsilon < \Omega_c$ the linear term is discernable in $j_{\pi/4} \text{Im} \Sigma = j_{\pi/4} \text{Im} \Sigma_{ph} + \text{Im} \Sigma^c$ $j_{\pi/4} \text{Im} \Sigma_{ph}(\epsilon_{ph}) + \text{Im} \Sigma^c$, while for $\epsilon > \epsilon_{ph}^{(70)}$ the slope of $j_{\pi/4} \text{Im} \Sigma(E)$ is




FIG. 2: (a) The quasiparticle spectrum $\omega(k)$ and (b) the imaginary self-energy $\text{Im } \Sigma(k; \omega)$ in the antinodal direction ($\theta = 0; \phi = \pi/2$) in the superconducting ($T = 0.2$ meV) and normal ($T = 6$ meV) state.

is steeper, since for $\lambda_{ph} (= 1)$ and $\lambda_c (= 0.3)$ the term $j \text{Im } \Sigma_{ph}(\omega_{ph})$ dominates. The "knee"-like shape of $\text{Im } \Sigma(k; \omega)$, as well as the non-shift of the kink at 70 meV, are "smoking gun" results for HTSC theories, which obviously favor the EP I as the pairing interaction. At present only the EP I-FSP theory is able to explain all distinctive features in ARPES spectra in a consistent way. The "knee"-like structure in the normal state was also obtained in [15], where the EP I and Coulomb interaction are treated phenomenologically. The EP I-FSP theory predicts also the "knee"-like structure in the antinodal region. However, in this case the closeness of the antinodal point to the van Hove singularity may influence $\text{Im } \Sigma(k; \omega)$ significantly and change its shape too. This will be studied elsewhere.

(IV) ARPES dip-hump structure – The EP I-FSP model explains qualitatively the dip-hump structure in $A(\theta; \omega) = -\text{Im } G(\theta; \omega)$ which was observed recently in ARPES [4]. In Fig. 3a it is seen that the dip-hump structure is realized in the normal state (also in the presence of impurities) already for a moderate coupling constant $\lambda_{ph} = 1$. The dip is more pronounced in the superconducting state where the peak in $A(\theta; \omega)$ is appreciably narrowed, what is in accordance with ARPES experiments [4]. Contrary to expectations, the dip-energy does not coincide with the (shifted) phonon energy at $\omega_{ph} = 40$ meV. However, the positions of the maxima of $-dA/d\omega$




FIG. 3: (a) The spectral function $A(\theta=0; \omega)$ and (b) $-dA(\theta=0; \omega)/d\omega$ in the antinodal direction in the superconducting ($T = 0.2$ meV) and normal ($T = 6$ meV) state for various impurity scattering rate γ_1 and $\gamma_2 = 0$; $\lambda_{ph} = 1$, $\lambda_c = 0.3$.

appear near the energies $(\pm \Delta_0 \pm n\omega_{ph})$ as it is seen in Fig. 3b. The calculations give also a dip in both, the antinodal and nodal density of states $N(\omega)$ (not shown) already for $\lambda_{ph} = 1$, which is more pronounced for larger $\lambda_{ph} > 1$.

Discussion and conclusions – In obtaining Eqs. (1–4) in the EP I-FSP model the Migdal vertex corrections due to the electron-phonon interaction are neglected. In [16] it is shown that these corrections may increase T_c significantly, at the same time decreasing the isotope effect, even for $\lambda_{ph} < 1$. However, these results can not change the qualitative picture obtained by the present theory.

In conclusion, the four distinctive features in the quasiparticle self-energy $\Sigma(k; \omega)$, obtained from the ARPES spectra in HTSC materials, are explained consistently by the theory in which the electron-phonon interaction (EP I) with the forward scattering peak (FSP) dominates over the Coulomb scattering. In particular, this theory explains why there is no shift of the nodal kink at 70 meV in the superconducting state, contrary to the clear shift of the antinodal singularity at 40 meV. The "non-shift" effect is a direct consequence of the existence of the FSP in the EP I, i.e. due to the long-range character of the electron-phonon interaction in HTSC oxides [17]. This is also supported by the pronounced long-range Madelung EP I, which is caused by the ionic-metallic character of layered HTSC oxides [1], [18]. However, for the quantitative theory the EP I-FSP model must be refined by including the realistic phonon and band structure of HTSC oxides.

Finally, based solely on the ARPES and tunnelling spectra, as well as on dynamical conductivity measurements, one can make a reliable phenomenological theory for the pairing in HTSC oxides. Its basic ingredient is the

electron-phonon interaction (which provides the strength for pairing) with the pronounced forward scattering peak, whatever is its cause, while the Coulomb scattering, in spite of its weakness compared to the EPI, triggers superconductivity to d-wave like [1], [11], [17]. This phenomenology is described by Eqs.(1-4), or their general-

ization to a realistic forward scattering peak with small but finite width Γ_w .

Acknowledgment – We thank Igor Mazin and O. Jepsen for careful reading of the manuscript. M. L. K. thanks Ulrich Eckern, Peter Kopietz, Igor and Lila Kulic for support.

-
- [1] M. L. Kulić, *Physics Reports* 338, 1 (2000)
 - [2] E. G. Maksimov, *Uspekhi Fiz. Nauk.* 170, 1033 (2000); P. B. Allen, *Nature*, 412, 494 (2001);
 - [3] A. Lanzara et al., *Nature*, 412, 510 (2001); X. J. Zhou, *Nature*, 423, 398 (2003)
 - [4] A. Damascelli, Z.-X. Shen, Z. Hussain, *Rev. Mod. Phys.*, 75, 473 (2003)
 - [5] X. J. Zhou et al., *cond-mat/0405130* (2004)
 - [6] T. Cuk et al., *cond-mat/0403521* (2004); Z.-X. Shen, talk at the Int. Symp. "Competing phases in novel condensed-matter systems, Würzburg, Germany, July 9-11 (2003)
 - [7] J. R. Schrieffer, D. J. Scalapino, J. W. Wilkins, *Phys. Rev. Lett.* 10, 336 (1963); D. J. Scalapino, inspiring talk at the Int. Symp. "Competing phases in novel condensed-matter systems, Würzburg, Germany, July 9-11 (2003)
 - [8] M. R. Norman, H. Ding, *Phys. Rev. B* 57, 11089 (1998)
 - [9] M. L. Kulić, I. M. Kulić, *Physica C* 391, 42 (2003)
 - [10] Ph. Bourges, in *The Gap Symmetry and Fluctuations in High Temperature Superconductors*, J. Bok, G. Deutscher, D. Pavuna, S. A. Wolf, Eds. (Plenum, New York, 1998), pp. 349-371; preprint *cond-mat/9901333* (1999)
 - [11] M. L. Kulić, R. Zeyher, *Phys. Rev. B* 49, 4395 (1994); R. Zeyher, M. L. Kulić, *Phys. Rev. B* 53, 2850 (1996)
 - [12] Z. Huang et al., *cond-mat/0306131* June 2003
 - [13] P. B. Allen, B. Mitrovic, in *Solid State Physics*, eds F. Seitz et al., 37, 1 (1982)
 - [14] E. Schachinger, J. J. Tu, J. P. Carbotte, *Phys. Rev. B* 67, 214508 (2003); S. Verga, A. Knigavko, F. Marsiglio, *Phys. Rev. B* 67, 054503 (2003)
 - [15] A. Greco, A. Dobry, *Solid St. Comm.*, 122, 111 (2002)
 - [16] C. Grimaldi, L. Pietronero, S. Strassler, *Phys. Rev. B* 52, 10516 (1995); *ibid.* 52, 10530 (1995)
 - [17] M. L. Kulić, O. V. Dolgov, *cond-mat/0308597* (2003); M. L. Kulić, *cond-mat/0404287* (2004)
 - [18] V. L. Ginzburg, E. G. Maksimov, *Supercond. Chem. Technol.* 5, 1505 (1992); A. A. Abrikosov, *Physica C* 244, 243 (1995);