Spin entropy as the likely source of enhanced therm opower in N $a_x C \, o_2 O_4$

Yayu W ang¹, Nyrissa S. Rogado², R. J. Cava^{2;3}, and N. P. Ong^{1;3}

 ^1D epartm ent of P hysics, ^2D epartm ent of C hem istry, ^3P rinceton M aterials Institute,

Princeton University, Princeton, New Jersey 08544.

ow of electrons in

(D ated: January 20th, 2003)

a solid produces an entropy current in addition to the familiar charge current. This Peltier e ect underlies all therm oelectric refrigerators. The upsurge in therm oelectric cooling applications has led to a search form ore e cient Peltier m aterials and to renew ed theoretical interest in how electron-electron interaction m ay enhance the therm opower Q of materials such as the transition-m etal oxides [1, 2, 3, 4]. An important factor in this enhancem ent is the electronic spin entropy, which is predicted [4, 5, 6] to dom inate the entropy current. How ever, the crucial evidence for the spin-entropy term, nam ely its com plete suppression in a longitudinal m agnetic

eld, the

In an electric

eld, has not been reported to date. Here we report evidence for such suppression in the layered oxide $Na_xCo_2O_4$, and present evidence that it is a strong-correlation e ect. The eld suppression of Q provides a rare, unam biguous exam ple of how strong interaction e ects can qualitatively alter electronic behavior in a solid. We discuss im plications for the search for better Peltier materials.

In a therm opower experiment, a tem perature gradient r T drives the di usion of charge carriers to the cooler end of the sample. The charge accumulation leads to a net electric eld E which determines the therm opower (or Seebeck coe cient) Q = E = jr T j [7]. In conventional metals, the ow of electrons induced by rT is nearly cancelled by a parallel ow of holes, so that Q is strongly reduced by the factor $T=T_F$ from the hatural value' $k_B = e 86 V/K$, where k_B is Boltzm ann's constant, e the electron charge and T_F the Ferm item perature [7]. M oreover, as the currents are indi erent to the spins, a longitudinalm agnetic eld H jj r T has virtually no e ect on Q. In materials with strong electron-electron interaction, however, the spin degrees are predicted to produce a large contribution of the Heikes form [2, 4, 6]

$$Q ! \frac{1}{eT} = -\frac{1}{e}; \qquad (1)$$

where is the chemical potential, and (the entropy per electron) equals $k_B \ln (g_s g_c)$ with g_s and g_c the spin and con guration degeneracies, respectively. From Eq.1, the enhancement to Q from spin entropy is of the order $k_B = e$, but it is suppressed to zero if the spin degeneracy is lifted in a magnetic eld (g ! 1).

Terasaki, Sasago, and U chinokura [8] recently reported the discovery that Q in $Na_xCo_2O_4$ (at 300 K) is 10 tim es larger than in typical metals, and suggested that spin- uctuations, as in heavy-ferm ion system s, m ay play a key role. Despite Halle ect 8], heat capacity [9] and nuclear spin-resonance [10] experiments, however, the enhancement in Q remains puzzling. Experiments have not ruled out either strong-interaction theories involving spin con gurations [1], or conventional interpretations based on sm all Ferm iSurfaces [12]. By investigating the therm opower and magnetization in both longitudinal and transverse H, we show that $Na_xCo_2O_4$ is in fact a strong-correlation system in which the spin entropy term accounts for virtually all of Q at 2 K and a dom inant fraction at 300 K .

In $Na_x Co_2 O_4$, the Co ions occupy the sites of a twodim ensional (2D) triangular lattice. Chem ical argum ents and band-structure calculations [12] show that the oxygen 2p states lie far below the C o-3d states and the chem ical potential falls within the band form ed from t_{2q} states in Co. Hence the electrons donated by Na ions are distributed among the Coions, a fraction of which are in the Co^{4+} state while the rest (1)) are $C \delta^+$. From x = 1.36 (determ ined by ICP chem ical analysis of our crystals), we nd = 0.32. The variation of the susceptibilities ab and c vs. tem perature T (Fig. 1a) t accurately to the Curie-W eiss form $(T +)^{1}$, im plying the existence of large local m om ents that are antiferromagnetically coupled. The plot of 1 = ab gives = 55 5 K and a moment $0.87_{\rm B}$ averaged over all Coions (B is the Bohr magneton). This experimentally constrains the Co^{4+} ions to be in the low-spin state with spin S = $\frac{1}{2}$ and m om ent $\frac{1}{3}$ B, while the Co³⁺ ions are in their low -spin S = 0 state (Fig. 1c), in agreement with Ref. [10].

The in-plane resistivity displays a T-linear variation below 100 K that is suggestive of strong-correlation behavior (dashed line in Fig. 1b). As noted in Ref. [8], Q (open circles) increases with T to values much larger than in conventional metals. However, it is the e ect of a magnetic eld on Q that is the most telling. The pronounced e ect of an in-plane eld H on Q is shown in Fig. 2 (H jj r T). Stringent precautions against spurious contributions to Q were adopted (see Supplem entary Information). Even at moderately high T (30 K), Q decreases signi cantly in a 14-Tesla eld. Lowering the temperature makes the eld-suppression of Q m ore pronounced, until at 4 K, Q changes sign and saturates near 12 T to a ' oor' value equal to -0.25 V/K.W ith further decrease in T, the oor value itself monotoni-

Nature 423, 425 (2003).



FIG.1: The temperature (T) dependence of magnetic and transport properties of single-crystal Na_xCo₂O₄ and electronic states in the Co ions. Panel (a) shows the T dependence of the inverse susceptibilities _{ab} and _c measured in a 5-Tesla eld applied in-plane and along the c-axis, respectively. In Panel (b), the in-plane therm opower Q (open symbols) and resistivity (solid curve) are plotted vs. T. The T-linear dependence of below 100 K is indicated by the dashed line. The inset (c) is a sketch of the low-spin t_{2g} states in the Co⁴⁺ and Co³⁺ ions. The hopping of a hole (arrow) is accompanied by the transfer of a spin- $\frac{1}{2}$ excitation.

cally decreases to zero. The trace at 2.5 K shows that Q decreases m onotonically to zero in a eld of 8 T, and remains at zero over an extended eld range.

The strong e ect of eld on Q is also observed with H jjc (norm alto plane), except that, above 6 K, we observe an additional term that produces an increase in Q in weak elds. At 4.2 K, Q displays the same eld pro-

Le as above, but with a proportionately weaker decrease (Fig. 3). As the sample is warm ed to 10 K and higher, the relative change in Q is initially positive in low elds. At higher elds, the negative trend becomes again apparent. The overall pattern in transverse eld is consistent with a positive contribution superposed on the term intrinsic to the spin degrees uncovered in the longitudinal eld.

The evidence that the H dependence of Q arises from the spin degrees of freedom derives from both the transport and susceptibility experiments. As an in-plane eld couples only to the spin degrees, but not the orbital degrees, the strong H dependence of Q in Fig. 3 m ust arise from the e ect of eld on the spins. In the geometry with H jp, we reason that the non-monotonic eld dependence of Q also arises entirely from the e ect of H on the spin



FIG. 2: The in-plane therm opower Q vs. an in-plane H k (rT) at selected T. At 4.4 K, Q asymptotes at high elds to a negative oor value (0.25 V/K). At the lowest T (2.5 K), Q approaches a value unresolved from zero when H exceeds 8 T. The applied temperature di erence T is less than 0.3 K below 4 K, and 0.5 K above 4 K. By using phosphor bronze as the voltage leads, we have elim inated background contributions to Q (Supplem entary Inform ation).

degrees, as the carrier m ean-free-path ' 100 A estim ated from is far too short to produce any orbitale ect in a eld of 14 Tesla. Com paring curves at 4 K in Figs. 2 and 3, we infer that a similar decrease in Q requires a c-axis eld that is 1.4 tim es larger than the in-plane eld. The close agreem ent between this ratio and the ratio of the bulk susceptibilities ab = c at 4 K strongly suggests that the eld an isotropies in the magnetization and thermopower experiments have the same origin. The eld suppression of Q is larger with the eld in-plane com pared with the eld along the c-axis because it is easier to align the spins with an in-plane eld. In conventional metals, a longitudinal eld merely changes the relative populations of the spin-up (+) and spin-down (-) electrons without signi cantly altering the entropy current in each spin population [7]. The complete suppression displayed in Fig. 2 is incompatible with a conventional band picture.

We next discuss how the eld suppression m ay be understood within a strong-correlation scenario. As shown in Fig. 4a (insert), in the 2D triangular lattice of the Co ons, a fraction $=\frac{1}{3}$ are in the Co⁴⁺ state in which $S = \frac{1}{2}$, while the rest are in the Co³⁺ state with S = 0 (the higher-lying e_q orbitals are unoccupied). The el-



FIG.3: The relative change in Q versus a transverse eld H jjc in N $a_x C o_2 O_4$. At 6 K and lower, Q decreases m onotonically with H, but at higher tem peratures, Q initially increases in weak eld before decreasing at larger H.

ementary charge transport process is the hopping of a hole from Co^{4+} to Co^{3+} (Fig. 1c). A large on-site repulsion excludes double-occupancy of a site by the holes. Because this process converts the Co^{4+} (S = $\frac{1}{2}$) to a Co^{3+} (S = 0) and vice versa, we also transfer a spin- $\frac{1}{2}$ along with the hole, which in plies a transfer of spin entropy = $k_B \ln 2$ in zero eld. The excitations are holes carrying charge + 1e and spin- $\frac{1}{2}$ m oving in a sea of Co^{3+} sites, which are m agnetically and electrically inert. An E

eld leads to the heat current $J_0 = nvk_B T \ln 2$ as well as the charge current J = nev (n is the hole concentration and v the average velocity). As the ratio $J_Q = J$ (called the Peltier coe cient) equals the product QT, we obtain the spin-entropy part of Q given in Eq. 1. Moreover, because the spin-entropy current is in the direction of the charge current, this contribution to Q is positive (hole-like) as observed. As T decreases below 50 K (the antiferrom agnetic exchange energy $J_{A\,F}$), the spin entropy must decrease rapidly with incipient magnetic ordering to vanish at T = 0. When T , the m a prity of the spins become antiferrom agnetically correlated with their neighbors, leaving only a sm all fraction T = to behave as free spins. In an E - eld, this residualpopulation of free spins carries the spin entropy although all the holes remain itinerant. This implies that the ratio $J_0 = J$ decreases steeply below , consistent with the observed behavior of Q in Fig. 1.



FIG.4: The suppression of the them opower by an in-plane magnetic eld in Na_xCo₂O₄. In Panel (a) the normalized Q is plotted versus $_0H = k_B T$. Curves measured at various T collapse to a universal curve. The inset in (a) shows the $\frac{1}{2}$ excitations in an inert background of Co³⁺ ions. Panel (b) compares the curve at 2.5 K (solid curve) with the expression in Eq. 2 (dashed curve).

In a magnetic eld, the residual spin entropy (H) is further decreased, eventually reaching 0 when H is strong enough to completely lift the 2-fold degeneracy. M odeling the residual free spins as non-interacting spins with the Land e g-factor g, we calculate the eld dependence of the entropy as

$$\frac{(H;T)}{(0)} = \frac{\ln (2\cosh u) \quad u \tanh u}{\ln 2}; \quad (u = \frac{g_{B}H}{2k_{B}T}): (2)$$

This dependence should apply to the component of Q derived from the spin entropy.

As shown in Fig. 4a, the curves of Q in Fig. 2 between 2.5 and 25 K can be collapsed onto a universal curve when plotted against the ratio H =T. U sing the curve at 2.5 K (which extends to the largest u), we nd that Eq. 2 provides a remarkably close t if the g-factor is 2.2 0:1 (Fig. 4b). We view the close t (achieved with a reasonable g) as con ming evidence that the entropy current observed in the therm opower indeed derives entirely from the spin $\frac{1}{2}$ excitations, and the com plete suppression of Q re ects the rem oval of the spin degeneracy by the applied eld.

W e remark that, at each T , the observed Q is com prised of several distinct contributions. Application of a strong longitudinal H completely suppresses only the spin-entropy term, leaving the remaining terms unaffected (the con guration entropy $k_B \ln g_c$, for instance) which are revealed as the oor value at high elds. In Fig. 2, these terms amount to 0:25 V/K at 4.4 K and rapidly vanish at lower T. We emphasize that the spin entropy contribution to Q is not restricted to low T.M easurements at high elds (30 T) show that Q is suppressed , the spin by 20% at 30 K.Assuming that, when T contribution asymptotes to $\frac{k_{\rm B}}{e} \ln 2$ 60 V/K,we nd $\frac{2}{3}$ of the total therm opower at 300 that it constitutes K, accounting form ost the enhanced therm opower.

The spin-entropy enhancement may be widespread in the transition-metal oxides. A key ingredient inferred

- M ahan, G., Sales, B. and Sharp, J. Therm celectric M aterials: New Approaches to an Old Problem . Phys. Today 50 (3), 42-47 (1997).
- [2] Beni, G. Them oelectric power of the narrow-band Hubbard chain at arbitrary electron density: A tom ic lim it. Phys. Rev. B 10, 2186-2189 (1974).
- [3] Palsson, G. and Kotliar, G. Them oelectric power near the density-driven M ott transition. Phys. Rev. Lett. 80, 4775-4778 (1998).
- [4] Chaikin, PM. and Beni, G. Them opower in the correlated hopping regime. Phys. Rev. B 13, 647-651 (1976).
- [5] Kwak, J.F. and Beni, G. Them oelectric power of a Hubbard chain with arbitrary electron density: Strongcoupling limit. Phys. Rev. B 13, 652-657 (1976).
- [6] Kwak, J.F., Beni, G. and Chaikin, P.M. Therm oelectric power in Hubbard-model systems with di erent densities: N-methylphenazim ium-tetracyanoquinodim ethane (NMP-TCNQ), and quinolinium ditetracyanoquinodim ethane. Phys. Rev. B 13, 641-646 (1976).
- [7] Ziman, J.M. Principles of The Theory of Solids. (Cambridge, London 1972), p.235.
- [8] Terasaki, I., Sasago, Y. and Uchinokura, K. Large thermoelectric power in NaCo₂O₄ single crystals. Phys. Rev. B 56, R12685-12687 (1997).
- [9] Ando, Y., M iyam oto, N., Segawa, K., Kawata, T. and Terasaki, I.Speci c-heat evidence for strong electron correlations in the therm coelectric material (Na,Ca) Co₂O₄. Phys.Rev.B 60, 10580-10583 (1999).
- [10] Ray, R., Ghoshray, A., Ghoshray, K. and Nakamura, S. 59C o NMR studies of metallic NaCo₂O₄.Phys.Rev.B 59, 9454–9461 (1999).
- [11] Koshibae, W., Tsutsui, K. and Maekawa, S. Thermopower in cobalt oxides. Phys. Rev. B 62, 6869-6872 (2000).
- [12] Singh, D. J., Electronic structure of $N\,aC\,o_2O_4$. Phys. Rev.B 61,13397–13402 (2000).

from our measurements is the motion of charge tied to boal moments of spin $\frac{1}{2}$ in a background of Co³⁺ ions that are magnetically inert (diamagnetic). Among the large class of cobalt oxides, the Co ions are nearly always in their low-spin state. In the Co oxides that can be made conducting, therefore, the therm opower is likely to be dom inated by spin-entropy terms, suggesting that this is a promising class of materials to search for improved Peltier materials.

W e acknowledge support from the U.S.National Science Foundation (NSF). Som e of the measurements were performed at the U.S.NationalHigh Magnetic Field Laboratory, Tallahassee, Fl., which is supported by NSF and the state of Florida. We thank Scott Hannahs for technical assistance.



FIG.5: (Supplem entary inform ation) The therm oelectric signal versus H with single-crystal La_{2 x} Sr_xCuO₄ (x = 0.17) serving as the reference sample. At each T, the voltm eter recording V_G is H -independent and close to zero until H exceeds the vortex solid melting eld H_m (T) (30 T at 5 K). At H_m (T), V_G increases abruptly re ecting the large therm opower in the vortex liquid state. The at behavior of V_G for H < H_m (T) veri es that the therm opower of phosphor bronze Q_w is eld independent at least up to H_m (T). The insert shows the closed loop 1–2–3–4–5–6 used in the derivation of Eq. 3.

Supplem entary M aterial

In high- eld m easurem ents of them opowerQ, there is an important source of background contribution, namely the them opowerQw of the voltage lead at the warm end of the sample. It is essential to determ ine separately the

eld dependence (if any) of Q_w . A fler testing æveral candidate m etals, we have found that phosphor bronze is nearly ideal because its Q_w is very sm all and shows no m easurable eld dependence at 5 K up to 30 Tesla.

In a therm opower experiment, one end of the sample (2) is held at temperature T + T while the other end 1 is anchored at the bath temperature T. The E - eld generated by the Seebeck e ect is determined from the potential di erence of the voltage leads electrically connected to the two sample ends. However, the Seebeck

coe cient Q $_{\rm W}$ of the voltage lead at the warm er end invariably contributes to the voltage reading. To see this, we consider potential changes around the close loop 1-2-3-4-5-6 (insert in Fig. 5). The voltage leads 23 and 16 are m ade of phosphor bronze while the long twisted pair 34 and 56 are m ade of copper. W ith V_G = V₄ V₅, we have

where E_w and E_{w^0} are the E - eld in phosphor bronze and in Cu, respectively. The 1st and 2nd terms are the potential drops across the sam ple, and the 'warm' voltage lead 23, respectively. The 3rd and 4th terms are the potential drops along the long, twisted pair of copper wires extending from the sam ple chamber to the pream pli er at room temperature. The 5th term, the potential drop in the 'bool' voltage lead 16, vanishes as nodes 1 and 6 are anchored at the bath temperature. In a carefully designed apparatus, the 3rd and 4th terms cancel to zero. How ever, the 2nd term can never be elim inated because the same temperature drop T falls across the sam ple and the voltage wire 23, i.e. $T_3 = T_1$. Using E = Q r T, and $T = T_2$ T₁ in Eq. 3, we have

$$V_{G} = (Q \qquad Q_{W}) \quad T:$$
(4)

In high-resolution experiments, the eld dependence of Q_w in the voltage lead material (phosphor bronze) must be measured separately. Ideally, if Q is rigorously zero up to the maximum H of interest, VG would just equal $-Q_w T$. In an extrem e type II superconductor, the therm opower is strictly zero in a magnetic eld if the vortices remain pinned (in the solid state). We used an optimally-doped crystal of $La_2 \times Sr_x CuO_4$ (x = 0.17) in which the melting eld of the vortex solid H_m (T) has been studied extensively. For elds $H < H_m$ (T), the voltmeter reading is then $V_G =$ Q_w T at each T.Hence any eld variation in Qw can be observed directly. Figure 5 shows that as H is increased, V_G increases abruptly at H $_{\rm m}$ (T) re ecting the increase in Q . However, below H_m (T), the volumeter reading is virtually independent of H, con ming that Q_w in phosphor bronze is eld independent (at least, up to ${\rm H}_{\,\rm m}$ (T)) and very sm all at these tem peratures. W ith this test, we verify explicitly that the eld dependences show n in Figs. 2 and 3 entirely derive from $Na_xCo_2O_4$.