

Superconductivity in ferromagnetic metals and in compounds without inversion centre

V.P. Mineev

Commissariat à l'Energie Atomique, DSM /DRFC /SPSMS

17 rue des Martyrs, 38054 Grenoble Cedex 9, France

(December 29, 2021)

Abstract

The symmetry properties and the general overview of the superconductivity theory in the itinerant ferromagnets and in materials without space parity are presented. The basic notions of unconventional superconductivity are introduced in broad context of multiband superconductivity which is inherent property of ferromagnetic metals or metals without centre of inversion.

I. INTRODUCTION

The recent discoveries of several materials UGe_2 , [1,2] ZrZn_2 , [3] and URhGe [4,5], where the superconductivity coexists with presumably itinerant ferromagnetism, put forward the problem of theoretical description of such type of ordered media. Along with the problem of a mechanism of pairing and critical temperature calculation which is intensively discussed now in literature in frame of different models [6-18], but still being far from its resolution, there was developed also the general symmetry approach to the theoretical description of superconductivity in ferromagnetic superconductors. The superconducting state in these materials have to be preferably spin triplet to avoid the large depairing influence of the exchange field. However, the theory of triplet superconductivity in ferromagnets cannot be simple replica of the theory of superfluid phases of liquid ^3He [19] or even its

anisotropic strong spin-orbit coupling generalization for superconducting states in crystals [20]{24}. Here the superconducting states appear from another ordered state – namely, ferromagnetic state. The latter has the broken time reversal symmetry and the classification of the superconducting states has its own specifics [25]{28}.

More or less at the same time another important achievement in the physics of superconductivity is committed. This time it was related with discovery of MgB_2 – the first superconducting material with two bands of conduction electrons where the existence of two energy gaps has been unambiguously demonstrated by thermodynamic and spectroscopic measurements [29]. Theoretical investigations of two-band superconductivity have been undertaken soon after BCS theory [30] were also restarted (see for example [31,32]). Recently it was revealed that the superconductivity in itinerant ferromagnetic superconductors and in conventional two band superconductors has a lot of similarity [33]. Indeed, in ferromagnetic superconductors the different bands filled by spin "up" and spin "down" electrons are always present. Hence one can construct the theoretical description of such the superconducting states in analogy with conventional multiband superconductivity.

Also, quite recently the first unconventional superconductor without inversion symmetry $CePt_3Si$ has been discovered [34]. The microscopic theory of superconductivity in metals without inversion has been developed by V Edel'stein [35] pretty long ago. The different aspects of theory of superconductivity in such type materials has been discussed about the same time [36]{38} and has been advanced further in more recent publications [39]{46}. Finally, the general symmetry approach to the superconductivity in the materials with space parity violation has been developed [47,48] and some its applications have been considered [49]{51]. It proves and we shall demonstrate it clearly below that again the description of superconductivity in such type of materials has many common features with conventional superconductivity in two band superconductors.

So, having in mind to present here the review of symmetry approach to the superconductivity in ferromagnetic materials and in the compounds without inversion centrum (ferroelectrics) we shall discuss the normal state properties of the materials with different

symmetry. There will be shown how the symmetry of normal metal one-electron states determines the possible types of pairing. We shall follow as far as it possible to analogy with multiband conventional superconductivity. We make an overview of symmetry description of superconducting states specific for materials with time reversal or space parity violation. At last the Gor'kov type formalism for multiband superconductivity in ferromagnetic and ferroelectric materials will be developed and some concrete applications will be discussed.

II. ONE BAND SUPERCONDUCTIVITY

To introduce notations and basic notions we start with well known description of the superconductivity in one band normal metal with centrum of space inversion [20-24]. The band states are Bloch type wave functions characterized by quasimomentum \mathbf{k} and $l=2$ projections of spin on the direction of the quantization axis. Each electronic eigen state is fourfold degenerate, another words, four different states $|\mathbf{k}; \uparrow, j = \uparrow, \downarrow\rangle$ and $|\mathbf{k}; \downarrow, j = \uparrow, \downarrow\rangle$ correspond to the same electron energy $\epsilon_{\mathbf{k}}$. The states with opposite momenta and the opposite spins form so called Kramers doublet: under the time inversion operation \hat{K} they are transformed to each other with a phase factor accuracy $\hat{K} |\mathbf{k}; \uparrow\rangle = e^{i\phi} |\mathbf{k}; \downarrow\rangle$. In its own turn the states with the opposite momenta are transformed to each other by means of the space parity operation \hat{P} . So, the presence of four degenerate electronic states $|\mathbf{k}; \uparrow, \downarrow\rangle$, $\hat{K} |\mathbf{k}; \uparrow, \downarrow\rangle$, $\hat{P} |\mathbf{k}; \uparrow, \downarrow\rangle$, and $\hat{K} \hat{P} |\mathbf{k}; \uparrow, \downarrow\rangle$ is the consequence of space and time inversion symmetries.

Now, if there is some pairing interaction, the scattering of electrons occupying the degenerate states with oppositely directed momenta near the Fermi surface and either antiparallel spins ($S = 0$) or parallel spins ($S = 1$) results in formation of superconducting state with order parameters depending of space coordinate \mathbf{r} and the relative direction of momenta of pairing particles $\hat{\mathbf{k}} = (\mathbf{k}_1 - \mathbf{k}_2)/2k_F$:

$$\psi^{S=0}(\mathbf{r}; \hat{\mathbf{k}}) = \psi(\mathbf{r}; \hat{\mathbf{k}}) i_y = \psi(\mathbf{r}; \hat{\mathbf{k}}) (j = \uparrow, \downarrow - j = \downarrow, \uparrow); \quad (1)$$

$$\begin{aligned}
s=1 \quad (r; \hat{k}) &= \frac{1}{2} \begin{pmatrix} 0 & 1 \\ 1 & 0 \end{pmatrix} \begin{pmatrix} \psi_0(r; \hat{k}) & \psi_1(r; \hat{k}) \\ \psi_0(r; \hat{k}) & \psi_1(r; \hat{k}) \end{pmatrix} = \frac{1}{2} \begin{pmatrix} \psi_0(r; \hat{k}) & \psi_1(r; \hat{k}) \\ \psi_0(r; \hat{k}) & \psi_1(r; \hat{k}) \end{pmatrix} \begin{pmatrix} 1 & 0 \\ 0 & 1 \end{pmatrix} \\
&= \frac{1}{2} \begin{pmatrix} \psi_0(r; \hat{k}) & \psi_1(r; \hat{k}) \\ \psi_0(r; \hat{k}) & \psi_1(r; \hat{k}) \end{pmatrix} \begin{pmatrix} 1 & 0 \\ 0 & 1 \end{pmatrix} = \frac{1}{2} \begin{pmatrix} \psi_0(r; \hat{k}) & \psi_1(r; \hat{k}) \\ \psi_0(r; \hat{k}) & \psi_1(r; \hat{k}) \end{pmatrix} \begin{pmatrix} 1 & 0 \\ 0 & 1 \end{pmatrix} \quad (2)
\end{aligned}$$

where $\sigma_x, \sigma_y, \sigma_z$ are the Pauli matrices.

According to the Pauli principle the particle permutation, that is interchange by places of first and second arrow in each $j :: i$ and change $\hat{k} \rightarrow -\hat{k}$, yields the change of sign of the order parameter (pair wave function). That is why the singlet pairing states are described only by even $\psi(\hat{k}) = \psi(-\hat{k})$ functions whereas triplet pairing states are always odd $\psi(\hat{k}) = -\psi(-\hat{k})$ in respect to relative wave vector direction of pairing particles. In the crystal with space inversion the parity of the superconducting state has definite value and the mixture of the singlet and triplet pairing states is inadmissible.

The scalar function of the order parameter for the singlet superconducting state is decomposed over the functions $\psi_i(\hat{k})$ of irreducible representation dimensionality d of the point symmetry group G of the crystal in the normal state

$$\psi(r; \hat{k}) = \sum_{i=1}^d \psi_i(r) \psi_i(\hat{k}) \quad (3)$$

Similar decomposition takes place for vectorial order parameter function in triplet state

$$\psi(r; \hat{k}) = \sum_{i=1}^d \psi_i(r) \hat{\psi}_i(\hat{k}) \quad (4)$$

Here

$$\hat{\psi}_i(\hat{k}) = \hat{x}_{xi} \psi_{xi}(\hat{k}) + \hat{y}_{yi} \psi_{yi}(\hat{k}) + \hat{z}_{zi} \psi_{zi}(\hat{k})$$

are vectorial functions of irreducible representation dimensionality d of the point symmetry group G represented as decomposition over spin unit vectors $\hat{x}, \hat{y}, \hat{z}$ pinned to the crystal axis. To each irreducible representation corresponds its own critical temperature T_c . Any one-dimensional representation describes only one superconducting state characterized by its own symmetry group – so called superconducting class which is a subgroup of the

group of symmetry of the normal state $G = I \times U(1) \times K$, where $U(1)$ is the group of gauge transformations. A multidimensional representation gives rise to several superconducting states. Their order parameters are given by the particular linear combinations in (3) or in (4) possessing of different symmetries, another words, belonging to different superconducting classes but being characterized by the same critical temperature.

III. MULTIBAND SUPERCONDUCTIVITY

Let us look now what kind of modifications must be introduced in the theory if we deal with superconducting state forming in a metal with several conduction bands. We shall speak for simplicity about two band situation. Each band has its own dispersion law $\epsilon_n(k)$, here n is the band index, and its own Fermi surface determined by equations $\epsilon_1(k) = \epsilon_F$ and $\epsilon_2(k) = \epsilon_F$. The electronic states in each of two bands obey the same fourfold degeneracy as before.

If there is some pairing interaction it acts in some energetic vicinity of Fermi surface. One can also say that the pairing of electronic states in given band happens in some layer in the reciprocal space around corresponding Fermi surface. The different bands layers where the pairing takes place can in principle intersect each other. Then the pairing is possible not only between the electrons occupying the electronic states from the same band but also between the electrons from the different bands with equal by the modulus and oppositely directed momenta and either antiparallel or parallel spins. On microscopic level of description we have to introduce not only doubled set of Bogolubov or Gor'kov equations written for each band but also additional equations for the Bogolubov interband pairing amplitudes or for the Gor'kov interband F_{12} Green functions. Hence the total system includes 6 coupled equations. On macroscopic level of the description we shall have coupled system of Ginzburg-Landau equations which, even in the simplest case of superconducting state corresponding to one-dimensional representation, will consists of three equations for three coordinate dependent pairing amplitudes. These amplitudes are different complex functions

with the coinciding phase factors (see below). In the linear approximation the system of Ginzburg-Landau equations has three different eigen values the largest of which determines the critical temperature or the upper critical field for the phase transition to the superconducting state. So, the multiband superconductivity has the peculiarities in the mathematical description.

Let us consider now more simple situation when the different bands layers in reciprocal space, where the pairing takes place, do not intersect each other. Then the pairing is possible only between the electrons with the opposite momenta \mathbf{k} and $-\mathbf{k}$ occupying electronic states in the same band. Certainly, in principle, one can consider also interband pairing. But the Cooper pairs formed by electrons from the different bands with different Fermi momenta $k_{F1}(\hat{\mathbf{k}})$ and $k_{F2}(-\hat{\mathbf{k}})$ will inevitably have a finite momentum and as result one can expect of appearance only of space modulated or Fulde-Ferrell-Larkin-Ovchinnikov superconducting state. We shall not discuss here this exotic possibility.

So, if we consider only intraband pairing we deal with two sets of Gor'kov equations written for each band. The coupling between them is carried out only due to the processes interband pair transitions which is taken into account by means of the self-consistency equation. Thus, in general, the order parameter consists of two parts of the same form as for one-band superconductivity. For the singlet superconducting state instead (3) we have

$$\langle r; \hat{\mathbf{k}} \rangle = \sum_{i=1,2} \sum_{\mathbf{d}} X_{\mathbf{d}}^i(r) \chi_{\mathbf{d}}^i(\hat{\mathbf{k}}); \quad (5)$$

where $\chi_{i1}(\hat{\mathbf{k}})$ and $\chi_{i2}(\hat{\mathbf{k}})$ are in principle different functions of the same irreducible representation dimensionality d of the point symmetry group G of the crystal in the normal state. Similar decomposition takes place for vectorial order parameter function in triplet state

$$\mathbf{d}(r; \mathbf{k}) = \sum_{i=1,2} \sum_{\mathbf{d}} X_{\mathbf{d}}^i(r) \chi_{\mathbf{d}}^i(\hat{\mathbf{k}}) \quad (6)$$

Let us take for clarity the case of one-dimensional representation, for instance conventional singlet two-band superconductivity which is intensively discussed now in connection with MgB_2 compound. In this case the order parameter has the form

$$(\mathbf{r}; \hat{\mathbf{k}}) = \psi_1(\mathbf{r}) \psi_1(\hat{\mathbf{k}}) + \psi_2(\mathbf{r}) \psi_2(\hat{\mathbf{k}}); \quad (7)$$

where the coordinate dependent complex order parameter amplitudes $\psi_1(\mathbf{r})$ and $\psi_2(\mathbf{r})$ are not completely independent:

$$\psi_1(\mathbf{r}) = j_1(\mathbf{r}) e^{i\varphi_1(\mathbf{r})}; \quad \psi_2(\mathbf{r}) = j_2(\mathbf{r}) e^{i\varphi_2(\mathbf{r})}; \quad (8)$$

Thus, being different by their modulus they have the same phase with an accuracy $\sim 10^{-3}$. The latter property guarantees the consistency of transformation of both parts of the order parameter under the time reversal.

In the space homogeneous case the coupled system of Ginzburg-Landau equations has the form

$$\begin{aligned} \psi_1 &= (g_{11} \psi_1 + g_{12} \psi_2) (T_{c0}); \\ \psi_2 &= (g_{21} \psi_1 + g_{22} \psi_2) (T_{c0}); \end{aligned} \quad (9)$$

The function $\psi(T)$ is

$$\psi(T) = 2 \sum_{n=0}^{\infty} \frac{1}{n!} T^n = \ln \frac{2}{T}; \quad (10)$$

$\ln 2 = 0.6931 \dots$ is the Euler constant, ϵ_F is an energy cutoff.

Thus, the critical temperature is given by [30,31]

$$T_{c0} = (2 \epsilon_F) \exp(-1/g); \quad (11)$$

where g is defined by the maximum of zeros of determinant of the system (9)

$$g = (g_{11} + g_{22})/2 + \sqrt{(g_{11} - g_{22})^2/4 + g_{12}g_{21}}; \quad (12)$$

In particular at $g_{12} = g_{21} = 0$; g_1, g_2 the critical temperature is determined by

$$g = \max(g_1, g_2); \quad (13)$$

IV . FERROMAGNETIC SUPERCONDUCTORS WITH TRIPLET PAIRING

A . The order parameters

In an itinerant ferromagnetic metal the internal exchange field lifts the Kramers degeneracy of the electronic states. The electrons with spin "up" fill the states in one band and the electrons with spin "down" occupy the states in another band. Hence we have the special example of multiband metal with states in each band filled by electrons with only one spin direction. This situation has relation also to the ferromagnetic metal where ferromagnetic moment originates from almost localized f-shells whereas for its metallic properties other electronic states from s and d delocalized bands are responsible. The exchange interaction is provided here for instance by Ruderman-Kittel mechanism. At the same time the back influence of ordered magnetic moments on the conduction electrons splits the bands with spin up and spin down electronic states magnetizing the conduction electron system.

Let us discuss for simplicity the two-band ferromagnet. Again as in the case of two band normal metal, if there is some pairing interaction, one can discuss intraband or spin "up" - spin "up" (spin "down"-spin "down") pairing of electrons, as well as interband or spin "up"-spin "down" pairing. In general the Fermi surfaces of spin up and spin down bands are situated in different places of the reciprocal space and have the different shape. That is why pairing of electrons from the different bands occurs just in the case of nesting of some pieces of the corresponding Fermi surfaces. In such the situation, similar to SDW or CDW ordering, the superconducting ordering is formed by Cooper pairs condensate with finite momentum known as Fulde-Ferrel-Larkin-Ovchinnikov state. We shall not discuss here this special possibility. So we neglect by pairing of electronic states from different bands giving Cooper pairs with zero spin projection. Hence, the only superconducting state should be considered it is the state with triplet pairing and the order parameter given by

$$d(\mathbf{R}; \mathbf{k}) = \frac{1}{2} [(\hat{x} + i\hat{y}) \cdot \mathbf{d}(\mathbf{R}; \mathbf{k}) + (\hat{x} - i\hat{y}) \cdot \mathbf{d}(\mathbf{R}; \mathbf{k})] \quad (14)$$

Superconducting states $d(\mathbf{R}; \mathbf{k})$ with different critical temperatures in the ferromagnetic

crystals are classified in accordance with irreducible co-representations of the magnetic group M of crystal [26,28]. All the co-representations in ferromagnets with orthorhombic, hexagonal, and cubic symmetries are one-dimensional. However, they obey of multicomponent order parameters determined through the coordinate dependent pairing amplitudes: one per each band populated by electrons with spins "up" or "down". For the two-band ferromagnet under discussion, they are

$$\psi_-(\mathbf{R}; \mathbf{k}) = \psi_1(\mathbf{R}) f_-(\mathbf{k}); \quad \psi_+(\mathbf{R}; \mathbf{k}) = \psi_2(\mathbf{R}) f_+(\mathbf{k}); \quad (15)$$

The coordinate dependent complex order parameter amplitudes $\psi_1(\mathbf{R})$ and $\psi_2(\mathbf{R})$ are not completely independent:

$$\psi_1(\mathbf{R}) = j_1(\mathbf{R}) \dot{\mathcal{P}}^{i'}(\mathbf{R}); \quad \psi_2(\mathbf{R}) = j_2(\mathbf{R}) \dot{\mathcal{P}}^{i''}(\mathbf{R}); \quad (16)$$

As in conventional two-band case (8), being different by their modulos they have the same phase with an accuracy π . The latter property is due to the consistency of transformation of both parts of the order parameter under the time reversal.

The general forms of odd functions of momentum directions of pairing particles on the Fermi surface $f_-(\mathbf{k}) = f_x(\mathbf{k}) - if_y(\mathbf{k})$ for the different superconducting states in ferromagnets can be found following the procedure introduced in [28] and it is described here on example of ferromagnetic orthorhombic crystal. The same results for the ferromagnets with orthorhombic and cubic symmetry in terms of the functions $f_x(\mathbf{k})$ and $f_y(\mathbf{k})$ one can find in the paper [28].

Let us consider a ferromagnetic orthorhombic crystal with spontaneous magnetization along one of the symmetry axis of the second order chosen as the z -direction. Its symmetry group

$$G = M \times U(1) \quad (17)$$

consists of the so called magnetic class [52], or black-white group M having a white subgroup H of index 2, and the group of the gauge transformations $U(1)$. In the given case M is equal

to $D_2(C_2^z) = (E; C_2^z) + K C_2^x$ ($E; C_2^z$) = $(E; C_2^z; K C_2^x; K C_2^y)$, where K is the time reversal operation, and $H = (E; C_2^z)$. The symmetry of any magnetic superconducting state arising directly from this normal state corresponds to the one of the subgroups of the group G characterized by broken gauge symmetry. As it was already mentioned the superconducting states $d(R; k)$ with different critical temperatures in the ferromagnetic crystals are classified in accordance with irreducible co-representations of the magnetic group M of crystal. The irreducible corepresentations of M are derived from the irreducible representations of H . The whole procedure was introduced by E Wigner and well described in [53,54]. For us, however, there will be convenient not to follow this general formalism but discuss first the symmetries of possible superconducting states in ferromagnetic material, another words, the ferromagnetic superconducting classes. According to general rules [20] they have to be given by the subgroups of G constructed by means of combining elements of M with phase factor e^i being an element of the group of the gauge transformations $U(1)$. The explicit structures of these subgroups isomorphic to the initial magnetic group $D_2(C_2^z)$ are

$$D_2(C_2^z) = (E; C_2^z; K C_2^x; K C_2^y); \quad (18)$$

$$\tilde{D}_2(C_2^z) = (E; C_2^z; K C_2^x e^i; K C_2^y e^i); \quad (19)$$

$$D_2(E) = (E; C_2^z e^i; K C_2^x e^i; K C_2^y); \quad (20)$$

$$\tilde{D}_2(E) = (E; C_2^z e^i; K C_2^x; K C_2^y e^i); \quad (21)$$

The general forms of the order parameters

$$d(R; k) = \frac{1}{2} [f_1(\hat{x} + i\hat{y})f(k) + f_2(\hat{x} - i\hat{y})f(k)] \quad (22)$$

compatible with symmetries (18)–(21) correspondingly are obtained by the following choice of the functions $f(k)$:

$$f^{A_1}(k) = k_x (u_1^{A_1} - u_4^{A_1}) + ik_y (u_2^{A_1} - u_3^{A_1}); \quad (23)$$

$$f^{A_2}(\mathbf{k}) = ik_x (u_1^{A_2} - u_4^{A_2}) + k_y (u_2^{A_2} - u_3^{A_2}); \quad (24)$$

$$f^{B_1}(\mathbf{k}) = k_z (u_1^{B_1} - u_4^{B_1}) + ik_x k_y k_z (u_2^{B_1} - u_3^{B_1}); \quad (25)$$

$$f^{B_2}(\mathbf{k}) = ik_z (u_1^{B_2} - u_4^{B_2}) + k_x k_y k_z (u_2^{B_2} - u_3^{B_2}); \quad (26)$$

where $u_1^{A_1}; \dots$ are real functions of $k_x^2; k_y^2; k_z^2$.

From the expressions for the order parameters one can conclude that the only symmetry dictated nodes in quasiparticle spectrum of superconducting A-states in orthorhombic ferromagnets are the nodes lying on the northern and southern poles of the Fermi surface $k_x = k_y = 0$. On the contrary for the B-states they are on the line of equator $k_z = 0$.

Similarly, it follows from the general forms of the functions $f(\mathbf{k}) = f_x(\mathbf{k}) - if_y(\mathbf{k})$ found in [28] that for A and B superconducting state of tetragonal magnetic class in cubic crystal the only symmetry nodes are on the northern and southern poles of the Fermi surface $k_x = k_y = 0$ and for E_+ and E_- superconducting states they are both on the poles and on the equator line. For trigonal magnetic class, states A have the nodes on the poles (the direction of the polar axis coincides here with the space diagonal of cube) and states E_+ and E_- have no symmetry nodes at all.

The classification of the states in quantum mechanics corresponds to the general statement by E. Wigner that the different eigenvalues are related to the sets of eigenstates belonging to the different irreducible representations of the group of symmetry of the hamiltonian. In particular, in absence of the time inversion symmetry violation, the superconducting states relating to the nonequivalent irreducible representations of the point symmetry group of crystal obey the different critical temperatures. Similarly the eigenstates of the particles in the ferromagnetic crystals are classified in accordance with corepresentations of magnetic group M of the crystal [53,54]. The latter differs from usual representations by the law of multiplication of matrices of representation which is $(g_1)(g_2) = (gg_2)$ for elements g_1, g_2 of group M if element g_1 does not include the time inversion operation and $(g_1)(g_2) = -(gg_2)$ if element g_1 does include the time inversion. The matrices

of transformation of the order parameters (22) by the symmetry operations of the group $D_2(C_2^z) = (E; C_2^z; KC_2^x; KC_2^y)$ are just numbers (characters). As usual for one-dimensional representations they are equal ± 1 . For the state A_1 (23) which is a conventional superconducting state obeying the complete point-magnetic symmetry of initial normal state they are $(1; 1; 1; 1)$. For the order parameter A_2 (24) they are $(1; 1; -1; -1)$ where -1 corresponds to the elements of the superconducting symmetry class (19) containing the phase factor e^i . The same is true for the table of characters of the other states. So all the corepresentations in the present case are real, however their difference from the usual representations manifests itself in the relationship of equivalence.

The two corepresentations of the group M are called equivalent [54] if their matrices $\Gamma(g)$ and $\Gamma^0(g)$ are transformed to each other by means of the unitary matrix U as $\Gamma^0(g) = U^{-1} \Gamma(g) U$ if the element g does not include the time inversion and as $\Gamma^0(g) = U^{-1} \Gamma(g) U$ if the element g includes the time inversion. The corepresentations for the pair of states A_1 and A_2 are equivalent. In view of one-dimensional character of these corepresentations the matrix of the unitary transformation is simply given by the number $U = i$. The states A_1 and A_2 belong to the same corepresentation and represent two particular forms of the same superconducting state. The state A_2 transforms as $i A_1$ and the state B_2 transforms as $i B_1$. It will be shown below that if we have state A_1 in the ferromagnetic domains with the magnetization directed up the superconducting state in the domains with down direction of the magnetization corresponds to the superconducting state A_2 . The same is true for the pair of states B_1 and B_2 .

The critical temperatures of equivalent states A_1 and A_2 , or equivalent states B_1 and B_2 , in the ferromagnetic domains with the opposite orientations of magnetization are equal (see below). At the same time the states A_1 and A_2 have the different symmetries, that means they belong formally to different ferromagnetic superconducting classes. In this respect the superconducting states in ferromagnet transform according to one-dimensional corepresentations of magnetic group M reveal sort of similarity on multicomponent superconducting states transforming according to multidimensional representation of the point

group of paramagnetic state.

All the listed above superconducting phases are in principle non-unitary and obey the Cooper pair spin momentum

$$S = i\hbar \sum_i d_i = \frac{\hbar}{2} \sum_j (j_z - j_z^\dagger) \quad (27)$$

and Cooper pair angular momentum

$$L = i\hbar \sum_k k \frac{\partial}{\partial k} d_i = \frac{i\hbar}{2} \sum_k k \frac{\partial}{\partial k} (j_z - j_z^\dagger) \quad (28)$$

where the angular brackets denote the averaging over k directions. As the consequence the magnetic moment of ferromagnet changes at the transition to the ferromagnetic superconducting state. We shall calculate this particular change below.

B. Gor'kov equations

The BCS Hamiltonian in two-band ferromagnet with triplet pairing is

$$H = \sum_{k, \alpha} \hbar k \hat{n}_{k\alpha} a_{k\alpha}^\dagger a_{k\alpha} + \frac{1}{2} \sum_{k, k', q} V(k; k') a_{k+q}^\dagger a_{k'-q}^\dagger a_{k'q} a_{kq} \quad (29)$$

where the band indices α and β are $(\uparrow; \#)$ or $(1; 2)$,

$$\hat{n}_{k\alpha} = \hat{n}_{k\alpha}^\dagger \hat{n}_{k\alpha} = 2 + U(r) \quad (30)$$

are one particle band energy operators, the functions $\hat{n}_{k\alpha}$ (including the exchange splitting) and \hat{g} - factor depend of projections of gauge invariant operator $\hat{\psi}^\dagger(r) + (e/c)A(r)$ on crystallographic directions. In the simplest case of isotropic bands without a spin-orbital coupling $g_{1,2} = 2H/H$. $U(r)$ is an impurity potential, $A(r)$ is vector potential such that

$$\nabla \times A = B = H + 4\pi M \quad (31)$$

M is the magnetic moment of the ferromagnet, H is a magnetic field, which should be determined from the Maxwell equations

$$\mathbf{r} \cdot \mathbf{H} = \frac{4}{c} \mathbf{j}; \quad \mathbf{r} \cdot \mathbf{B} = 0; \quad (32)$$

with Maxwell boundary conditions of the continuity of B_n and H_t at the boundary of the sample and $\mathbf{H} \rightarrow \mathbf{H}_{\text{ext}}$ at infinity. The equations for determination the moment \mathbf{M} and current \mathbf{j} densities see below.

The pairing potential interaction is expanded over

$$V(\mathbf{k}; k^0) = V'_{-}(\mathbf{k})'_{-}(k^0); \quad (33)$$

where

$$'_{-}(\mathbf{k}) = f_{-}(\mathbf{k}); \quad '_{+}(\mathbf{k}) = f_{+}(\mathbf{k}); \quad (34)$$

It contains four different interaction terms corresponding to: (i) a pairing between electrons with the same spin polarization (intraband interaction) and (ii) the interband scattering terms with $V'_{\pm} = V_{\mp}$ describing the transitions of the pair electron from one sheet of the Fermi surface to the other sheet by reversing the pair spin orientation with the help of the spin-orbit coupling.

When the interband scattering is negligible $V'_{\pm} = V_{\mp} = 0$, the pairing of the electrons occurs first only in one of the sheets of the Fermi surface like in the A_1 phase of ^3He . In general the superconductivity in each band is not independent.

The full system of equations describing the magnetostatic behavior of ferromagnetic superconductor consists of Gor'kov equations for the Green functions in two bands,

$$\sum_{k_1} \hbar k_1 j_1 \hat{n} \hat{h} j_1 i G(k_1; k^0; !_n) + \sum_q (k; q) F^y(k - q; k^0; !_n) = (k - k^0); \quad (35)$$

$$\sum_{k_1}^{k_1} \hbar k_1 j_1 \hat{n} + \hat{h} j_1 k i F^y(k_1; k^0; !_n) + \sum_q^q F^y(k; q) G(k + q; k^0; !_n) = 0; \quad (36)$$

$$\sum_{k_1}^{k_1} \hbar k_1 j_1 \hat{n} \hat{h} j_1 i F(k_1; k^0; !_n) + \sum_q^q (k; q) G(k - k^0; k + q; !_n) = 0; \quad (37)$$

combined with the self-consistency equation

$$(k; q) = T \sum_n \sum_{k^0} V(k; k^0) F(k^0 + \frac{q}{2}; k^0 - \frac{q}{2}; !_n); \quad (38)$$

here $\epsilon_n = (2n + 1) T$ are fermionic Matsubara frequencies, Maxwell equations (31), (32) and definitions of current density

$$j(k) = 2eT \sum_{n, p, p^0} \sum_{\sigma} \left(\frac{\partial}{\partial p} + \frac{\partial}{\partial p^0} \right) \text{tr} \left[\hat{J}^{\sigma} \hat{p}^0 iG \left(\frac{p + p^0 + k}{2}; \frac{p + p^0 - k}{2}; \epsilon_n \right) \right]; \quad (39)$$

and magnetic moment density

$$M(k) = \hat{z} \sum_{n, p} \sum_{\sigma} [G_{\sigma}(p + k/2; p - k/2; \epsilon_n) - G_{\sigma}(p + k/2; p + k/2; \epsilon_n)]; \quad (40)$$

We want to determine the Green's functions of ferromagnetic superconductors in the absence of external field and impurity scattering. Even under these simple conditions, the system is not spatially uniform due to the inherent presence of $4M$. If we artificially neglect by $4M$ as internal field acting diamagnetically on electron charges taking $A = 0$, the system is spatially uniform. Then, we can write the Gor'kov equations in the form

$$(i\epsilon_n - k) G(k; \epsilon_n) + (k) F^{\vee}(k; \epsilon_n) = 1 \quad (41)$$

$$(i\epsilon_n + k) F^{\vee}(k; \epsilon_n) + \vee(k) G(k; \epsilon_n) = 0 \quad (42)$$

where $k = \epsilon_k - \epsilon_F$. The equations for each band are only coupled through the order parameter given by the self-consistency condition

$$(k) = T \sum_{n, k^0} \sum_{\sigma} V_{\sigma}(k; k^0) F^{\vee}(k^0; \epsilon_n); \quad (43)$$

The superconductor Green's functions are

$$G(k; \epsilon_n) = \frac{i\epsilon_n + k}{\epsilon_n^2 + E_k^2}; \quad (44)$$

$$F^{\vee}(k; \epsilon_n) = \frac{(k)}{\epsilon_n^2 + E_k^2}; \quad (45)$$

where $E_k = \sqrt{\epsilon_k^2 + j(k)^2}$. Obviously, the superconductivity in ferromagnetic superconductors is non-unitary.

The disregard by the electromagnetic field $4M$ acting on electron charges does not mean the absence of magnetic moment M due to difference in the electron spin up and spin down populations. For the normal state moment density we obtain from the eqn (40)

$$M_n = \hat{z}_B T \int_n^X \int^Z d \frac{h_-(\hat{p})}{i!_n} \frac{h_+(\hat{p})}{i!_n} = \hat{z}_B (N_- - N_+); \quad (46)$$

where $h_-(\hat{p})$ and N_- are the density of states averaged over the solid angle and the density of particles in the corresponding band. The magnetic moment in superconducting state acquires an extra value. Near the critical temperature it is

$$\begin{aligned} M_s = M_n - M_n &= \hat{z}_B T \int_n^X \int^Z d \frac{h_-(\hat{p})j_-(p)f_i}{(i_n^2 + \mu^2)^2} - \frac{h_+(\hat{p})j_+(p)f_i}{(i_n^2 + \mu^2)^2} \\ &= \frac{\hat{z}_B}{4} [h_-^{(0)}(0;p)j_-(p)f_i \ln \frac{2\gamma_-}{T_c} - h_+^{(0)}(0;p)j_+(p)f_i \ln \frac{2\gamma_+}{T_c}]; \end{aligned} \quad (47)$$

where $h^{(0)}(0;p)$ is the derivative of the density of states at the Fermi surface and μ is the pairing interaction energy cutoff in the corresponding band. It is instructive to compare this expression with the Cooper pair spin momentum (27).

C. The order parameter equations near the superconducting transition

We shall be interested by the simplest applications of the general theory formulated in the previous subsection such that the critical temperature suppression by the impurities and upper critical field calculation. For this purpose we need the system of the linear equations for the order parameter arising from Gor'kov equations averaged over impurities. This system consists of two equations for the order parameter components with spin polarizations "up" and "down",

$$\begin{aligned} (R; r) &= T \int_n^X \int^Z dr V; (r; r^0) G^0(r; t_n) G^0(r^0; -t_n) \\ &\exp[i\tau D(R)] (R; r^0) + (t_n; R); \end{aligned} \quad (48)$$

and two equations for the impurity self-energy components

$$\begin{aligned} (t_n; R) &= n_i u^2 \int^Z dr G^0(r; t_n) G^0(r; -t_n) \exp[i\tau D(R)] \\ &+ (R; r) + (t_n; R)g; \end{aligned} \quad (49)$$

where $\tau_n = \tau_n + \text{sign } \tau_n = 2$, and τ is the quasi-particle mean free time in the different bands. These mean free times are related in the Born approximation to the impurity concentration n_i through

$$\frac{1}{2} = n_i N_0 u^2; \quad (50)$$

with u - the amplitude of the impurity scattering and N_0 - the density of electronic states in each band.

The operator of covariant differentiation is

$$D(R) = i \frac{\partial}{\partial R} + \frac{2e}{c} A(R):$$

The normal metal electron Green functions are

$$G^0(r; \tau_n) = \frac{1}{(2\pi)^3} \int d^3p e^{ip \cdot r} (i\tau_n - \epsilon_p + \epsilon_F) \delta(\tau_n - \tau_p) : \quad (51)$$

The order parameter components in different bands are determined in accordance with (15):

$$\psi_1(R; r) = \psi_1(R) f_1(r); \quad \psi_2(R; r) = \psi_2(R) f_2(r): \quad (52)$$

Let us take now $H_{\text{ext}} = 0$; $r = A = 4 M$. Consider two superconducting states A_1 and A_2 determined by the equal functions $\psi_1^{A_1} = \psi_1^{A_2}$. It is clear in this case that

$$\psi_1 = \psi_1 f_1^{A_1} = \psi_1 (f_1^{A_2}); \quad (53)$$

$$\psi_2 = \psi_2 f_2^{A_1} = \psi_2 (f_2^{A_2}): \quad (54)$$

We see, that if the superconducting state A_1 is a solution of the equations (48), (49), then the state A_2 also obeys the same equations but with interchanged band indices 1 & 2 that is accompanied according to eqns (46), (48) by the change of magnetic moment direction. It means, that these A_1 and A_2 superconducting states possess the same critical temperature but they are realized in the ferromagnetic domains with the oppositely directed magnetic moments.

D. The critical temperature T_{c0}

In the absence of an external field let us first find the critical temperature T_c in the formally spatially uniform situation of negligible electromagnetic field $4\pi M = 0$ acting diamagnetically on the electron charges. This case the anomalous in-purity self-energy part $\langle \epsilon_n; R \rangle = 0$ and from (48) we obtain the system of equations

$$\begin{aligned} 1 &= (g_{1-1} + g_{12-2}) (T_{c0}); \\ 2 &= (g_{21-1} + g_{2-2}) (T_{c0}); \end{aligned} \quad (55)$$

where $g_1 = V_{++} \hbar f_-(k) \int N_{0+}(\hat{k}) i$, the angular brackets mean the averaging over the Fermi surface, $N_{0+}(\hat{k})$ is the angular dependent density of electronic states at the Fermi surface of the band "+". Correspondingly $g_{12} = V_{\#} \hbar f_+(k) \int N_{0\#}(\hat{k}) i$, $g_{21} = V_{\#} \hbar f_-(k) \int N_{0+}(\hat{k}) i$, $g_2 = V_{\#} \hbar f_+(k) \int N_{0\#}(\hat{k}) i$. The function $\psi(T)$ is

$$\psi(T) = 2 \sum_{n=0}^{\infty} \frac{1}{n!} = \ln \frac{2}{T}; \quad (56)$$

$\ln 2 = 0.6931 \dots$ is the Euler constant, ϵ_F is an energy cutoff for the pairing interaction. We assume here that it has the same value for both bands.

Thus, similar to [30,31] the critical temperature is given by

$$T_{c0} = (2 \epsilon_F) \exp(-1/g); \quad (57)$$

where g is defined by the maximum of zeros of determinant of the system (55)

$$g = (g_1 + g_2) \left[2 + \frac{g_1 g_2}{(g_1 - g_2)^2 + g_{12} g_{21}} \right]; \quad (58)$$

In particular at $g_{12} = g_{21} = 0$; g_1, g_2 the critical temperature is determined by

$$g = \max(g_1, g_2); \quad (59)$$

All the properties of metal depend on pressure. In ferromagnetic metal the pressure shifts the Fermi surface position and changes the densities of spin up and spin down electron

populations. Density of states at the Fermi surface in each band and the superconducting interaction are also changed. The critical temperature changes following to the relative changes of the effective constant of pairing interaction g . In the case of one band pairing the latter can be roughly represented as sum of relative change of density of states due to the Fermi energy shift and relative change of pairing amplitude $g = g / \mu_F = \mu_F + V = V$. The situation with changes of the pairing interaction is far to be clear. In assumption that the relative change of density of states gives the main contribution we have

$$T_c(P) = T_c(P_0) \left[1 + \frac{\mu_F}{\mu_F} \ln \frac{2}{T_c(P_0)} \right] : \quad (60)$$

The Fermi energy shift can be somehow magnetization dependent. In the simplest case one can expect $\mu_F / \mu_B \propto M$. Thus the magnetization changes can cause the growing up (as well as falling down) of the superconducting transition temperature. This has been proposed [25] as an explanation of a "stimulation" of superconductivity by ferromagnetism observed in $ZrZn_2$ [3]. On the other hand a superconductivity is always suppressed by the diamagnetic currents. We shall make the comparison of these two mechanisms of $T_c(P)$ dependence after the calculation of the upper critical field.

E. The critical temperature dependence on impurities concentration

Triplet superconductivity is suppressed by non-magnetic impurities [55]. The law of suppression of superconductivity is given by the universal Abrikosov-Gorkov (AG) dependence [56]

$$\ln t = -\frac{1}{2} + \frac{x}{4t} - \frac{1}{2} \quad (61)$$

valid for any unconventional superconducting state and applicable in particular to a concrete unconventional superconductor independently of the pressure [24]. Here t is the digamma function. The variable $t = T_c/T_{c0}$ is the ratio of the critical temperature of the superconductor with a given concentration of impurities n_i to the critical temperature of the clean

superconductor, and $x = n_i/n_{ic} = x_c$ is the ratio of the impurity concentration in the superconductor to the critical impurity concentration destroying superconductivity, or the inverse ratio of the corresponding mean free particle lifetimes. The critical mean free time is given by $\tau_c = \tau_0 = T_{c0}$. This dependence has been demonstrated (although with some dispersion of the experimental points) for the triplet superconductor Sr_2RuO_4 [57].

Deviations from the universality of the AG law can be caused by the anisotropy of the scattering which takes place in the presence of extended imperfections in the crystal. Such a modification of the theory applied to UPt₃ has been considered in the paper [58]. However, a complete experimental investigation of the suppression of superconductivity by impurities in this unconventional superconductor, in particular the study of the universality of the behavior, has not been performed.

The nonuniversality of the suppression of superconductivity can also be caused by any inelastic scattering mechanism by impurities with internal degrees of freedom of magnetic or nonmagnetic origin. For the simplest discussion of this, see [59].

Finally, universality is certainly not expected in multiband superconductors. Theories for this case have been developed with regard to the unconventional superconductivity in Sr_2RuO_4 (p-wave, two-band two-dimensional model [60]) and conventional superconductivity in MgB_2 (anisotropic scattering two-band model [61]).

A simple modification of the universal AG law for the suppression of the superconductivity by impurities in a two-band ferromagnetic superconductor is derived here. Our consideration is limited to the simplest case of scattering by ordinary point-like impurities. Then, due to spin conservation, one can neglect interband quasiparticle scattering and take into account only the intraband quasiparticle scattering on impurities. At finite impurity concentration the similar to (55) system of equations is:

$$\begin{aligned} \tau_1 &= g_{11}^{-1}(T) \tau_1 + g_{12}^{-1}(T) \tau_2; \\ \tau_2 &= g_{21}^{-1}(T) \tau_1 + g_{22}^{-1}(T) \tau_2; \end{aligned} \tag{62}$$

where

$$g_{12}(T) = \frac{1}{2} - \frac{1}{2} + \frac{1}{4g_1 T} + \ln \frac{T_{c0}}{T} + (T_{c0}): \quad (63)$$

Hence the critical temperature is determined from the equation

$$(g_{11}(T) - 1)(g_{22}(T) - 1) - g_{12}g_{21}(T) = 0: \quad (64)$$

In particular at $g_{12}; g_{21} = g_1; g_2$ the critical temperature is determined by the maximum $(T_{c1}; T_{c2})$ of the solutions of equations

$$\ln \frac{T_{c0}}{T_{c1}} = \frac{1}{2} + \frac{1}{4g_1 T_{c1}} - \frac{1}{2} + \frac{1}{g_1} (T_{c0}); \quad (65)$$

$$\ln \frac{T_{c0}}{T_{c2}} = \frac{1}{2} + \frac{1}{4g_2 T_{c2}} - \frac{1}{2} + \frac{1}{g_2} (T_{c0}): \quad (66)$$

Let us accept for definiteness that $g_1 > g_2$ hence the maximal critical temperature in absence of impurities is defined by $1/g_1 = (T_{c0})$. Then at small impurity concentrations the solutions of (65) and (66) are the linear functions of impurities concentration:

$$T_{c1} = T_{c0} - \frac{1}{8g_1}; \quad (67)$$

$$T_{c2} = T_{c0} - \frac{1}{g_2} + \frac{1}{g_1} - \frac{1}{8g_2}: \quad (68)$$

These lines can in principle intersect each other, as result an upturn on the critical temperature dependence of impurity concentration $T_c(n_i)$ is appeared. Such the type of deviations of the $T_c(n_i)$ dependence from the AG-law present the direct manifestation of the two-band character of the superconductivity. On the other hand, an absence of strong deviations from the universal one-band curve if it would found experimentally in a ferromagnetic superconductor means that the superconductivity is developed in one-band with only electrons with "up" spins paired and the "down" spin electrons leave normal (or vice versa).

Another specific feature of the ferromagnetic superconductors is that even in the absence of an external magnetic field a ferromagnet produces an electromagnetic field $4\pi M = 4\pi_B k_F^3$ acting via the electronic charges on the orbital motion of electrons, and

suppressing the superconductivity [62]. Hence, the actual critical temperature in ferromagnetic superconductors is always smaller by the value $4 M = H_{c2}(T = 0)$ relative to the (imaginary) ferromagnetic superconductor without $4 M$. The upper critical field H_{c2} is also purity dependent. That is why the impurity concentration dependence of the actual T_c in a ferromagnetic superconductor might be determined not only directly by the suppression of superconducting correlations by the impurity scattering as in any nonconventional superconductor but also indirectly through the suppression of H_{c2} . In fact the second indirect mechanism has a smaller influence because the ratio $4 M = H_{c2}(T = 0)$ is less than 1=10 for superconductors with an upper critical field of the order of several Teslas.

Thus the problem of determination of the critical temperature in superconducting ferromagnet is at bottom the problem of determination of the upper critical field in single domain ferromagnet.

F. The upper critical field

The equations for determination of upper critical field at least near T_c is easily derived from the system (48), (49). Keeping only the lowest order gradient terms we have

$$\begin{aligned} (R; r) = & \int_{-n}^X \int_{-Z}^Z dr^0 V; (r; r^0) G^0(r; t_n) G^0(r^0; t_n) \\ & \int_{-1}^n (r^0 D(R))^2 = 2 \quad (R; r^0) + (ir^0 D(R)) \quad (t_n; R) ; \end{aligned} \quad (69)$$

and

$$\begin{aligned} (t_n; R) = & n_i u^2 \int_{-Z}^Z dr G^0(r; t_n) G^0(r; t_n) \\ & f(ir^0 D(R)) \quad (R; r) + \quad (t_n; R) g; \end{aligned} \quad (70)$$

Finding $(t_n; R)$ from the last equation and substituting to (31) we obtain after all the necessary integrations the pair of the Ginzburg-Landau equations for two components of the order parameter

$$\begin{aligned} \psi_1 &= V_{11} \psi_1 + V_{12} \psi_2; \\ \psi_2 &= V_{21} \psi_1 + V_{22} \psi_2; \end{aligned} \quad (71)$$

where operator \hat{V}_1 consists of previously determined homogeneous part and second order gradient terms

$$\hat{V}_1 = \hbar^2 \nabla^2 N_0(\hat{k}) i \nabla_1(T) - K_{ij} D_i D_j; \quad (72)$$

The gradient terms coefficients are

$$\begin{aligned} K_{ij} &= \hbar^2 \nabla^2 N_0(\hat{k}) v_{F,i}(\hat{k}) v_{F,j}(\hat{k}) i \frac{\partial}{\partial k_i} \frac{1}{v_F} \\ &+ \hbar^2 N_0(\hat{k}) v_{F,i}(\hat{k}) i \hbar^2 \nabla^2 N_0(\hat{k}) v_{F,j}(\hat{k}) i \frac{\partial}{\partial k_j} \frac{1}{v_F} \end{aligned} \quad (73)$$

Operator \hat{V}_2 is obtained from here by the natural substitutions $1 \rightarrow 2, \psi_1 \rightarrow \psi_2, + \rightarrow -$.

Now the problem of the upper critical field finding is just the problem of solution of the two coupled equations (71). There are a lot of different situations depending of crystal symmetry, direction of spontaneous magnetization and the external field orientation. The simplest case is when the external magnetic field is parallel or antiparallel to the easy magnetization axis. If the latter coincides with 4-th order symmetry axis in the cubic crystal like it is in $ZrZn_2$ when the gradient terms in the perpendicular plane are isotropic and described by two constants $K_{ij} = K_{\perp ij}, K_{\parallel ij} = K_{\parallel ij}$. This case formally corresponds to the problem of determination of upper critical field parallel to the c-direction in two-band hexagonal superconductor MgB_2 solved in [31]. Then the linearized Ginzburg-Landau equations describe a system of two coupled oscillators and have the solution in the form $\psi_1 = c_1 f_0(x)$ and $\psi_2 = c_2 f_0(x)$, where $f_0(x) = \exp(-hx^2/2)$ and h is related to the upper critical field by means

$$\hbar^2 c_2^2 = 4 M_j = \frac{\hbar^2 \psi_0}{2}; \quad (74)$$

where ψ_0 is the flux quantum.

Let us for the simplicity limit ourselves by the impurityless case. Then $\kappa = 1$, $T = T_0$ and the equation for the determination of upper critical field is

$$\begin{aligned}
& [g_1 (1 + (T_{c0})) + V_{xx} K_{xx} h_1] [g_2 (1 + (T_{c0})) + V_{yy} K_{yy} h_2] \\
& [g_2 (1 + (T_{c0})) + V_{xx} K_{xx} h_1] [g_1 (1 + (T_{c0})) + V_{yy} K_{yy} h_2] = 0
\end{aligned} \tag{75}$$

This is a simple square equation and as before if we consider the case $g_{12}; g_{21} = g_1; g_2$ and $g_1 > g_2$ then we obtain the following two roots

$$h_1(\tau) = \frac{g_1}{V_{xx} K_{xx}}; \tag{76}$$

$$h_2(\tau) = \frac{g_2}{V_{yy} K_{yy}} + \frac{1}{g_1} - \frac{1}{g_2} \tag{77}$$

These two lines can in principle intersect each other, then an upturn on the temperature dependence of the upper critical field given by the $\max(h_1; h_2)$ is appeared.

In the more anisotropic situation such as in orthorhombic crystals UGe_2 and $URhGe$ even for the external field direction parallel or antiparallel to the easy magnetization axis all the coefficients $K_{xx}, K_{yy}, K_{xx}, K_{yy}$ are different. Then our system of equations can be solved following a variational approach developed in [31]. Again an upturn in $h(\tau)$ dependence can be possible.

The comparison with experiment shall be always not easy masked by the presence of many ferromagnetic domains. The monodomain measurements are possible in high enough fields. To work in this region one can easily obtain the forth order gradient terms to the Ginzburg-Landau equations. However the problem of theoretical determination of the upper critical field at arbitrary temperature has the same principal difficulties as in any conventional anisotropic superconductor [63].

At last, we shall discuss the problem of stimulation of superconductivity by the ferromagnetism. The simple estimation from the equation (76) shows that in the absence of an external field the diamagnetic suppression of critical temperature of ferromagnetic superconductor by its own ferromagnetic moment is

$$T_c / T_{c0} = 1 - \frac{B_M m v_F^2}{T_{c0}^2} : \tag{78}$$

Hence the comparison of this expression with formula (60) yields the criterium for the stimulation of superconductivity by ferromagnetism

$$\frac{\mu_F}{\mu_B} > \frac{M}{T_{c0}^2} \frac{v_F^2}{2} \quad (79)$$

It looks like unrealistic. Hence the explanation of stimulation of superconductivity by ferromagnetism in $ZrZn_2$ introduced in the paper [25] seems unpalatable. We remind, however, that criterium (79) was obtained in the assumption of absence of changes of the pairing amplitude with pressure which could be the main source of the critical temperature changes.

V. SUPERCONDUCTIVITY IN THE METALS WITHOUT INVERSION CENTRUM

The multiband classification of electronic states in ferromagnetic metals appears as the result of the level splitting due to an exchange field. Another reason for the level splitting always exists in a metal without inversion center. This is spin-orbital coupling. It causes not only electron level splitting but also the nontrivial spinor structure of the electronic states being important for the proper description of superconductivity in the metals with broken space parity. The good introduction in general formalism of the Bloch states and superconductivity in noncentrosymmetric crystals is given in paper [48] where also discussed the particular form of the theory in the limit of small spin-orbit coupling. Here in somewhat different manner we introduce the basic theoretical notions. Unlike to the paper [48] and several others cited in Introduction we shall speak only about the situation with strong spin-orbital coupling producing the big band splitting and preventing the pairing of electronic states from different bands. The recently discovered noncentrosymmetric superconductor $CePt_3Si$ belongs to this category. The band structure calculation for this material found [47] that the bands for the states close to Fermi level are split due to the spin-orbital coupling by 50-200 meV, which is more than thousand times larger than the temperature of superconducting transition $T_c = 0.75K$ [34]. In this case the theory acquires the features of similarity on the theory of superconductivity for ferromagnetic superconductors.

A. Electronic states and pairing in noncentrosymmetric metals

Let us start from description of normal state in the crystal without inversion center. For each band its single-electron Hamiltonian has the form

$$H = \epsilon_k^0 + \mathbf{h}_k \cdot \mathbf{j}_k; \quad (80)$$

where \mathbf{k} is the wave-vector, the $\epsilon_k^0 = \epsilon_{-\mathbf{k}}^0$ is even function of \mathbf{k} , the spin-orbital coupling is described by an odd pseudovectorial function $\mathbf{h}_k = h_k \mathbf{n}_k$, $\mathbf{n}_k = (n_x; n_y; n_z)$ is the vector consisting of Pauli matrices. The eigen values and eigen functions of this Hamiltonian are

$$\epsilon_k = \epsilon_k^0 \pm h_k j_k \quad (81)$$

$$\psi_{\pm}(\mathbf{k}) = C_p \begin{pmatrix} 0 & 1 \\ k_x + i k_y & k_z + j_k j_y \end{pmatrix} \begin{pmatrix} B \\ A \end{pmatrix}; \quad \psi_{\pm}(\mathbf{k}) = C_p \begin{pmatrix} 0 & 1 \\ k_z + j_k j_y & k_x + i k_y \end{pmatrix} \begin{pmatrix} B \\ A \end{pmatrix}; \quad (82)$$

$$C_p = (2j_k j_y (k_z + j_k j_y))^{-1/2};$$

So, we have obtained the band splitting and $n = 0, 1$ is the band index. As result, there are two Fermi surfaces determined by equations

$$\epsilon_k = \epsilon_F; \quad (83)$$

which may of course have the degeneracy points or lines for some directions of \mathbf{k} . The symmetry of directions of the dispersion laws ϵ_k has to correspond to the crystal symmetry. Particular attention however deserves the operation of reflection \mathbf{k} to $-\mathbf{k}$ which creates the time reversed states.

By application of operator of time inversion $\hat{K} = i_y K_0$, where K_0 is the complex-conjugation operator one can see that the state $\psi_{\pm}(\mathbf{k})$ and the state inversed in time

$$\hat{K} \psi_{\pm}(\mathbf{k}) = t_{\pm}(\mathbf{k}) \psi_{\pm}(-\mathbf{k}); \quad t_{\pm}(\mathbf{k}) = e^{i(\phi_{\pm}(\mathbf{k}) - \phi_{\pm}(-\mathbf{k}))}; \quad \phi_{\pm} = \arg(k_x \hat{x} + k_y \hat{y}) \quad (84)$$

are degenerate. Another words, they correspond to the same energy $\epsilon_k = \epsilon_{-k}$. So, the Fermi surfaces in a crystal without inversion center still have mirror symmetry. This is the consequence of time inversion symmetry.

Let us note also the important fact that the phase factor in (84) is the odd function of k :

$$t(-k) = -t(k) \quad (85)$$

If we have the normal one-electron states classification in a crystal without inversion symmetry it is quite natural to describe the superconductivity directly in the basis of these states. So, if we consider the pairing only between the states with some k and its negative then the BCS Hamiltonian in the space homogeneous case looks as follows

$$H_{BCS} = \sum_k \epsilon_k a_k^\dagger a_k + \frac{1}{2} \sum_{k, k^0} V(k, k^0) a_{k, \uparrow}^\dagger a_{k, \downarrow}^\dagger a_{k^0, \downarrow} a_{k^0, \uparrow} \quad (86)$$

where k, k^0 are the band indices for the bands introduced above and

$$\epsilon_k = \epsilon_k \quad (87)$$

are the band energies counted from the chemical potential. Due to big difference between the Fermi momenta we neglect in Hamiltonian by the pairing of electronic states from different bands. The structure of theory is now very similar to the theory of ferromagnetic superconductors with triplet pairing. However, here there is some special peculiarity. The operators $a_{k, \uparrow}$ and $a_{k, \downarrow}^\dagger$, with fixed band index k , that are related to the states in one particular band, they still are the spinor operators. In particular, the time inversion transforms them in accordance with the rule (84):

$$K a_{k, \uparrow}^\dagger = t(k) a_{k, \downarrow}^\dagger; \quad K a_{k, \downarrow} = t(k) a_{k, \uparrow} \quad (88)$$

Let us introduce as usual the molecular fields

$$\Delta_k = \sum_{k^0} V(k, k^0) \langle a_{k^0, \downarrow} a_{k^0, \uparrow} \rangle \quad (89)$$

Then the hamiltonian can be rewritten as

$$H_{BCS} = \sum_k a_k^\dagger a_k + \frac{1}{2} \sum_k a_k^\dagger a_k^\dagger + \sum_k a_k a_k + \text{const} \quad (90)$$

It follows immediately from the anticommutation of the Fermi operators [47] that

$$a_k^\dagger = -a_{-k} \quad (91)$$

On the other hand the hamiltonian (90) should be time reversal invariant. By application \hat{K} to (90) and using rule (88) and property (85) we find the condition of the time invariance:

$$t^{-2}(k) \hat{K} a_k^\dagger = a_{-k}^\dagger \quad (92)$$

The solution of this equation is

$$a_k = t(k) \phi(k) \quad (93)$$

where $\phi(k)$ is an even function of k , which is easily established from (89) if we chose for the pairing potential

$$V(k; k^0) = V(k; k^0) t(k) t(k^0) \sum_i \phi_i(k) \phi_i(k^0) \quad (94)$$

Here $\phi_i(k)$ are the even functions of an irreducible representation dimensionality d of the group of the crystal symmetry G .

Thus, in the noncentrosymmetric crystal the decomposition of the pairing potential over the functions of irreducible representation contains nontrivial phase factors. The latter are odd functions of k and due to this reason the order parameter function a_k , being according to (91) an odd function of k is transforming at the same time according to even function of irreducible representation of the crystal symmetry group

$$a_k / t(k) \phi_i(k) \quad (95)$$

The group of symmetry of the compound CePt_3Si is C_{4v} . It has four one-dimensional irreducible representations: $A_1; A_2; B_1; B_2$ and one two-dimensional E . The examples of

even functions of its irreducible representations are $\Gamma_{A_1} / (k_x^2 + k_y^2 + k_z^2)$; $\Gamma_{A_2} / k_x k_y (k_x^2 + k_y^2)$; $\Gamma_{B_1} / (k_x^2 - k_y^2)$; $\Gamma_{B_2} / k_x k_y$; $(\Gamma_{E_1}; \Gamma_{E_2}) / (k_z k_x; k_z k_y)$. For given superconducting state the functions Γ_i relating to the different bands can be in principle different functions transforming according to the same irreducible representation. The symmetry dictated nodes in the quasiparticle spectrum of superconducting CePt₃Si are absent in the case of realization of A_1 state. They are placed on the lines: $k_x = 0; k_y = 0; k_x = -k_y$ for A_2 state, $k_x = -k_y$ for B_1 state, $k_x = 0; k_y = 0$ for B_2 state, and $k_z = 0$ and $k_x = k_y = 0$ for E state.

For Gor'kov equations in each band we have

$$(i\partial_n - \xi_k) G(k; !_n) + \sum_k F^Y(k; !_n) = 1 \quad (96)$$

$$(i\partial_n + \xi_k) F^Y(k; !_n) + \sum_k G(k; !_n) = 0: \quad (97)$$

The equations for each band are only coupled through the order parameters given by the self-consistency equations

$$\Delta_k = T \sum_n \sum_{k^0} X_k X_{k^0} V(k; k^0) F(k^0; !_n): \quad (98)$$

The superconductor Green's functions are

$$G(k; !_n) = \frac{i\partial_n + \xi_k}{(i\partial_n - \xi_k)(i\partial_n + \xi_k) - \sum_k \Delta_k \Delta_k^Y} \quad (99)$$

$$F^Y(k; !_n) = \frac{\sum_k \Delta_k}{(i\partial_n - \xi_k)(i\partial_n + \xi_k) - \sum_k \Delta_k \Delta_k^Y}: \quad (100)$$

The energies of elementary excitations are given by

$$E_k = \frac{\xi_k}{2} \pm \sqrt{\frac{\xi_k^2}{2} + \sum_k \Delta_k \Delta_k^Y}: \quad (101)$$

The structure of the Gor'kov theory in the ferromagnetic and noncentrosymmetric superconductors has only formal similarity. If in two band ferromagnets the states in different bands have fixed opposite spin projections, in two band noncentrosymmetric crystal the states in each band are the spinors with spin projection depending on momentum direction. To make this distinction more transparent let us write the Gor'kov equation in the initial spinor basis, consisting of two states with spin up and spin down projection:

$$i!_n \quad {}^0_k \quad {}_k \quad \hat{G}(\mathbf{k};!_n) + \hat{F}^y(\mathbf{k};!_n) = \hat{1} \quad (102)$$

$$i!_n + {}^0_k + {}_k \quad \hat{F}^y(\mathbf{k};!_n) + \hat{G}(\mathbf{k};!_n) = 0; \quad (103)$$

where ${}^0_k = {}^0_k$,

$$\hat{G}(\mathbf{k};!_n) = \hat{P}_+ G_+(\mathbf{k};!_n) + \hat{P}_- G_-(\mathbf{k};!_n); \quad (104)$$

$$\hat{F}^y(\mathbf{k};!_n) = \hat{g}^t \hat{P}_+ F_+^y(\mathbf{k};!_n) + \hat{P}_- F_-^y(\mathbf{k};!_n) \quad ; \quad (105)$$

$$\hat{g}_k = \hat{P}_+ \hat{g}_{k^+} + \hat{P}_- \hat{g}_{k^-} \quad ; \quad (106)$$

$$\hat{P}_\pm = (1 \pm \hat{\sigma}_y)/2, \hat{g} = i\hat{\sigma}_y, \hat{g}_k = \hat{g}_{k^+} \hat{g}_{k^-}.$$

Thus, superconducting order parameter consists of sum singlet and triplet parts

$$\hat{g}_k = \frac{k^+ + k^-}{2} \hat{g} + \frac{k^+ - k^-}{2} \hat{g}_k \quad ; \quad (107)$$

At the same time in the absence of the external field the superconducting state is unitary

$$M = \sum_{n,k} \hat{G}(\mathbf{k};!_n) = 0: \quad (108)$$

It is worth noting that the basic equations (102)-(107) have the same structure as in the theory with weak spin-orbital interaction initially developed in [35]. There is however an important distinction that the pairing potential is given now by eqn (94). On the other hand one can naively start from the pairing of the "initial" states which are formed in the crystal with strong spin-orbital coupling which do not introduce the parity violation and only after this to add the parity violating terms. Then, for the triplet case with vector $\mathbf{d}(\mathbf{k})$ of the order parameter, the theory acquires very complicated form originating of presence of the three physically different vectors $\mathbf{d}(\mathbf{k})$, $\mathbf{d}(\mathbf{k})$ and $\mathbf{d}(\mathbf{k})$ $\mathbf{d}(\mathbf{k})$.

B. Electronic states in noncentrosymmetric metal and pairing under magnetic field

Let us look now on the modifications which are appeared by the application of external magnetic field.

It is known [64] that the diamagnetic influence of field is taken into consideration by the Peierls substitution $\mathbf{k} \rightarrow \mathbf{k} + (e\hbar/c)\mathbf{A}(\mathbf{r})$. We shall be interested here in pure paramagnetic effects. Neglecting by the term with magnetic field in the Peierls substitution we take into account only direct paramagnetic influence of magnetic field

$$H = \epsilon_k^0 + \sum_{ij} \gamma_{ij} H_{ij}; \quad (109)$$

where $\gamma_{ij} = \gamma_{ji}$ is even tensorial function of \mathbf{k} . In the isotropic approximation $\gamma_{ij} = \gamma_B g_{ij}/2$, where g is gyromagnetic ratio. The eigen values of this Hamiltonian are

$$\epsilon_k = \epsilon_k^0 + \sum_{ij} \gamma_{ij} H_{ij}; \quad (110)$$

It is obvious from here that the time reversal symmetry is lost $\epsilon_{\mathbf{k}} \neq \epsilon_{-\mathbf{k}}$ and the shape of the Fermi surfaces do not obey the mirror symmetry. The same situation takes place in the ferromagnetic metal without inversion symmetry. The degeneracy of states \mathbf{k} and $-\mathbf{k}$ is lifted by the exchange field and, in general, in a ferromagnet without inversion like MnSi can not be superconducting. On the contrary the discovery of superconductivity in monoclinic ferromagnet UIr is already reported [65]. It could be either due to crystalline anisotropy leading to weak influence of exchange field on some group of charge carriers, or due to realization of more exotic possibility like FFLO state. The first possibility is related to the problem of the paramagnetic limiting field in noncentrosymmetric superconductors [51] which we discuss here.

For simplicity let us assume that we have pairing only in one band: $\psi = \psi_+$. The treatment of general case is similar but more lengthy. Also we are limited ourselves by consideration only one-dimensional representations when we have $V_{++}(\mathbf{k}; \mathbf{k}^0) = V_t(\mathbf{k})t(\mathbf{k}^0)^* \hat{\mathbf{k}}^* \hat{\mathbf{k}}^0$. The equation for critical temperature that is the linear version of (98) has in this case the form

$$\begin{aligned} \chi(\mathbf{k}) &= \sum_{\mathbf{n}} \sum_{\mathbf{k}^0} V_t(\mathbf{k}) t(\mathbf{k}^0)^* \hat{\mathbf{k}}^* \hat{\mathbf{k}}^0 G^0(\mathbf{k}^0; i\omega_n) G^0(\mathbf{k}; -i\omega_n) \\ &= \sum_{\mathbf{n}} \sum_{\mathbf{k}^0} V_t(\mathbf{k}) t(\mathbf{k}^0)^* \hat{\mathbf{k}}^* \hat{\mathbf{k}}^0 \frac{1}{(i\omega_n - \epsilon_{\mathbf{k}^0}) (i\omega_n - \epsilon_{\mathbf{k}})}; \end{aligned} \quad (111)$$

Here $\epsilon_k = \epsilon_k^0$ and ϵ_k^0 is given by (110). We also have taken into consideration the relation (93).

It is clear that the coherence between the normal metal states with states with Green functions $G^0(k; i\omega_n)$ and $G^0(-k; -i\omega_n)$ is broken by magnetic field. The oppositely directed momenta k and $-k$ on the Fermi surface have the different length. Hence the magnetic field will suppress superconductivity that means the critical temperature will be decreasing function of magnetic field. It is clear also that it will be anisotropic function of the field orientation in respect of crystallographic directions.

For tetragonal crystal $CePt_3Si$ one can take as the simplest form of gyromagnetic tensor $g_{ij} = g_B (\delta_{ij} + \hat{z}_i \hat{z}_j) + g_k \hat{z}_i \hat{z}_j$ and the pseudovector function $\epsilon_k = (\hat{z} \cdot k) + 2k_x k_y k_z (k_x^2 - k_y^2)$. The latter is chosen following the discussion in the paper [50]. Then for the normal metal energy of excitations we have

$$\epsilon_k = \epsilon_k^0 + \frac{r}{(k_y + \frac{g_B}{2} H_x)^2 + (k_x - \frac{g_B}{2} H_y)^2 + (k_x k_y k_z (k_x^2 - k_y^2) + \frac{g_k}{2} H_z)^2} \quad (112)$$

As result of simple calculation near T_c we obtain

$$T_c(H) = T_c - 1 \frac{7}{32} \frac{(3)B}{T_c^2} a g_B^2 (H_x^2 + H_y^2) + b g_k^2 H_z^2 + \dots; \quad (113)$$

that looks like similar to usual superconductivity with singlet pairing. Here a and b are coefficients of the order of unity. Its exact values depend on the particular form of $\epsilon(k)$ functions in pairing interaction as well on particular form of ϵ_k .

On the other hand, let us assume that due to some particular reason coefficient ϵ_k is small. Then for the field direction $H = H \hat{z}$ for $g_B H \ll k_F^5$ we have for the excitations energy

$$\epsilon_k = \epsilon_k^0 + \frac{r}{(k_y)^2 + (k_x)^2 + (\frac{g_k}{2} H_z)^2}; \quad (114)$$

that is now the even function of the wave vector $\epsilon_k = \epsilon_{-k}$.

The equation for the critical temperature has the form

$$T_c(k) = \frac{V}{N} \frac{\int_{-Z}^Z d\epsilon \int_{S_F} d\Omega \frac{dS_{\hat{k}^0}}{S_F} \frac{(\hat{k}^0 \cdot \hat{k})' (\hat{k}^0 \cdot \hat{k}^0)}{(i\epsilon_n) (i\epsilon_n')}; \quad (115)$$

Here we can first integrate over the energy variable ϵ and then over the Fermi surface. After the first integration the magnetic field dependence is disappeared from equation and we obtain standart BCS formula $T_c = (2/\pi) \exp(-1/g)$ for critical temperature determination. So, the suppression of critical temperature by magnetic field is saturated at finite value which differs from its value at $H = 0$ due to field variation of density of states and pairing interaction at $\epsilon = 0$.

This results can be in principle valid for any direction of magnetic field if paramagnetic interaction exceeds a spin-orbital splitting $j_1 H_{1j} > j_2 j_3$. Of course the superconductivity in the region of the large fields still exists if g is positive on the Fermi surface $\epsilon = 0$. Thus at large fields the situation is similar to that we have in the superconductors with triplet pairing.

We have demonstrated that the paramagnetic suppression of superconducting state in a crystal without inversion centrum certainly exists and the effect depends of field orientation in respect of crystal axes. The paramagnetic suppression of superconductivity takes place due to magnetic field lifting of degeneracy of electronic states with opposite momenta k and $-k$ forming the Cooper pairs. For some directions of fields the degeneracy is recreated. That is why the paramagnetic limit of superconductivity in the crystals without inversion can be in principle absent.

To demonstrate the time inversion violation in its pure form we have calculated the paramagnetic influence of external field on superconductivity in the noncentrosymmetric material in complete neglect of the diamagnetic currents. Certainly the latter play the main role in the superconductivity suppression. The general Gor'kov equations in this case have the same form (35)–(38) etc as for two band ferromagnet. One needs to remember only that the electron states and energies in these two cases have quite different spinor structure and parity in respect to k . One can find the treatment of several inhomogeneous problems as the upper critical field calculation in Ginzburg-Landau region in the papers [40,49,50].

REFERENCES

- [1] S.S.Saxena, P.Agarwal, K.Ahilan, F.M.Grosche, R.K.W.Hasselwimmer, M.J.Steiner, E.Pugh, I.R.Walker, S.R.Julian, P.Monthoux, G.G.Lonzarich, A.Huxley, I.Sheikin, D.Braithwaite, and J.Fluquet, *Nature* 406, 587 (2000).
- [2] A.Huxley, E.Ressouche, B.Grenier, D.Aoki, J.Fluquet and C.Peiderer, *J Phys.: Condens.Matter* 15, S1945 (2003).
- [3] C.Peiderer, M.Uhlarz, S.Heiden, R.Vollmer, H.v.Lohnen, N.R.Bernhoeft, and G.G.Lonzarich, *Nature* 412, 58 (2001).
- [4] D.Aoki, A.Huxley, E.Ressouche, D.Braithwaite, J.Fluquet, J-P.Brisson, E.Lhotel and C.Paulsen, *Nature* 413, 613 (2001).
- [5] F.Hardi, A.Huxley et al, to be published (2004).
- [6] D.Fay and J.Appel, *PhysRev B* 22, 3173 (1980).
- [7] A.B.Shick and W.E.Pickett, *PhysRev.Lett.*86, 300 (2001).
- [8] T.R.Kirkpatrick, D.Belitz, T.Vojta and R.Narayanan, *PhysRev.Lett.*87, 127003 (2001).
- [9] H.Suhl, *PhysRev.Lett.*87, 167007 (2001).
- [10] A.A.Abrikosov, *J Phys.: Condens.Matter* 13, L943 (2001).
- [11] Z.Wang, W.Mao and K.Bedell, *PhysRev.Lett.*87, 257001 (2001).
- [12] R.Roussev and A.J.Millis, *PhysRev B* 63, 140504(R) (2001).
- [13] D.Santi, S.B.Dugdale, and T.Jarlborg, *PhysRev.Lett.*87, 247004 (2001).
- [14] A.V.Chubukov, A.M.Finkelstein, R.Haslinger and D.K.Morr, *PhysRev.Lett.*80, 077002 (2003).
- [15] M.Dzero and L.P.Gorkov, *PhysRev B* 69, 092501 (2004).

- [16] P M onthoux and G G Lonzarich, PhysRev.B 59, 14598 (1999); PhysRev.B 63, 054529 (2001); PhysRev.B 66, 224504 (2002);
- [17] K G Sandeman, G G Lonzarich and A J Schofeld, PhysRev.Lett.90, 167005 (2003).
- [18] T R Kirkpatrick and D Belitz, PhysRev.B 67, 024515 (2003).
- [19] A Leggett, RevModPhys. 47, 331 (1975).
- [20] G E Volovik and L P Gor'kov Zh.Eksp.TeorFiz.88, 1412 (1985) [Sov.Phys.-JETP 61, 843 (1985)].
- [21] K Ueda and T M Rice, PhysRev.B 31, 7144 (1985).
- [22] E I Blunt, PhysRev.B 31, 2935 (1985).
- [23] M Sigrist and K Ueda, RevModPhys.63, 239 (1991).
- [24] V P. Mineev and K V. Samokhin, Introduction to Unconventional Superconductivity (Gordon and Breach, New York, 1999).
- [25] M B Walker and K V Samokhin, PhysRev.Lett.88, 207001 (2002).
- [26] K V Samokhin and M B Walker, Phys.Rev.B 66, 024512 (2002); K V Samokhin and M B Walker, Phys.Rev.B 66, 174501 (2002); K V Samokhin, Phys.Rev.B 66, 212509 (2002).
- [27] I A Fomin, Pis'ma Zh.Eksp. Teor. Fiz. 74, 116 (2001) [JETP Letters 74, 111 (2001)]; I A Fomin, Zh.Eksp. Teor. Fiz. 122, 1089 (2002) [Sov.Phys. JETP 95, 940 (2002)].
- [28] V P. Mineev, Phys.Rev.B 66, 134504 (2002).
- [29] Special issue on MgB₂ Physica (Amsterdam) 385C, 1-305 (2003).
- [30] H. Suhl, B T Matthias, and L R Walker, Phys. Rev. Lett. 3, 552 (1959).
- [31] M E Zhitomirskii and V H Dao, Phys. Rev. B 69, 054508 (2004).

- [32] A E K oshelev and A A G olubov, Phys.Rev.Lett. 92, 107008 (2004).
- [33] V P M ineev and T Cham pel, Phys.Rev.B 69, 144521 (2004).
- [34] E Bauer, G H ilscher, H M ichor, Ch Paul, E W Scheidt, A G ribanov, Yu Seropegin, H Noel, M Sigrist, and P Rogl, PhysRevLett. 92, 027003 (2004).
- [35] V M Edel'stein, Zh Eksp.TeorF iz.95, 2151 (1989) [Sov.Phys.JETP 68, 1244 (1989)].
- [36] L S Levitov, Yu V Nazarov, and G M Eliashberg, Pis'm a Zh Eksp.TeorF iz.41, 365 (1985) [JETP Letters41, 445 (1985)].
- [37] V P M ineev, Pis'm a Zh Eksp.TeorF iz.57, 659 (1993) [JETP Letters57, 680 (1993)].
- [38] V P M ineev and K V Sam okhin, Zh Eksp.TeorF iz.105, 747 (1994) [Sov.Phys.JETP 78, 401 (1994)].
- [39] V M Edel'stein, PhysRevLett. 75, 2004 (1995);
- [40] V M Edel'stein, J Phys.: Condens.M atter 8, 339 (1996).
- [41] V M Edel'stein, Pis'm a Zh Eksp.Teor.F iz. 69, 363 (1999) [JETP Letters69,392 (1999)].
- [42] L P G or'kov and E I Rashba, PhysRevLett. 87, 037004 (2001).
- [43] V Barzykin and L P G or'kov, PhysRevLett. 89, 227002 (2002).
- [44] S K Y ip, PhysRevB 65, 144508 (2002).
- [45] V M Edel'stein, PhysRevB 67, 020505 (2003).
- [46] P A Frigeri, D F Agterberg, A K oga, and M Sigrist, PhysRevLett. 92, 097001 (2004).
- [47] K V Sam okhin, E S Zijlstra, and S K Bose, Phys.Rev.B 69, 094514 (2004).
- [48] I A Sergienko and S H Cumoe, preprint cond-m at/0406003 (2004).
- [49] K V Sam okhin, preprint cond-m at/0404407 (2004).

- [50] K.V. Samokhin, preprint cond-mat/0405447 (2004).
- [51] V.P. Mineev, preprint cond-mat/0405672 (2004).
- [52] L.D. Landau and E.M. Lifshitz, "Electrodynamics of continuous media", Nauka, Moscow, 1982, Pergamon, NY, 1984.
- [53] E.P. Wigner, "Group Theory", Academic Press, New York and London, 1959.
- [54] C.J.Bradley and A.P.Cracknell "The mathematical theory of symmetry in solids", Clarendon Press, Oxford, 1972.
- [55] A.I. Larkin, Pis'ma ZhETF 2, 205 (1965) [JETP Letters 2, 130 (1965)].
- [56] A.A. Abrikosov, L.P. Gor'kov, ZhETF 39, 1781 (1960) [Sov. Phys. JETP 12, 1243 (1961)].
- [57] A.P. Mackenzie, R.K.W. Haselwimmer, A.W. Tyler, G.G. Lonzarich, Y. Mori, S. Nishizaki, and Y. Maeno, Phys. Rev. Lett. 80, 161 (1998).
- [58] J.B. Kycia, J.I. Hong, M.J. Graf, J.A. Sauls, D.N. Seidman, and W.P. Halperin, PhysRev.B 58, 603 (1998).
- [59] V.P. Mineev, Pis'ma ZhETF 51, 399 (1990) [JETP Letters 51, 453 (1990)].
- [60] D.F. Agterberg, Phys. Rev. B 60, R749 (1999).
- [61] I.I. Mazin, O.K. Andersen, O. Jepsen, O.V. Dolgov, J. Kortus, A.A. Golubov, A.B. Kuz'menko, and D. van der Marel, Phys. Rev. Lett. 89, 107002 (2002).
- [62] This is correct of course only if $4M > H_{c1}$ (where H_{c1} is the lower critical field).
- [63] P.C. Hohenberg and N.R. Werthammer, Phys. Rev. 153, 493 (1967).
- [64] E.M. Lifshits and L.P. Pitaevskii, Statistical Physics Part II, Butterworth-Heinemann. Oxford (1995).

- [65] T Akazawa, T Akazawa, H Hidaka, T Fujiwara, T C Kobayashi, E Yamamoto, Y Haga, R Settai, and Y Onuki, J Phys.: Condens. Matter 16, L29 (2004).