

# Single particle spectrum of the flux phase in the FM Kondo Model

M. Daghofer<sup>a,\*</sup> W. Koller<sup>b</sup> W. von der Linden<sup>a</sup> H. G. Evertz<sup>a</sup>

<sup>a</sup>*Institute for Theoretical and Computational Physics, Graz University of Technology, Petersgasse 16, A-8010 Graz, Austria*

<sup>b</sup>*Department of Mathematics, Imperial College, 180 Queen's Gate, London SW7 2BZ, UK*

---

## Abstract

We investigate the 2D ferromagnetic Kondo lattice model for manganites with classical corespins at Hund's rule coupling  $J_H = 6$ , with antiferromagnetic superexchange  $0.03 \leq J' \leq 0.05$ . We employ canonical and grand canonical unbiased Monte Carlo simulations and find paramagnetism, weak ferromagnetism and the Flux phase, depending on doping and on  $J'$ . The observed single particle spectrum in the flux phase differs from the idealized infinite lattice case, but agrees well with an idealized finite lattice case with thermal fluctuations.

*Key words:*

manganites, double exchange, flux phase

---

The ferromagnetic Kondo lattice model is believed to describe the electronic degrees of freedom of compounds such as manganites. In these materials the spins of the itinerant electrons have a strong ferromagnetic coupling to localized corespins  $\mathbf{S}_i$ , leading to an Effective Spinless Fermion (ESF) Hamiltonian [1]

$$\hat{H} = - \sum_{\langle i,j \rangle} t_{i,j}^{\uparrow\uparrow} c_i^\dagger c_j - \sum_{i,j} \frac{t_{i,j}^{\uparrow\downarrow} t_{j,i}^{\downarrow\uparrow}}{2J_H} c_i^\dagger c_i + J' \sum_{\langle i,j \rangle} \mathbf{S}_i \cdot \mathbf{S}_j, \quad (1)$$

where  $c_i^\dagger$  creates an electron at site  $i$  with its spin parallel to  $\mathbf{S}_i$ , and  $J_H = 6$  throughout this work. The hopping of these spinless electrons is modulated by the factor  $t_{i,j}^{\uparrow\uparrow} = \cos(\vartheta_{ij}/2) e^{i\psi_{ij}}$ , which depends on the relative angles  $\vartheta_{ij}$  of the two neighboring corespins and carries a complex phase  $\psi_{ij}$ . On a two-dimensional lattice, this complex phase leads to the so call "Flux phase" around half filling of the lower Kondo band (doping  $x = 50\%$ ) [2]. While the system is ferromagnetic at half filling for  $J' \lesssim 0.025$ , the Flux phase has been shown [2] to be the ground state at half filling for larger values of  $J'$ .

We performed canonical and grand canonical unbiased Monte Carlo simulations [3]. The magnetic phases can be observed in the corespin structure factor which is depicted in Fig. 1 for  $J' = 0.05$ . In the polaronic regime with high compressibility at  $x \approx 18\%$  holes [3], only an AFM signal is visible. At  $x \approx 24\%$ , the compressibility is suddenly much reduced and the system becomes homogeneous but a small AFM peak persists. At  $x \approx 28\%$  no magnetic structure at all is visible. The flux phase appears at  $x \approx 44\%$  and  $x = 50\%$  with signals at  $(\pi, 0)$  and  $(0, \pi)$ . The only FM signal exists, weakly, at even larger doping  $x \approx 62\%$ .

Fig. 2 shows the normalized FM corespin moment  $S(q=0) = |\sum_i \mathbf{S}_i|/L$  as a function of doping, where  $L$  is the number of lattice sites. It is expected to vanish in the Flux phase. One sees that the doping range of the Flux phase becomes smaller at smaller  $J'$ . The lattice is weakly ferromagnetic at slightly lower doping  $x \approx 40\%$ . All our data are compatible with the existence of a flux phase in the region where  $S(q=0) \simeq 0$ .

The corespin structure in an idealized flux phase is depicted in Fig. 3(a). While all corespins are drawn parallel to the  $xy$ -plane for better visibility, a global rotation in spin space leads to equivalent configurations. In such corespin configurations,  $|t_{i,j}^{\uparrow\uparrow}| = 1/\sqrt{2}$  is constant. However, the hopping carries a complex phase  $\psi_{ij}$ . Di-

---

\* daghofer@itp.tu-graz.ac.at




Fig. 1. Corespin structure factor for  $J_H = 6$ ,  $\beta = 50$ ,  $J' = 0.05$  and various doping levels. Simulations were done on a  $12 \times 14$  lattice, i. e. for  $L = 168$  lattice sites.




Fig. 2. FM corespin Moment  $S(q = 0)$  as a function of doping for various values of  $J'$ , remaining parameters as Fig. 1.

agonalizing the ESF Hamiltonian for the four site unit cell of the Flux phase leads to the dispersion relation

$$\epsilon(k_x, k_y) = -\frac{1}{J_H} \pm \sqrt{2(\cos^2 k_x + \cos^2 k_y)}. \quad (2)$$

The one-particle DOS of these bands for the infinite lattice with the corespins aligned in the perfect Flux phase is depicted in Fig. 3(b); it features a pseudogap at half filling. The dispersion and the DOS of the full Kondo model and for  $J_H \rightarrow \infty$  can be found in [2].

The spectral density of the Flux phase is subject to strong finite size effects, which are caused by the fact that only a very small part of the Brillouin zone contributes to the few states around the pseudogap at  $(\pi/2, \pi/2)$ . In order to ascertain that we did indeed observe the Flux phase, we therefore compared our MC results to a model system. We started from a perfect Flux phase configuration of the corespins on a finite lattice, added random perturbations, and diagonalized the resulting ESF Hamiltonian. The amount of fluctuations was chosen to fit the width of the peaks in the full MC results. Fig. 4 compares the average spectral den-




Fig. 3. Perfect Flux phase: (a): Schematic plot of the corespin configuration. The dashed square delimits the unit cell. All spins are drawn parallel to the  $xy$ -plane. (b): Electronic DOS for the ESF Hamiltonian with  $J_H = 6$  on an infinite lattice.




Fig. 4. Spectral density for the Flux phase at half filling for  $J' = 0.05$ ;  $\beta = 50$  (left) and  $\beta = 80$  (right) on a  $14 \times 12$ -lattice. Dashed lines: MC results for the ESF model. Solid lines: ideal Flux phase with random deviations.

sity and the DOS thus obtained to MC simulations for the ESF model exhibiting almost perfect agreement, while there is a notable difference between the DOS in Fig. 4 and the idealized case in Fig. 3(b), The system can thus indeed be well described by thermal fluctuations about the Flux phase on a finite lattice.

**Acknowledgments:** We would like to thank the Austrian Science Fund (FWF project P15834) and the EPSRC (Grant GR/S18571/01) for financial support.

## References

- [1] W. Koller, A. Prüll, H. G. Evertz and W. von der Linden, Phys. Rev. B **66**, 144425 (2002)
- [2] H. Aliaga, B. Normand, K. Hallberg, M. Avignon, and B. Alascio, Phys. Rev. B **64**, 024422 (2001); D. F. Agterberg and S. Yunoki, Phys. Rev. B **62**, 13816 (2000); M. Yamanaka, W. Koshibae and S. Maekawa, Phys. Rev. Lett. **81**, 5604 (1998)

- [3] M. Daghofer, W. Koller, H. G. Evertz, and W. von der Linden, cond-mat/0312394, to appear in J. Phys.: Condens. Matter