Temperature-dependent soft x-ray photoemission and absorption studies of charge disproportionation in $La_{1-x}Sr_xFeO_3$

H. Wadati,^{1,*} A. Chikamatsu,² R. Hashimoto,² M. Takizawa,¹ H. Kumigashira,²

A. Fujimori,¹ M. Oshima,² M. Lippmaa,³ M. Kawasaki,⁴ and H. Koinuma⁵

¹Department of Physics and Department of Complexity Science and Engineering,

University of Tokyo, Kashiwanoha 5-1-5, Kashiwa, Chiba 277-8561, Japan

²Department of Applied Chemistry, University of Tokyo, Bunkyo-ku, Tokyo 113-8656, Japan

Institute for Solid State Physics, University of Tokyo,

Kashiwanoha 5-1-5, Kashiwa, Chiba 277-8581, Japan

⁴Institute for Materials Research, Tohoku University, 2-1-1 Katahira, Aoba, Sendai 980-8577, Japan

⁵Materials and Structures Laboratory, Tokyo Institute of Technology,

4259 Nagatsuta, Midori-ku, Yokohama 226-8503, Japan

(Dated: January 9, 2022)

We have measured the temperature dependence of the photoemission and x-ray absorption spectra of $\text{La}_{1-x}\text{Sr}_x\text{FeO}_3$ (LSFO) epitaxial thin films with x = 0.67, where charge disproportionation $(3\text{Fe}^{3.67+} \rightarrow 2\text{Fe}^{3+} + \text{Fe}^{5+})$ resulting in long-range spin and charge ordering is known to occur below $T_{CD} = 190$ K. With decreasing temperature we observed gradual changes of the spectra with spectral weight transfer over a wide energy range of ~ 5 eV. Above T_{CD} the intensity at the Fermi level (E_F) was relatively high compared to that below T_{CD} but still much lower than that in conventional metals. We also found a similar temperature dependence for x = 0.4, and to a lesser extent for x = 0.2. These observations suggest that a local charge disproportionation occurs not only in the x = 0.67 sample below T_{CD} but also over a wider temperature and composition range in LSFO. This implies that the tendency toward charge disproportionation may be the origin of the unusually wide insulating region of the LSFO phase diagram.

PACS numbers: 71.28.+d, 71.30.+h, 79.60.Dp, 73.61.-r

I. INTRODUCTION

It has been well known that carrier doping into Mott insulators causes various intriguing physical phenomena [1]. Among them, charge ordering (CO) and associated metal-insulator transition (MIT) have attracted particular interest in relation to charge stripes in high- T_c cuprates [2] and spin-charge-orbital ordering in 'colossal' magnetoresistive manganites. $La_{1-x}Sr_xFeO_3$ (LSFO) with $x \simeq 2/3$ exhibits a charge disproportionation (CD) from the average valence state of $Fe^{3.67+}(d^{4.33})$ into $2 \text{Fe}^{3+}(d^5) + \text{Fe}^{5+}(d^3)$, a unique type of CO, below $T_{CD} =$ 190 K [3], accompanied by both a resistivity jump by an order of magnitude and antiferromagnetic ordering. A neutron diffraction study by Battle et al. [4] revealed a spin-density wave (SDW) of sixfold periodicity and a charge-density wave (CDW) of threefold periodicity along the $\langle 111 \rangle$ direction. They also reported the apparent absence of structural distortion in the charge ordered state, whereas electron diffraction study by Li et al. [5] revealed superspots corresponding to a local structural distortion along the $\langle 111 \rangle$ direction for the sample of x = 0.7. Optical conductivity spectra showed a splitting of optical phonon modes due to the folding of the phonon dispersion branch, caused by the lattice distortion below T_{CD} [6]. Cluster-model analyses of photoemission spectra revealed that the charge disproportionation is better described as $3d^5\underline{L}^{0.67} \rightarrow 2d^5 + d^5\underline{L}^2$, where \underline{L} denotes a hole in the O 2p band, rather than $3d^{4.33} \rightarrow 2d^5 + d^3$, because of the oxygen p character of holes doped into the charge-transfer insulator LaFeO₃ [7]. Matsuno *et al.* [8] studied temperature dependent changes near the Fermi level (E_F) in the photoemission spectra of LSFO with x = 0.67 and found that the intensity at E_F clearly changed across the transition temperature. They also reported smaller but finite changes for x = 0.55 and 0.80 and suggested that a local charge disproportionation may occur even away from x = 0.67. It was recently reported that Mössbauer spectra of LSFO with x = 0.5[9] show temperature-dependent valence changes similar to x = 0.67.

In the previous work, we have performed soft x-ray photoemission and absorption measurements of highquality $La_{1-x}Sr_xFeO_3$ single crystals epitaxially grown by the pulsed laser deposition (PLD) method *in situ* [10]. Owing to the atomically flat, well-defined surfaces of the single-crystal thin films and the use of high energy soft xrays ($h\nu = 600 - 710 \text{ eV}$) compared to the previous work ($h\nu = 21.2 - 100 \text{ eV}$) [8], the photoemission spectra, especially of the valence band, revealed well-resolved structures directly related to the Fe 3*d* states, enabling detailed electronic structure studies of this material. In the present work, we address the questions of how the electronic structure of LSFO changes when the CD occurs as a function of temperature, using soft x-ray photoemission and absorption. We have also utilized Fe $2p \rightarrow 3d$ res-

^{*}Electronic address: wadati@wyvern.phys.s.u-tokyo.ac.jp



FIG. 1: Electrical resistivity of $La_{1-x}Sr_xFeO_3$ thin films.

onant photoemission effect to further enhance the Fe 3d contribution. We have investigated LSFO with x = 0.67 to observe the change of the electronic structure accompanied by charge disproportionation, as well as x = 0, 0.2, and 0.4 samples.

II. EXPERIMENT

The experiment was performed at BL-2C and BL-1C of Photon Factory (PF), High Energy Accelerators Research Organization (KEK), using a combined laser molecular beam epitaxy (MBE) photoemission spectrometer system. The experimental setup is the same as that in Ref. [10] and described in detail in Ref. [11]. Epitaxial thin films of LSFO were fabricated from ceramic targets of desired chemical compositions by the PLD method. Single crystals of Nb-doped SrTiO₃ were used as substrates. Nb doping was necessary to avoid charging effects during the PES measurements. A Nd:YAG laser was used for ablation in its frequency-tripled mode $(\lambda = 355 \text{ nm})$ at a repetition rate of 0.33 Hz. The substrates were annealed at 1050°C at an oxygen pressure of $\sim 1 \times 10^{-6}$ Torr to obtain an atomically flat TiO₂terminated surface [12]. LSFO thin films of ~ 100 monolayers were deposited on the substrates at 950°C at an oxygen pressure of $\sim 1 \times 10^{-4}$ Torr. The films were postannealed at 400°C at an atmospheric pressure of oxygen to remove oxygen vacancies. The samples were then transferred from the MBE chamber to the spectrometer under an ultrahigh vacuum. The surface morphology of the measured films was checked by *ex-situ* atomic force microscopy. The electrical resistivity of x = 0.67 sample showed a jump at 190 K (= T_{CD}), whereas the other samples showed insulating behaviors in the whole temperature range, as shown in Fig. 1.

Photoemission measurements were performed under an ultrahigh vacuum of $\sim ~10^{-10}$ Torr from room temper-



FIG. 2: (Color) Temperature dependence of the valence-band photoemission spectra of La_{0.33}Sr_{0.67}FeO₃. (a): $h\nu = 710$ eV (on Fe $2p \rightarrow 3d$ resonance), (b): $h\nu = 600$ eV.

ature down to 10 K. The PES spectra were measured using a Scienta SES-100 electron-energy analyzer. The total energy resolution was about 200 meV at the photon energy of 600 eV, about 250 meV at that of 710 eV (on Fe $2p \rightarrow 3d$ resonance), and about 35 meV at that of 40 eV. The E_F position was determined by measuring gold spectra. The XAS spectra were measured in the totalelectron-yield mode. The stoichiometry of the thin films was characterized by analyzing the relative intensities of relevant core levels, confirming that the compositions of the samples were nearly those of the ceramic targets [10].

III. RESULTS AND DISCUSSION

A. $La_{0.33}Sr_{0.67}FeO_3$

Figures 2 and 3 show the temperature dependence of the valence-band photoemission spectra of $La_{0.33}Sr_{0.67}FeO_3$ taken at $h\nu = 710 \text{ eV}$ (on Fe $2p \rightarrow 3d$ resonance), 600 eV and 40 eV. The spectra taken at $h\nu = 710 \text{ eV}$ are considered to represent the Fe 3d partial DOS (PDOS) with extra enhancement of the satellite around -11 eV, whereas those taken at $h\nu = 40 \text{ eV}$ are dominated by the O 2p PDOS and those taken at $h\nu = 600 \text{ eV}$ are mixtures of the Fe 3d and O 2p PDOS according to the corresponding atomic orbital photoionization cross-sections [13]. In Fig. 2, the spectra have been normalized to the area from 1 eV to -14 eV. One can observe four structures, namely, A ($e_{a\uparrow}$ band), B $(t_{2q\uparrow} \text{ band}), C$ (Fe 3d-O 2p bonding states), and the satellite structure. The intensity at E_F is considerably low without a clear Fermi-level cutoff even at room temperature. A similar observation was reported for Fe₃O₄ [14, 15, 16], which also shows charge ordering below ~ 120 K. The spectra change gradually with temperature. With decreasing temperature, spectral weight is transferred from -(4-5) eV to structure A ($e_{q\uparrow}$ band) while the height of structure B $(t_{2g\uparrow} \text{ band})$ remains almost unchanged. In Fig. 3 (a) (b) and thereafter we have normalized the spectra to the height of structure B, and concentrate on the spectra within $\sim 3 \text{ eV}$ of E_F . The spectra for 710 eV and 600 eV clearly indicate a transfer of spectral weight from the vicinity of E_F to structure A, that is, within the $e_{q\uparrow}$ band region with decreasing temperature. The energy range in which spectral weight transfer occurs is two orders of magnitude larger than the transition temperature $T_{CD} = 190$ K ($\sim 22 \text{ meV}$). Spectral weight transfer over such a wide energy range was also reported in other transition-metal oxides such as $La_{1-x}Sr_xMnO_3$ [17], $La_{1-x}Ca_xMnO_3$ [18], $Nd_{1-x}Sr_xMnO_3$ [19], $Pr_{1-x}Sr_xMnO_3$ [20] and $Nd_{1-x}Sm_xNiO_3$ [21, 22]. The 40 eV spectrum [Fig. 3 (c)] does not show appreciable changes on the same energy and intensity scales, but near E_F a clear spectral weight transfer is observed [Fig. 3 (d)]. From those photon energy dependences, we conclude that the temperaturedependent part of O 2p states are distributed within $\sim 0.8 \text{ eV}$ of E_F and the temperature-dependent part of Fe 3d states within $\sim 2 \text{ eV}$ of E_F .

In order to characterize the spectral weight transfer more clearly, we have plotted the spectral weight of the 710 eV spectrum (Fe 3d PDOS) integrated from -2.0eV to +0.3 eV and that of the 40 eV spectrum (O 2pPDOS) integrated from -1.0 eV to +0.3 eV as a function of temperature in Fig. 4 (a). We have also plotted the spectral weight integrated from -0.3 eV to +0.3 eV for the same photon energies in Fig. 4 (b). A dramatic but gradual change of spectral weight is observed across the transition temperature in both plots. While the spectral weight within $\sim 2 \text{ eV}$ of E_F increases with decreasing temperature, reflecting the spectral weight transfer from -(4-5) eV to structure A, spectral weight in the vicinity of E_F decreases with decreasing temperature, reflecting the spectral weight transfer from near E_F to structure Α.

Next, Fig. 5 shows the temperature dependence of the Fe 2p and O 1s XAS spectra. One cannot observe any changes in the Fe 2p XAS spectra within experimental errors, whereas there is a significant change in the O 1s XAS spectra. Upon cooling, the peaks in the empty Fe 3d band region become sharp, and the first peak corresponding to the doping-induced $e_{q\uparrow}$ band becomes more



FIG. 3: (Color) Temperature dependence of the valence-band photoemission spectra of La_{0.33}Sr_{0.67}FeO₃. (a): $h\nu = 710 \text{ eV}$ (on Fe $2p \rightarrow 3d$ resonance), (b): $h\nu = 600 \text{ eV}$, (c) and (d): $h\nu = 40 \text{ eV}$. (d) shows an enlarged plot of (c) near E_F .



FIG. 4: Spectral weight in the $e_{g\uparrow}$ band region for La_{0.33}Sr_{0.67}FeO₃ as a function of temperature : (a) Spectral weight integrated from -2.0 eV to +0.3 eV for $h\nu = 710 \text{ eV}$ (representing the Fe 3d PDOS) and from -1.0 eV to +0.3 eV for $h\nu = 40 \text{ eV}$ (representing the O 2p PDOS). (b) Spectral weight near E_F integrated from -0.3 eV to +0.3 eV for $h\nu = 710 \text{ eV}$ and 40 eV

intense. This spectral change is opposite to the change of the photoemission spectra in the vicinity of E_F but is the same as the increase of structure A. At the same time, spectral weight on the higher energy side of the first peak decreases upon cooling, resulting in the overall shift of the first peak toward lower energies. In addition, the structure at ~ 530 eV changes its lineshape and is shifted to lower energies.



FIG. 5: (Color) Temperature dependence of XAS spectra of $La_{0.33}Sr_{0.67}FeO_3$. (a) Fe 2p (b) O 1s.



FIG. 6: Schematic picture of the spectral changes with decreasing temperature in $La_{0.33}Sr_{0.67}FeO_3$.

To summarize those spectral changes, we show a schematic picture in Fig. 6. Below E_F , upon cooling spectral weight is transferred from the near- E_F states as well as from the states at -(4-5) eV of Fe 3d character to the states of Fe 3d character and O 2p character at ~ -2 eV and ~ -1 eV, respectively (composing structure A). Correspondingly, there is an increase in the O 2p DOS at $\sim +1$ eV above E_F upon cooling. We believe that the DOS in the vicinity of E_F decreases above E_F , too, since a gap should open at E_F , but the change associated with the gap opening may be too small to be observed with the resolution of O 1s XAS.

The gradual temperature dependence indicates that CD does not occur abruptly at T_{CD} but occurs gradually from well above T_{CD} , namely, that a local CD occurs well above T_{CD} and continues to develop below T_{CD} , too. It would be interesting to investigate other Fe oxides which undergoes charge ordering such as CaFeO₃ and Fe₃O₄ to see whether such a temperature-dependent spectral weight transfer is a common phenomenon or not.

B. $La_{1-x}Sr_xFeO_3$ with x = 0, 0.2, 0.4

We have also measured LSFO thin films with x = 0, 0.2, and 0.4 by photoemission and O 1s XAS to see whether the temperature dependence seen for x = 0.67



FIG. 7: (Color) Temperature dependence of the valence-band photoemission spectra of $\text{La}_{1-x}\text{Sr}_x\text{FeO}_3$ taken at $h\nu = 710$ eV, i.e. Fe $2p \rightarrow 3d$ resonance. (a) x = 0 (b) x = 0.2 (c) x = 0.4.

is unique to this composition or not. For x = 0, 0.2, and 0.4, the system is insulating at all temperatures without any abrupt change in the resistivity as shown in Fig. 1 and exhibits only antiferromagnetic transitions above room temperature (at about 740 K, 520 K, and 320 K, respectively).

In Fig. 7, we show the temperature dependence of the valence-band photoemission spectra of LSFO with x = 0, 0.2, and 0.4 taken at $h\nu = 710$ eV, i.e., on Fe $2p \rightarrow 3d$ resonance. The intensity of peak A increases with decreasing x due to the increase in the $e_{g\uparrow}$ band filling, as reported in the previous paper [10]. There was only very weak temperature dependence for x = 0, as expected. As for x = 0.2 and 0.4, however, the spectra change gradually with temperature as in the case of x = 0.67, that is, the intensity of peak A increases and that in the vicinity of E_F decreases with decreasing temperature. Surprisingly, the magnitude of the changes for x = 0.4 is comparable to that of x = 0.67.

We also measured the temperature dependence of the O 1s XAS spectra, as shown in Fig. 8. The spectra for all x's show appreciable temperature dependence. Particularly for x = 0.4, the change is as dramatic as in the case of x = 0.67. From Figs. 7 and 8, we conclude that the temperature dependence becomes stronger with increasing x until x = 0.67 but that x = 0.4 shows as strong temperature dependence as x = 0.67.

Although there is no long-range charge ordering in the x = 0.4 sample, the temperature dependence comparable to x = 0.67 suggests that a local charge disproportionation occurs at low temperatures for x = 0.4,



FIG. 8: (Color) Temperature dependence of the O 1s XAS spectra of $La_{1-x}Sr_xFeO_3$. (a) x = 0 (b) x = 0.2 (c) x = 0.4.

too. The present results together with the previous report on the temperature-dependent photoemission study of x = 0.55 and 0.80 [8] suggest that the local charge disproportionation occurs over a wide composition range around x = 0.67. If all Fe⁴⁺ (predominantly of the $d^5\underline{L}$ configuration) ions in the Fe⁴⁺ –Fe³⁺ mixed valence state disproportionate into Fe³⁺ (d^5) and Fe⁵⁺ ($d^5\underline{L}^2$), the degree of the temperature dependence would be proportional to the concentration of the Fe⁴⁺ ions and hence to x, which may be consistent with the result that the spectral change of x = 0.4 is comparable to that of x = 0.67. The Mössbauer spectra of LSFO with x = 0.5 [9], which show valence changes similar to the case of x = 0.67, support our scenario of local charge disproportionation. For x > 0.67, the local charge-disproportionated state may become unstable because this system approaches SrFeO₃, where the metallic state is stable.

One striking feature of the LSFO phase diagram is that the insulating phase is unusually wide (0 < x < 0.9 at low temperatures, and 0 < x < 0.5 at room temperature) [8]. The observation that there is a gap at E_F for all values of x in the photoemission and XAS spectra [10] is naturally related to the wide insulating phase of this material. From the present work, we propose that the wide insulating region with the gap or pseudogap are due to the local charge disproportionation. Search for, e.g., diffuse scattering corresponding to the local charge disproportionation in samples with $x \neq 0.67$ is desired to test our proposal.

IV. CONCLUSION

We have measured the temperature dependence of the photoemission and XAS spectra of $La_{0.33}Sr_{0.67}FeO_3$ to study the spectral change across the transition temperature of charge disproportionation. We observed gradual changes of the spectra with temperature. Above T_{CD} the intensity at the Fermi level (E_F) becomes relatively high compared to that below T_{CD} but shows no clear Fermi-level cutoff and still remains much lower than that in conventional metals. Below E_F , spectral weight transfer was observed. Spectral weight is transferred from the near- E_F states of mixed Fe 3d-O 2p character to the states of both Fe 3d and O 2p character well below E_F primarily within the $e_{g\uparrow}$ band. Strong temperature dependence was also observed above E_F in the O 1s XAS spectra. We also measured the temperature dependence of the photoemission and XAS spectra of $La_{1-x}Sr_xFeO_3$ with x = 0, 0.2, 0.4. For x = 0.4, temperature dependence comparable to x = 0.67 was observed. Those observations suggest that a local charge disproportionation occurs not only in the x = 0.67 sample below 190 K but over a wider temperature and composition range. We propose that this local charge disproportionation is the origin of the wide insulating region of the LSFO phase diagram.

Acknowledgment

The authors would like to thank D. Kobayashi for sample preparation and T. Mizokawa for informative discussions. We are also grateful to K. Ono and A. Yagishita for their support at KEK-PF. This work was supported by a Grant-in-Aid for Scientific Research (A16204024) from the Ministry of Education, Culture, Sports, Science and Technology, Japan. This work was done under the approval of the Photon Factory Program Advisory Committee (Proposal No. 2003G149).

- M. Imada, A. Fujimori, and Y. Tokura, Rev. Mod. Phys. 70, 1039 (1998).
- [2] J. M. Tranquada, B. J. Sternlieb, J. D. Axe, Y. Nakamura, and S. Uchida, Nature **375**, 561 (1995).
- [3] M. Takano, J. Kawachi, N. Nakanishi, and Y. Takeda, J. Solid. State Chem. 39, 75 (1981).
- [4] P. D. Battle, T. C. Gibb, and P. Lightfoot, J. Solid. State Chem. 84, 271 (1981).
- [5] J. Q. Li, Y. Matsui, S. K. Park, and Y. Tokura, Phys. Rev. Lett. **79**, 297 (1997).
- [6] T. Ishikawa, S. K. Park, T. Katsufuji, T. Arima, and Y. Tokura, Phys. Rev. B 58, R13326 (1998).
- [7] A. E. Bocquet, A. Fujimori, T. Mizokawa, T. Saitoh, H. Namatame, S. Suga, N. Kimizuka, Y. Takeda, and M. Takano, Phys. Rev. B 45, 1561 (1992).
- [8] J. Matsuno, T. Mizokawa, A. Fujimori, K. Mamiya, Y.

Takeda, S. Kawasaki, and M. Takano, Phys. Rev. B **60**, 4605 (1999).

- [9] S. H. Yoon and C. S. Kim, J. Korean Phys. Soc. 44, 369 (2004).
- [10] H. Wadati, D. Kobayashi, H. Kumigashira, K. Okazaki, T. Mizokawa, A. Fujimori, K. Horiba, M. Oshima, N. Hamada, M. Lippmaa, M. Kawasaki, and H. Koinuma, Phys. Rev. B in press, cond-mat/0404435.
- [11] K. Horiba, H. Oguchi, H. Kumigashira, M. Oshima, K. Ono, N. Nakagawa, M. Lippmaa, M. Kawasaki, and H. Koinuma, Rev. Sci. Instr. 74, 3406 (2003).
- [12] M. Kawasaki, K. Takahashi, T. Maeda, R. Tsuchiya, M. Shinohara, O. Ishihara, T. Yonezawa, M. Yoshimoto, and H. Koinuma, Science 266, 1540 (1994).
- [13] J. J. Yeh and I. Lindau, At. Data Nucl. Data Tables 32, 1 (1985).
- [14] A. Chainani, T. Yokoya, T. Morimoto, T. Takahashi, and S. Todo, Phys. Rev. B 51, 17976 (1995).
- [15] J.-H. Park, L. H. Tjeng, J. W. Allen, P. Metcalf, and C. T. Chen, Phys. Rev. B 55, 12813 (1997).
- [16] D. Schrupp, M. Sing, M. Tsunekawa, H. Fujiwara, S. Kasai, A. Sekiyama, S. Suga, T. Muro, V. A. M. Brabers,

and R. Claessen, cond-mat/0405623.

- [17] D. D. Sarma, N. Shanthi, S. R. Krishnakumar, T. Saitoh, T. Mizokawa, A. Sekiyama, K. Kobayashi, A. Fujimori, E. Weschke, R. Meier, G. Kaindl, Y. Takeda, and M. Takano, Phys. Rev. B 53, 6873 (1996).
- [18] J.-H. Park, C. T. Chen, S.-W. Cheong, W. Bao, G. Meigs, V. Chakarian, and Y. U. Idzerda, Phys. Rev. Lett. 76, 4215 (1996).
- [19] S. Suga, T. Matsushita, M. Tsunekawa, T. Iwasaki, J. Samejima, Y. Kuwata, A. Kimura, A. Sekiyama, A. Fujimori, H. Ishii, T. Miyahara, H. Kuwahara, and Y. Tokura, Physica B **237-238**, 413 (1997).
- [20] A. Chainani, H. Kumigashira, T. Takahashi, Y. Tomioka, H. Kuwahara, and Y. Tokura, Phys. Rev. B 56, R15513 (1997).
- [21] I. Vobornik, L. Perfetti, M. Zacchigna, M. Grioni, G. Margaritondo, J. Mesot, M. Medarde, and P. Lacorre, Phys. Rev. B 60, R8426 (1999).
- [22] K. Okazaki, T. Mizokawa, A. Fujimori, E. V. Sampathkumaran, M. J. Martinez-Lope, and J. A. Alonso, Phys. Rev. B 67, 073101 (2003).