N onom ura and H u R eply: In the preceding comment [1], O Isson and Teitel questioned the possible vortex slush (VS) phase in the frustrated XY modelw ith point defects reported by the present authors [2]. The VS phase was originally proposed in order to explain an experiment of irradiated $YBa_2Cu_3O_7$ (YBCO) [3]. This phase was also observed in an optim ally-doped pristine YBCO [4], where the VS phase locates above the Bragg glass (BrG) phase in the H-T phase diagram . In M onte C arlo sim ulations of the frustrated XY model by the present authors [2], a rst-order transition was observed between the vortex liquid (VL) and VS phases up to a certain density of point defects. The structure factor in the VS phase shows obscure Bragg peaks, which was interpreted as a shortrange order in the abplane. In comparison with the BrG phase for lower density of point defects, the VS phase showsmuch larger density of dislocations in the ab plane and the vanishing helicity modulus along the z axis.

O lsson and Teitel simulated the same model for the same parameterization as used in Ref. [2]. On the basis of the structure factors observed in layer by layer, they argued that the VS phase observed by the present authors may be an artifact of a nite system size, and that this region may be included in the BrG phase in the therm odynamic limit. However, their argument in the Comment is not justi ed su ciently by the provided num erical data for the following reasons.

First, they observed strong hysteresis behavior by sweeping the pinning strength of point defects in the VS region, and took this behavior as the evidence for a wide coexistence region of the st-order melting of the Bragg glass. However, this behavior can alternatively be interpreted as m erging of the consequent VL-VS and rst-order phase transitions due to a sm all sys-VS-BrG tem size. The two-step behavior in the hysteresis curve of the peak value of the structure factor in Fig. 1 (b) of Ref. [1] looks consistent with the latter picture. It should also be pointed out that the hysteresis behavior m ay be enhanced by their -sweeping procedure. Since the annealing process is not included in this procedure in spite of possible drastic changes of the con gurations of ux lines caused by varying , M onte C arlo steps necessary for equilibration in this procedure may be much larger than those in the tem perature sweeping adopted in our previous article [2].

Second, they argued that the energy loss due to a m ism atch in di erent layers is proportional to J_LL^2 with the transverse system size L. This scaling argument is based on the assumption that the m ism atch characterized by the change of peak positions of B ragg peaks occurs as abruptly as a domain wall of the Ising model. However, the m ism atches displayed in Fig. 2 of Ref. [1] relax across a number of layers. When the relaxation takes place across L_w layers, the energy loss is proportional to $J_zL^2=L_w$. It is natural to expect that L_w depends on the thickness of the system L_z . Provided L_w is propor-

tional to L_z L, the energy loss caused by a m ism atch is proportional to $J_z L$, instead of $J_z L^2$. Then, their conclusion should be changed completely [5]. In order to address the issue su ciently, one should vary the system size and check the size dependence of the relaxation between m ism atches and the num ber of m ism atches.

On the other hand, we have to say that our previous study [2] cannot completely exclude the possibility that the $\$ rst-order VL-VS phase boundary" may actually be the melting line of the nger-like wiggled BrG region stretching into the VL phase [6]. Such a narrow BrG region (see Fig. 1 of Ref. [6]) may be weakened by thermal uctuations and the inverse melting behaviorm ay be masked by nite-size e ects in numerical simulations or by some experimental conditions. Even if it is the case, the shape of the vortex phase diagram is qualitatively di erent from that obtained by O lsson and Teitel [7].

We also notice that the vortex phase diagram including the VS phase as Ref. [4] was also reported in a YBCO thin

Im [8], and that there exist several theoretical studies [9, 10, 11, 12] consistent with our num erical results.

In sum m ary, the scaling argum ent which plays a key role in the preceding C om m ent cannot be su ciently justi ed by the provided num erical data. Their data are indeed consistent with our previous article.

Yoshihiko Nonomura and Xiao Hu

C om putational M aterials Science C enter, N ational Institute for M aterials Science, T sukuba, Ibaraki 305-0047, Japan

Received M arch 22, 2024

PACS numbers: 7425Qt, 74.62Dh, 7425Dw

- [L] P.O lsson and S.Teitel, preceding Comment, Phys. Rev. Lett.xx, xxxxxx (2005).
- [2] Y. Nonomura and X. Hu, Phys. Rev. Lett. 86, 5140 (2001).
- [3] T.K.W orthington et al, Phys. Rev. B 46, 11854 (1992).
- [4] T. Nishizaki et al., Physica C 341-348, 957 (2000);
 K.Shibata et al., Phys. Rev. B 66, 214518 (2002).
- [5] The scaling form of the energy gain proportional to J_{ab}L³⁼² should also be changed in a BrG region. See T.G iam archi and P.Le Doussal, Phys. Rev. Lett. 72, 1530 (1994); Phys. Rev. B 52, 1242 (1995).
- [6] D. Li and B. Rosenstein, Phys. Rev. Lett. 90, 167004 (2003).
- [7] P. O Isson and S. Teitel, Phys. Rev. Lett. 87, 137001 (2001).
- [8] H.H.W en et al, Phys. Rev. B 64, 054507 (2001).
- [9] J. K ierfeld and V. V inokur, Phys. Rev. B 61, R14928 (2000).
- [10] R. Ikeda, J. Phys. Soc. Jpn. 70, 219 (2001).
- [11] G.P.M ikitik and E.H.Brandt, Phys. Rev. B 68, 054509 (2003).
- [12] J.P.Rodriguez, Phys. Rev. B 69, 100503 (R) (2004).