

Comments on "Thermal conductivity of nanotubes: Effects of chirality and isotope impurity" [cond-mat/0501194]

Andrew Das Arulsamy¹

¹Condensed Matter Group, Division of Exotic Matter, No. 22,
Jalan Melur 14, Taman Melur, 68000 Ampang, Selangor DE, Malaysia

(Dated: March 23, 2022)

Based on Zhang and Li's molecular dynamics calculations, the heat conductivity (κ) of metallic single-wall Carbon nanotubes (SNTs) was incorrectly concluded as mainly influenced by the radius. Apart from that, their isotope effect interpretation on $\kappa(T)$ for the metallic SNTs using solely the phonon scattering mechanism is also highlighted to be incorrect.

PACS numbers: 65.80.+n; 73.61.Wp; 66.70.+f

Keywords: Carbon nanotube, Thermal conductivity

Recently, G. Zhang and B. Li (ZL) have attempted to propose a model that explains how thermal conductivity is related to chirality and isotope concentration by using the non-equilibrium molecular dynamics [1]. In their calculations, they have utilized the Hamiltonian with the Tersoff empirical potential [2], which is given by, $H = \sum_i [(p_i^2/2m_i) + (1/2) \sum_{j,j \neq i} f_c(r_{ij})(V_R(r_{ij}) + b_{ij}V_A(r_{ij}))]$. f_c is a function of the atomic distance, $V_{R,A}$ denotes the repulsive and attractive potentials respectively. Whereas b_{ij} describes the bonding nature of atoms i and j , or implicitly describes how the valence electrons of Carbons influences the phonons vibrational properties. The heat gradient was achieved with the Nosé-Hoover heat baths [3, 4]. In addition, the thermal current, $J = -\kappa \nabla T$ is used by assuming a steady state heat flow. It has been shown that the T -profile along the nanotube, dT/dx is identical between (9,0)-metallic and (10,0)-semiconducting nanotubes. The data listed in Table 1 of Ref. [1] are plotted in Fig. 1. From the definition, a chiral molecule cannot be superimposed on its own mirror image [5]. Therefore, $(n,0)$ and (n,n) are achiral SNTs. SNTs are usually characterized by the index (n,m) , which originates from the roll-up or chiral vector, $C_h = n\mathbf{a}_1 + m\mathbf{a}_2$ where \mathbf{a}_1 and \mathbf{a}_2 are the 2D graphite-sheet lattice vectors while n and m are integers [6]. Refer to Figs. 2 and 3, which clearly point out that the chirality exists for the chiral angle, ζ in the range of $0^\circ < \zeta < 30^\circ$. Note that the Figs. 2 and 3 were carbon-copied from the Ref. [7] and Ref. [6] respectively. In a first order approximation, SNTs can be made metals if $(n-m)/3$ equals an integer, otherwise they are semiconductors [6]. In other words, (9,0) (5,5) are metals, whereas (10,0) is a semiconductor.

ZL should realize that the Landauer theory of purely phononic scenario discussed by Yamamoto *et al.* [8] is limited to the semiconducting SNTs. As such, the total heat conductivity for metallic SNTs should be written as $\kappa = \kappa_e + \kappa_{ph}$ [8]. Consequently, $\kappa_{(9,0)}^{\zeta=0^\circ} > \kappa_{(10,0)}^{\zeta=0^\circ}$ and $\kappa_{(5,5)}^{\zeta=30^\circ} > \kappa_{(10,0)}^{\zeta=0^\circ}$ from Table 1 of Ref. [1] do not indicate that the changes in κ as mainly from r since $\kappa_{(9,0)}^{\zeta=0^\circ}$ and

FIG. 1: Calculated heat conductivity (κ) versus SNT's radius based on Zhang and Li [1]'s calculations.

FIG. 2: Single-walled carbon nanotubes exist in a variety of structures corresponding to the many ways a sheet of graphite can be wrapped into a seamless tube [7].

$\kappa_{(5,5)}^{\zeta=30^\circ}$ are also influenced by κ_e significantly. It is unclear and disturbing as to why ZL have sidestepped the contribution of κ_e even in the metallic (9,0) and (5,5) SNTs.

Subsequently, interpreting the results plotted in Fig. 2b of Ref. [1] based on phonon scattering mechanism alone is absurd because (5,5) is likely a metallic SNT. Therefore, $\kappa_e(T)$ is definitely a non-negligible term [8], complying with the arguments mentioned above. In simple words, isotope effect pops out in the total heat conductivity as given in Eqs. (1) and (2) below

$$\kappa^{12C}(T) = \kappa_{ph}^{12C}(T) + \kappa_e(T). \quad (1)$$

$$\kappa^{12C+14C}(T) = \kappa_{ph}^{12C+14C}(T) + \kappa_e(T). \quad (2)$$

These equations simply suggest that $\kappa_e(T)$ remains the same, regardless of isotope doping. As a consequence, ZL should first identify and isolate $\kappa_e(T)$ from Fig. 2b of Ref. [1] in order to justify the phonon scattering mechanism for $\kappa_{ph}^{12C}(T)$ and $\kappa_{ph}^{12C+14C}(T)$. Alternatively, they should either show that the (5,5) SNT is a relatively large-gap semiconductor or their Hamiltonian does not contain electrons, which is meaningless for condensed matter applications anyway. Otherwise, their analyses presented in the cond-mat/0501194 are literally incorrect.

The author is grateful to Arulsamy Innasimuthu, Sebastianm Innasimuthu, Arokia Das Anthony and Cecily Arokiam of CMG-A for their hospitality. I also thank Chong Kok Boon for providing some of the references.

FIG. 3: Schematic of a 2D graphene sheet illustrating lattice vectors \mathbf{a}_1 and \mathbf{a}_2 , and the roll-up vector $C_h = n\mathbf{a}_1 + m\mathbf{a}_2$, as well as the translation vector \mathbf{T} along the nanotube axis that defines the 1D unit cell. [6].



- [1] G. Zhang, B. Li, cond-mat/0501194.
- [2] J. Tersoff, Phys. Rev. B 39 (1989) 5566; Phys. Rev. Lett.

- 61 (1988) 2879; Phys. Rev. B 37 (1988) 6991; Phys. Rev. B 38 (1988) 9902.
- [3] S. Nosé, J. Chem. Phys. 81 (1984) 511.
- [4] W. G. Hoover, Phys. Rev. A 31 (1985) 1695.
- [5] J. March, Advanced Organic Chemistry, Wiley, 1992.
- [6] T. W. Odom, J.-L. Huang, P. Kim, C. M. Lieber, J. Phys. Chem. B 104 (2000) 2794.
- [7] R. B. Weisman, The Industrial Physicist (2002).
- [8] T. Yamamoto, S. Watanabe, K. Watanabe, Phys. Rev. Lett. 92 (2004) 75502.





