

Quantum critical 5f-electrons avoid singularities in $\text{URu}_2\text{Rh}_2\text{Si}_2$ A. V. Silhanek,¹ N. Harrison,¹ C. D. Batista,² M. Jaime,¹ A. Lacerda,¹ H. Amitsuka,³ and J. A. Mydosh^{4,5}¹National High Magnetic Field Laboratory, Los Alamos National Laboratory, MS E536, Los Alamos, NM 87545, USA²Los Alamos National Laboratory, MS B262, Los Alamos, NM 87545, USA³Graduate School of Science, Hokkaido University, N10W 8 Sapporo 060-0810, Japan⁴Kam erlingh Onnes Laboratory, Leiden University, 2300RA Leiden, The Netherlands⁵Max-Planck-Institut für Chem ische Physik fester Sto e, 01187 Dresden, Germany

(Dated: March 23, 2024)

We present specific heat measurements of 4% Rh-doped URu_2Si_2 at magnetic fields above the proposed metamagnetic transition field $H_m > 34$ T, revealing striking similarities to the isostructural Ce analog CeRu_2Si_2 , suggesting that strongly renormalized hybridized band models apply equally well to both systems. The vanishing bandwidths as $H \rightarrow H_m$ are consistent with a putative quantum critical point close to H_m . The existence of a phase transition into an ordered phase in the vicinity of H_m for 4% Rh-doped URu_2Si_2 , but not for CeRu_2Si_2 , is consistent with a stronger super-exchange in the case of the U 5f system, with irreversible processes at the transition revealing a strong coupling of the 5f orbitals to the lattice, most suggestive of orbital or electric quadrupolar order.

A quantum-critical point is a singular feature in the phase diagram of matter at the absolute zero of temperature [1, 2]. At this point, the quantum fluctuations that result from the Heisenberg uncertainty principle acquire a divergent characteristic length [1, 2]. Quantum fluctuations originating from this singularity influence the physical properties of matter over an expanding region of phase space (pressure, magnetic field and chemical doping) as the temperature increases [3]. Several unexpected ordered states in strongly correlated matter, including unconventional superconductivity in f-electron intermetallics [4] and d-electron oxides [5, 6], occur in the vicinity of a magnetic quantum critical point. Consequently, theoretical models have focused on the role of symmetry-breaking quantum-critical points in their formation [3, 4, 5].

In this paper, we present the first direct thermodynamic evidence for the avoidance of a non-symmetry-breaking quantum-critical point by the creation of a new low temperature ordered state. In this case, quantum criticality is caused by metamagnetism induced by strong magnetic fields in 4% Rh-doped URu_2Si_2 [7], where Rh substitutes Ru so as to yield $\text{URu}_{1.92}\text{Rh}_{0.08}\text{Si}_2$. Our specific heat measurements reveal the presence of narrow 5f-bands at high magnetic fields, whose entropy then drops abruptly upon ordering at a distinct first-order phase transition. Irreversibility of the transition yields that it is of first order, suggestive of a strong coupling of the ordering 5f-electron degrees of freedom to the lattice.

URu_2Si_2 [8] and its Rh-doped alloys [9] belong to a class of strongly-correlated metals [10], that includes CeRu_2Si_2 [11], UPt_3 [12] and $\text{Sr}_3\text{Ru}_2\text{O}_7$ [13], in which the d- or f-electrons are itinerant (i.e. they contribute to the metallic properties of the material) but are on the

threshold of becoming localized and giving rise to magnetism. By coupling directly to their spin degrees of freedom, strong magnetic fields can coax the d- or f-electrons into a polarized state. Metamagnetism results when this transformation occurs abruptly at a critical magnetic field H_m , as depicted in Fig. 1a. Should H_m evolve from a crossover at finite temperatures into a phase transition (analogous to that of a liquid-gas phase transition) very close to absolute zero [14], it then develops all of the characteristics of an isolated non-symmetry-breaking quantum critical point [15], as depicted in Fig. 1b. Stoichiometric URu_2Si_2 , CeRu_2Si_2 and $\text{Sr}_3\text{Ru}_2\text{O}_7$ [13] are sufficiently close to quantum criticality at H_m for their physical properties to be strongly influenced by fluctuations at temperatures $T > 1$ K.

Being composed of 5f-electrons that have properties intermediate between those of the d-electrons in transition metal oxides and 4f-electrons in rare earth intermetallics [16], actinide intermetallics such as URu_2Si_2 occupy a unique vantage point for understanding the dynamics of quantum criticality in the formation of new states. While not as spatially extended as d-orbitals, the 5f-orbitals of U exhibit a sizeable degree of super-exchange between neighbouring U sites [10], greatly increasing the likelihood of an ordered state over its 4f analogue, Ce. As with 4f-electrons, however, the on-site Coulomb repulsion between 5f-electrons is sufficiently strong to facilitate the formation of renormalized (narrow) bands upon their hybridization with regular conduction bands [17]. This has two immediate benefits:

Firstly, the narrow 5f-band can be completely polarized by magnetic fields that are available in the laboratory. H_m in $\text{URu}_{1.92}\text{Rh}_{0.08}\text{Si}_2$ occurs at $34 < H_m < 37$ T [7], bringing it well within the limits (< 45 T) of the highest available static magnetic fields. Secondly, the Fermi temperature ($T_F < 20$ K) of these quasi-particle bands is significantly lower than the characteristic Debye temperature ($T_D \approx 30$ K) of the phonons (or lattice vibra-

Correspondence and requests for materials should be addressed to N. H. (e-mail: nharrison@lanl.gov)

tions) [18], making the magnetic field-dependent degrees of freedom of these polarized bands readily accessible to fundamental thermodynamic probes such as the specific heat [19]. By comparison, the comparatively large energy scale for d-bands in the cuprates [5] continues to be a major impediment in attempts to identify a possible link between quantum criticality and phase formation in the high temperature superconductors.

Figure 2a shows the temperature dependence of the specific heat of $\text{URu}_{1.92}\text{Rh}_{0.08}\text{Si}_2$ divided by temperature C_p/T at several values of the magnetic field H . The relatively small contribution from the phonons for $T < 20$ K (estimated from non-magnetic ThRu_2Si_2) [18] implies that C_p/T in Fig. 2a is dominated by the electronic contribution, having an appearance similar to that of a Schottky anomaly, but with an additional quadratic tail at low temperatures. In order to understand this behaviour for C_p/T , it is instructive to compare it with similar data obtained by van der Meulen et al [20] for the isostructural Ce analog CeRu_2Si_2 (also a metamagnet) shown in Fig. 2b, for which super-exchange interactions between neighbouring 4f-sites are expected to be comparatively unimportant [10]. The overall electronic structure of CeRu_2Si_2 at fields $H > H_m$ has already been shown to be consistent with the general theoretical framework of the Anderson lattice model in which the 4f¹ magnetic doublets are hybridized with a broad conduction band [21, 22]. Following the qualitative picture of Edwards and Green [22] for the evolution of the quasiparticle up and down bands, we can approximate the corresponding density of electronic states (per unit of energy) by

$$D(\epsilon) = D_0 \left[1 + \frac{q V^2}{(\epsilon - \epsilon_0)^2 + \frac{1}{2}} \right]^{-1} \quad (1)$$

D_0 is the density of states of the broad unperturbed conduction band, V is the hybridization potential, while ϵ_0 is the energy shift of each quasiparticle band due to the interplay between the Kondo interaction and the Zeeman (or magnetic field) coupling at fields $H > H_m$. q^{-1} represents the extent to which the density of electronic states is renormalized by the strong Coulomb interactions between f-electrons [22]. The parameter $q V^2 = D_0$ has to be adjusted to accommodate one electron per formula unit, becoming the effective width of the hybridized bands [22]. Although the important spectral weight around the bare f-level is missing in this approach, it is entirely adequate for calculating C_v of CeRu_2Si_2 in the limit $j'' \rightarrow j' > 0$. Hence, Equation 1 develops a simple Lorentzian form.

Figures 2c, 2d illustrate the results of fits for C_p/T versus T (shown as solid lines in Figs. 2a and b) where $C_p = C_v + T \partial^2 F / \partial T^2$ is calculated numerically from the free energy $F = \int_{-\infty}^{\infty} D(\epsilon) \ln(1 + \exp(-\epsilon/k_B T)) d\epsilon$ [23] and where each spin component $j' = j'' = 1/2$ is considered

independent in the present hybridized-band approximation. These fits confirm that one spin component of the hybridized band, which we shall assume to be spin-up, $j'_{1/2}$ [21, 22], is closer to the chemical potential and crosses at $H = H_m$, in accordance with theoretical expectations for the Anderson lattice [21, 22].

The close similarity of Fig. 2a to 2b and Fig. 2c to 2d implies that there exists an extensive range of magnetic fields and temperatures for which the hybridized band model applies equally well to the 5f-electrons in $\text{URu}_{1.92}\text{Rh}_{0.08}\text{Si}_2$ as it does to the 4f-electrons in CeRu_2Si_2 . It also implies that the orbital manifold of U in $\text{U}(\text{Ru,Rh})_2\text{Si}_2$ is a doublet, as opposed to a singlet, which has been one of the pivotal areas of debate in attempts to understand the Hidden Order phase in pure URu_2Si_2 (suppressed in Rh-doped URu_2Si_2) [8, 9, 10, 24, 25, 26]. The similarity of the form of C_p/T in Fig. 2 to that in pure URu_2Si_2 [19], implies that the existence of this doublet is not significantly affected by small amount of Rh-doping. Figure 3 further shows that the fitted bandwidth for both $\text{URu}_{1.92}\text{Rh}_{0.08}\text{Si}_2$ and CeRu_2Si_2 plotted versus $H - H_m$, is the same for both systems, within experimental uncertainty. For both systems, ω/q , revealing that the bands become progressively more narrow as the spin fluctuations intensify, since $q^{-1} \propto |H - H_m|^{-1}$ exhibits a divergent behaviour near H_m . The dotted line in Fig. 3 shows an independent estimate of the Fermi temperature T_F of the quasiparticle bands obtained from magnetotransport measurements on $\text{URu}_{1.92}\text{Rh}_{0.08}\text{Si}_2$ [7]. Its consistency with ω/q provides the first confirmation of a direct correlation between features observed in the electrical resistivity and the hybridized bandwidth [21, 22].

While $\text{URu}_{1.92}\text{Rh}_{0.08}\text{Si}_2$ and CeRu_2Si_2 possess many similarities for $H - H_m > 4$ T, significant differences emerge as $H \rightarrow H_m$, as shown in Fig. 4. This can be seen rather directly in $\text{URu}_{1.92}\text{Rh}_{0.08}\text{Si}_2$ as soon as $\mu_0 H$ is reduced from 38 T to 37.5 T in Fig. 4a. At temperatures above 6 K, C_p/T at $\mu_0 H = 37.5$ T conforms to the solid curve calculated using fitting results for $j'_{1/2}$ and $j''_{1/2}$ extrapolated from $\mu_0 H = 38$ T in Fig. 2c. Thus, at higher temperatures, the specific heat of $\text{URu}_{1.92}\text{Rh}_{0.08}\text{Si}_2$ at 37.5 T continues to be consistent with quasiparticle bands that become progressively more narrow and closer to ϵ_0 as $H \rightarrow H_m$. At temperatures below 6 K, however, a significant redistribution of entropy occurs with respect to the calculated curve (cyan shaded area), establishing rather conclusively that the same 5f-electrons involved in the formation of the quasiparticle bands condense into a new state at low temperatures. The sharp anomaly at 4.8 K at 37.5 K provides unambiguous evidence for the existence of a phase transition. Figure 4b further shows that the amount of energy required to heat the sample during the specific heat measurement differs considerably between initial (open symbols) and subsequent (filled symbols) 0.1 K cycles

of the temperature, using the relaxation method. Hence, the actual phase transformation itself is an energetically costly process, resulting in considerable hysteretic losses characteristic of a first order phase transition. This observation closely reproduces that observed at the valence transition in YbInCu_4 [28, 29], at which a change in the orbital manifold of the f-electrons is coupled to the lattice parameters [30]. This finding in $\text{URu}_{0.92}\text{Rh}_{0.08}\text{Si}_2$ is most suggestive of orbital or electric quadrupolar order [26].

CeRu_2Si_2 , by contrast, does not transform into a new state at low temperatures [11]. The similarity in the intensity of the fluctuations in the two systems suggests that while they play a crucial role in driving the system towards instability at H_m , the increased tendency for direct or super-exchange between 5f-orbitals compared to 4f-orbitals appears to be the decisive factor in whether a new ordered phase actually occurs. The very appearance of ordered phases in $\text{URuRh}_2\text{Si}_2$ in connection with an isolated non-symmetry-breaking quantum-critical point (as opposed to one that is symmetry breaking), suggests that the tendency to form new states of matter is ubiquitous to both forms of quantum criticality. Such a finding may have far reaching implications, for if it proves to be generic (i.e. not unique to metamagnetism) it would eliminate the need to associate the pseudogap regime in the cuprates with a true broken-symmetry phase [5, 31]. Finally, if it is the exchange between the orbitals that ultimately optimizes conditions for the formation of an ordered phase, this would help to explain the common trend in maximum ordering transition temperatures in progressing from 4f to 5f to d-electrons.

This work was performed under the auspices of the National Science Foundation, the Department of Energy (US) and the State of Florida.

- [9] Y. Miyako et al. *J. Magn. Magn. Mater.* 108, 190-192 (1992).
- [10] P. Fazekas, *Lecture notes on electron correlation and magnetism* (World Scientific, Singapore, 1999).
- [11] J. Flouquet, et al. *Physica B* 319, 251-261 (2002).
- [12] P. H. Frings and J. J. M. Franse, *Phys. Rev. B* 31, 4355-4360 (1985).
- [13] R. S. Perry et al. *Phys. Rev. Lett.* 86, 2661-2664 (2001).
- [14] S. A. Grigera et al., *Science* 294, 329-332 (2001).
- [15] A. J. M. Illis, A. J. Schoeld, G. G. Lonzarich, and S. A. Grigera, *Phys. Rev. Lett.* 88, 217204/1-4 (2002).
- [16] J. L. Smith and E. A. Kmetko, *J. Low-Temp. Phys.* 90, 83-8 (1983).
- [17] A. C. Hewson, *The Kondo problem to heavy fermions* (Cambridge University Press, Cambridge, 1993).
- [18] H. Amitsuka and T. Sakakibara, *J. Phys. Soc. Japan* 63, 736-47 (2002).
- [19] M. Jaime et al., *Phys. Rev. Lett.* 89, 287201/1-4 (2002).
- [20] H. P. van der Meulen et al., *Phys. Rev. B* 44, 814-18 (1991).
- [21] S. M. Evans, *Europhys. Lett.* 17, 469-74 (1992).
- [22] D. M. Edwards and A. C. M. Green, *Z. Phys. B* 103, 243-9 (1997).
- [23] K. D. Schotte and U. Schotte, *Phys. Lett. A* 55, 38-40 (1975).
- [24] V. Barzykin and Gorkov, *Phys. Rev. Lett.* 70, 2479-82 (1993).
- [25] P. Santini and G. Amoretti, *Phys. Rev. Lett.* 73, 1027-30 (1994).
- [26] F. J. Ohkawa and H. Shimizu, *J. Phys.: Condens. Matter* 11, L519-24 (1999).
- [27] P. Chandra, P. Coleman, J. A. Mydosh, and V. Tripathi, *Nature* 417, 831-4 (2002).
- [28] J. L. Sarrao et al., *Phys. Rev. B* 58, 409-13 (1998).
- [29] A. Silhanek et al. (to be published).
- [30] C. Dallera et al., *Phys. Rev. Lett.* 88, 196403/1-4 (2002).
- [31] F. F. Balakirev et al. *Nature* 424, 912-15 (2003).

FIG. 1: A schematic of metamagnetic quantum criticality. (a) shows an illustration of the inflection point in the magnetization at H_m which is anticipated to acquire an inflection slope at $T = 0$ (blue line), but which becomes broadened at finite temperatures $T > 0$ (red line). (b) shows the resultant magnetic field H versus temperature T phase diagram, with a heavy Fermi liquid (strongly correlated electron fluid) region at $H < H_m$ and polarized Fermi liquid region at $H > H_m$. In the ideal case, the system is a non-Fermi liquid at $T = 0$ at $H = H_m$ (black spot). At finite temperatures $T > 0$, the region of phase space occupied by the non-Fermi liquid expands, giving rise to the recognizable funnel shape and, in doing so, relieves the necessity for the quantum criticality being precisely tuned by pressure, chemical doping or magnetic field at $T = 0$.

-
- [1] S. Sachdev, *Quantum phase transitions*. (Cambridge University Press, Cambridge, 1999).
 - [2] S. Sachdev, *Science* 288, 475-80 (2000).
 - [3] P. Coleman and A. J. Schoeld, *Nature* 433, 226-229 (2005).
 - [4] P. Coleman, C. Pepin, Q. M. Si, and R. Ramazashvili, *J. Phys.: Condens. Matter* 13, R723-38 (2001).
 - [5] L. Ali et al. *Nature* 422, 698-701 (2003).
 - [6] S. Chakravarty, H.-Y. Kee, and K. V. Iker, *Nature* 428, 53-5 (2004).
 - [7] K. H. Kim, et al. *Phys. Rev. Lett.* 93, 206401/1-4 (2004).
 - [8] T. T. M. Palstra et al. *Phys. Rev. Lett.* 55, 2727-30 (1985).

FIG. 2: The measured specific heat divided by temperature C_p/T together with the results of modelling. (a) shows C_p/T for $URu_{1.92}Rh_{0.08}Si_2$ versus temperature T at several different values of the magnetic field $H > H_m$ depicted using different symbols and colours as indicated. Solid lines indicate fits to the hybridized band model. (b) gives similar results for $CeRu_2Si_2$. (c) shows fitted values for the position of the spin-up $\epsilon_{1=2}$ (up arrows) and spin down $\epsilon_{+1=2}$ (down arrows) hybridized bands in $URu_{1.92}Rh_{0.08}Si_2$, with red line linear fits added to guide the eye. A pseudospin notation of $1=2$ is used for up- and down-spin states, respectively. The grey dot represents the approximation location of the quantum critical point or H_m obtained from published magnetotransport and magnetization measurements. (d) shows similar fitted values for $CeRu_2Si_2$.

FIG. 3: Fitted values of ϵ (the hybridized bandwidth) for both $URu_{1.92}Rh_{0.08}Si_2$ and $CeRu_2Si_2$, as indicated, plotted versus $H - H_m$ with error bars. The dashed grey lines denote the regions of Fermi liquid and non-Fermi liquid recently identified from a crossover T^* in the electrical resistivity [7]. The vertical axes ϵ and T are scaled only by the Boltzmann constant k_B , revealing a mutual consistency between experiments in which the Fermi temperature T_F approximately corresponds to ϵ . The various coloured regions are labelled in accordance with Fig. 1, with the addition of a new phase (hashed region) which forms only in $URu_{1.92}Rh_{0.08}Si_2$ (not $CeRu_2Si_2$) as a means to avoid the putative quantum critical point.

FIG. 4: Evidence for ordering in $URu_{1.92}Rh_{0.08}Si_2$. (a) compares actual C_p/T data (diamonds) with a curve (solid line) calculated from parameters extrapolated to 37.5 T, obtained by fitting the resonance model for $\mu_0 H = 38$ T. The calculated curve matches the data for $T > 6$ K, but the difference (shaded regions) reveals a significant redistribution of entropy below 6 K. This firmly establishes the involvement of the 5f doublets in ordering. (b) shows C_p versus T at several different magnetic fields (different colours) on both the initial 0.1 K increase of the temperature (open symbols) and subsequent increases of temperature after cooling (filled symbols). The difference between them provides definitive evidence for hysteretic losses, which typically result from phase coexistence.

This figure "figure1.jpg" is available in "jpg" format from:

<http://arxiv.org/ps/cond-mat/0502628v1>

This figure "figure2.jpg" is available in "jpg" format from:

<http://arxiv.org/ps/cond-mat/0502628v1>

This figure "figure3.jpg" is available in "jpg" format from:

<http://arxiv.org/ps/cond-mat/0502628v1>

This figure "figure4.jpg" is available in "jpg" format from:

<http://arxiv.org/ps/cond-mat/0502628v1>