P hase separation in the S = 1 frustrated antiferrom agnet G eN $\frac{1}{2}O_4$

T. Lancaster, S. J. Blundell, D. Prabhakaran, and W. Hayes

C larendon Laboratory, O xford University D epartm ent of Physics, Parks Road, O xford, O X1 3PU, UK

F.L.Pratt

ISIS Facility, Rutherford Appleton Laboratory, Chilton, Oxfordshire OX11 0QX, UK

(D ated: January 14, 2022)

W e present the results of a muon-spin relaxation ($^+$ SR) study of G eN $_2O_4$. W e provide further clari cation of the two transitions to the antiferrom agnetic state and measure the magnetic eld dependence of the heat capacity up to 14 T.B oth oscillatory and relaxing signals are observed below the lower transition (at temperature $T_{\rm N\,2}$) in the muon-decay positron asymmetry spectra, arising from two distinct types of magnetic environment. This is consistent with phase separation into long-range and short-range ordered regions at low temperatures. The signal associated with short-range order is seen to persist across both transitions but disappears into the param agetic phase above the upper transition temperature $T_{\rm N\,1}$.

PACS num bers: 75.50 Ee, 76.75.+ i, 75.40.-s, 75.50.-y

M aterials experiencing geom etric frustration have been the topic of much recent interest. Their rich behavior is due to a large ground-state degeneracy, which renders them highly unstable to perturbations¹. In the case of a frustrated model system comprising H eisenberg-type antiferrom agnetic nearest-neighbour interactions, cooperative param agnetic behavior (i.e. uctuations at all tem peratures down to absolute zero) is expected. This state of a airs is altered, how ever, by perturbations due to other interactions (including next-nearest neighbour, dipole, crystal eld etc.) which cause a variety of low tem perature states to be realised, including spin-liquids² and spin-loes³ in som e rare-earth pyrochlores and structural phase transitions for som e spinels with transition m etal ions on the frustrated B sublattice^{4,5}.

Many geometrically frustrated systems with halfinteger spins relieve the frustration by undergoing a structural phase transition at low tem peratures to a m agnetically ordered state; this is the case for the spinels $ZnCr_2O_4$ (S = 3=2)⁴, GeCo₂O₄ (S = 3=2) and powder sam ples of $ZnFe_2O_4$ (S = 5=2)^{5,6} (although we note that a magnetic transition is not observed in single crystal sam ples⁷). The integer spin (S = 1) frustrated antiferrom agnet G eN 1/0 4 has been therefore of recent interest, since it undergoes a transition to an antiferrom agnetically ordered state below 12 K (observed in both powder and single crystal sam ples^{8,9,10}) with no accom panying structural transition. GeN 1/04 has the norm alspinel structure, having N \dot{f}^+ ions (3d⁸) at the vertices of corner sharing tetrahedra (the spinel B site), coordinated by a nearly regular octahedron of oxygen ions, resulting in a ³A_{2q} triplet ground state. The crystal eld lowers the degeneracy of this triplet, further splitting it into a close lying spin-singlet and doublet expected to be separated by only a few cm¹. Recent experimental studies of this system by C raw ford et al.9 show that the ordered state is reached by two separate transitions at $T_{N1} = 12:13$ K and $T_{N2} = 11.46 \text{ K}$. It was found from heat capacity measurements that the magnetic entropy of $G \in \mathbb{N}_2 \cup \mathbb{Q}_4$ is only



FIG.1: Heat capacity measured in (a) zero eld and in an applied magnetic eld of (b) 7T and (c) 14T. (d) Deduced magnetic phase diagram (phases I and II are antiferrom agnetic phases, phase III is paramagnetic).

half of the expected $2R \ln 3$ per mole⁹, with the same m easurem ents suggesting the existence of both gapped and gapless excitations within the N eel state.

In recent years, muon-spin relaxation ($^+$ SR) measurements have been highly successful in observing frustration-related behaviour in several frustrated systems, including the observation of spin-ice behaviour and cooperative paramagnetism (see e.g.^{2,11}). In this paper we report on the rst muon-spin relaxation measurements on G eN $\frac{1}{2}O_4$. We have probed the magnetically ordered region from a local view point and provide evidence for muons stopping in separate environments in the ordered state. The experimental results are consistent with phase separation into spatially distinct regions



FIG.2: ZF spectra measured (a) at 1.80 K, in phase I (T < T_{N2}), (b) at 11.55 K and 12.00 K, in phase II (T_{N2} T T_{N1}) and (c) at 12.32 K, in phase III (T > T_{N1}). The oscillations seen in (a) are observed to vanish above T_{N2} (b), with the Gaussian component dram atically decreasing in amplitude above T_{N1} (c).

show ing di erent m agnetic behaviour.

Polycrystalline GeN i204 was prepared by the solidstate reaction technique using high purity (> 99:99 %) GeO₂ and N iO chem icals. The stochiom etric m ixed powder was calcined in an O₂ ow atmosphere at 1200 C for 48 hours. The sam ple was characterised using X-ray di raction analysis (which revealed no contribution from in purities) and heat capacity measurements. The latter were carried out on a sintered pellet sample on warm ing using a 14T Quantum Design PPMS system. Heat capacity data taken in zero eld (ZF) and in an applied eld of 7T and 14T are shown in Fig.1 (a-c). The ZF results show two sharp maxima at T_{N1} and T_{N2} , in agreement with previous studies^{9,10}. In addition, we nd a small should er below T_{N1} , also observed by H ara et al.¹⁰ who speculated about a possible third transition. The tem perature of the two main peaks decreases markedly with applied eld (as expected for an antiferrom agnet, see e.g. Ref, 12), as shown in the suggested phase diagram in Figure 1(d). Both main peaks broaden and decrease in intensity with increasing eld, the e ect being m ore pronounced for the lower tem perature peak. We note that no spin-ip transition has been observed in magnetization m easurem ents up to 23 T 13 .

Zero-eld muon-spin relaxation measurements have been made on a polycrystalline sample of GeN i_2O_4 using the DOLLY instrument at the Swiss Muon Source, PaulScherrer Institute (PSI), Villigen, Switzerland. The sample of GeN i_2O_4 was wrapped in 25 m Ag foil and mounted on an Ag backing plate. In a ⁺SR experiment, spin-polarized positive muons are stopped in a target sample, where the muon usually occupies an interstitial position in the crystal. The observed property in the experiment is the time evolution of the muon spin polarization, the behaviour of which depends on the local magnetic eld B at the muon site, and which is proportional to the positron asymmetry function A (t)¹⁴.

Example spectra are shown in Fig2 for the cases (a) phase I (T < T_{N2}), (b) phase II (T_{N2} T T_{N1}) and (c) phase III (T > T_{N2}). For phase I, oscillations in the

asymmetry are clearly discernible, though with a rather sm allam plitude, and a fast initial relaxation of them uon polarization is visible at early times. The oscillations are characteristic of a quasistatic local magnetic eld at the m uon site, which causes a coherent precession of the spins of those m uons with a component of their spin polarization perpendicular to this local eld; their presence provides strong evidence for the existence of long range m agnetic order (LRO) in phase I, in agreem ent with previous neutron di raction m easurem ents⁹. The frequency of the oscillations is given by $_{i} =$ $B_i=2$, where is the 135:5 M H z T 1), and muon gyrom agnetic ratio (2 B_i is the local eld at the ith muon site. The oscillations were found at two distinct frequencies corresponding to muons at two separate muon sites in the crystal experiencing a quasistatic local magnetic eld. Because of the additional relaxation signals in the data, a full description also required two additional relaxing components. One is Gaussian in form, $A_G \exp(-t^2 t^2)$, with a large relaxation rate (= 2 B 2 =2, where B 2 = h(B hB i) 2 i is the second moment of the local eld distribution), while the other was an exponential $A_{L} \exp(t)$. Thus the spectra were found to be best tted across the entire tem perature range with the resulting functional form

$$A (t) = A_{m ag}^{(1)} a_{k} + a_{2}^{(1)} \exp(1t) \cos(2t) t)$$

$$+ a_{2}^{(2)} \exp(2t) \cos(2t) t)$$

$$+ A_{G} \exp(2t^{2}) + A_{L} \exp(-t); \quad (1)$$

where, in the ts, the initial asymmetry (= $A_{mag} + A_{G} + A_{L}$) was held xed. In phase I, the presence of the oscillatory component (A_{mag}) together with both relaxing components (A_{G} and A_{L}) are required to t the data. For phase II, the oscillations are no longer discernible (i.e. A_{mag} 0), and the spectra are best described with only the relaxing components described above, with $A_{G} > A_{L}$. For data in phase III, the spectra continue to be described by these relaxing components, although now $A_{G} < A_{L}$ and the behaviour is dom inated by dynamic uctuations

of the local eld.

The existence of oscillations in the asymmetry in a polycrystalline sam ple is a signature of a narrow distribution of the magnitudes of the static local magnetic elds at sym m etry-related m uon sites in the crystal associated with LRO. A broader distribution of these elds leads to the occurrence of the Kubo-Toyabe (KT) function, which is well approximated by a Gaussian function at early times (slow dynamics often cause the later time behaviour of the KT function to be unobservable) and this corresponds to a phase exhibiting short-range order (SRO). In contrast, an exponential function is often the result of fast, dynamic uctuations in the local eld, in which case the relaxation rate $\ / \ ^2$ B $^2 =$, where is the uctuation rate¹⁵. The presence of multiple com ponents (see Eq. 1) in phase I and II is evidence for the coexistence of both static and dynam ic m agnetic regions of the sample, and in phase I for the coexistence of LRO and SRO. This phase separation into LRO and SRO regions m ay also explain the m issing entropy observed by Craw ford et al. The results of the tting procedure¹⁶ are shown in Fig.3 and we now describe these results in detail.

Phase I (T < T_{N2}): The amplitude A_{mag} is found to be approximately constant up to T 9 K (Fig.3(a)), where it is seen to decrease as the transition at $T_{N\,2}$ is approached from below. This is accompanied by a corresponding rise in the amplitude of the Gaussian component A_G . The frequencies of the oscillations (Fig.3(b)) vary little below the transition tem perature $T_{\rm N\,2}$, at which point A_{mag} ! 0, indicating rst-order behaviour, in agreem ent with the heat capacity measurem ents'. We also note that the stability of the two frequencies across the tem perature range means that we see no e ect due to the depopulation of the upper level of the split ${}^{3}A_{2a}$ triplet state at low tem peratures. The am plitudes of the di erent com ponents detected in the asym m etry spectra are expected to be proportional to the volum e of the separate phases. As $T_{N\,2}$ is approached from below, the decreasing am plitude of the oscillatory signal corresponds to a shrinking of the volume led by the LRO fraction, leading to a greater probability that the muon stops in the SRO regions, contributing to the Gaussian signal.

Phase II (T_{N2} T_{N1}): Above T_{N2} the oscilla-Т tory component vanishes. With increasing temperature T_{N1} , we see instead (Fig.3(b)) in the region T_{N2} Т the increase of the uctuating component (A L increases) coexisting with a decreasing fraction of the SRO component (A_G decreases). In this regime, we therefore have the static, broad distribution of local elds, coexisting with a fraction of the sam ple where the local eld at the m uon sites are undergoing fast uctuations on the m uon time scale. As the temperature is increased, this contribution from the dynam ic fraction increases, becoming dom inant above $T_{N 1}$. The most straightforward explanation of the two transitions in GeN i_2O_4 is analogous to C sN iC h^{17,18} in which, on cooling, spins order rst along an axis and then a component of the spin orders



FIG.3: Results of ts to equation (1). (a) Amplitudes of the magnetic component A_{mag} (open circles) and G aussian component A_G (closed circles) as a function of temperature. A_G is seen to rise as T_{N2} is approached from below. Between the transitions, A_G decreases suddenly, while A_L increases (open triangles). (b) The precession frequencies remain approximately constant for 1.8 K T T_{N2} . (c) The relaxation rate is seen to fall smoothly across both transitions.

in-plane¹⁹. Our nding is that there is su cient spin disorder in the interm ediate phase II to preclude the observation of coherent spin precession, and moreover the SRO spin-disordered phase persists well into phase I. In fact, the relaxation rate characterising the SRO phase is seen to decrease smoothly across the entire temperature range (Fig.3(c)), showing no features corresponding to either of the transition temperatures. The smooth decrease of with increasing temperature (Fig.3(c)) suggests that this parameter is dominated by the magnitude of the local eld distribution in the SRO regions as seen in other muon studies of magnetically ordered system s^{20} . We therefore have a picture of the SRO regions as having a eld magnitude that decreases continuously across both transitions, but with a rapidly changing volum e fraction around them . We note further that our interpretation of the ⁺SR results is not dissimilar to that proposed for measurements on powder samples of the S = 5=2 spinelZnFe₂O₄⁶. In that compound a SRO component is found in the antiferrom agnetic state which persists above the Neel temperature, coexisting with a component attributed to a paramagnetic fraction. As with the SRO component in the present case, the amplitude of the SRO fraction is seen to go through a maximum at the ordering transition.

P hase III ($T > T_{N1}$): Above T_{N1} , the behavior is more conventional and the relaxation is dom inated by an exponential signal corresponding to uctuating param agnetic moments.

In conclusion, the + SR m easurements on GeN $\frac{1}{2}O_4$ provide further clarication of the nature of the two m agnetic transitions and are suggestive of phase separation into spatially separate regions of the material associated with di erent magnetic behaviour. One of these components is consistent with the existence of SRO that coexists with LRO below $T_{N\,2}$ and may persist above $T_{N\,1}$. In order to reliably separate those parts of the signal arising from angular averaging of a powder sample, it would be also be desirable to carry out measurements on single crystal samples of this material. The unusual ordering behaviour and smaller than expected magnetic entropy may stem from the integer spin, which may also be the case for the recently reported pyrochlore $Y_2 R u_2 O_7^{21}$.

Part of this work was carried out at the Swiss M uon Source, Paul Scherrer Institute, V illigen, Switzerland. W e thank H ubertus Luetkens and R obert Scheuerm ann for technical assistance. This work is supported by the EPSRC.T L acknow ledges support from the European C om m ission under the 6th Fram ew ork P rogram m e through the K ey A ction: Strengthening the European R esearch A rea, R esearch Infrastructures. C ontract no: R II3-C T -2003-505925

E lectronic address: t.lancaster10 physics.ox.ac.uk

- ¹ R.Moessner, Can.J.Phys.79 1283 (2001). A P.Ram irez, Annu.Rev.Mater.Sci.24 453 (1994).
- ² JS.Gardner, SR.Dunsiger, BD.Gaulin, MJP.Gingras, JE.Greedan, RF.Kie, MD.Lumsden, WA.MacFarlane, NP.Rajı, JE.Sonier, I.Swainson, Z.Tun Phys. Rev.Lett., 82 1012 (1999)
- ³ S.T. Bram well and M.J.P. Gingras, Science 294 1495 (2001)
- ⁴ S.H.Lee, C.Broholm, T.H.Kim, W.Ratcli and S.W. Cheong, Phys. Rev. Lett 84, 3718 (2000).
- ⁵ Q.Huang, JW.Lynn, M.K.Craw ford, R.L.Harlow, R.B. Flippen and J.Horm adaly, Proceedings of N inth International Conference on Composites Engineering San Diego, Ca, 2002 pp. 305 and 306; M.K.Craw ford et.al. (unpublished)
- ⁶ W. Schiessl, W. Potzel, H. Karzel, M. Steiner, G.M. Kalvius, A. Martin, M.K. Krause, I. Halevy, J. Gal, W. Schafer, G.W ill, M. Hillberg and R.W appling, Phys. Rev. B 53 9143 (1996)
- ⁷ T.Usa, K.Kamazawa, H.Sekiya, S.Nakamura, Y.Tsunoda, K.Kohn and M.Tanaka, J.Phys.Soc.Japan 73 2834 (2004); T.Suzuki, Y.Aikawa and T.Katsufuji, J.Phys. Soc.Japan 74 863 (2005)
- ⁸ E F. Bertaut, V. V. Q iu, R. Pauthenet and A. Murasik, J Phys. (France) 25 516 (1964).
- ⁹ M K.Craw ford, R.L.Harlow, P.L.Lee, Y.Zhang, J.Horm adaly, R.Flippen, Q.Huang, J.W.Lynn, R.Stevens, B.F.W ood eld, J.Boerio-Goates and R.A.Fisher, Phys. Rev.B 68, 220408 (R) (2003).
- ¹⁰ S.Hara, Y.Yoshida, S.-I. Ikeda, N.Shirakawa, M.K.Crawford, K.Takase, Y.Takano and K. Sekizawa, J.Phys.Soc. Japan, 73 2959 (2004)

- ¹¹ IM .M arshall et al., J.Phys.: Condens.M atter 14, L157, (2002); M J.H arris et al., J.M agn.M agn, M ater, 177 757 (1998); J.S.G ardner et al., Phys Rev Lett. 82 1012 (1999); J.A.H odges et al., Phys. Rev. Lett. 88 77204 (2002).
- ¹² R.Leidland W .Selke, Phys. Rev. B 70, 174425 (2004).
- ¹³ S.Diaz, S. de Brion, M. Holzapfel, G. Chouteau and P. Strobel, Physica B 346, 146 (2004).
- ¹⁴ S.J.B lundell, Contem p. Phys. 40, 175 (1999).
- ¹⁵ R.S. Hayano, Y.J. Uem ura, J. Im azato, N. Nishida, T. Yam azakiand R.Kubo, Phys. Rev. B 20 850 (1979)
- ¹⁶ The factor multiplied by A_{mag} accounts for the magnetically ordered component of the spectra (normalised to 1), expected to be made up from contributions from those muons with spin components parallel to the local magnetic eld a_k (xed at 0.67) and those with perpendicular components $a_2^{(1)}$ (found to be constant with $a_2^{(1)} = 0.12$ and $a_2^{(2)} = 0.21$). The value of a_k is much higher than expected. The corresponding relaxation rates $_{1,2}$, were found to be constant at $_1 = 2.26$ M Hz and $_2 = 6.12$ M Hz across the entire temperature range. Below T_{N2} , A_L took the constant value 1.54%, while = 0.92 M Hz. Above T_{N2} , was un xed.
- ¹⁷ W B.Yelon and D E.Cox, Phys. Rev. B 7, 2024 (1973).
- ¹⁸ H.Kadowaki, K.Ubukoshiand K.Hirakawa, J.Phys.Soc. Japan, 56 751 (1987)
- ¹⁹ X.Zhu and M B.W alker, Phys. Rev. B 36, 3830 (1987).
- ²⁰ T.Lancaster, S.J.B lundell, F.L.Pratt, C.H.Gardiner, W. Hayes, and A.T.Boothroyd, J.Phys.: Condens. M atter, 15 8407 (2003)
- ²¹ M. Tachibana, H. Kawajiand T. Atake, Phys. Rev. B 71, 060402 (R) (2005).