arXiv:cond-mat/0504324v1 [cond-mat.dis-nn] 13 Apr 2005

Molecular dynamic investigations of liquid nickels structural properties

A. Kimmel*, V. Ladyanov*, I. Gusenkov**

January 9, 2022

* *Physical Technical Institute of Ural branch of Russian Academy of Sciences, 132, Kirov Str., Izhevsk, Russia, 426000*
* *Udmurt State University, 1, Universitetskaya Str., Izhevsk, Russia, 426034*

PACS numbers: 61.20.Ja, 61.20.Ne, 66.20.+d

Abstract

The effective pair potentials of liquid nickel have been derived by means of the inverse self-consistent method from the experimental diffraction data. The potentials provide highly accurate coincidence of experimental and simulated structural properties. The statistical analysis of Voronoi polyhedral and Delaunau simplices has shown that in the vicinity of the melting point in the structure of liquid nickel there are relatively stable spatial polytetrahedral formations with local 5-folder symmetry. With temperature rise such formations evolve to isolate and compact ones with preserving of the local five-folder symmetry.

1 Introduction

In the last few years, extensive studies have been performed on a variety of ionic, covalent, and metallic liquids in order to understand their structural and dynamic behavior from a microscopic perspective. Transition metals, such as nickel, are very interesting in this record. The structure of liquid

nickel has been studied in many works by means of direct diffraction methods and investigations of structural sensitive properties [1, 2, 3]. Significant modifications of structure parameters were obtained above the nickel melting point. Authors of the work [2] have obtained the fuzzy maximum located close to the line (200) of the hypothetical BCC structure. However, by means of the levitation techniques in conjunction with the neutron scattering experiment the authors of the work [3] unambiguously proved the Franks hypothesis [4], which states that the icosahedral short range order is already revealed above the melting temperature in transition metals, such as Ni, Fe, Co.

Computer simulations give us a new information about system, such as coordinates of all particles of modelling system, which can not be obtained by means of usual experimental methods. However, using atomic coordinates to calculate the pair correlative function (PCF) or structure factors to compare them with experimental data is not an effective method for investigating the liquid structure. One of the best prospective approach to solving such tasks is the Voronoi polyhedra (VP) and Delaunay simlices (DS) method [5, 6].

Computer simulation methods allow us to advance in understanding the atomic structure of the amorphous and liquid state of matter. But the main problem of methods, such as molecular dynamic (MD) or Monte-Carlo, is a choice of adequate potentials of the interactions between atoms. Usually, the disparities of the computer and experimental results are connected with a non-correspondence of used potentials.

Generally, the task of finding the exact and universal interatomic potentials is quite difficult. Therefore, inverse methods [7, 8], in which the effective pair potentials are derived from the experimental structural data, are one of the best methods for obtaining the effective pair potentials and computing structure, corresponding with real matter. Moreover, the deriving potentials are effective and can be considered as potentials that include many-particle correlation, which is typical for liquid state.

In this work we used the self-consistence inverse method [8] for obtaining the effective pair potentials of liquid nickel at different temperatures above its melting point from the experimental structural data [9]. The potentials allow us to get an adequate structure of liquid nickel, carry out Voronoi-Delaunay statistical-geometrical analysis of local atomic structure and investigate its temperature evolution.

2 Formalism

2.1 Self-consistent method for deriving the effective pair potentials

In this study the predictor-corrector method, originally proposed by Schommers [8], was used as an accurate method for solving the inverse problem. This self-consistent method is based on the integral equations theory and computer simulations. The procedure of deriving $'(r)$ is iterative. The zero-approximation of the effective potential called predictor, is given by:

$$'^{0}(r) = k_b T \ln g^{exp}(r); \quad (1)$$

where $g^{exp}(r)$ is the experimental PCF, k_b - is Boltcman constant and T is the absolute temperature of the system. Atomic configuration, simulated by means of MD with known potential $'^{0}(r)$, corresponds to the pair correlation function $g^{1}(r)$. The next iteration, called corrector, constructs the corrected potential $'(r)$:

$$'(r) = '^{0}(r) + k_b T \ln \frac{g^{exp}(r)}{g^{1}(r)}: \quad (2)$$

The agreement between experimental and model PCFs is improved with each next iteration. The iterative process is repeated until the discrepancy between the criterion (experimental) and simulated PCFs becomes smaller than the desired accuracy:

$$= \frac{1}{n_1 \; n_2} \sum [g^{exp}(r) - g(r)]^2; \quad (3)$$

where n_1 and n_2 - are the numbers of initial and final points of histogram, respectively.

2.2 Voronoi-Delaunay statistical-geometrical analysis

Models of dense disordered systems of spherical atoms have definite statistical motives in the arrangement of these structural elements. Unlike crystals, in which the structural motives are described in terms of the translation order, in this case the methods need to be different from those in crystallography.

Thus, Voronoi-Delaunay structural analysis was carried out for describing the local atomic configurations as function of the atomic coordinates.

The most widely applicable forms of the statistical-geometrical analysis of random systems by VP are topological (distribution of the number of faces and number of edges per face and topological types) and metric (distribution of VP volumes, face areas, the sphericity coefficient etc.) properties [5]. The distribution of the coefficient of the sphericity K_{sph} of VP was chosen in the present work, where the sphericity coefficient is defined by the expression:

$$K_{sph} = \frac{36\ V^2}{S^2}: \tag{4}$$

Here, V is the volume, and S is the surface area of given polyhedron. Thus, this measure defines a deviation of the shape of VP from regular sphere and characterizes homogeneity of atomic environment.

It is well known, that packing of four spherical particles in vertexes of regular tetrahedron is the most energetically advantageous atomic configuration. Since each DS is a tetrahedron, it is convenient to choose the deviation of the simplex shape from an ideal tetrahedron as a quantitative measure of the DS. So, the measure of tetrahedricity, Tr, we used was proposed in [6]:

$$Tr = \frac{\sum (l_i\ l_j)^2}{15 < l >^2}; \tag{5}$$

where l_i is the length of the i-th edge; $< l >$ is the average length for this simplex. This measure was constructed to be zero for an ideal tetrahedron and to increase with distortion. The relative weight of tetrahedricity, $Tr_b = 0{:}018$, is taken from [6], where it was proposed as boundary value for perfect tetrahedra.

However the most interesting features of disordered systems are seen in the space structural correlation. Since, there is unique correspondence between the Voronoi and Deluanay networks, so using Tr as quantitative measures of DS each vertex of Voronoi network can be assigned a value equal to this measure. To discriminate aggregates of atoms with Tr surrounding them it is convenient to use coloring. In this case only vertices which have values less than the chosen boundary value are colored. Thus, the analysis of the spatial arrangement of atoms with different structural patterns in the structure of liquid reduces to the analysis of typical graphs in the Voronoi network.

2.3 Time correlative Van Hove function

Time correlation Van Hove function describes the temporal relaxation of atoms local order and allows us to determine the local order destruction time. The Van Hove function determines the number of particles $N(r; t)$ at the time t, were situated on the distance interval from r to $r + dr$, under the condition, that the particle was at the center point at the initial time and $_0$ is the particle's volume:

$$G_d(r; t) = \frac{N(r; t)}{_0 4 r^2 dr}: \quad (6)$$

However, it would be interesting to examine the Van Hove function only for particles that remain in the tetrahedral formations during time interval t. So, the function allows us to estimate the life time of such atomic configurations.

3 Simulation procedure

3.1 Effective pair potentials

In this work the experimental PCFs, $g^{exp}(r)$, obtained for liquid nickel at 1773, 1873, 1923, 2023K [9], are used as criterion functions in the inverse method. The derived effective pair potentials are shown in fig. 1. They have some variations for the four temperatures and display long-ranged oscillations, that can be associated with Friedel's oscillations. In our study performed in the microcanonical ensemble, we used molecular dynamical models with $N = 1688$ spherically symmetric particles, arranged in a cubical box with the density from $0:07921$ to $0:07942$ Å ^{3}, corresponding to investigated temperatures [10]. The MD computations, based on the effective potentials $'(r)$, reproduce the PCFs, which are given in insertions on fig.1. The deviation between the calculated and experimental functions reaches 10^{4}.

The good agreement between the computed and experimental structural properties allows us to use Voronoi-Delaunay analysis of liquid nickel's local structure at different temperatures.

3.2 Local structure analysis

Distributions of the sphericity coefficient for different temperatures are presented on the fig. 2. Asymmetrical K_{sph}-distribution, with a most probable value $K_{sph} = 0{:}712$ and a shoulder at $K_{sph} = 0{:}69$, corresponds to the temperature $T = 1773K$. A contribution to the main maximum forms 12-14 facets VP which have a prevalent content of 5-edged facets. Polyhedron in shape of the dodecahedron (formed from twelve regular 5-edged facets) corresponds to full icosahedral atom packing. So, atoms, which correspond to VP with value $K_{sph} = 0{:}712$ and have edge numbers higher then 12, can only correspond to segments of dense icosahedral packing. We can suggest, that two competitive types of VP exist in the liquid nickel's structure at $T = 1773K$.

K_{sph}-distributions, corresponding to $T > 1773K$, became symmetrical with maxima position at $K_{sph} = 0{:}69$. This value coincide with shoulder position for the K_{sph}-distribution at $T = 1773K$. At the same time, in these structures there are no VP having a several bordering regular 5-edged facets. This fact confirms that MD-models at $T > 1773K$ do not contain sufficiently large segments of icosahedral atom packing.

Investigation of the space structural correlations on the Voronoi network by means of the vertex coloring under condition $T_r < T_{r_b}$, has shown, that tetrahedral configurations tend to unit into spatial formations (T_r-clusters) with a regular simplicial surrounding. However, properties of these clusters, such as size, local order, life time are changed with temperature rise.

Fig. 3a demonstrates typical tetrahedral formations in the structure at $T = 1773K$. The size of T_r-clusters at this temperature reaches $5\ 10$ Å. On the Voronoi network such clusters are mainly composed by 5-membered graphs bounded by the mutual edge. This graph corresponds to the atomic configuration with 5-folder symmetry in shape of the pentagonal biprism. So, in the simulated liquid nickel's structure at $T = 1773K$ the T_r-clusters are represented by various polytetrahedral atomic configurations with 5-folder local symmetry with an icosahedral configuration among them. K_{sph}-distributions for the liquid nickel configurations.

At temperatures $T > 1773K$ the structure of tetrahedral formations is simplified. T_r-clusters become isolated and compact, their size reaches as little as $5\ 6$ Å. Typical element of these formations is presented by 5-membered graphs.

3.3 Van Hove function

Advantageous energetic atomic disposition in the Tr-clusters allows us to expect, that such formations should be time stable. We checked this suggestion with help of analysis of time correlative Van Hove functions. The Van Hove functions, calculated at T = 1773K , are shown on fig. 4a. The first and the second shells of the neighbors in the Tr-clusters are preserved at least during 4 t= 10 ^{11}s, that is larger than thermal fluctuation's time.

Fig. 4 (b, c and d) displays the Van Hove functions, calculated at temperatures T > 1773K . Only the first coordination shell is preserved during t = 5 10 ^{12}s. We suggest, that it is connected on the one hand, with increasing of the dynamic mobility of particles with temperature rise, in the other hand, with an absence of pronounced icosahedral segments in liquid structure at high temperatures.

4 Conclusions

In the work the effective pair potentials were derived from the experimental data for liquid nickel at four temperatures. Good agreement between computed and experimental structural properties of the simulated system has made it possible to perform Voronoi-Delaunay analysis of local structure.

The results of these simulations allow us to draw a conclusion that in liquid nickel's local structure in the vicinity of the melting point there are spatial polytetrahedral formations with local 5-folder symmetry (with an icosahedron among them, as the best-known candidate for a basic structural unit of liquid). The results obtained complement a well-known point of view about the existence of the icosahedral short-range order in liquid metals, which does not depend on their pre-melting structural type [3]. With temperature rise tetrahedral formations evolve to isolate and compact ones with preserving of the local five-folder symmetry. At the same time their life time is decreased due to the increase of diffusion atom motions.

The appearance of the spatial formations in liquid structure can leads to the essential change of structural viscosity [11]. Existent results of the experimental investigations of the transition metals alloys of iron group (Fe;Co) [12, 13] demonstrate the uneven decreasing of the alloys viscosity at rising temperature. This doesn't contradict the above mentioned arguments.

These facts can be the evidence of the structural transitions, which exist in the alloys with rising temperature. Hence, one can expect that the nickel melt will exhibit the ordinary Newton-liquids properties, since the structural clusters are very small. However, the clusters size and their concentration growth with temperature decrease. Because of these processes the melt can have structured-liquid properties, in particular, viscosity dependence on flow velocity gradient can appear.

References

[1] B.A. Baum, G.A. Khasin, G.V. Taygunov, et al., Liquid Steel (Mettalurgiya, Moskow, 1984);

[2] N.A. Vatolin and E.A. Pastukhov, Diffraction studies of the Structures of High-Temperature Melts (Nauka, Moscow, 1980);

[3] T. Schenk, D. Holland-Moritz, V. Simonet, R. Bellissent, D.M. Herlach, Phys. Rev. Lett. 89, 075507 (2002);

[4] F. C. Frank, Proc. R. Soc. London A 215, 43 (1952);

[5] N.N. Medvedev and Y.I. Naberukhin, J.Computer Phys. 67, 223 (1986);

[6] N.N. Medvedev, J.Phys. Condens.Matter, 2, 9145 (1990);

[7] L. Reatto , D. Levesque , J.J. Weis, Phys. Rev. A 33, 3451 (1986);

[8] W. Schommers, Phys. Rev. A 28, 3599 (1983);

[9] Y. Waseda, The Structure of Non-Crystalline Materials (McGraw-Hill, New York, 1980), an electronic database can be found at http://www.iamp.tohoku.ac.jp/database/scm/index.html;

[10] C.J. Smithell, Smithells Metals reference book (Butterworths, London, 1983);

[11] Ya.I. Frenkel, Kinetic Theory of Liquids (Nauka, Leningrad, 1975);

[12] V.I. Lad'yanov, A.L. Beltyukov, et al., JETP Let. 72, 6, 301 (2000);

[13] V.I. Lad'yanov and A.L. Beltyukov, JETP Let. 7, 2, 128 (2000);


Figures:


Fig. 1:The effective pair potentials of liquid nickel at different temperatures 1773K , 1823K , 1923K , 2023K and corresponding pair correlation functions (circles - experimental data, solid lines - simulated data).


Fig. 2:K_{sph}-distributions for configurations of liquid nickel at different temperatures.


Fig. 3:Tetrahedral formations on the Voronoi network (thick lines) and corresponding atomic configurations (spheres) a) T = 1773K : The dodecahedron on the Voronoi network corresponds to full icosahedral atomic configuration; b) T = 2023K : T r-clusters became isolated and compact, with typical element as the pentagonal biprism.


Fig. 4:Van Hove functions G d(r; t), calculated for atoms, which remain in the T r-clusters during the time interval t.


1773
1873
1923
2023
2
1.5
1
0.5
N_{Ksph}
0.5
0.6
0.7
0.8
K_{sph}


Gd(r,δt)
0.5
0.0
1.2
2.4
3.6
4.8
6.0
7.2
8.4
9.6
r, A


Gd(r,δt)
0.5
0.0
1.2
2.4
3.6
4.8
6.0
7.2
8.4
9.6
r, A


1923 K
c
δt=5 ps
δt=10 ps
Gd(r,δt)
1.0
0.5
0.0
0.0
1.2
2.4
3.6
4.8
6.0
7.2
8.4
9.6
r, A


2023 K
d
δt=5 ps
δt=10 ps
Gd(r,δt)
1.0
0.5
0.0
0.0
1.2
2.4
3.6
4.8
6.0
7.2
8.4
9.6
r, A