

NMR relaxation rate in non-centrosymmetric superconductors

K. V. Samokhin

Department of Physics, Brock University, St. Catharines, Ontario, Canada L2S 3A1

(Dated: March 23, 2022)

The spin-lattice relaxation rate of nuclear magnetic resonance in a clean superconductor without inversion center is calculated for arbitrary pairing symmetry and band structure, in the presence of strong spin-orbit coupling.

PACS numbers: 74.25.Nf, 74.20.Rp, 74.70.Tx

Most superconducting materials have an inversion center in their crystal lattices. Among a few exceptions are the heavy-fermion compounds CePt₃Si [1] and UIr [2]. The peculiar feature of superconductivity without inversion center is that there are fewer pairing channels available than in a centrosymmetric crystal, because the spin degeneracy of the bands is lifted in the presence of strong spin-orbit coupling [3, 4]. Other properties of non-centrosymmetric superconductors studied recently include paramagnetic limit and Knight shift [5, 6, 7, 8, 9, 10, 11], helical superconducting phases [12, 13, 14], and magnetoelectric phenomena [15, 16, 17]. The determination of the pairing symmetry however presents a considerable challenge. Although there are strong indications that the gap in CePt₃Si has lines of nodes, the decisive proof, including the determination of the nodal locations, is still lacking.

A powerful probe of the quasiparticle properties in superconductors is the spin-lattice relaxation rate T_1^{-1} of nuclear magnetic resonance (NMR). The presence of the coherence, or Hebel-Slichter, peak in T_1^{-1} below the critical temperature [18] provided an early strong support for the Bardeen-Cooper-Schrieffer theory of superconductivity [19]. More recently, the power-law behavior of the relaxation rate at low temperatures commonly observed in heavy-fermion compounds, see e.g. Ref. [20], has been used as an argument in favor of the existence of gapless excitations in those materials. Indeed, if there are line (point) nodes in the gap, then $T_1^{-1} \propto T^3$ (T^5) as $T \rightarrow 0$ [21].

The measurements of the NMR relaxation rate in CePt₃Si [22] indicate the likely presence of line nodes. On the other hand, a small Hebel-Slichter peak just below T_c observed in Ref. [22] was not found in other experiments [23]. Theoretically, the standard analysis of the NMR relaxation rate in superconductors, see e.g. Ref. [19], is not directly applicable in the non-centrosymmetric case because of a complicated spin structure of the non-degenerate bands. The purpose of the present Rapid Communication is to calculate T_1^{-1} in a non-centrosymmetric superconductor with arbitrary pairing symmetry. Our analysis does not rely on any specific model for the band structure, the only assumption being that the bands are well split due to strong spin-orbit coupling, which is the case for CePt₃Si [3]. In these circumstances, it is convenient to use the exact band representation of the order parameter introduced in Ref. [3],

see also Ref. [4], in which the possibility of superconducting states with lines of nodes at high-symmetry locations appears naturally. In the alternative approach developed in Ref. [8], the spin-orbit coupling is introduced using the Rashba model, and the order parameter becomes a mixture of spin-singlet and spin-triplet components, which does not in general have the lines of nodes required by symmetry.

We consider the NMR spin-lattice relaxation due to the interaction between the nuclear spin magnetic moment $\gamma_n \mathbf{I}$ (γ_n is the nuclear gyromagnetic ratio) and the hyperfine field \mathbf{h} created at the nucleus by the conduction electrons. The system Hamiltonian is $H = H_e + H_n + H_{int}$, where H_e describes the electron subsystem, $H_n = -\gamma_n \mathbf{I} \mathbf{H}$ is the Zeeman coupling of the nuclear spin with the external field \mathbf{H} , and $H_{int} = -\gamma_n \mathbf{I} \mathbf{h}$ is the hyperfine interaction. For $I = 1/2$, we have two nuclear spin states $I_z = \pm 1/2$ with the energies $E_{I_z} = -\omega_0 I_z$, where $\omega_0 = \gamma_n H$ is the NMR frequency (the spin quantization axis is parallel to \mathbf{H}). Using the Fermi Golden Rule, the spin-lattice relaxation rate can be expressed [24] in terms of the retarded correlator of the transverse components of the hyperfine fields:

$$R \equiv \frac{1}{T_1 T} = -\frac{\gamma_n^2}{2\pi} \lim_{\omega \rightarrow 0} \frac{\text{Im } K_{+-}^R(\omega_0)}{\omega_0} \quad (1)$$

where K_{+-}^R is obtained by an analytic continuation of the Fourier transform of the Matsubara correlator $K_{+-}(\tau) = -\langle T_\tau e^{H_e \tau} h_+ e^{-H_e \tau} h_- \rangle$, with $h_\pm = h_x \pm i h_y$ (in our units $k_B = \hbar = 1$).

In general, the hyperfine field \mathbf{h} can be represented as a sum of the Fermi contact, the orbital, and the spin-dipolar contributions [24]. Their relative importance depends on the electronic structure and therefore varies for different systems. Let us first assume that the Fermi contact interaction is dominant, then $\mathbf{h} = \alpha \mathbf{S}(\mathbf{0})$, where $\alpha = -(8\pi/3)\gamma_e$, γ_e is the electron gyromagnetic ratio, and $\mathbf{S}(\mathbf{r}) = (1/2)\boldsymbol{\sigma}_{\sigma\sigma'}\psi_\sigma^\dagger(\mathbf{r})\psi_{\sigma'}(\mathbf{r})$ is the electron spin density ($\boldsymbol{\sigma}$ is a vector composed of Pauli matrices, and $\sigma = \uparrow, \downarrow$ is the spin projection). The relaxation rate (1) is then proportional to the retarded correlator of the electron spin densities at the nuclear site, which can be calculated by writing the spin operators $S_\pm = S_x \pm i S_y$ in the band representation.

In a non-centrosymmetric crystal with spin-orbit coupling, the electron bands are non-degenerate almost everywhere, except along some high-symmetry lines in the

Brillouin zone. Using the Bloch theorem, the spinor field operators can be written as

$$\psi_\sigma(\mathbf{r}) = \frac{1}{\sqrt{V}} \sum_{i,\mathbf{k}} \chi_{i,\mathbf{k}}(\mathbf{r}, \sigma) e^{i\mathbf{k}\mathbf{r}} c_{i,\mathbf{k}}, \quad (2)$$

where V is the system volume, i is the band index, $c_{i,\mathbf{k}}$ are the destruction operators of band electrons, and $\chi_{i,\mathbf{k}}(\mathbf{r}, \sigma) = \langle \mathbf{r}, \sigma | i, \mathbf{k} \rangle$ are periodic functions in the unit cell, satisfying the normalization condition

$$\frac{1}{\Omega} \int_{\text{unit cell}} d^3\mathbf{r} [|\chi_{i,\mathbf{k}}(\mathbf{r}, \uparrow)|^2 + |\chi_{i,\mathbf{k}}(\mathbf{r}, \downarrow)|^2] = 1$$

(Ω is the volume of the unit cell). The band energies are $\epsilon_i(\mathbf{k}) = \epsilon_i(-\mathbf{k})$. We introduce the notations $u_{i,\mathbf{k},\sigma} = \chi_{i,\mathbf{k}}(\mathbf{0}, \sigma)$.

There exist certain relations between the Bloch amplitudes, which follow from the invariance of the system with respect to time reversal. The time-reversal operation $K = (i\sigma_2)K_0$ (K_0 is the complex conjugation) transforms the Bloch spinor corresponding to \mathbf{k} in band i into a spinor corresponding to $-\mathbf{k}$ in the same band: $K|i, \mathbf{k}\rangle = t_i(\mathbf{k})|i, -\mathbf{k}\rangle$, where $t_i(\mathbf{k})$ is a non-trivial phase factor. From $K^2 = -1$ one immediately obtains $t_i(-\mathbf{k}) = -t_i^*(\mathbf{k})$ [4]. Then it is straightforward to show that

$$u_{i,-\mathbf{k},\uparrow} = t_i^*(\mathbf{k})u_{i,\mathbf{k},\downarrow}^*, \quad u_{i,-\mathbf{k},\downarrow} = -t_i^*(\mathbf{k})u_{i,\mathbf{k},\uparrow}^*. \quad (3)$$

Since the phases of the Bloch functions can be rotated independently at different \mathbf{k} , there is some freedom in choosing $u_{i,\mathbf{k},\sigma}$ and $t_i(\mathbf{k})$. For this reason, no observable quantity can depend on $t_i(\mathbf{k})$.

As an example, let us consider the generalized Rashba model, in which the free-electron Hamiltonian is written as $H_0 = \epsilon_0(\mathbf{k}) + \gamma(\mathbf{k})\sigma$, where $\epsilon_0(\mathbf{k})$ is an even function of \mathbf{k} . The effects of spin-orbit coupling are described by a real pseudovector $\gamma(\mathbf{k}) = -\gamma(-\mathbf{k})$, whose momentum dependence is determined by the point symmetry of the crystal (the case of the tetragonal group C_{4v} relevant for CePt₃Si is discussed in Refs. [8, 10, 13]). The diagonalization of H_0 gives two Rashba bands with the energies $\epsilon_\pm(\mathbf{k}) = \epsilon_0(\mathbf{k}) \pm |\gamma(\mathbf{k})|$ and $u_{\pm,\mathbf{k},\uparrow} = (1/\sqrt{2})\sqrt{1 \pm \gamma_z/|\gamma|}$, $u_{\pm,\mathbf{k},\downarrow} = \pm(\gamma_x + i\gamma_y)/\sqrt{2|\gamma|(|\gamma| \pm \gamma_z)}$. Applying the time reversal operation, one obtains $t_\pm(\mathbf{k}) = \pm e^{-i\phi(\mathbf{k})}$, where $\phi = \arg(\gamma_x, \gamma_y, 0)$. It is easy to check that the relations (3) are indeed satisfied.

The Hamiltonian H_e of the electron subsystem consists of the free-electron part and the interaction responsible for the Cooper pairing. The pairs are formed by electrons in the degenerate time-reversed states $|i, \mathbf{k}\rangle$ and $K|i, \mathbf{k}\rangle$. The large band splitting strongly suppresses the pairing of electrons from different bands. An anisotropic multi-band generalization of the mean-field BCS model reads

$$H_e = \sum_{i,\mathbf{k}} \xi_{i,\mathbf{k}} c_{i,\mathbf{k}}^\dagger c_{i,\mathbf{k}} + \frac{1}{2} \sum_{i,\mathbf{k}} \left[\Delta_{i,\mathbf{k}} c_{i,\mathbf{k}}^\dagger c_{i,-\mathbf{k}}^\dagger + \Delta_{i,\mathbf{k}}^* c_{i,-\mathbf{k}} c_{i,\mathbf{k}} \right], \quad (4)$$

where the chemical potential μ is included in the free-electron part, i.e. $\xi_{i,\mathbf{k}} = \epsilon_i(\mathbf{k}) - \mu$. The pairing amplitudes $\Delta_{i,\mathbf{k}} = -\Delta_{i,-\mathbf{k}}$ can be written as $\Delta_{i,\mathbf{k}} = t_i(\mathbf{k})\hat{\Delta}_{i,\mathbf{k}}$, where the auxiliary gap functions $\hat{\Delta}_{i,\mathbf{k}} = \hat{\Delta}_{i,-\mathbf{k}}$ all have the same symmetry, determined by an even irreducible representation Γ of the crystalline point group. The last observation allows us to write $\hat{\Delta}_{i,\mathbf{k}} = \sum_{a=1}^{d_\Gamma} \eta_a^{(i)} \phi_a^{(i)}(\mathbf{k})$, where d_Γ is the dimensionality of Γ , $\phi_a^{(i)}(\mathbf{k})$ are the even basis functions (which can have different \mathbf{k} -dependence in different bands while having the same transformation properties and sharing the same symmetry-imposed zeros), and $\eta_a^{(i)}$ are the order parameter components satisfying the mean-field self-consistency equations [25].

In the band representation, the spin raising and lowering operators take the following form:

$$S_+(\mathbf{0}) = \frac{1}{V} \sum_{ij,\mathbf{k}\mathbf{k}'} u_{i,\mathbf{k},\uparrow}^* u_{j,\mathbf{k}',\downarrow} c_{i,\mathbf{k}}^\dagger c_{j,\mathbf{k}'}, \quad (5)$$

and $S_-(\mathbf{0}) = S_+^\dagger(\mathbf{0})$. Inserting these expressions in the Matsubara spin correlator one arrives at a two-particle Green's function, which can be decoupled in the mean-field approximation and represented in terms of the normal and anomalous Green's functions for the Hamiltonian (4): $-\langle T_\tau c_{i,\mathbf{k}}(\tau) c_{j,\mathbf{k}'}^\dagger(0) \rangle = \delta_{ij} \delta_{\mathbf{k},\mathbf{k}'} G_i(\mathbf{k}, \tau)$ and $\langle T_\tau c_{i,\mathbf{k}}(\tau) c_{j,\mathbf{k}'}(0) \rangle = \delta_{ij} \delta_{\mathbf{k},-\mathbf{k}'} F_i(\mathbf{k}, \tau)$. Using the relations (3), we arrive at the following expression for the spin correlator:

$$K_{+-}(\nu_m) = \alpha^2 T \sum_n \frac{1}{V^2} \sum_{ij,\mathbf{k}\mathbf{k}'} |u_{i,\mathbf{k},\downarrow}|^2 |u_{j,\mathbf{k}',\uparrow}|^2 \times [G_i(\mathbf{k}, \omega_n + \nu_m) G_j(\mathbf{k}', \omega_n) + t_i(\mathbf{k}) t_j^*(\mathbf{k}') F_i^\dagger(\mathbf{k}, \omega_n + \nu_m) F_j(\mathbf{k}', \omega_n)], \quad (6)$$

where $\omega_n = (2n+1)\pi T$ and $\nu_m = 2m\pi T$ are the fermionic and bosonic Matsubara frequencies respectively, and

$$G_i(\mathbf{k}, \omega_n) = -\frac{i\omega_n + \xi_{i,\mathbf{k}}}{\omega_n^2 + \xi_{i,\mathbf{k}}^2 + |\Delta_{i,\mathbf{k}}|^2}$$

$$F_i(\mathbf{k}, \omega_n) = \frac{\Delta_{i,\mathbf{k}}}{\omega_n^2 + \xi_{i,\mathbf{k}}^2 + |\Delta_{i,\mathbf{k}}|^2},$$

$F_i^\dagger(\mathbf{k}, \omega_n) = F_i^*(\mathbf{k}, \omega_n)$. One can see that the phase factors $t_i(\mathbf{k})$ drop out of the spin correlator (6), as expected.

The next steps are standard: first, we perform the summation over n , followed by the analytical continuation $K_{+-}^R(\omega) = K_{+-}(\nu_m)|_{i\nu_m \rightarrow \omega + i0^+}$, then take the thermodynamic limit $V \rightarrow \infty$ and neglect the electron-hole asymmetry, which allows us to write the momentum sums as the Fermi-surface integrals. The final result for the relaxation rate (1) is

$$R = \alpha^2 \gamma_n^2 \int_0^\infty d\omega \left(-\frac{\partial f}{\partial \omega} \right) \{ N_\uparrow(\omega) N_\downarrow(\omega) + \text{Re} [M_\uparrow^*(\omega) M_\downarrow(\omega)] \}, \quad (7)$$

where $f(\omega) = (e^{\omega/T} + 1)^{-1}$ is the Fermi function, and

$$\begin{aligned} N_\sigma(\omega) &= \sum_i N_{F,i} \left\langle |u_{i,\mathbf{k},\sigma}|^2 \frac{\omega}{\sqrt{\omega^2 - |\tilde{\Delta}_{i,\mathbf{k}}|^2}} \right\rangle_i, \\ M_\sigma(\omega) &= \sum_i N_{F,i} \left\langle |u_{i,\mathbf{k},\sigma}|^2 \frac{\tilde{\Delta}_{i,\mathbf{k}}}{\sqrt{\omega^2 - |\tilde{\Delta}_{i,\mathbf{k}}|^2}} \right\rangle_i. \end{aligned} \quad (8)$$

Here the angular brackets denote the Fermi-surface average, and $N_{F,i} = (1/8\pi^3) \int dS_F / |\mathbf{v}_{F,i}|$ is the density of states at the Fermi level in the i th band. The angular integration is restricted by the condition $|\tilde{\Delta}_{i,\mathbf{k}}| \leq \omega$.

We see that the intra-band contributions to the NMR relaxation rate in a non-centrosymmetric superconductor are similar to those in the centrosymmetric case, despite a nontrivial spin structure of the single-electron bands. The only difference is that it is the auxiliary gap functions $\tilde{\Delta}_{i,\mathbf{k}}$ that enter Eqs. (8). It is important however that, in addition to the intra-band terms, there are inter-band interference contributions to R , which are present even without any inter-band scattering mechanisms due to electron-electron interactions or impurities [26]. The origin of these contributions can be traced back to the local character of the hyperfine coupling \mathbf{IS} , which mixes together the electron states near the Fermi surface from different bands.

The low-temperature properties of the system are controlled by the Bogoliubov quasiparticles of energy $E_{i,\mathbf{k}} = \sqrt{\xi_{i,\mathbf{k}}^2 + |\tilde{\Delta}_{i,\mathbf{k}}|^2}$. The experimental data for CePt₃Si seem to point to the presence of lines of nodes in $\tilde{\Delta}_{i,\mathbf{k}}$. Symmetry-imposed gap nodes exist only for the order parameters which transform according to one of the non-unity representations of the point group. For all such non-trivial gap symmetries, the Fermi-surface averages of $\tilde{\Delta}_{i,\mathbf{k}}$ vanish, and therefore $M_\uparrow(\omega) = M_\downarrow(\omega) = 0$. Then the relaxation rate in the superconducting normalized to its normal-state value can be written as

$$\frac{R_s}{R_n} = 2 \int_0^\infty d\omega \left(-\frac{\partial f}{\partial \omega} \right) \frac{N_\uparrow(\omega) N_\downarrow(\omega)}{N_{n,\uparrow} N_{n,\downarrow}}, \quad (9)$$

where $N_{n,\sigma} = \sum_i N_{F,i} \langle |u_{i,\mathbf{k},\sigma}|^2 \rangle_i$ are the local densities of states of the spin-up (spin-down) electrons at the nuclear site $\mathbf{r} = \mathbf{0}$ in the normal state. Note that, although $|u_{i,\mathbf{k},\uparrow}|^2 + |u_{i,\mathbf{k},\downarrow}|^2 = 1$ in the generalized Rashba model, this does not have to be the case in general, so that $N_{n,\uparrow} + N_{n,\downarrow} \neq N_F$, where $N_F = \sum_i N_{F,i}$ is the total density of states at the Fermi level for both spin projections.

Since the order parameters induced by the inter-band pair scattering have the same symmetry in all bands, the low-energy behavior of all terms in $N_\sigma(\omega)$, see Eq. (8), is characterized by the same power law. If there are line (point) nodes in the gap, then $N_\sigma(\omega) \propto \omega$ (ω^2) at $\omega \rightarrow 0$ [25], and $R \propto T^2$ (T^4) at $T \rightarrow 0$ [21, 27]. However, a complicated multi-band structure with considerably different

local densities of states and gap magnitudes in different bands can obscure the simple power-law behavior. In particular, in the extreme multi-band case, when some of the Fermi-surface sheets remain normal (which might be the case in CePt₃Si [1]), then $R = \text{const} + aT$ for line nodes, and $R = \text{const} + aT^2$ for point nodes. While the residual relaxation comes from the gapless excitations on the unpaired sheets, the unusual power laws are due to the inter-band contributions to R [26]. At temperatures close to T_c , there might still exist the Hebel-Slichter peak due to a weak singularity in $N_\sigma(\omega)$ (for instance, for a d -wave gap the singularity is logarithmic, leading to the peak of a much smaller magnitude than in the isotropic case). In general, the presence and the magnitude of the Hebel-Slichter peak depend on the gap anisotropy and the band structure.

If the orbital and the spin-dipolar terms are not negligible, then the calculations become more involved. The hyperfine field at the nucleus can be written quite generally as a bilinear combination of the band electron operators:

$$\mathbf{h} = \frac{1}{V} \sum_{ij,\mathbf{k}\mathbf{k}'} \mathbf{\Lambda}_{ij}(\mathbf{k},\mathbf{k}') c_{i,\mathbf{k}}^\dagger c_{j,\mathbf{k}'}, \quad (10)$$

where $\mathbf{\Lambda}$ is a pseudovector function, $\mathbf{\Lambda}^\dagger = \mathbf{\Lambda}$ [for the Fermi contact interaction considered above, it is factorized: $\mathbf{\Lambda}_{ij}(\mathbf{k},\mathbf{k}') = (\alpha/2) u_{i,\mathbf{k},\sigma}^* \boldsymbol{\sigma}_{\sigma\sigma'} u_{j,\mathbf{k}',\sigma'}$]. Under time reversal, $c_{i,\mathbf{k}}^\dagger \rightarrow t_i(\mathbf{k}) c_{i,-\mathbf{k}}^\dagger$ and $\mathbf{h} \rightarrow -\mathbf{h}$, which gives the following property:

$$\mathbf{\Lambda}_{ij}(-\mathbf{k}, -\mathbf{k}') = -\mathbf{\Lambda}_{ji}(\mathbf{k}', \mathbf{k}) t_i(\mathbf{k}) t_j^*(\mathbf{k}'). \quad (11)$$

The symmetry of the Hamiltonian with respect to the point group rotations and reflections imposes some additional constraints on the $\mathbf{\Lambda}$'s, which shall not be discussed here.

Assuming that both $\mathbf{\Lambda}_{ij}(\mathbf{k},\mathbf{k}')$ and $\tilde{\Delta}_{i,\mathbf{k}}$ are weakly dependent on $\xi_{i,\mathbf{k}}$, using the relations (11), and repeating all the calculation steps from the Fermi-contact case above, we obtain

$$\frac{R_s}{R_n} = 2 \int_0^\infty d\omega \left(-\frac{\partial f}{\partial \omega} \right) \frac{\sum_{ij} N_{F,i} N_{F,j} A_{ij}^{(s)}(\omega)}{\sum_{ij} N_{F,i} N_{F,j} A_{ij}^{(n)}}, \quad (12)$$

where

$$\begin{aligned} A_{ij}^{(s)}(\omega) &= \left\langle |\Lambda_{ij}^-(\mathbf{k},\mathbf{k}')|^2 \right. \\ &\quad \times \left. \frac{\omega^2 + \text{Re}[\tilde{\Delta}_{i,\mathbf{k}}^* \tilde{\Delta}_{j,\mathbf{k}'}]}{\sqrt{\omega^2 - |\tilde{\Delta}_{i,\mathbf{k}}|^2} \sqrt{\omega^2 - |\tilde{\Delta}_{j,\mathbf{k}'}|^2}} \right\rangle_{ij}, \\ A_{ij}^{(n)} &= \langle |\Lambda_{ij}^-(\mathbf{k},\mathbf{k}')|^2 \rangle_{ij}. \end{aligned} \quad (13)$$

The angular brackets here denote the average over the Fermi surface in the i th and j th bands, and $\Lambda^\pm = \Lambda^x \pm i\Lambda^y$ (recall that the spin quantization axis is along

the external field \mathbf{H}). One can see from Eq. (13) that $A_{ij}^{(s)}(\omega) \propto \omega^2$ (ω^4) at $\omega \rightarrow 0$ for line (point) nodes, assuming non-vanishing anisotropic gaps in all bands and neglecting the possibility of the vertex $\Lambda_{ij}^-(\mathbf{k}, \mathbf{k}')$ going to zero accidentally at the gap nodes. Therefore, the low- T behavior of the relaxation rate is characterized by the familiar exponents: $R \propto T^2$ for line nodes, and $R \propto T^4$ for point nodes.

In conclusion, we calculated the NMR relaxation rate in a non-centrosymmetric superconductor with strong spin-orbit coupling, using the exact band representation of the gap functions and the spin density operators. The temperature dependence of T_1^{-1} is determined by the interplay of intra-band and inter-band terms, with the local densities of states weighing the contributions from different bands. The only robust qualitative conclusion that can be drawn from our results is that the low-temperature behavior of T_1^{-1} is determined by the same power laws as in the centrosymmetric case: $T_1^{-1} \propto T^3$ for line nodes, and $T_1^{-1} \propto T^5$ for point nodes.

The determination of the gap symmetry in CePt₃Si using the NMR relaxation data, beyond the conclusion there are likely lines of nodes somewhere on the Fermi surface, does not seem to be possible at the moment, since it would require a detailed knowledge of the band

structure and the local densities of states. The absence or presence of the Hebel-Slichter peak, especially of the magnitude observed in the experiments, cannot be used as an argument for or against unconventional superconductivity. In addition, the experiments were done at finite fields, in the presence of vortices, which might obscure information about the underlying gap symmetry and complicate the comparison with the theory presented here.

Note added: In a very recent theoretical investigation of the NMR relaxation rate in CePt₃Si [28], a different approach was used, in which the spin-orbit band splitting is described by the Rashba model, and the gap function has both singlet and triplet components. In order to explain the observed T^3 behavior of T_1^{-1} , the parameters of the model had to be fine-tuned for the gap to have accidental lines of nodes.

Acknowledgments

The author is grateful to B. Mitrović for numerous stimulating discussions. This work was supported by the Natural Sciences and Engineering Research Council (NSERC) of Canada.

-
- [1] E. Bauer, G. Hilscher, H. Michor, Ch. Paul, E. W. Scheidt, A. Gribanov, Yu. Seropegin, H. Noël, M. Sigrist, and P. Rogl, Phys. Rev. Lett. **92**, 027003 (2004).
 - [2] T. Akazawa, H. Hidaka, T. Fujiwara, T. C. Kobayashi, E. Yamamoto, Y. Haga, R. Settai, and Y. Onuki, J. Phys.: Condens. Matter **16**, L29 (2004).
 - [3] K. V. Samokhin, E. S. Zijlstra, and S. K. Bose, Phys. Rev. B **69**, 094514 (2004) [Erratum: **70**, 069902(E) (2004)].
 - [4] I. A. Sergienko and S. H. Curnoe, Phys. Rev. B **70**, 214510 (2004).
 - [5] L. N. Bulaevskii, A. A. Guseinov, and A. I. Rusinov, Zh. Eksp. Teor. Fiz. **71**, 2356 (1976) [Sov. Phys. – JETP **44**, 1243 (1976)].
 - [6] V. M. Edelstein, Zh. Eksp. Teor. Fiz. **95**, 2151 (1989) [Sov. Phys. – JETP **68**, 1244 (1989)].
 - [7] L. P. Gor'kov and E. I. Rashba, Phys. Rev. Lett. **87**, 037004 (2001).
 - [8] P. A. Frigeri, D. F. Agterberg, A. Koga, and M. Sigrist, Phys. Rev. Lett. **92**, 097001 (2004).
 - [9] P. A. Frigeri, D. F. Agterberg, and M. Sigrist, New J. Phys. **6**, 115 (2004).
 - [10] K. V. Samokhin, Phys. Rev. Lett. **94**, 027004 (2005).
 - [11] V. P. Mineev, Phys. Rev. B **71**, 012509 (2005).
 - [12] V. M. Edelstein, J. Phys.: Condens. Matter **8**, 339 (1996).
 - [13] K. V. Samokhin, Phys. Rev. B **70**, 104521 (2004).
 - [14] R. P. Kaur, D. F. Agterberg, and M. Sigrist, preprint cond-mat/0408149 (unpublished).
 - [15] L. S. Levitov, Yu. V. Nazarov, and G. M. Eliashberg, Pis'ma Zh. Eksp. Teor. Fiz. **41**, 365 (1985) [JETP Lett. **41**, 445 (1985)].
 - [16] V. M. Edelstein, Phys. Rev. Lett. **75**, 2004 (1995).
 - [17] S. K. Yip, Phys. Rev. B **65**, 144508 (2002).
 - [18] L. C. Hebel and C. P. Slichter, Phys. Rev. **113**, 1504 (1959).
 - [19] M. Tinkham, *Introduction to Superconductivity* (McGraw-Hill, New York, 1996).
 - [20] J. Flouquet, preprint cond-mat/0501602 (unpublished).
 - [21] M. Sigrist and K. Ueda, Rev. Mod. Phys. **63**, 239 (1991).
 - [22] M. Yogi, Y. Kitaoka, S. Hashimoto, T. Yasuda, R. Settai, T. D. Matsuda, Y. Haga, Y. Onuki, P. Rogl, and E. Bauer, Phys. Rev. Lett. **93**, 027003 (2004).
 - [23] K. Ueda, K. Hamamoto, T. Kohara, G. Motoyama, and Y. Oda, preprint cond-mat/0409638 (2004).
 - [24] C. P. Slichter, *Principles of Magnetic Resonance*, 3rd ed. (Springer-Verlag, Berlin, 1990).
 - [25] V. P. Mineev and K. V. Samokhin, *Introduction to Unconventional Superconductivity* (Gordon and Breach, London, 1999).
 - [26] K. V. Samokhin and B. Mitrović, preprint cond-mat/0504154 (unpublished).
 - [27] If the lines of nodes intersect, then there are logarithmic corrections to both $N_\sigma(\omega)$ and R , see Y. Hasegawa, J. Phys. Soc. Jpn. **65**, 3131 (1996).
 - [28] N. Hayashi, K. Wakabayashi, P. A. Frigeri, and M. Sigrist, preprint cond-mat/0504176 (unpublished).