Topological defects in triplet superconductors UPt3, Sr2RuO4, etc.

 $K.Maki_{r}^{1} S.Haas_{r}^{1} D.Parker_{r}^{1}$ and $H.Won^{2}$

¹D epartm ent of Physics and Astronomy, University of Southern California, Los Angeles, CA 90089-0484 USA ²D epartm ent of Physics, Hallym University, Chuncheon 200-702, South Korea

A fler a brief introduction on nodal superconductors, we review the topological defects in triplet superconductors such as UPt3, Sr_2RuO_4 , etc. This is in part motivated by the surprising discovery of AnaCeliaM ota and her colleagues that in some triplet superconductors the uxmotion is completely impeded (the ideal pinning). Among topological defects the most prominent is Abrikosov's vortex with quantum ux $_0 = \frac{hc}{2e}$. Abrikosov's vortex is universal and ubiquitous and seen in both conventional and unconventional superconductors by the Bitter decoration technique, small angle neutron scattering (SANS), scanning tunneling microscopy (STM), micromagnetometer and more recently by Lorentz electron micrograph. In order to interpret the experiment by Mota et al a variety of textures are proposed. In particular, in analogy to super uid ^3He-A the 6 -soliton and 6 -soliton play the prominent role. We review these notions and point out possible detection of these domain walls and half-quantum vortices in some triplet superconductors.

PACS num bers:

I. INTRODUCTION

We shall rst survey the new world of nodal superconductors, which appeared on the scene in 1979. Indeed nodal superconductors are a child of the 21st century [1, 2, 3]. Although the presence of nodal superconductors in heavy-ferm ion superconductors like $C \in C \cup_2 Si_2$, UPt_3 , UBe_{13} and others was found in the late eighties [1], the system atic study of the gap function (k) began only after the discovery of the high-T c cuprates $La_2 \times Ba_x C \cup_4$ by Bednorz and Muller [4] in 1986. The d-wave symmetry of high-T c cuprates YBCO, Bi-2212, etc. was established circa 1994 through the elegant Josephson interferom etry [5, 6] and the powerful angle resolved photoem ission spectrum (ARPES) [7] among others. In 1993 Volovik [8] derived the quasiparticle density of states of the vortex state in nodal superconductors within the sem iclassical approximation. The surprising H dependence of the special heat has been seen in YBCO [9], LSCO [10], and Sr_2Ruo_4 [11, 12]. Later Volovik's approach was extended in a variety of directions: a) the study of the thermal conductivity [13, 14]; b) for an arbitrary eld direction [15]; and c) for different classes of (k) [16]. These are summarized in Ref.[17]. Until now the powerful ARPES and Josephson interferom etry have not been applied outside of high-T c cuprate superconductors.

Since 2001 Izawa et al have determ ined the gap function (k) in Sr_2RuO_4 [18], $CeCoIn_5$ [19], (ET), $Cu(NCS)_2$ [20], YNi_2B_2C [21], and $PrOs_4Sb_{12}$ [22, 23] via the angle-dependent magnetotherm alconductivity. These j (k) is are shown in Figure 1. In addition, the gap function of UPt_3 was established around 1994-6 as E_{2u} through the anisotropy in the therm alconductivity [24] and the constancy of the Knight shift in NMR [25]. Somewhat surprisingly all these superconductors are nodal and their quasiparticle density of states increases linearly in E j for E :

$$N(E)$$
 $\Xi = (1)$

For example, this implies that the p-wave superconductivity in Sr_2RuO_4 as proposed in Ref. 26 is not consistent with




FIG. 1: From top left, order parameters for $\rm Sr_2RuO_4$, $\rm CeCoIn_5$ and phases)

 $(ET)_2Cu(NCS)_2$, YNi_2B_2C , $PrOs_4Sb_{12}$ (A and B




FIG.2: Phase diagram of U $_{1}\,$ $_{x}\,T\,h_{x}\,B\,e_{13}$ from He ner et al [41].

the speci c heat data [11]. A lso as discussed elsewhere [27, 28], the two gap model is of little help in this matter. More recently the quasiparticle density of states in the vortex state in Sr₂RuO₄ has been reported [29]. Indeed the observed quasiparticle density of states is very consistent with that predicted for an f-wave order parameter [30]. A lso many of these superconductors are triplet: UPt₃, Sr₂RuO₄, (TMTSF)₂PF₆, U_{1 x}Th_xBe₁₃, URu₂Si₂, PrO s₄Sb₁₂, UN i₂A l₃ and CePt₃Si, for example.

II. TEXTURES IN TRIPLET SUPERCONDUCTORS

Here we consider possible textures in triplet superconductors. For simplicity we concentrate on two f-wave superconductors: UPt3 (3-dim ensional) and Sr2RuO4 (quasi 2-dim ensional), which we understand well. M ota et al [33, 34] have discovered the ideal pinning in the B phase of UPt3 and below T = 70 mK in Sr2RuO4. Also these systems are characterized by $^{^{\land}}$ and $^{\hat{\alpha}}$ sim ilarly to super uid $^{^{3}}$ H e-A $^{[35,36]}$. Here $^{^{\land}}$ is the direction of the pair angular momentum. But unlike super uid ³He-A îs xed to be parallel to one of the crystal axes: îk îc. can be called the chiral vector. On the other hand describes the spin con guration of the pair and is perpendicular to the pair spin S_{pair} . In the equilibrium con quration dk in super uid He-A, UPt3 and Sr2RuO4 [26]. Also we believe that some triplet superconductors m ay not have \hat{i} and \hat{d} vectors, as observed in super uid ^3He-B . So it is very in portant to know if the superconductivity breaks the chiral sym metry, as observed in the experiments by M ota et al [33, 34] on the B phase in U_{1} xThxBe₁₃ (see Fig. 2). But it is possible that the superconductor in UBe₁₃ does not have \hat{i} and \hat{d} . Also we conjecture that the superconductivity in the B phase of PrOs₄Sb₁, has 'and d'vectors [23] and that probably all other quasi 2-dim ensional systems such as URu_2Si_2 , UNi_2Al_3 and $CePt_3Si$ do as well. Therefore we can think of a variety of dom ain walls as in super uid 3 He-A [38, 39]. Indeed the $^{\circ}$ -soliton in Sr_2RuO_4 has been considered by Signist and Agterberg [40]. The ^-soliton is created when in one side of the wall ^k c, while in the other side ^k c. The chirality changes across the \(^\cdot\)-soliton. However, unlike in super uid \(^3\)He-A \(^\)is practically xed to be parallel to $^{\circ}$ C. For example, when $^{\circ}$ is in the ab-plane there will be little superconducting order parameter left. Therefore we can estim ate the '-soliton energy per unit area as

$$f_{\gamma} ' \frac{1}{4} N_0^2 (T) (T)$$
 (2)
 $' \frac{1}{4} N_0 V_F (T)$ (3)

where (T) is the maximum value of the energy gap and $v_{\rm F}$ is the Ferm i velocity.

On the other hand the \hat{d} -soliton m ay be much more easily created [42]. The crucial element here is the spin-orbit energy which binds \hat{d} parallel to \hat{d} . The relevant energy can deduced from the NMR data of UPt₃ [43] and Sr₂RuO₄ [44]. We estimate (T)= (T) for UPt₃ and Sr₂RuO₄: (T)= (T) 0:5 10 3 (B phase) and 0:2 10 4 respectively. Here (T) is the characteristic frequency associated with the \hat{d} and \hat{d} coupling [42]. Then the areal energy for the \hat{d} -soliton is given by

$$f_{\hat{d}} ' \frac{1}{4} N_0 V_F (\Gamma)$$
: (4)

This is smaller than f_* for UPt $_3$ and Sr_2RuO_4 by factors of 0:5 10^{-3} and 0:2 10^{-4} , respectively. Also $_d=v_F=$ (T) gives the spatial extension of the domain well. This ranges from 10^{-8} m $_1$ m $_2$ m.

In the presence of $^{^{\circ}}$ -solitons vortices m ay enter into the superconducting state as observed in the vortex sheet of super uid 3 He-A [45, 46]. O therw ise the motion of the vortex across the $^{^{\circ}}$ -soliton is completely in peded as discussed in [40]. When an Abrikosov vortex encounters a \hat{d} -soliton, the vortex appears to split into two half-quantum vortices (HQV) in the vicinity of T $^{\prime}$ T_c. At lower temperatures it appears that Abrikosov's vortex should tunnel through the \hat{d} -soliton. This type of HQV was rst predicted in the context of super uid 3 He-A [47, 48, 49]. However, these HQV's have not yet been observed in super uid 3 He-A [50]. Therefore half-quantum vortices may be rst observed in triplet superconductors.

III. HALF-QUANTUM VORTICES

Here we shall consider a pair of half-quantum vortices (HQV) attached to a \hat{d} -soliton [42]. The texture free energy is given by

$$f_{pair} = \frac{1}{2} _{N} C^{2} dy dz (K (r)^{2} + X) \mathcal{D}_{ij} \hat{J} + d^{2} sin^{2} ())$$
 (5)

where C is the spin wave velocity, d = C (T) = (T) and

$$K = \frac{s}{sispin} = \frac{1 + \frac{1}{3}F_1}{1 + \frac{1}{2}F_1^a} \frac{1 + \frac{1}{3}F_1^a (1 \frac{0}{s})}{1 + \frac{1}{2}F_1^a (1 \frac{0}{s})}$$
(6)

where $_{\rm S}$ and $_{\rm S;spin}$ are the super uid density and the spin super uid density respectively. Here F $_{\rm 1}$ and F $_{\rm 1}^{\rm a}$ are the Landau parameters and $_{\rm S}^{\rm 0}$ (T) is the super uid density when F $_{\rm 1}$ = F $_{\rm 1}^{\rm a}$ = 0. The super uid density for UPt $_{\rm 3}$ and Sr $_{\rm 2}$ RuO $_{\rm 4}$ are shown in Fig. 3. In this analysis we assumed that j (k)j jcos sin jcos jin UPt [51] and Sr $_{\rm 2}$ RuO $_{\rm 4}$ respectively. We note that $_{\rm S}^{\rm 0}$ in Sr $_{\rm 2}$ RuO $_{\rm 4}$ is the same as in d-wave superconductivity [52]. In particular, for T in the vicinity of T $_{\rm C}$ we obtain

$$_{\rm s}^{\rm 0}$$
 ' $\frac{4}{3} \ln \left(\frac{\rm T}{\rm T_{\rm c}}\right)$ for $\rm Sr_2 R \, uO_4$ (7)

$$' \frac{143}{105} \ln \left(\frac{T}{T_c}\right) \text{ for UPt}_3 \tag{8}$$

respectively. Here we assumed that H k \hat{a} and that the domain wall extends in the y-z plane. Here we consider 2 typical cases as shown in Fig. 4a) and b). In Fig. 4a) the \hat{d} -soliton runs parallel to the c axis while in Fig. 4b) it runs parallel to the b-axis. For the rst con guration (i.e. a) we parametrize $\hat{d} = \cos \hat{z} + \sin \hat{y}$ with

$$(y;z) = \frac{1}{2} \left(\arctan\left(\frac{z + (R=2)}{y}\right) \quad \arctan\left(\frac{z - (R=2)}{y}\right)\right)$$
(9)

with 2 HQV located at (y;z) = (0;R=2) and (0;R=2) while in the second con guration (b)

$$(y;z) = \frac{1}{2} \left(\arctan\left(\frac{y + (R=2)}{z}\right) + \arctan\left(\frac{y - (R=2)}{z}\right)\right)$$
 (10)

Also in Eq.(7) is the phase of the order parameter (k). Then the total free energy reduces to

$$f_{pair} = \frac{1}{2} _{N} C^{2} (K \ln (=R) + \ln (R=) + \frac{R}{2} _{d})^{2} \ln (4 d=R)$$
 (11)




FIG . 3: The super uid density for the B phase of UPt $_3$ (solid line) and Sr $_2$ RuO $_4$ are shown




FIG. 4: The spatial orientation of the d-vector

where and are the magnetic penetration depth and the coherence length respectively. By m in im izing f_{pair} with respect to R , we obtain

$$R_0^2 = 2_d^2 (K 1) = [ln (\frac{4_f}{eR_0})] > 0$$
 (12)

where R $_0$ is the optim aldistance of a pair of H Q V s. First in order to have a pair of H Q V s we need K > 1, which is guaranteed when F $_1$ > F $_1^a$ and T ' T $_c$. A lso it is necessary to have

$$R_0 < \frac{4}{p_e} d \tag{13}$$

In particular when K 1 1, we obtain

$$R_0 = d$$
 ' $\frac{4}{p = e}$ $\frac{p = e}{2}$ (K 1) (14)

where e = 2.71828 : ... Also the separation between a pair of HQV should be of the order of d 10 m 1 mm.

IV. CONCLUDING REMARKS

We have described an abundance of triplet superconductors. Meany of their order parameters possess the \hat{i} and \hat{d} vectors: (k) in the Bephase of UPt 3, Sr₂RuO₄, both the Aeand Bephase of PrO s_4 Sb₁₂ and perhaps meany other systems. In these systems the \hat{d} -soliton is the most common domain wall. The presence of the \hat{d} -soliton can impede the ux motion in a variety of ways. The most intriguing is the splitting of an Abrikosov vortex into a pair of half-quantum vortices as discussed in [42]. We expect that some of the techniques used to observe Abrikosov's vortex can be used in the present circum stances. These techniques include the Bitter decoration technique [53], small angle neutron scattering (SANS) [54], scanning tunneling microscopy (STM) [55], micromagnetometer [56] and more recently Lorentz electron micrograph [57]. We expect the exploration of these topological defects in triplet superconductors will enhance our understanding of these exotic superconductors. Also they will provide ideal laboratories to check rich eld-theoretical concepts at moderately low temperatures from 1 100 mK. Therefore the future of topological defects in nodal superconductors is still wide open.

A cknow ledgm ents

W e have bene tted from collaborations with Balazs D ora, Hae-Young Kee, Yong Baek Kim, Andras Vanyolos and Attila Virosztek on related subjects.

```
[1] M. Sigrist and K. Ueda, Rev. Mod. Phys, 63, 239 (1991).
 [2] H. Won, S. Haas, D. Parker, K. Maki, Phys. Stat. Sol. (6) 242, 363 (2005).
 [3] K. Maki, S. Haas, D. Parker, H. Won, Chinese Journal of Physics (in press).
 [4] J.G. Bednorz and K.A. Muller, Z. Phys. B 64, 189 (1986).
 [5] D.J. van Harlingen, Rev. Mod. Phys. 67, 515 (1995).
 [6] C.C.T suei and J.R.K irtley, Rev.M od.Phys. 72, 969 (1995).
 [7] A.Damascelli, Z.Houssain and Z.X.Shen, Rev.Mod.Phys.45, 473 (2003)
 [8] G.E. Volovik, JETP Lett. 58, 496 (1993).
 [9] K A . M oler et al, Phys. Rev. Lett. 72, 2744 (1994).
[10] S.J. Chen et al, Phys. Rev. B 58 14753 (R), (1998).
[11] S.N ishizaki, Y.M aeno and Z.M ao, J.Phys.Soc.Jpn.69, 573 (2000).
[12] H.W on and K, Maki, Europhys. Lett. 52, 427 (2000).
[13] C. Kubert and J. P. Hirschfeld, Phys. Rev. Lett. 80, 4963 (1998)
[14] H.W on and K.M aki, cond-m at/0004105.
[15] I. Vekhter, J.P. Carbotte and E.J. Nicol, Phys. Rev B 69, 7123 (1999).
[16] T.Dahm, K.Makiand H.Won, cond-m at/0006307.
[17] H.Won, S. Haas, D. Parker, S. Telang, A. Vanyolos and K. Maki, cond-mat/0501463.
[18] K. Izawa et al, Phys. Rev. Lett. 86, 2653 (2001).
[19] K. Izawa et al, Phys. Rev. Lett. 87, 57002 (2001).
[20] K. Izawa et al, Phys. Rev. Lett. 88, 027002 (2002).
[21] K. Izawa et al, Phys. Rev. Lett. 89, 137006 (2002).
[22] K. Izawa et al, Phys. Rev. Lett. 90, 117001 (2003).
[23] K. Maki, S. Haas, D. Parker, H. Won, K. Izawa and Y. Matsuda, Europhys. Lett. 68, 720 (2004).
[24] B. Lussier, B. Ellm an and L. Taillefer, Phys. Rev. Lett. 23, 3294 (1994).
[25] H. Tou, Y. Kitaoka, K. Asayama, N. Kimura, Y. Onuki, Y. Yamamoto and K. Maegawa, Phys. Rev. Lett. 77, 1374 (1996).
[26] A P.M ackenzie and Y.M aeno, Rev.M od.Phys. 75, 657 (2003).
[27] B.Dora, K.Maki, A.Virosztek, Europhys. Lett. 62, 426 (2003).
[28] H-Y.Kee, K.Maki, C.H.Chung, Phys. Rev. B 67 86534(R) (2003).
[29] C. Lupien, S.K. Dutta, B.I. Barker, Y.M aeno and J.C. Davis, cond-mat/0503317.
[30] M. Kato, H. Suematsu and K. Maki, Physica C 408-410, 53 (2004).
[31] E.Bauer et al, Phys. Rev. Lett. 92, 027003 (2004).
[32] P.A. Frigeri et al, Phys. Rev. Lett. 92, 097001 (2004).
[33] A.Amann, A.C.Mota, M.B.Maple and H.v.Lohneysen, Phys. Rev. B 57, 3640 (1998).
[34] E.Dum ont and A.C.Mota, Phys.Rev.B 65, 144519 (2000).
[35] D. Vollhardt and P. Wole, The Super uid Phases of Helium -3", (Taylor and Francis, New York, 1990).
[36] G E . Volovík, Exotic Properties of Super uid Helium ", (World Scientic Pub. Co., Singapore, 1991).
[37] R H . H a ner et al, Phys. Rev. Lett. 65, 2816 (1990).
```

[38] K.Makiand P.Kumar, Phys. Rev. B 17, 1088 (1978).

- [39] K. Maki in \Solitons", edited by S.E. Trullinger, V.E. Zakharov and V.L. Pokrovskii (North-Holland, Amsterdam, 1986).
- [40] M. Sigrist and D. F. Agterberg, Prog. Theor. Phys. 102, 965 (1999).
- [41] R H . He ner et al, Phys. Rev. Lett. 65, 2816 (1990).
- [42] H.-Y.Kee, Y.B.Kim and K.Maki, Phys. Rev. B 62 R 9275 (2000).
- [43] H. Tou et al, Phys. Rev. Lett. 80, 3129 (1998).
- [44] H.Murakamiet al, Phys. Rev. Lett. 93, 167004 (2004).
- [45] M. T. Heinila and G. E. Volovik, Physica B 210, 300 (1995).
- [46] U. Parts et al, Physica B 210, 311 (1995).
- [47] M M . Salom aa and G E . Volovik, Phys. Rev. Lett. 55, 1184 (1985).
- [48] K.Maki, Phys.Rev.Lett.56, 1312 (1986).
- [49] C.R. Hu and K.Maki, Phys. Rev. B 36, 6871 (1987).
- [50] G E. Volovik in \Vortices in Unconventional Super uids and Superconductors", edited by G E. Volovik, N. Schopohland PR. Huebner (Springer, Berlin 2002).
- [51] G. Yang and K. Maki, Euro. Phys. J. B 21, 61 (2001).
- [52] H.W on and K.Maki, Phys. Rev. B 49, 1397 (1994).
- [53] P.L.Gammel, D.J.Bishop, J.P.Rice and D.M.Ginsburg, Phys.Rev.Lett. 68, 3343 (1992).
- [54] B.Keim er et al, Phys. Rev. Lett. 73, 3459 (1994).
- [55] I.M aggio-Aprile et al, Phys. Rev. Lett. 75, 2764 (1995).
- [56] J.R. K irtley et al, Appl. Phys. Lett. 66, 1138 (1995).
- [57] A. Tonom ura et al, Nature 397, 308 (1999).