

# Electronic structure and magnetism of $\text{LaVO}_3$ and $\text{LaMnO}_3$

R. J. Radwanski

Center of Solid State Physics, Śnił Filip 5, 31-150 Krakow, Poland,  
Institute of Physics, Pedagogical University, 30-084 Krakow, Poland

Z. Ropka

Center of Solid State Physics, Śnił Filip 5, 31-150 Krakow, Poland

In this contribution we derive and discuss energy levels of the strongly-correlated  $d^2$  configuration of the  $\text{V}^{3+}$  ion ( $\text{LaVO}_3$ ) and of  $d^4$  configuration of the  $\text{Mn}^{3+}$  ion ( $\text{LaMnO}_3$ ) in the octahedral surroundings in the presence of the spin-orbit coupling and the resulting magnetic properties. We take into account very strong correlations among the  $d$  electrons and work with strongly-correlated atomic-like electronic systems, ground term of which is, also in a solid, described by two Hund's rules quantum numbers. In a solid we take into account the influence of crystal-field interactions, predominantly of the cubic (octahedral) symmetry. We describe both paramagnetic state and the magnetically-ordered state getting a value of  $1.3 \mu_B$  for the  $\text{V}^{3+}$ -ion magnetic moment in the ordered state at 0 K for  $\text{LaVO}_3$  ( ${}^3\text{T}_{1g}$ ) and of  $3.7 \mu_B$  for  $\text{LaMnO}_3$  ( ${}^6\text{E}_g$ ). A remarkably consistent description of both zero-temperature properties and thermodynamic properties indicates on the high physical adequacy of the applied atomic approach. We point out the necessity to unquench the orbital moment in 3d-ion compounds. We claim that the intra-atomic spin-orbit coupling and strong electron correlations are indispensable for the physically adequate description of electronic and magnetic properties of  $\text{LaVO}_3$  and  $\text{LaMnO}_3$ .

PACS numbers: 75.10.Dg, 71.70.-d

Keywords: Crystalline Electric Field, 3d oxides, magnetism, spin-orbit coupling,  $\text{LaVO}_3$ ,  $\text{LaMnO}_3$

## I. INTRODUCTION AND THE AIM

$\text{LaVO}_3$  and  $\text{LaMnO}_3$  attract a great scientific interest by more than 50 years [1,2]. Despite of it there is still strong discussion about the description of its properties and its electronic structure. A controversy starts already with the description of the electronic ground state. For  $\text{V}_2\text{O}_3$ , a canonical compound of  $\text{LaVO}_3$  there is within a localized paradigm a long-standing controversy between a  $S=1$  model without an orbital degeneracy [3] and the historically first  $S=1/2$  orbitally degenerate model of Castellani et al. [1]. A spin-1 model with three degenerate orbitals was worked out by Di Matteo [4] whereas Refs [5,6] develop a model where the fluctuations of  $t_{2g}$  orbitals and frustrations play prominent role in magnetism of  $\text{LaVO}_3$ .

In all of these considerations it is agreed that  $\text{LaVO}_3$  is an insulating antiferromagnet with the Neel temperature of 135–140 K.  $\text{LaMnO}_3$  is also insulating antiferromagnet with  $T_N$  of 140 K. The basis for all theories is the description of the  $\text{V}^{3+}$  ion (2  $d$  electrons) and the  $\text{Mn}^{3+}$  ion (4  $d$  electrons) and their electronic structure in the perovskite crystallographic structure. In the perovskite-based structure of  $\text{LaVO}_3$  and  $\text{LaMnO}_3$  the V and Mn ions are placed in a distorted oxygen octahedron.

The aim of this paper is to present a consistent description of the low-energy electronic structure and of the magnetism of  $\text{LaVO}_3$  and  $\text{LaMnO}_3$  as originating

from the atomic-like electronic structure of the strongly-correlated  $3d^2$  and  $3d^4$  electronic systems occurring in the  $\text{V}^{3+}$  and  $\text{Mn}^{3+}$  ions. In our description local atomic-scale effects, the orbital magnetism and the intra-atomic spin-orbit coupling play the fundamentally important role in determination of properties of the whole compound.

## II. d STATES OF THE $\text{V}^{3+}$ ION IN ATOMIC PHYSICS

According to our approach to 3d compounds, that seems to be very natural, but is far from being accepted within the magnetic community, two  $d$  electrons of the  $\text{V}^{3+}$  ion in the incomplete 3d shell in  $\text{LaVO}_3$  form the strongly correlated intra-atomic  $3d^2$  electron system. These strong correlations among the 3d electrons we account for by two Hund's rules, that yield the  ${}^3\text{F}$  ground term, Fig. 1a. In the oxygen octahedron surroundings, realized in the perovskite structure of  $\text{LaVO}_3$ , the  ${}^3\text{F}$  term splits into two orbital triplets  ${}^3\text{T}_{1g}$ ,  ${}^3\text{T}_{2g}$  and an orbital singlet  ${}^3\text{A}_{2g}$ . In the octahedron with negative oxygen ions the ground subterm is orbital triplet  ${}^3\text{T}_{1g}$  as is shown in Fig. 1b. All orbital states are triply spin degenerated. This degeneration is removed by the intra-atomic spin-orbit coupling that is always present in the ion/atom. The effect of the spin-orbit coupling is shown in Fig. 1c. For low-temperature properties the lowest 5 states of nine states of the  ${}^3\text{T}_{1g}$  subterm are important. Octahedral distortions causes further splitting of the shown states – important is that there is no more low-energy states as only shown. The present calculations have been performed with a realistic octahedral CEF




FIG. 1: Lowest part of the electronic structure of the  $d^2$  ( $V^{3+}$  ion) in  $LaVO_3$  and of the  $d^4$  configuration ( $Mn^{3+}$  ion) in  $LaMnO_3$  in the strongly-correlated limit. d) schematic electronic structures customarily recalled in the current literature – these single-electron crystal-field states are, according to us, completely oversimplified. a) Hund’s rules ground terms, b) – effect of the octahedral CEF interactions, c) – the many-electron CEF approach with strong intra-atomic correlations propagating by us. c) many-electron CEF states in the octahedral CEF in the presence of the intra-atomic spin-orbit coupling.

parameter  $B_4 = -40$  K ( $\approx 10Dq = 600B_4 = 2.06$  eV) and the spin-orbit coupling as is observed in the free ion, i.e.  $\lambda = +150$  K. The spin-orbit coupling effect amounts only to 3% the CEF effect but it has enormous influence on the eigenfunctions and low-temperature properties.

The derived many-electron electronic structure of the  $d^2$  configuration is completely different from very simplified electronic structure, shown in Fig. 1d, usually presented in the current literature with two parallel spin-electrons in the triply degenerated  $t_{2g}$  orbitals. We do not know, why such an oversimplified scheme is usually shown despite of the fact that the many-electron CEF approach is known already by almost 70 years, though it is true that it was rather used not to a solid, but to 3d ions as in impurities in Electron Paramagnetic Resonance (EPR) experiments [7]. For completeness of the description of the  $d^2$  configuration we can add that for two d electrons there is in total 45 states that in the free  $V^{3+}$  ion are arranged into 5 terms ( ${}^3F$ ,  ${}^1D$ ,  ${}^3P$ ,  ${}^1G$  and  ${}^1S$ ). The 21-fold degenerated  ${}^3F$  term is the lowest one according to two Hund’s rules ( $S=1$ ,  $L=3$ ) – it is a reason that its splitting we show in Fig. 1. The octahedral CEF splits these 45 states in 5 terms into 11 subterms as has been calculated almost 50 years ago by Tanabe and Sugano [8]. A  $t_{2g}^2$  state, usually recalled in the literature, is related to the very strong crystal-field limit notation and is 15-fold degenerated. It contains 4 sub-




FIG. 2: Calculated temperature dependence of the paramagnetic susceptibility for the strongly-correlated  $d^2$  configuration for different physical situations. A dramatic effect of the spin-orbit coupling on the  $\chi^{-1}$  vs  $T$  dependence should be noticed.

terms:  ${}^3T_{1g}$ ,  ${}^1T_{2g}$ ,  ${}^1E_g$ ,  ${}^1A_{1g}$  with the lowest  ${}^3T_{1g}$  subterm. In our approach, Quantum Atomic Solid-State Theory, to 3d-ion compounds we assume the CEF to be stronger than the spin-orbit coupling, but not so strong to destroy intra-atomic correlations. Thus we are working in an intermediate crystal-field limit.

### III. INFLUENCE OF THE SPIN-ORBIT COUPLING ON LOW-TEMPERATURE SUSCEPTIBILITY

In Fig. 2 we present results of our calculations for the paramagnetic susceptibility for different physical situations, without the spin-orbit coupling and with and without octahedral crystal field, which are shown in the  $\chi^{-1}$  vs  $T$  plot. These two curves, without the spin-orbit coupling, resemble the Curie law but with the paramagnetic effective moment much larger than expected for the free  $S=1$  spin, of  $2.82 \mu_B$ . An introduction of the spin-orbit interactions causes dramatic change of the  $\chi^{-1}$  vs  $T$  plot – the Curie law is broken. If one would like to analyze this  $\chi^{-1}$  vs  $T$  plot within the conventional paradigm would infer a Curie-Weiss law with an appearance of AF interactions with  $C_W$  of about 500 K. However, such the C-W behaviour appears here as the effect of the intra-atomic spin-orbit coupling.

### IV. MAGNETIC STATE OF $LaVO_3$

For calculations of the magnetic state apart of the a single-ion like CEF Hamiltonian we take into account additionally intersite spin-dependent interactions ( $n_{dd}$  – molecular field coefficient, magnetic moment  $m_d = -(L+2S) \mu_B$ ) [9]:




FIG. 3: Temperature dependence of the magnetic moment of the  $V^{3+}$  ion in  $LaVO_3$ . An anomaly at low temperatures is due to an accidental double degeneracy.

$$H = H_{CF} + H_{dd} =$$

$$\sum_n \sum_i B_n^m O_n^m + n_{dd} m_d \hbar m_{di} - \frac{1}{2} \hbar m_{di}^2 : \quad (1)$$

In Equation (1) the first term is the crystal-field Hamiltonian: here we work with  $B_4 = -40$  K (an ordinary point-charge octahedron with the V-O distance of 2.0 Å gives  $B_4 = -18$  K) and a small tetragonal distortion  $B_2 = -60$  K. The second term takes into account intersite spin-dependent interactions that is necessary to produce the magnetic order below  $T_N$ . The self-consistent calculations have been performed similarly to that presented in Ref. [9] for  $FeBr_2$ . The calculated temperature dependence of the magnetic moment is shown in Fig. 3. A value of  $1.3 \mu_B$  and  $T_N$  of 140 K are in perfect agreement with experimental observations. We have to add, however, that due to 5 closely lying discrete states the  $V^{3+}$  ion is very susceptible to lattice distortions and details of magnetic interactions.

#### V. d STATES OF THE $Mn^{3+}$ ION IN ATOMIC PHYSICS

In our view, the four d electrons of the  $Mn^{3+}$  ion in the incomplete 3d shell in  $LaMnO_3$  form the strongly correlated intra-atomic  $3d^4$  electron system. These strong correlations among the 3d electrons we account for by two Hund's rules, that yield the  $^5D$  ground term, Fig. 1a, with  $S=2$  and  $L=2$ . In the oxygen octahedron surroundings, realized in the perovskite structure of  $LaMnO_3$ , the  $^5D$  term splits into the orbital doublet  $^5E_g$  as the ground subterm, Fig. 1b, and the excited orbital triplet  $^5T_{2g}$ .

The  $E_g$  ground subterm comes out from ab initio calculations for the octupolar potential, the  $A_4$  CEF coefficient acting on the  $Mn^{3+}$  ion from the oxygen negative charges. Such the atom-like  $3d^4$  system interacts with the charge and spin surroundings in the solid.

In Ref. 10 we have described  $LaMnO_3$  with the octahedral CEF parameter  $B_4 = -13$  meV,  $B_2^0 = +10$  meV, the spin-orbit coupling parameter  $\xi_o = +33$  meV and the molecular-field coefficient  $n = -26.3$  T/ $\mu_B$ . We get a value of  $3.72 \mu_B$  for the  $Mn^{3+}$ -ion ordered magnetic moment that orders magnetically along the  $a$  axis within the tetragonal plane. The magnetic interactions set up at 0 K the molecular field of 108 T (in case of  $LaVO_3$  we get 156 T). The calculated magnetic moment of  $3.72 \mu_B$  is built up from the spin moment of  $+3.96 \mu_B$  and from the orbital moment of  $-0.24 \mu_B$ . Although the orbital moment is relatively small its presence modifies completely the electronic structure similarly as occurs in case of the  $V^{3+}$  ion.

We advocate by years for the importance of the crystal-field-based approach to transition-metal compounds. Of course, we do not claim that CEF explains everything (surely CEF itself cannot explain the formation of a magnetic ordering, for which in Eq. 1 we add the second term), but surely the atom-like  $4f/5f/3d$  cation is the source of the magnetism of a whole solid. The atom-scale magnetic moment is determined by local effects known as crystal field and spin-orbit interactions as well as very strong electron correlations. These strong electron correlations are predominantly of the intra-atomic origin and are taking into account, in the first approximation, via on-site Hund's rules. These strong correlations lead to many-electron version of the CEF approach in contrary to the single-electron version of the CEF presently popular.

Finally, we use a name "d electrons", as often is used in literature. Of course, d electrons are not special electrons but it means electrons in d states. d states have well defined characteristics, like the orbital quantum number  $l$ . By identifying states in a solid we can identify d electrons, in particular their number.

#### VI. CONCLUSIONS

We have calculated electronic structures of  $d^2$  and  $d^4$  systems occurring in  $V^{3+}$  and  $Mn^{3+}$  ions in  $LaVO_3$  and  $LaMnO_3$  taking into account strong electron correlations and the spin-orbit coupling. On basis of our studies we reject a possibility for an orbital liquid both in  $LaVO_3$  and  $LaMnO_3$ . Both ions are strongly susceptible to lattice distortions. We reproduce a value of  $1.3 \mu_B$  for the  $V^{3+}$ -ion magnetic moment as well as the Neel temperature. We advocate for years for an atomistic crystal-field approach to 3d-ion compounds with a discrete electronic structure and the insulating ground state as an alternative to the band picture [11] knowing its enormous shortage in description of 3d oxides (metallic instead ionic ground state, for instance). Our approach accounts both for the insulating ground state, magnetism as well as thermodynamical properties.

Dedicated to the Pope John Paul II, a man of freedom and truth in life and in Science.

- 
- [1] C. Castellani, C. R. Natoli, and J. Ranninger, *Phys. Rev. B* **18**, 5001 (1978).
- [2] Y. Tokura, N. Nagaosa, *Science* **288**, 462 (2000).
- [3] S. Yu. Ezhov, V. I. Anisimov, D. I. Khomskii, and G. A. Sawatzky, *Phys. Rev. Lett.* **83**, 4136 (1999).
- [4] S. Di Matteo, N. B. Perkins, and C. R. Natoli, *Phys. Rev.* **65**, 054413 (2002).
- [5] A. M. Oleś, *Acta Phys. Pol. B* **32**, 3303 (2001).
- [6] P. Horsch, G. Khaliullin, and A. M. Oleś, *Phys. Rev. Lett.* **91**, 257203 (2003).
- [7] A. Abragam and B. Bleaney, *Electron Paramagnetic Resonance of Transition Ions*, Clarendon, Oxford, 1970.
- [8] Y. Tanabe and S. Sugano, *J. Phys. Soc. Japan* **9**, 753 (1954).
- [9] Z. Ropka, R. Michalski and R. J. Radwanski, *Phys. Rev. B* **63**, 172404 (2001).
- [10] R. J. Radwanski and Z. Ropka, *J. Magn. Magn. Mater.* **272-276**, e259 (2004).
- [11] see for instance, M. S. Laad, L. Craco, and E. Müller-Hartmann, *Phys. Rev. Lett.* **91** (2003) 156402; cond-mat/0505317.