

Imperfections in Focal Conic Domains : the Role of Dislocations

M. Kleman^{1,*}, C. Meyer², and Yu. A. Nastishin^{1,3}

¹*Laboratoire de Minéralogie-Cristallographie de Paris,
CNRS UMR 7590, T16 case 115, Université Pierre et Marie Curie,
4 Place Jussieu, F-75252 Paris Cedex 05, France*

²*Laboratoire de Physique de la Matière Condensée, Université
de Picardie, 33 rue Saint-Leu, 80039 Amiens, France*

³*Institute of Physical Optics, 23 Dragomanov str. Lviv 79005 Ukraine*

(Dated: October 6, 2018)

Abstract

It is usual to think of Focal Conic Domains (FCD) as perfect geometric constructions in which the layers are folded into Dupin cyclides, about an ellipse and a hyperbola that are conjugate. This ideal picture is often far from reality. We have investigated in detail the FCDs in several materials which have a transition from a smectic A (SmA) to a nematic phase. The ellipse and the hyperbola are seldom perfect, and the FCD textures also suffer large transformations (in shape or/and in nature) when approaching the transition to the nematic phase, or appear imperfect on cooling from the nematic phase. We interpret these imperfections as due to the interaction of FCD's with dislocations. We analyze theoretically the general principles subtending the interaction mechanisms between FCD's and finite Burgers vector dislocations, namely the formation of kinks on disclinations, to which dislocations are attached, and we present models relating to some experimental results. Whereas the principles of the interactions are very general, their realizations can differ widely in function of the boundary conditions.

PACS numbers: 61.30Jf, 61.72Lk

*Electronic address: maurice.kleman@mines.org

I. INTRODUCTION

The discussion that follows, about the behavior of defects in the SmA (smectic A) phase is inspired by a few experimental polarized light microscopy observations reported in [1] and summarized below. These observations have since been developed [2]. They relate to a domain of temperature that extends approximately $1^\circ C$ below the SmA \rightarrow N phase transition, some of the most relevant experiments having been done with an accuracy of $\pm 1mK$. The very near vicinity of the transition, where phenomena usually qualified of transitional do happen, is not investigated here. But, even in the domain we have searched, the focal conic domains suffer considerable visible modifications, which we attribute to their interactions with dislocations. It is precisely the nature of these interactions that we wish to describe in the present article.

The defects and textures of the SmA and N phases are reasonably well understood at mesoscopic and macroscopic scales, at least for their static physical and topological properties. Contrariwise, the role played by the smectic defects at the phase transition has been little investigated. It is precisely in this region that the FCD's (focal conic domains), the only defects that are fully observable in light microscopy, show large modifications that, we believe, are essentially due to their interactions with dislocations. The SmA \rightarrow N phase transition has been the object of many investigations (for a review, see [3]). The compression modulus B becomes smaller and tends towards a finite value (equal to or slightly different from zero, see e.g., [4, 5, 6]); its variation is noticeable in a large temperature range (more than half a degree in the compounds that we have investigated). Note that in this range, K_1 (the splay modulus) stays practically constant. The question of \overline{K} (the saddle-splay modulus) has been little investigated yet, either theoretically or experimentally (see [7] for the nematic phase); the results that follow have been interpreted by assuming that \overline{K} too stays practically constant. K_2 (the twist modulus) is infinite in layered media, twist being forbidden by the layer geometry.

Let us now recall some defect features of the SmA phase. These defects are of two types, focal conic domains (which are special types of disclinations) and dislocations:

- *focal conic domains (FCD's)*: the layers are parallel, so that there is no strain energy but only curvature energy. The normals to the layers envelop two focal surfaces on which the curvature is infinite (the energy diverges). The focal surfaces are degenerate into lines

in order to minimize this large curvature energy. These lines are necessarily two confocal conics, an ellipse and a hyperbola, observable by optical microscopy [8, 9, 10]. The layers are folded along *Dupin cyclides*, surfaces that have the topology of tori. And indeed the simplest geometric case is when the ellipse E is degenerate into a circle - the confocal hyperbola H being degenerate into a straight line perpendicular to the plane of the circle and going through its centre. In this case the layers are nested tori, restricted in fact to those parts of the tori that have negative Gaussian curvature $G = \sigma_1\sigma_2$. The $G < 0$ case is indeed the most usual case met experimentally in generic Dupin cyclides, see [11, 12]. We shall not consider in the sequel the situations where the layers are restricted to those parts that have positive Gaussian curvature; and as a matter of fact the mixed case is not observed. In the toric case just alluded, the focal conic *domain* is the region of space occupied by those nested layers restricted to their $G < 0$ parts; it is bound by a cylinder parallel to H and whose cross section is E. In the generic case, the region of space where the layers have $G < 0$ is bound by two half-cylinders of revolution, that meet on the ellipse, and whose generatrices are parallel to the hyperbola asymptotes Fig.1a. This is the picture of an ideal, *complete*, FCD. Fig.1b illustrates a case where $G < 0$ and $G > 0$ regions are visible in the same FCD; it does not correspond to any situation met in practice. Models for *incomplete* FCD's are shown farther ahead (Fig.9 (a and b)). The important question how FCD's are packed in space [9, 10] will be approached, but just incidentally.

The curvature energy f_{FCD} of an entire, ideal, focal conic domain depends on K_1 and \bar{K} :

$$f_{FCD} = f_{bulk} + f_{core} = 4\pi a(1 - e^2)K(e^2)[K_1 \ln \frac{2b}{\xi} - 2K_1 - \bar{K}] + f_{core} \quad (1)$$

where a is the semi-major axis of the ellipse, b the semi-minor axis, e the eccentricity and $K(e^2)$ the complete elliptic integral of the first species [11]. It is believed that the energy f_{strain} attached to the thickness variation of the layers is negligible compared to f_{FCD} . Very little is known about the core contribution f_{core} , but it is usually assumed that it scales as aK_1 . Thus, at a and e constant, the FCD total energy does not vary significantly in the domain of temperature under investigation, if our assumptions about the temperature variation of K_1 and \bar{K} turn to be true.

- *screw dislocation lines and edge dislocation lines*: : their line energies per unit length can be written:

$$f_s = \frac{1}{128} \frac{B b_{disl}^4}{r_{c,screw}^2} + f_{core}, f_e = \frac{1}{2} \sqrt{K_1 B} \frac{b_{disl}^2}{r_{c,edge}} + f_{core}, \quad (2)$$

where $b_{disl} = n d_0$ is the dislocation Burgers vector (d_0 is the layer thickness) and r_c is the core radius. It is visible that the elastic contributions (the off-core terms in Eq. 2) decrease when T gets closer to T_{AN} , because B decreases and the core energies are expected to be approximately constant - in a naïve model inspired by the solid-liquid transition, these energies are of order $k_B(T_{AN} - T) \frac{\pi r_c^2}{\delta^2 d_0}$ per unit length of dislocation line, *i.e.* small, $\delta^2 d_0$ being the volume occupied by a molecule, and r_c being perhaps of order δ for a screw dislocation, d_0 for an edge dislocation, *i.e.* practically constant. The decrease of B is effective on a large temperature domain before the transition, probably larger than $1^\circ C$, see [4, 5]. The core radii scale as the correlation lengths very close to the transition, but this region is of no interest to us.

Comments on the experimental conditions

The FCD's are static in the lower range of the domain of temperature we have investigated, they quite often display variations to their ideal shape. The transformation of the FCD's, when approaching the transition, is visible with a simple optical microscopy set up. It appears as a rather sudden phenomenon, about half a degree below T_{AN} , at a temperature T^* that depends slightly on the boundary conditions. We shall assume that it is due to an abrupt multiplication of dislocations, which then interact with FCD's when they are mobile enough.

The spontaneous multiplication of screw dislocations close to the SmA \rightarrow N transition is a well documented fact in *lyotropic* systems [13, 14, 15]. Our observations relate to *thermotropic* compounds, two belonging to the cyanobiphenyl series, 8CB, 9CB and one belonging to the cholesteryl series (CN, nonanoate) which also have a Sm A \rightarrow N transition; they incline us to believe that the phenomenon of spontaneous multiplication of dislocations (screw but also edge) is very general. In these compounds the focal conic domains suffer considerable modifications in the region close to the transition. In all cases, either the FCD's disappear by shrinking before the phase transition, or the ellipse and the hyperbola

transform into disclinations in the nematic phase; the first situation occurs usually for small and medium size FCD's slowly heated, the second one occurs for large FCD's, when they are brought to the transition under faster heating. When cooling down from the nematic phase, the FCD texture in 8CB, 9CB and 8OCB usually does not display ideal FCD's. Instead FCD fragments grow, join and form domains, which in many cases are not ideal FCD's. The double helical objects described in [16], which are splitting modes of giant screw dislocations, are obtained this way. These *imperfect* FCD's can be quenched to lower temperatures where they stabilize due to anchoring and viscosity barriers. The boundary conditions play an important role in the definition of the final texture.

There is little doubt that the transformations of the FCD texture in 8CB, 9CB, CN, when approaching the nematic phase, as well as the formation of imperfect FCD's when coming from above, are due to the interaction of the FCD's with free dislocations. Dislocations are generally not visible by optical microscopy, except when their Burgers vector is large (micron size), which situation occurs for edge dislocations, clustering into oily streaks [8, 9, 10] or screw dislocations split into two $k = \frac{1}{2}$ disclinations [16, 17]. We argue here that the presence of numerous dislocations can be visualized via their distorting action on the FCD's, which are visible.

II. GEOMETRIC RULES FOR IDEAL FOCAL CONIC DOMAINS

Essential for a better understanding of the modifications suffered by FCD's when interacting with dislocations are the following properties, that characterize them when they are in an *ideal* state.

(a)- Projected orthogonally upon a plane, along any direction, the ellipse E and the hyperbola H cross at right angles, Fig.2a. This is a particular case of Darboux's theorem [18], which states that if a congruence of straight lines is orthogonal to a set of parallel surfaces, the two focal surfaces Σ_1 and Σ_2 (that this congruence generically envelops) are such that the planes tangent to Σ_1 and Σ_2 at the contact points M_1 and M_2 of any line Δ of the congruence are orthogonal. This is the reason why the projections of the ellipse E and the hyperbola H belonging to the same FCD look orthogonal. Here the straight line Δ is a normal to the Dupin cyclides, and indicates the average direction of the molecules.

Darboux's theorem is empirically satisfied by a number of FCD's, which in that sense are ideal FCD's; when it is not, (see Fig.2b) it implies that the FCD in question is geometrically interacting with other defects, as we shall discuss in the sequel.

(b)- Two neighboring ideal FCD's whose ellipses are in the same plane and tangent at some point M are in contact along at least one line segment joining M to a point P at which the two hyperbolae intersect. This geometry, frequently observed, is a particular realization of the law of corresponding cones [8, 9, 10], a geometrical property that rules the way FCD's pack in space. A tilt grain boundary whose angle of misorientation ω is neither too small nor too large is usually made of a FCD packing such that the ellipses belong to the grain boundary, have a constant eccentricity $e = \sin \frac{\omega}{2}$, the asymptotes of the hyperbolae being parallel [19], see Fig.3.

(c)- in a solid crystal, a tilt grain boundary is usually split into dislocations. The same is of course possible for a tilt grain boundary in a layered medium. And indeed the FCD free interstices (the packing of ellipses in the plane of the grain boundary cannot be perfect), are filled with dislocations [19]. There is therefore a relation of equivalence between dislocations and focal conic domains [20, 21]. As a matter of fact, the ellipse of an isolated FCD is the termination of a set of dislocations whose total Burgers vector $b_{dist} = 4ae = 4c$, as explained below.

III. KINKS ON DISCLINATIONS

A. Wedge and twist disclinations. FCD confocal conics are disclinations.

Disclinations are typical line defects in a medium endowed with a director order parameter [22]. One distinguishes *wedge* disclinations, whose rotation vector $\vec{\Omega}$ is along the disclination line, and *twist* disclinations, whose rotation vector $\vec{\Omega}$ is orthogonal to the disclination line. As shown in [8, 9], there are necessarily dislocations attached to a line segment of twist character. Let us remind that the focal lines of a FCD, are, by nature, disclinations. The hyperbola is a disclination of strength $k = 1$, whose rotation vector ($\vec{\Omega} = 2\pi \vec{t}$) varies in direction (not in length) all along the hyperbola: at each point of the hyperbola it is parallel to the tangent \vec{t} at this point. The layer geometry is

axial-symmetric in the vicinity of the hyperbola. Insofar as it is a disclination, the hyperbola is of wedge character; there are no attached dislocations. The ellipse is a disclination of strength $k = \frac{1}{2}$, whose rotation vector ($\vec{\Omega} = \pi \vec{t}$) varies in direction but (not in length) all along the ellipse; \vec{t} is in the plane of the ellipse and tangent to the layer inside the ellipse, Fig.4. The twist component induces the attachment of dislocations [12, 19, 23], see below.

B. Kinks, generic properties.

Modifications to the twist/wedge character of a disclination can be achieved in the generic case by attaching/detaching new dislocations to the line. Such operations modify the shape of the line, by the introduction of *kinks*, Fig.5. For instance, in order to attach at some point A on a wedge line \mathcal{L} a set of dislocations of total Burgers vector \vec{b}_{dist} , one has to introduce a kink \vec{AB} , with a component perpendicular to \mathcal{L} , (*i.e.* a segment \vec{AB} having a twist component), such that

$$\vec{b}_{dist} = 2 \sin \frac{\Omega}{2} \vec{t} \times \vec{AB}, \quad (3)$$

where \vec{t} is a unit vector tangent to the line and $\vec{\Omega}$ ($\vec{\Omega} = \Omega \vec{t}$) is the rotation invariant carried by the disclination; see [10, 23] and appendix for a demonstration of Eq. (3). In practice lines of interest are of strength $|k| = \frac{1}{2}$; $|\vec{\Omega}| = \pi$. Reciprocally, the presence of a kink reveals the presence of dislocations attached to the line. The above picture of a kink says nothing about the nature (edge or screw) of the attached dislocations, and the way they relax and disperse through space about the disclination line. The line flexibility, *i.e.* the main property at work when the medium is deformed, elastically or by flow, takes its origin here, in this interplay of the disclination line with dislocations.

A kink can be infinitesimally small;

$$\vec{db}_{dist} = 2 \sin \frac{\Omega}{2} \vec{t} \times \vec{ds}, \quad (4)$$

where \vec{ds} is an infinitesimal element along the line [23]. A density of infinitesimally small kinks modifies the curvature of the line. A dislocation attached to an infinitesimally small kink has an infinitesimally small Burgers vector; a dislocation attached to a finite kink may

have a finite Burgers vector, as we see now.

C. Kinks in a SmA

Let us now consider in more detail the geometry of the attachment of dislocations to a focal line in a FCD. We first state some general properties, and then consider separately the case of the ellipse and the case of the hyperbola. Again, the dislocations emanating from the kink have to belong to one of the two following categories: they are either dislocations with infinitesimal Burgers vectors whose directions are parallel to the layer dislocations of the layer stacking, or with Burgers vectors $|\vec{b}_{disl}| = nd_0$ perpendicular to the layer (these are the usual SmA quantified dislocations). Note that in both cases the Burgers vectors are translation symmetry vectors; they are perfect Burgers vectors in the sense of the Volterra process. We consider them successively.

Infinitesimal Burgers vectors relate to dislocation densities that relax by the effect of viscosity; they affect the curvature of the layers and consequently, as alluded just above, they also affect their thickness, since the layers have to keep in contact. We shall not expatiate on such defects, which are not relevant to our subject. Just note that the theory has been developed for solids since long; see [24] for a general review. An essential point worth emphasizing is that a continuous density of infinitesimal dislocations can be attended by a strainless, elastically relaxed, state. In our case, this would correspond to a state where the layers keep parallel. Continuous dislocation with Burgers vectors parallel to the layers do not introduce any kind of singularity of the SmA order parameter. Eq. 4 indicates that the related kink \vec{ds} and that \vec{t} are both perpendicular to \vec{db}_{disl} , which condition does not specify any special direction for $d\vec{s}$.

Finite Burgers vectors: this case is better represented by Eq. 3, because the Burgers vector and the kink \vec{AB} are finite. \vec{AB} and \vec{t} have both to be in a plane tangent to the local layer. To an elementary dislocation $|\vec{b}_{disl}| = d_0$ corresponds an elementary kink. An elementary kink is microscopic ($AB = 2d_0$); one can thus possibly have a density of such elementary kinks, rendering the line curved when observed at a mesoscopic scale. This does not exclude the possibility that infinitesimally small dislocations are attached to finite kinks. Simple as they look, the application of these criteria requires however some care.

D. Quantified Burgers vectors attached to an ellipse.

Fig.4 is a schematic view of the properties of an ellipse, belonging to an ideal FCD, which are in relation to its $k = \frac{1}{2}$ disclination character. The layer geometry is different inside and outside the ellipse. Inside, the Dupin cyclide layers intersect the plane of the ellipse *perpendicularly*. Outside, the layers are planar and *perpendicular* to the asymptotic directions, as more detailed below. The change of geometry between the inside and the outside is achieved by a rotation of the layers about the local rotation vector $\vec{\Omega} = \Omega \vec{t}$; $\vec{\Omega}$ is parallel to the layers (inside and outside) and is along the intersection of the layers with the plane of the ellipse, inside.

The layer at M (M being a running point on the ellipse) is indeed folded inside about the local \vec{t} direction, is singular at M (it is a conical point), and extends outside along a fold made of two half planes symmetrical with respect the ellipse plane, each perpendicular to one or the other of the two asymptotic directions of the confocal hyperbola, and thereby making an angle about a direction parallel to the minor axis of the ellipse (see [10], chapter 10). The ellipse plane outside the ellipse is therefore a tilt boundary of misorientation angle ω , which can be accommodated by edge dislocations of Burgers vectors multiple of d_0 , perpendicular to the plane of the tilt boundary, *i.e.* the plane of the ellipse outside. There is one such dislocation $|\vec{b}_{disl}| = 2d_0$ per layer counted inside the ellipse.

The same result can be obtained by using Eq. 4. Let us parameterize the ellipse in polar coordinates with the origin at the physical focus, Fig.6.

$$r = \frac{p}{1 + e \cos \phi}, \quad (5)$$

where $p = \frac{b^2}{a}$ and ϕ is the polar angle. One then finds that the $k = \frac{1}{2}$ ellipse disclination is partially of twist character, with an attached Burgers vector

$$db_{disl} = 2dr, \quad (6)$$

The total Burgers vector attached to the ellipse is $\int_{\phi=0}^{\phi=\pi} db_{disl} = 4c$, as indicated above. If one takes $dr = d_0$, - an approximation which makes sense (up to second order), since d_0 is so small compared to the size a of the ellipse - it is visible that the points $M\{r, \phi\}$ and $N\{r + dr, \phi + d\phi\}$ are on two parallel smectic layers at a distance d_0 . Notice that the density of dislocations is constant if measured along the major axis: $\frac{db_{disl}}{dx} = -2e$. There are no dislocations attached to the singular circle of a toric FCD, as the eccentricity e vanishes. An ellipse can be thought of as a circle kinked at the layer scale.

IV. KINKED FOCAL CONIC DOMAINS

A. Frequent geometries for a kinked ellipse.

The kinking of the ellipse takes different geometries, whether the dislocations at stake are located outside (where \vec{b}_{disl} is perpendicular to the plane) or inside (where \vec{b}_{disl} is in the plane) the FCD.

Outside the FCD: the Mouse (Fig.7). If the dislocation lines attached to the ellipse disperse *away outside* the focal conic domain, *i.e.* in a region of space where the layers are in the plane of the ellipse; \vec{t} , which varies in direction all along the ellipse, is in this plane. Applying Eq. 3, it appears that the kinks have to be in the plane of the ellipse. This configuration has been observed, in a situation where the kinks are so small and have such a high density that the kinked ellipse appears to be continuous, but its shape departs considerably from a 'perfect' ellipse; it is smoothly distorted by the in-plane kinks: we call it a 'Mouse' (Fig.7a). Fig.7b provides a model for such kinks, (which always go by pairs), drawn here at a scale which has no relation with the real scale. The photograph of Fig.7a is taken from the rim of a free standing film, in a region where the thickness d of the film is quickly changing, and the wedge angle ω between the opposite free boundaries varies monotonically. The anchoring conditions are homeotropic; there is therefore a tilt boundary in the mid-plane of the film, but with a variable misorientation angle. The Mouse is in this mid-plane; the extra dislocations attached to the kinks (edge dislocations in the mid-plane) relax the variation of ω by contributing to the modification of the density $\frac{db_{disl}}{ds}$ of dislocations in this plane; see [2] for a more detailed account.

Inside the FCD: the Giraffe (Fig.8). The layers rotate about \vec{t} by an angle of π ; hence they become perpendicular to the plane of the ellipse, *inside* the FCD. Therefore the dislocations that disperse away inside are attached to kinks that are perpendicular to the plane of the ellipse, on average. A pair of elementary kinks (not at scale at all in the figure), symmetric with respect to the major axis, can be linked by a unique dislocation (Fig.8b). Our observations (Fig.8a) indicate the existence of another mode of kinking, with screw dislocations joining the kink (of macroscopic size) to the hyperbola; another kink should then exist on the hyperbola, but is not visible. We call such a departure from the perfect ellipse, distorted by off-plane kinks, a 'Giraffe'. One can eventually imagine elementary kinks of the sort in discussion, all of the same sign, having a high density on the ellipse and continuously tilting its plane. Such tilted ellipses have been observed in 8CB and 9CB [1]. The situation observed in Fig.8a results from the presence of a quasi planar *pretilted* anchoring. A unique direction of pretilt is in conflict with the presence of an entire ellipse parallel to the boundary in its close vicinity; hence opposite displacements of different parts of the ellipse along the vertical direction, to the point that one part gets off the boundary, and is virtual; see [2] for a more detailed account of this geometry and other geometries implying different kink types. Fig.8c illustrates a double-kinked ellipse of a Giraffe type observed from the side in a thick ($\approx 200\mu m$) 8OCB sample.

B. On the origin of deviations from Darboux's theorem

The just alluded kinking processes can bring large deviations to Darboux's law; reciprocally it is clear that the deviations from Darboux's law mean a modification of the shape of the ideal FCD conics, i.e. the presence of kinks (at the scale of the layers, since they are not visible with the optical microscope) and of their attached dislocations. These dislocations necessarily disperse through the medium, outside and/or inside the FCD. Infinitesimal dislocations, if alone, would result, as stated above, in an extra curvature of the layers; two cases arise: either the deformed layers keep parallel, hence the layer normal keep straight, and one gets eventually a new ideal FCD, or there is a deviation to straightness of the layer normals, and consequently a layer thickness variation (this case falls within the province of the Kroener's dislocation densities [24]), i.e. a process of high energy if not relaxed, at least in part, by finite edge dislocations. It suffices then to consider only those latter. The

edge components of the attached dislocations that are dispersed inside the FCD break the parallelism of the inside layers. The congruence of the layer normals is thus no longer a set of straight lines. This is another way of explaining the variation to Darboux's theorem. This could have been stated from the start: *edge dislocation densities break Darboux's theorem, because they break the layer parallelism.* But this statement comprehends deviations to Darboux's theorem that are more general than those where the focal manifolds are degenerate to lines. The focal manifolds of a congruence of curved normals are generically 2D surfaces, not lines. We see that the fact that these surfaces are degenerate into lines comes from the fact that the dislocations in question are *attached* to the original focal lines. To conclude, the occurrence of deviations to Darboux's theorem for a set of focal *lines* means that the conics are (densely) kinked and dislocations attached to those kinks.

C. The kinked (split) hyperbola.

The shape of the layers is cylindrical about the central zone of the hyperbola, near its apex (which is also the physical focus of the ellipse). But the layers are practically perpendicular to the hyperbola at a distance of order a to the plane of the ellipse; the wedge disclination smoothly vanishes far from the ellipse plane. In between, the layers display cusps, the lesser pronounced the more distant from the ellipse. Hyperbolae are lines of easy coalescence of screw dislocations, as observed long ago [25].

The presence of kinks on the hyperbola is a delicate matter; because it is a $k = 1$ wedge disclination ($\Omega = 2\pi$), Eq. 3 and 4 do not apply directly. A way of solving the question is to consider that the line is made of two $k = \frac{1}{2}$ lines, indicating that dislocations with total Burgers vectors twice as large can attach to a kink of the same size as in the $k = \frac{1}{2}$ case.

Another situation is worth considering. In fragmented focal domains of the type represented Fig.9b (called *fragmented* domains), the hyperbola belongs to the boundary of the domain. It is then no longer a $k = 1$ disclination but a $k = \frac{1}{2}$ disclination, as if it were split all along its length. Such an object, noted sFCD for short, and already recognized by G. Friedel [9], is easily obtained in a confined sample. A sFCD is bound by a segment of the ellipse and by a segment of the hyperbola, and four fragments of cones of revolution. Thus both segments are $k = \frac{1}{2}$ disclination line segments.

As a consequence, sFCDs are generally aligned, attached by the ends of the disclination segments, such attachments being required by the conservation of the disclination strength. But observe that a hyperbola H (resp. an ellipse E) can be attached indifferently either to another H (resp. an E) or to an E (resp. a H).

One can imagine that the ellipse E_1 of a FCD_1 is attached to H_2 of a FCD_2 , while the hyperbola H_1 of the FCD_1 is attached to E_2 of the FCD_2 . Such a set of line segments attached by their extremities is topologically equivalent to a double helix. This geometry, with sequences of the ...HEHEH... type, was observed long ago by C. E. Williams [16] at the $N \rightarrow Sm$ transition; it is at the origin of helical giant screw dislocations.

Let us also mention the observation, also reported in [1], of a mobile kink (several microns long) perpendicular to the $k = \frac{1}{2}$ hyperbola of a sFCD, moving in the direction of the physical focus, but nucleated far from it, at a distance large compared to a . There is no doubt that dislocations, dragged along the hyperbola, are attached to this mobile kink; their Burgers vectors, that are perpendicular to the layers, are practically parallel to the asymptotic direction of the hyperbola, at a distance from the ellipse plane, which indicates that they are of screw character. This might be an indication of a mechanism by which screw dislocations align along a (split) hyperbola.

D. Focal Conic Domains at the $Sm \rightarrow N$ transition

FCD's that are immersed in the bulk (they are of the type represented Fig.9a, and generally gather into tilt boundaries) disappear rather suddenly about $0.5^\circ C$ before the transition, by an instability mechanism which certainly implies a sudden multiplication of dislocations. The capture of free edge dislocations by the ellipse modifies its geometric features e and a , Fig.10. Free dislocations of the same (resp. opposite) sign as the dislocations attached to the ellipse, if captured, would increase (resp. decrease) its size ($2a \rightarrow 2a + b_{disl}$), either at e constant (then the asymptotic directions stay constant), or not. Boundary conditions play a dominant role in this relaxation process. Notice that, after a possible increase in size, the ellipses eventually always decrease in size when the temperature increases, the smallest ellipses disappearing first. For the ellipses belonging to a grain boundary, this implies that the boundary area occupied by dislocations (the

so-called residual boundary) increases with temperature. This is in agreement with the model developed in [19], which relates the residual boundary to the material constants; in particular a decrease of the compression modulus B must result in an increase of the residual area. Another important issue here is the existence of the instability. Both topics will be discussed in more details in a forthcoming publication.

V. CONCLUSIONS

This paper investigates from a theoretical point of view some features of the FCD transformations that have been observed, in the smectic phase, when approaching the nematic phase. These very spectacular phenomena happen in a large temperature domain ($\Delta T = T_{AN} - T^* \approx$ half a degree in 8CB, which is the chemical we used for quantitative observations; the other compounds yield qualitatively equivalent results) in which it is believed that the variations of the material constant B are large enough to allow significant variations of the dislocation line energy and the multiplication of fresh dislocations. At the same time K_1 and also \bar{K} (as we assume) do not vary in comparable proportion, so that the energy of focal conic domains is not appreciably changed.

We have tried to discuss the general principles at the origin of these transformations that are due to the direct interaction between FCDs and finite Burgers vector dislocations. There is no doubt that infinitesimally small Burgers vector dislocations are also playing a role, in particular in the phenomena of viscous relaxation [10, 26], but this is not discussed. The general principles that we advance are geometrical and topological in essence. The mechanisms that obey these principles seem to be plenty, depending in particular on the boundary conditions and the precise FCD texture. The examples we have given are few, and are chosen for the sake of illustration. A description of several more observed transformations, interpreted in the same terms, will be given somewhere else.

The SmA \rightarrow N transition is one of the most debated liquid crystal phase transitions [3, 27, 28, 29]. This is not the place to enter into the detail of this debate, inasmuch as our results, even if they stress the importance of defect interplays in the critical region, are not directly related to the very proximity of the transition, which has been examined by several authors with great accuracy (*e.g.* [6]).

The question which is at stake is rather why the interactions occur at temperatures definitively lower than T_{AN} . We interpret this phenomenon as an instability for the multiplication of dislocations, much akin to a Kosterlitz-Thouless transition [30] under temperature, but also under stress (the boundary conditions), of the sort proposed in [31] for a completely different type of transition. More details on the quantitative nature of the transition will be given in a forthcoming publication.

VI. APPENDIX

We envision a curved disclination line \mathcal{L} , carrying a rotation vector $\vec{\Omega}$ constant in length and in direction. Let P be a point on the cut surface bound by \mathcal{L} .

We first assume that $\vec{\Omega}$ is attached to some well-defined point O (Fig.11). The relative displacement of the two lips of the cut surface at P is:

$$\vec{d}_P(O) = \vec{\Omega} \times \overrightarrow{OP} \quad (7)$$

which is large on the line \mathcal{L} if P is taken at some point M on \mathcal{L} . Consequently in the generic case $\mathcal{L}(0, \Omega)$ has a very large core singularity, thus large accompanying stresses and a large core energy. On the other hand the cut surface displacement vanishes at M if $\vec{\Omega}$ is attached to \mathcal{L} at M , but then it does not vanish at $N = M + \overrightarrow{dM}$. There is still a large core singularity along \mathcal{L} , except at M . The Volterra process, when applied in its standard form, does not provide a solution to the construction of a curved disclination with well relaxed stresses.

An extended conception of the Volterra process solves the problem. Assume that there is a copy of the rotation vector $\vec{\Omega}$ attached to all the points of \mathcal{L} , and consider the effect of such on a point P belonging to the cut surface of all these $\vec{\Omega}'$ s. We have, for each other M belonging to \mathcal{L} , another value of the relative displacement of the lips of the cut surface:

$$\vec{d}_P(M) = \vec{\Omega} \times \overrightarrow{MP} \quad (8)$$

This difficulty is easily solved by the introduction of a set of *infinitesimal* dislocations attached to the disclination line all along (Fig.12). Let M and $N = M + \overrightarrow{dM}$ be two infinitesimally close points on \mathcal{L} . We have:

$$d_{\mathbf{P}}(\overrightarrow{M} + \overrightarrow{dM}) - d_{\mathbf{P}}(\overrightarrow{M}) = \vec{\Omega} \times \overrightarrow{dM} \quad (9)$$

which is independent of P . The quantity $d\vec{b}(M) = \vec{\Omega} \times d\vec{M}$ is the infinitesimal Burgers vector of the infinitesimal dislocation attached to \mathcal{L} at point M [23].

The above equations are established for a small angle of rotation vector $|\vec{\Omega}|$. In the general case Ω has to be replaced by $\frac{1}{2} \sin \frac{\vec{\Omega} \cdot \vec{t}}{2}$, where $\vec{\Omega} = \Omega \vec{t}$.

Acknowledgments

We acknowledge fruitful discussions with V. Dmitrienko and J. Friedel. We are grateful to J.-F. Blach for providing us with glass plates treated for special anchoring conditions.

-
- [1] C. Meyer and M. Kleman, ILCC2004, Mol. Cryst. and Liq. Cryst., under press.
 - [2] Yu. A. Nastishin, C. Meyer and M. Kleman, in preparation.
 - [3] P. G. De Gennes and J. Prost, *The Physics of Liquid Crystals*, 2nd edition, Clarendon Press (1993).
 - [4] M. Benzekri, T. Claverie, J.-P. Marcerou, and J.-C. Rouillon, Phys. Rev. Lett. **68**, 16 (1992).
 - [5] F. Beaubois, T. Claverie, J.-P. Marcerou, J.-C. Rouillon, and H.-T. Nguyen, C.W. Garland and H. Haga, Phys. Rev. E **56**, 5 (1997).
 - [6] A. Yethiraj, J. Bechhoefer, Phys. Rev. Lett. **84**, 16 (2000).
 - [7] G. Barbero and V. M. Pergamenschchik, Phys. Rev. E **66** 051706 (2002).
 - [8] G. Friedel et F. Grandjean, Bull. Soc. Fr. Minér. **33**, 192, 409 (1910).
 - [9] G. Friedel, Ann. Phys. (Paris) **18**, 273 (1922).
 - [10] M. Kleman and O. D. Lavrentovich, *Soft Matter Physics. An Introduction*, Springer N.Y. (2003).
 - [11] M. Kleman and O. D. Lavrentovich, Phys. Rev. E **61**, 1574 (2000).
 - [12] P. Boltenhagen, O. Lavrentovich and M. Kléman, Phys. Rev. A **46**, 1743 (1992).
 - [13] M. Allain and J.-M. diMeglio, Mol. Cryst. Liq. Cryst. **124**, 115 (1985), Europhys. Lett. **2**, 597 (1986).
 - [14] M. Allain and M. Kleman, J. de Physique **48**, 1799 (1987).
 - [15] O. Dhez, S. König, D. Roux, F. Nallet and O. Diat, Eur. Phys. J. E **3**, 377 (2000).
 - [16] C.E. Williams, Philos. Mag. **32**, 313 (1975).

- [17] M. Kleman, O. D. Lavrentovich and Yu. A. Nastishin, in *Dislocations in Solids*, F. R. N. Nabarro and J. P. Hirth, eds, North-Holland, Amsterdam vol. **12**, 147 (2004).
- [18] G. Darboux, *Leçons sur la théorie générale des surfaces*, 2^{ème} partie, Gauthier-Villars, Paris (1914).
- [19] M. Kleman and O. D. Lavrentovich, *Eur. Phys. J.* **E2**, 47 (2000).
- [20] L. Bourdon, M. Kléman and J. Sommeria, *J. de Physique* **43**, 77 (1982).
- [21] P. Boltenhagen, O. D. Lavrentovich and M. Kléman, *J. Phys. II France* **1**, 1233 (1991).
- [22] F. C. Frank, *Discuss. Faraday Soc.* **25**, 19 (1958).
- [23] J. Friedel and M. Kléman, *J. de Phys.* **30**, C4:43 (1969).
- [24] E. Kroener, in *Physics of Defects*, Les Houches 1980 Session XXXV (eds. R. Balian, M. Kléman and J.P. Poirier), North-Holland, Amsterdam, (1981).
- [25] C. E. Williams and M. Kléman, *Philos. Mag.* **33**, 213 (1976).
- [26] J. Friedel, private communication.
- [27] J. Toner and D. Nelson, *Phys. Rev.* **B24**, 363 (1981).
- [28] J. Toner, *Phys. Rev.* **B26**, 1 (1982).
- [29] W. Helfrich, *J. de Physique* **39**, 1199 (1978).
- [30] J.M. Kosterlitz and D. J. Thouless, *J. Phys. C: Solid State Phys.*, **6**, 1181 (1973).
- [31] M. Khanta, D. P. Pope and V. Vitek, *Phys. Rev. Lett.* **73**, 684 (1994).

Figure Captions

Fig.1: a) Complete FCD with negative Gaussian curvature Dupin cyclides, sitting inside cylinders of revolution meeting on the ellipse. The cyclides cross the ellipse plane at right angles; their intersections with the ellipse and the hyperbola, when they exist, are conical points. b) Dupin cyclides fragments with positive and negative Gaussian curvature, so chosen that the ellipse is still singular but the hyperbola has no physical realization. An opposite situation (ellipse with no physical realization, hyperbola still singular) is illustrated in [10].

Fig.2: In an ideal FCD the ellipse and the hyperbola project orthogonally along two conics which intersect at right angles, as observed (long side of photographs $\approx 200\mu\text{m}$): a) 8OCB thick ($\approx 200\mu\text{m}$) sample annealed during about 48 hours deeply in the SmA phase (7°C below the transition from the nematic phase) between two untreated glass substrates;

Darboux's theorem obeyed; the set of the FCD's with parallel hyperbolae asymptotes form a grain boundary of the type schematically shown in Fig.3; b) 8CB (0.5°C below the transition to the nematic phase); Darboux's theorem disobeyed as demonstrated for the lower photograph: solid lines are tangents to the disclinations and the dashed lines are orthogonal; a very visible deviation from the Darboux's theorem is encircled on the upper photograph.

Fig.3: Tilt boundary split into FCDs. a) schematic, adapted from [10]; b) 8CB, polarized light microscopy observation; the tilt boundary is seen edge-on; the edge of the photograph $\approx 100\mu\text{m}$ long.

Fig.4: F, the physical focus, is the center of the (circular) intersections of the layers with the plane of the ellipse, inside the ellipse; \vec{t} is a unit vector along the local rotation vector; the $k = \frac{1}{2}$ disclination ellipse is of mixed (twist-wedge) character all along, except at the ends of the major axis, where it is wedge.

Fig.5: Kink on a wedge disclination line, see text.

Fig.6: The ellipse in polar coordinates. The radius of curvature of the circle centered in the focus F and tangent to the apex is $a - c$, which is smaller than the radius of curvature $\frac{b^2}{a}$ of the ellipse at the apex. This circle is thus entirely inside the ellipse. All the circles and the arcs of circles of the figure are centered in F. They figure intersections of the smectic layers with the plane of the ellipse.

Fig.7: Double kinks with a dislocation *outside* the FCD; a) Mouse patterns in 8CB, free standing film, rim region; the thickness decreases downwards; long side of the photograph $\approx 200\mu\text{m}$); b) model.

Fig.8: Views of a double kink with a dislocation *inside* the FCD (long side of photographs $\approx 200\mu\text{m}$): a) Giraffe patterns in 8CB, demonstrating that the ellipses are divided into two parts not located at the same level as depicted in the model below, the screw dislocations attached to the kinks are visible; b) model of a double kink linked by a unique dislocation located inside the FCD; c) - a double kinked ellipse (kinks are shown by arrows) of the Giraffe type observed from the side (8OCB in a gap of the thickness $\approx 200\mu\text{m}$ between two untreated glass substrates).

Fig.9: Incomplete FCD's. a) FCD bound by two cones of revolution meeting on the ellipse, with apices at the terminations of the hyperbola segment; b) A hyperbola-split fragmented FCD (sFCD). The sFCD is bound by i) two fragments of cones of revolution with apices at the terminations of the hyperbola segment and limited to the ellipse segment,

ii) two fragments of cones of revolution with apices at the terminations of the ellipse segment and limited to the hyperbola segment. The director field on the boundaries is indicated, not the cyclide intersections.

Fig.10: Edge dislocations mobile in the plane of the ellipse and attaching to it. The consecutive relaxation process modifies the FCD according to the boundary conditions.

Fig.11: The classic Volterra process for a rotation vector $\vec{\Omega}$ attached to O . At a point P on the cut surface, the lips of the cut surface suffer a relative displacement $\vec{d}_P(O) = \vec{\Omega} \times \vec{OP}$.

Fig.12: The extended Volterra process for a rotation vector $\vec{\Omega}$ attached locally to each point on \mathcal{L} . Infinitesimal dislocations are attached all along the disclination line.

This figure "Fig01a.jpg" is available in "jpg" format from:

<http://arxiv.org/ps/cond-mat/0507024v1>

This figure "Fig01b.jpg" is available in "jpg" format from:

<http://arxiv.org/ps/cond-mat/0507024v1>

This figure "Fig02a.jpg" is available in "jpg" format from:

<http://arxiv.org/ps/cond-mat/0507024v1>

This figure "Fig02b.jpg" is available in "jpg" format from:

<http://arxiv.org/ps/cond-mat/0507024v1>

This figure "Fig03.jpg" is available in "jpg" format from:

<http://arxiv.org/ps/cond-mat/0507024v1>

This figure "Fig04.jpg" is available in "jpg" format from:

<http://arxiv.org/ps/cond-mat/0507024v1>

This figure "Fig05.jpg" is available in "jpg" format from:

<http://arxiv.org/ps/cond-mat/0507024v1>

This figure "Fig06.jpg" is available in "jpg" format from:

<http://arxiv.org/ps/cond-mat/0507024v1>

This figure "Fig07a.jpg" is available in "jpg" format from:

<http://arxiv.org/ps/cond-mat/0507024v1>

This figure "Fig07b.jpg" is available in "jpg" format from:

<http://arxiv.org/ps/cond-mat/0507024v1>

This figure "Fig08a.jpg" is available in "jpg" format from:

<http://arxiv.org/ps/cond-mat/0507024v1>

This figure "Fig08b.jpg" is available in "jpg" format from:

<http://arxiv.org/ps/cond-mat/0507024v1>

This figure "Fig08c.jpg" is available in "jpg" format from:

<http://arxiv.org/ps/cond-mat/0507024v1>

This figure "Fig09a.jpg" is available in "jpg" format from:

<http://arxiv.org/ps/cond-mat/0507024v1>

This figure "Fig09b.jpg" is available in "jpg" format from:

<http://arxiv.org/ps/cond-mat/0507024v1>

This figure "Fig10.jpg" is available in "jpg" format from:

<http://arxiv.org/ps/cond-mat/0507024v1>

This figure "Fig11.jpg" is available in "jpg" format from:

<http://arxiv.org/ps/cond-mat/0507024v1>

This figure "Fig12.jpg" is available in "jpg" format from:

<http://arxiv.org/ps/cond-mat/0507024v1>