

Reduction of activation energy barrier of Stone-Wales transformation in endohedral metallofullerenes

Woon Ih Choi,¹ Gunn Kim,^{2,3} Seungwu Han,⁴ and Jisoon Ihm^{1,*}

¹School of Physics, Seoul National University, Seoul 151-747, Korea

²BK 21 Physics Research Division, Seoul National University, Seoul 151-747, Korea

³Department of Physics, North Carolina State University, NC 27695-7518, USA

⁴Department of Physics, Ewha Womans University, Seoul 120-750, Korea

(Dated: December 21, 2021)

Abstract

We examine effects of encapsulated metal atoms inside a C_{60} molecule on the activation energy barrier to the Stone-Wales transformation using ab initio calculations. The encapsulated metal atoms we study are K, Ca and La which nominally donate one, two and three electrons to the C_{60} cage, respectively. We find that isomerization of the endohedral metallofullerene via the Stone-Wales transformation can occur more easily than that of the empty fullerene owing to the charge transfer. When K, Ca and La atoms are encapsulated inside the fullerene, the activation energy barriers are lowered by 0.30, 0.55 and 0.80 eV, respectively compared with that of empty C_{60} (7.16 eV). The lower activation energy barrier of the Stone-Wales transformation implies the higher probability of isomerization and coalescence of metallofullerenes, which require a series of Stone-Wales transformations.

PACS numbers: 81.05.Tp, 34.10.+x, 61.48.+c

*corresponding author. Electronic address: jihm@snu.ac.kr

Since its discovery,[1] the fullerene has been extensively studied both theoretically and experimentally because of its potential applications in the fields of nanomaterials and biomedical science. Although the fullerene molecule usually has the highest icosahedral symmetry allowed by sixty constituent carbon atoms, transformations to other isomers of lower symmetry are still possible. One of the most plausible processes for isomerization of the fullerene is the so-called Stone-Wales (SW) or "pyracylene" rearrangement, which is the 90° rotation of two carbon atoms about the midpoint of the bond.[2] The SW transformation is also used to describe the structural changes of sp^2 -bonded carbon nanosystems.[3] For example, it has been proposed that the fusion process of fullerenes or carbon nanotubes may be explained in terms of a sequence of this rearrangement.[4, 5, 6] A problem in this proposal is that the activation energy barrier of 7 eV,[7] on the basis of cutting two bonds, is somewhat too high to overcome at experimental temperature for the merging process (1000–1500 °C).[8, 9] Nevertheless the transformation is useful to explain the production of all isomers of fullerenes and carbon nanotubes. Eggen et al. found that the activation barrier for this rearrangement was substantially reduced in the presence of a loosely bound carbon atom located preferentially in the region of paired pentagons.[10] Therefore pentagon rearrangements which are necessary steps in the growth of fullerenes may considerably result from autocatalysis by carbon. Ohsawa et al. reported the catalytic effect of various kinds of elements or ions in the bowl-shaped $C_{34}H_{12}$. [11] However, relatively few studies have been devoted to the SW transformation of the endohedral metallofullerene. In this paper, we investigate effects of encapsulated metal atoms on the activation energy barrier in the SW transformation of the $M@C_{60}$ molecule, where $M = K, Ca$ or La . We shall show below that isomerization of the endohedral metallofullerene via the Stone-Wales transformation can occur more easily than that of the bare fullerene owing to the charge transfer from the encapsulated metal atoms to the fullerene. Experimentally, metallofullerenes are much easier to fuse than empty fullerenes in peapods.[12, 13]

In the present study, we perform *ab initio* pseudopotential calculations using the plane wave basis set [14] within the local density approximation (LDA) for the exchange-correlation effect. The ultrasoft pseudopotential [15] is adopted with the cutoff energy of 30 Ry. The supercell size is $29 \times 29 \times 29 a_B^3$, where a_B is the Bohr radius, which can keep the undesirable interfullerene interaction sufficiently small. For La , we treat all 11 valence electrons ($5s^2 5p^6 6s^2 5d^1$) explicitly since the 5s and 5p orbitals cannot be considered to be frozen as

core electrons.[16] The scalar relativistic effects are taken into account because the effects are important in heavy elements such as La. We start the optimization of the La position on a three-fold axis 1.5 Å away from the center of the cage and obtain the stable position of the La atom in the C_{60} cage. For $K@C_{60}$ and $Ca@C_{60}$, the starting positions for optimization are at the center[17] and on a five-fold axis 1.5 Å away from the center of the cage,[18] respectively. The atomic positions are relaxed until the normal component of the atomic force becomes less than 0.02 eV/Å. We use the nudged elastic band (NEB) method[19] to calculate the activation energy barrier in the SW transformation of the fullerene. The NEB method is efficient in finding the reaction pathway with minimum energy when both the initial and final states are known. Regarding SW transformation of metallofullerene, we rotate the C-C dimer which is the closest to the metal atom (Ca and La). Thirteen replicas are chosen including the initial and final ones to construct the elastic band. We also calculate the climbing image of the highest energy replica to pick up the exact transition state which is regarded as a saddle point in the potential energy surface.

In the relaxation of the metal atom in C_{60} , the K atom prefers to be at the center of C_{60} . On the other hand, the stable position of the La atom is off-center and the distance between the La atom and the nearest C atom is 2.5 Å. The Ca atom shows the same tendency as La. Upon encapsulation of the La atom, the three-fold degeneracy of the t_{1u} states is split into 2+1 since the off-centered La atom breaks the icosahedral symmetry of an isolated C_{60} . [20] Almost three electrons are transferred from the La atom to the doubly degenerate states (four-fold degeneracy including spins) of C_{60} . [20, 21] The two-fold degeneracy is split again by the charging of odd number of electrons. It is found that a nearly symmetric pathway which has a C_2 symmetry appears at the saddle point (transition state) and the activation energy profile [shown in Figs. 1(a) and (b)]. Comparing C_{60} and $La@C_{60}$, the rotating carbon dimer has a bond length of 1.23 (1.27) Å, with 1.40 (1.39) Å bonds to each of the two nearest carbon atoms for C_{60} ($La@C_{60}$). This result is in agreement with the previous studies.[7, 22]

We identify the atomic geometry of the transition state (TS) in SW transformations of C_{60} and $La@C_{60}$ as depicted in Figs. 3(a) and (b). Table I lists the activation barriers (E_a) of the SW transformations in various sp^2 -bonded carbon systems. E_a in the SW transformation of the fullerene is lower than in the graphene layer (9.2 eV, the highest among the systems we study). Lowering of the barrier in fullerenes is due to the curvature effect associated

with the deviation from the sp^2 bonding.[6] When K, Ca and La atoms are encapsulated inside the fullerene, the activation energy barriers are lowered by 0.30, 0.55 and 0.80 eV, respectively compared with that of bare C_{60} . Reduction of the activation energy is smaller than in the case of the autocatalysis and other covalent materials.[10, 11] To examine the major effect of the encapsulated metal atom on the lowering of the activation barrier, we perform calculations for fullerenes charged with one or two electrons. Note that we do not show the data for C_{60}^3 . The third donated electron is not bound to the fullerene. When a fullerene is charged, the activation barrier becomes lower than that of the neutral cage. The barrier reduction is approximately proportional to the number of donated electrons. E_a in the SW transformation of C_{60} (C_{60}^2) is almost the same as that of $K@C_{60}$ ($Ca@C_{60}$). Therefore, the main role of the incorporated metal atom is the electron donation.

We find the reaction energy ($E_r = E_{\text{product}} - E_{\text{reactant}}$) shows the same trend as E_a in Table I. The C_{2v} -symmetry C_{60} with two pairs of fused pentagons (obtained by the SW transformation) is 1.59 eV higher in energy than the I_h -symmetry C_{60} . This value is in agreement with other group's results in the literature.[23] By contrast, for $La@C_{60}$, E_r is 0.3 eV, which is much smaller than that of C_{60} . It represents that an isomer of the metallofullerene which has adjacent pentagons can exist with higher probability than bare C_{60} . In the case of $K@C_{60}$, E_r has an intermediate value. The K atom at the center of the cage does not move during the process of the SW transformation. By contrast, the La atom in the fullerene moves by 1.0 Å toward the paired pentagons in the process of dimer rotation. The displacement of the La atom induces a large elongation of the C_{60} cage compared with the empty C_{60} molecule. The geometry of an empty fullerene is governed by the isolated-pentagon rule (IPR),[24, 25] which says that the most stable structure is that in which all pentagons are surrounded by five hexagons. The IPR-violating cages such as $Sq@C_{66}$ and $Sc_3N@C_{68}$, however, are stabilized by the electron transfer between the encapsulated metal atoms and the carbon cage, which significantly decreases the strain energy caused by paired pentagons and thus stabilizes the fullerene.[26, 27] Owing to the 108° bond angles of the pentagon, the apex atoms in the fused (paired) pentagon regions of the empty fullerene have a hybridization very close to sp^3 and exhibit a dangling-bond-like character which cannot be hybridized with any other electronic state.[28] For metallofullerenes, on the other hand, the electron donation from the metal atom weakens the dangling-bond-like character.

To clarify the role of the encapsulated metal atom, we have investigated the electronic

structures of C_{60} and $La@C_{60}$ in detail. The projected density of states (PDOS) to the 6s and 5d orbitals of La for each reactant, transition state and product are drawn (not shown). It is observed that the energy levels of the La atom lie mostly above the Fermi level. It means that almost three electrons move from La to the fullerene in $La@C_{60}$. In Fig. 2(a), the highest occupied molecular orbital (HOMO) at 0.2 eV corresponds to the dangling-bond-originated state as illustrated in Fig. 2(b). This state is above the HOMO of C_{60} (i.e., the five-fold states originating from the HOMO of empty C_{60} which are split now). Energy level which has the dangling bond character in $La@C_{60}$ is at 0.7 eV (HOMO + 2) as shown in Fig. 2(c) by arrow and the wave function in Fig. 2(d). Here we can see the three electrons coming from the La atom occupy the upper one and half level which is the lowest unoccupied molecular orbital (LUMO) and LUMO + 1 state in the transition state of C_{60} . The overall shape of two wave functions [Figs. 3(b) and (d)] is the same with small change originating from the perturbation of the La atom. Figures 3(c) and (d) show the PDOS into 2p-orbitals of two carbon atoms [labeled A, B and A^0, B^0 in Figs. 3(a) and (b)] which have the dangling bonds in the transition state. In the case of empty C_{60} , the PDOS of A and B are exactly the same. For $La@C_{60}$, on the other hand, the charge density of nonbonding states at site A^0 (between -1 and 0 eV) is not identical to the density at site B^0 . This difference arises from the hybridization between the La atom and the C atom at site B. In the TS configuration of empty C_{60} , the HOMO and LUMO are both localized states within the hemisphere containing two dangling atoms (A and B). By contrast, the TS geometry of $La@C_{60}$ has the HOMO and LUMO delocalized on the whole cage. Consequently, the electron donation and hybridization between the fullerene and metal atom inside reduce the activation energy barrier of the SW transformation in the endohedral metallofullerene.

We have studied the effect of encapsulated metal atoms inside a C_{60} molecule on the activation energy barrier of the SW transformation using the ab initio density functional calculations. The metal atoms in our study are K, Ca and La, which donate one, two and three electrons to the C_{60} cage, respectively. We have found that isomerization of the endohedral metallofullerene by the SW transformation can occur more easily than that of the empty fullerene owing to the charge transfer. The reduction of the activation energy barrier by the electron transfer may also explain the fact that metallofullerenes are much easier to coalesce than empty fullerenes inside nanotubes.

We thank Professor H. Shinohara for valuable discussions. This work is supported by

the CNNC of Sungkyunkwan University, the BK 21 project of KRF, the Samsung SDI-SNU Display Innovation, and the MOST through the NSTP (grant No. M1-0213-04-001). The computations are performed at Supercomputing Center of KISTI through the Supercomputing Application Support Program using the PWSCF code.[31]

-
- [1] H. W. Kroto, J. R. Heath, S. C. O'Brien, R. F. Curl, and R. E. Smalley, *Nature* 318, 162 (1985).
 - [2] A. J. Stone, D. J. Wales, *Chem. Phys. Lett.* 128, 501 (1986).
 - [3] F. Diederich et al., *Science* 252, 548 (1991).
 - [4] S. Han, M. Yoon, S. Berber, N. Park, E. Osawa, J. Ihm, D. Tománek, *Phys. Rev. B* 70, 113402 (2004).
 - [5] Y. Zhao, B. I. Yakobson, and R. E. Smalley, *Phys. Rev. Lett.* 88, 185501 (2002).
 - [6] M. Yoon et al., *Phys. Rev. Lett.* 92, 75504 (2004).
 - [7] H. F. Bettinger, B. I. Yakobson and G. E. Scuseria, *J. Amer. Chem. Soc.* 125, 5572 (2003).
 - [8] B. W. Smith and D. E. Luzzi, *Chem. Phys. Lett.* 321, 169 (2000).
 - [9] S. Bandow, M. Takizawa, K. Hirahara, M. Yudasaka, and S. Iijima, *Chem. Phys. Lett.* 337, 48 (2001).
 - [10] B. R. Eggen, M. I. Heggie, G. Jungnickel, C. D. Latham, R. Jones, P. R. Briddon, *Science* 272, 87 (1996).
 - [11] Z. Slanina, X. Zhao, F. Uhlik, M. Ozawa, E. Osawa, *J. Organometallic Chem.* 599, 57 (2000).
 - [12] T. Ozakaki, K. Suenaga, K. Hirahara, S. Bandow, S. Iijima and H. Shinohara, *J. Am. Chem. Soc.* 123, 9673 (2001).
 - [13] H. Shinohara, private communications.
 - [14] J. Ihm, A. Zunger, and M. L. Cohen, *J. Phys. C* 12, 4409 (1979).
 - [15] D. Vanderbilt, *Phys. Rev. B* 41, R7892 (1990).
 - [16] K. Laasonen, W. Andreoni and M. Parrinello, *Science* 258, 1916 (1992).
 - [17] Y.-G. Yoon, M. S. C. Mazzoni, and S. G. Louie, *Appl. Phys. Lett.* 83, 5217 (2003).
 - [18] L. S. Wang et al., *Chem. Phys. Lett.* 207, 354 (1993).
 - [19] G. Henkelman and H. Jonsson, *J. Chem. Phys.* 113, 22 (2000).
 - [20] S. Han, *J. Korean Phys. Soc.* 44, 889 (2004).

- [21] Jing Lu, Xinwei Zhang, and Xiangeng Zhao, *Chem. Phys. Lett.* 332, 51 (2000).
- [22] Y. Kumeda and D. J. Wales, *Chem. Phys. Lett.* 374, 125 (2003).
- [23] B. R. Eggen, C. D. Lantham, M. I. Heggie, B. Jones, and P. R. Briddon, *Synth. Met.* 77, 165 (1996).
- [24] H. Kroto, *Nature* 329, 529 (1987).
- [25] T. G. Schmalz, W. A. Seitz, D. J. Klein, and G. E. Hite, *J. Am. Chem. Soc.* 110, 1113 (1988).
- [26] C. R. Wang et al., *Nature* 408, 426 (2000).
- [27] S. Stevenson et al., *Nature* 408, 427 (2000).
- [28] E. Kaxiras, in *Atomic and Electronic Structure of Solids* (Cambridge University Press, Cambridge, 2003).
- [29] D. M. Ceperley and B. J. Alder, *Phys. Rev. Lett.* 45, 566 (1980).
- [30] P. Jensen, J. Gale, and X. Blase, *Phys. Rev. B* 66, 193403 (2002).
- [31] S. Baroni, A. Dal Corso, S. de Gironcoli, and P. Giannozzi, <http://www.pwscf.org>.

[Table Caption]

Table I. Activation barrier (E_a) and reaction energy (E_r) of the SW transformation in various sp^2 -bonded carbon systems. All energy values are in eV.

[Figure Captions]

Figure 1: Schematic energy diagram and the atomic configuration along the reaction coordinate in the Stone-Wales transformation of empty C_{60} . (a) Energy profile along the reaction coordinate. The dots represent the energies of the replicas in the SW transformation in the NEB method. (b) Atomic rearrangement from the I_h isomer to the C_{2v} isomer of the empty C_{60} molecule.

Figure 2: (color online) Density of states (DOS) for C_{60} and $La@C_{60}$ in the transition state [(a) and (c) respectively] and the isodensity surface plots of particular wave functions for C_{60} and $La@C_{60}$ [(b) and (d)]. The energy levels of the wave functions in (b) and (d) are indicated with an arrow in (a) and (c), respectively. The values for the red and blue isodensity surfaces are $0.0014 \text{ e}/\text{\AA}^3$.

Figure 3: (color online) Atomic structure of the transition state configuration for (a) C_{60} and (b) $La@C_{60}$, and PDOS of two atoms [labeled A, B and A^0 , B^0 in (a) and (b)] which have the remnant dangling bonds in the transition state for (c) C_{60} and (d) $La@C_{60}$. The defect states due to the dangling bonds and distorted bonding configurations are indicated by arrows. The red solid and blue dotted lines are the PDOS decomposed into 2p-orbitals of A, A^0 and B, B^0 atoms, respectively.

System	E_a	E_r
C_{60}	7.16	1.59
$K @ C_{60}$	6.85	1.07
$Ca @ C_{60}$	6.61	0.59
$La @ C_{60}$	6.36	0.30
C_{60}	6.87	1.12
C_{60}^2	6.59	0.67
$C_{42}H_{16}$ (for graphene)	9.20	3.07

Table I

W . I. Choi, G . K in , S . H an and J . Ihm