

Temperature dependent Eu 3d-4f X-ray Absorption and Resonant Photoemission Study of the Valence Transition in $\text{EuN}_{1/2}(\text{Si}_{0.2}\text{Ge}_{0.8})_2$

K. Yamamoto,^{1,2} K. Horiba,² M. Taguchi,² M. Matsunami,² N. Kamakura,² A. Chainani,²
Y. Takata,² K. Minura,¹ M. Shiga,³ H. Wada,³ Y. Senba,⁴ H. Ohashi,⁴ and S. Shin^{2,5}

¹Graduate School of Engineering, Osaka Prefecture University, Sakai, Osaka 599-8531, Japan

²RIKEN/SPRING-8, Mikazuki-cho, Sayo-gun, Hyogo 679-5148, Japan

³Department of Materials Science and Engineering, Kyoto University, Kyoto 606-8501, Japan

⁴JASRI/SPRING-8, Mikazuki-cho, Sayo-gun, Hyogo 679-5198, Japan

⁵The Institute for Solid State Physics, The University of Tokyo, Kashiwa, Chiba 277-8581, Japan
(Dated: December 27, 2021)

We study the mixed valence transition ($T_v \approx 80$ K) in $\text{EuN}_{1/2}(\text{Si}_{0.2}\text{Ge}_{0.8})_2$ using Eu 3d-4f X-ray absorption spectroscopy (XAS) and resonant photoemission spectroscopy (RESPES). The Eu^{2+} and Eu^{3+} main peaks show a giant resonance and the spectral features match very well with atomic multiplet calculations. The spectra show dramatic temperature (T)-dependent changes over large energies (~ 10 eV) in RESPES and XAS. The observed non-integral mean valencies of 2.35 ± 0.03 ($T = 120$ K) and 2.70 ± 0.03 ($T = 40$ K) indicate homogeneous mixed valence above and below T_v . The redistribution between $\text{Eu}^{2+} 4f^7 + [\text{spd}]^0$ and $\text{Eu}^{3+} 4f^6 + [\text{spd}]^1$ states is attributed to a hybridization change coupled to a Kondo-like volume collapse.

PACS numbers: 74.25.Jb, 74.25.Kc, 79.60.-i

An important issue of enduring interest in f-electron systems which exhibit mixed-valence (MV) transitions and the related Kondo effect is the role of purely ionic-like states compared to delocalized or hybridized states.^{1,2,3,4,5} For example, in SmS , which exhibits a pressure dependent MV transition⁶, the relevant ionic states are $\text{Sm}^{2+} 4f^6$ and $\text{Sm}^{3+} 4f^5$ states. It is clear that such a transition requires the role of the 5d electrons of Sm , or more generally, the $[\text{spd}]$ electrons of the conduction band.¹ The necessary condition of charge balance for SmS would indicate that the transition involves $\text{Sm}^{2+} 4f^6$, and the $\text{Sm}^{3+} 4f^5 + [\text{spd}]^1$ electron configurations. The MV transition then occurs between two stable states, each defined by relative contributions of the $4f^n$ and $4f^{n-1} + [\text{spd}]^1$ configurations. Each state can be a homogeneous MV state having the same non-integral valence at each site, due to a quantum mechanical mixing of the relevant configurations.⁷ In contrast, a static or inhomogeneous MV state is one in which electron configurations are different at different sites, representing one specific electron configuration at a site. While the MV in f-electron systems are often homogeneous, there do exist exceptions.^{1,8}

Many f-electron systems exhibit a MV transition induced by temperature (T), magnetic field and/or pressure. These include the f -transition in Ce metal,¹ the pressure-induced transitions in SmS ,⁶ and TmTe ,⁹ the T -dependent transitions in YbInCu_4 ,¹⁰ Tm monochalcogenides,¹¹ as well as Eu -based intermetallics, EuPd_2S_2 ,¹² $\text{Eu}(\text{Pd}_{1-x}\text{Au}_x)_2\text{S}_2$,¹³ and $\text{EuN}_{1/2}(\text{Si}_{1-x}\text{Ge}_x)_2$.¹⁴ Among T -induced transitions, the Eu systems exhibit the largest change in valency, $\nu \approx 0.3$ - 0.5 .^{12,13,14} And of these, $\text{EuN}_{1/2}(\text{Si}_{1-x}\text{Ge}_x)_2$ has been extensively studied to show T -,^{14,15} magnetic field-¹⁵ and pressure-¹⁶ induced valence transitions. By tuning composition $[x$ in $\text{EuN}_{1/2}(\text{Si}_{1-x}\text{Ge}_x)_2]$, the tran-

sition is observed to be first-order like for compositions close to $x = 0.8$, with a hysteresis as a function of T , pressure and magnetic field.^{15,16,17} The MV transition in $\text{EuN}_{1/2}(\text{Si}_{0.2}\text{Ge}_{0.8})_2$ has thus been investigated across the critical T (T_v) of ~ 80 K by magnetic susceptibility, high-energy bulk-sensitive Eu L-edge X-ray absorption spectroscopy (XAS), and X-ray diffraction to show that the transition is accompanied by a Kondo-like volume collapse across T_v .^{14,15,16,17}

XAS and resonant photoemission spectroscopy (RESPES) are important techniques for studying the electronic structure (ES) of f-electron systems.^{18,19,20} In XAS applied to a solid, a core electron of a particular site or element is excited to an empty state, and hence, it probes site-specific angular momentum projected unoccupied states of a solid.²¹ RESPES is a complementary technique which probes the resonantly enhanced partial occupied density of states (DOS) of a solid.²⁰ These techniques provide important insights into the physical properties of strongly correlated materials, including MV, Kondo effect, heavy fermion behavior, etc. However, recent studies using ultraviolet photoemission spectroscopy (PES) of MV systems revealed modifications of the surface ES compared to the bulk.^{22,23,24} While signatures of T -dependent MV are observed, the mean valence estimated from these measurements are incompatible with bulk thermodynamic studies. Significantly, the important role of hard X-ray (HX: $h\nu \approx 3$ to 8 keV) PES in general,^{25,26,27,28,29,30,31} as well as soft X-ray (SX: $h\nu \approx 1$ to 1.5 keV) PES²² and RESPES^{32,33} of f-electron systems, has been reiterated for studying bulk character ES.

In this work we study T -dependence of the MV transition in $\text{EuN}_{1/2}(\text{Si}_{0.2}\text{Ge}_{0.8})_2$ using XAS and RESPES across the Eu 3d-4f threshold. We observe a giant resonance of Eu^{2+} and Eu^{3+} main peaks and dramatic T -dependent changes in the XAS and RESPES data.

The mean valence estimated from the data are consistent with bulk sensitive results, indicating non-integral homogeneous mean valencies of 2.35 ± 0.03 (above T_v) and 2.70 ± 0.03 (below T_v). The XAS data are analyzed using atomic multiplet calculations for Eu^{2+} and Eu^{3+} states. The RESPES valence band spectra as a function of energy are also consistent with atomic calculations. The T-dependent transition redistributes occupancies of $\text{Eu}^{2+} 4f^7 + [\text{spd}]^0$ and $\text{Eu}^{3+} 4f^6 + [\text{spd}]^1$ configurations, attributed to a hybridization change coupled to a Kondo-like volume collapse.

$\text{EuNi}_{1/2}(\text{Si}_{0.2}\text{Ge}_{0.8})_2$ polycrystalline samples were prepared by melting stoichiometric amounts of constituent elements in an argon furnace.¹⁵ $\text{EuNi}_{1/2}(\text{Si}_{0.2}\text{Ge}_{0.8})_2$ was characterized to exhibit $T_v \approx 80$ K by magnetic susceptibility. The sample was single phase with the ThCr_2Si_2 -type structure, as confirmed by X-ray diffraction. The Eu 3d-4f XAS and RESPES experiments were performed at SX undulator beam line BL17SU of SP ring-8 using a grazing incidence monochromator. The XAS measurements were carried out by recording sample drain current as a function of photon energy. The RESPES experiments used a hemispherical high energy-resolution electron analyzer, SCIENTA SES-2002. The total energy resolution at the 3d-4f threshold was about 300 meV and the vacuum was 4×10^{-8} Pa. A clean surface was obtained by fracturing at 40 K. The measurements were performed at 120 K and 40 K in a T-cycle to confirm T-dependent changes.

Figures 1 (a) and (b) show the Eu 3d-4f XAS ($M_{4,5}$ -edge) spectra of $\text{EuNi}_{1/2}(\text{Si}_{0.2}\text{Ge}_{0.8})_2$ obtained at a sample T of 120 K (above T_v) and 40 K (below T_v), respectively. The spectra show multiple peak structures and the intensities of the peaks show large changes over a large energy range (~ 10 eV in the M_5 region), as a function of T. In order to identify the character of the various features, we calculated the Eu 3d-4f XAS spectra and compared them with experimental results, as shown in Fig. 1. The calculations are atomic multiplet calculations for the Eu^{2+} and Eu^{3+} free ions.³⁴ The Slater integrals and spin-orbit coupling constants are calculated by the Hartree-Fock method with relativistic corrections. As usual, the Slater integrals are reduced to 80%.³⁴ The Eu^{2+} and Eu^{3+} discrete energy states are plotted as a bar diagram in Fig. 1 (c). The discrete energy states were broadened by a Gaussian for the experimental resolution and by a Lorentzian to represent the lifetime broadening. The calculated spectra (Fig. 1 (a) and (b)) show very good match with all the divalent and trivalent multiplet features, confirming that intra-atomic multiplet effects account for the observed features. The spectral intensities required to match the experiment indicate non-integral homogeneous mean valencies of 2.35 ± 0.03 at 120 K, which changes to 2.70 ± 0.03 at 40 K. These values match with the mean valence estimated from bulk-sensitive L-edge XAS¹⁴ and HXPES of Eu 3d core levels²⁵, which showed a mean valence change from 2.75 to 2.40.³⁵ An important point to note is that the lowest unoccupied states with signifi-




FIG. 1: (Color online) Comparison of the Eu 3d-4f XAS experimental spectra with calculated spectra at (a) $T = 120$ K and (b) 40 K. The spectral intensities change strongly across $T_v \approx 80$ K, over large energy scales. The spectra are derived from intra-atomic multiplet excitations of Eu^{2+} and Eu^{3+} ions by broadening the discrete energy states (Fig. 1 (c)).

cant intensity for Eu^{2+} and Eu^{3+} configurations are close in energy and constitute the feature labelled 1 shaded region. This seems, at first glance, quite surprising because the Eu^{2+} and Eu^{3+} features are well-separated in the core levels³⁵ and valence band (discussed below) due to the strong on-site Coulomb correlations in the f states ($U_{ff} \approx 5$ eV). However, in the atomic multiplet approximation for XAS, if we consider the 3d-4f excitations to be dominated by U_{ff} and the core hole attraction U_{fc} , the 3d-4f excitation energy difference between Eu^{2+} and Eu^{3+} is obtained to be $U_{ff} - U_{fc}$. Since $U_{ff} \approx 1.2U_{fc}$, it suggests that a lower energy scale, such as hybridization between f and conduction band [spd] states, can play a major role in the MV transition.

Fig. 2 shows the Eu 3d-4f valence band RESPES obtained at $T = 120$ and 40 K for energies labelled 0-4 in Fig. 1 [corresponding to incident photon energies of $h\nu = 1121.0$ eV (o-resonance), 1125.7 eV, 1128.2 eV, 1130.2 eV and 1133.9 eV]. All the spectra are normalized to the Ge 3d shallow core levels which do not change shape as a function of T and incident photon energy, as shown in inset for the o-resonant spectra over a larger energy scale (0-35 eV). In the o-resonant spectra, the feature at 0.8 eV binding energy (BE) is the bulk $\text{Eu}^{2+} 4f$ state, and the feature at 1.5 eV BE, composed of the Ni 3d and the surface $\text{Eu}^{2+} 4f$ states, has higher intensity.^{24,36} This results in effectively masking the T-dependent changes in o-resonant spectra as the $\text{Eu}^{2+} 4f$ state does not




FIG. 2: (Color online) The T-dependent Eu 3d-4f RESPES spectra at incident photon energies marked 0-4 in Fig. 1. Inset shows normalization procedure using off-resonance (off-res0) spectra. The resonantly enhanced features originate from partial 4f DOS of Eu^{2+} and Eu^{3+} ions. Note absence of T-dependence in Eu^{2+} surface-state at 1.7 eV BE (on-res2).

participate in the MV transition.^{24,37} In contrast, the on-resonant spectra at energies on-res1-4 show dramatic changes in spectral features and intensity as a function of T and incident photon energy. We discuss all the spectral features and peak assignments using atomic multiplet calculations for the RESPES data at the energies on-res1-4, shown in Fig. 3.

The spectra at the photon energy on-res1 is enhanced for the bulk Eu^{2+} feature at 0.8 eV and surface feature at 1.7 eV BE (Fig. 2). The bulk feature shows a further clear enhancement at 120 K compared to 40 K, while the surface Eu^{2+} feature shows negligible change in spectral intensity with T. Weak features between 6-8 eV BE indicate T-dependent changes between 120 and 40 K (Fig. 3(a)), with strongly reduced intensity at 120 K. The atomic multiplet calculations (dotted lines, Fig. 3(a)) confirm the Eu^{2+} character of the feature at 0.8 eV and the Eu^{3+} character between 6-8 eV with very weak features at higher energies.

At the energy on-res2, the Eu^{2+} features are strongly enhanced, as this energy corresponds to the main peak of Eu^{2+} character in XAS (Fig. 1). It is a giant resonant enhancement because the intensity increase at the bulk Eu^{2+} peak is 140 times compared to the off-resonance data at 120 K.³⁸ At this energy, the features between 6-8 eV BE which originate in Eu^{3+} states, also show clear T-dependence: the spectral intensity nearly vanishes at




FIG. 3: (Color online) Comparison of the Eu 3d-4f RESPES experimental spectra with atomic multiplet calculations at incident photon energies from on-res1 to on-res4, at 40 K (left panel) and 120 K (right panel).

120 K but is observed at 40 K. This observation confirms that the T-dependence is due to intrinsic mixed valency changes and not due to oxidation at high T, as oxidation would lead to an increase in Eu-trivalency at 120 K. The calculations match the bulk Eu^{2+} and Eu^{3+} features.

On increasing the energy to on-res3, the Eu^{3+} features are strongly enhanced with a simultaneous reduction of the Eu^{2+} features. This energy being the main peak of Eu^{3+} derived states in XAS, the weaker Eu^{3+} multiplets are also significantly enhanced up to a BE of nearly 12 eV (Fig. 2 and Fig. 3(c)). The Eu^{3+} main peak also shows a giant resonance: 100 times increase compared to off-resonance at 40 K. Note also the strong T-dependence in the Eu^{3+} features at this energy (Fig. 2). Interestingly, while the calculations match the Eu^{2+} and Eu^{3+} derived features as obtained at lower energies, a new feature is obtained between the main Eu^{2+} and Eu^{3+} features (Fig. 3(c)). This is seen as a weak tail between 3-6 eV i.e. at BEs lower than the main Eu^{3+} peak. This is assigned to the intermediate spin- $\dot{\pi}$ satellites, as is known from earlier work.³⁹ The spin- $\dot{\pi}$ states ($4f^{5n,1\#}$) lie between the ($4f^{6n}$) and ($4f^{5n}$) photoemissional states of Eu^{2+} and Eu^{3+} initial states, respectively³⁹ and also exhibit T-dependence.^{24,36} At the energy on-res4, an overall reduction of the spectral intensities of the Eu^{2+} and Eu^{3+}

is observed, and the features are in agreement with the calculations (Fig. 3(d)). The Eu^{2+} surface state which was nearly absent at on-resonance energy is again recovered as a weak feature.

The success of the present XAS results in revealing the MV transition consistent with bulk sensitive L-edge XAS and HX-PES, is because we fractured the surface instead of scraping it.^{35,36} Hence, the intrinsic ES of a strongly correlated f electron system undergoing a MV transition as a function of T can be measured across the 3d-4f threshold. The energy dependent RESPES reveal the partial 4f DOS in the valence band. It is surprising that the 3d-4f XAS and RESPES data can all be explained with atomic multiplet calculations, above and below T_v , because it can't explain the MV transition. Since the MV transition is coupled to a Kondo-like volume collapse in the low-T phase, as is known from diffraction studies,^{14,17} the volume collapse must increase hybridization between the ionic f states and the conduction band [spd] states.

The change in occupancies is attributed to changes in hybridization above and below T_v .

In conclusion, the Eu 3d-4f XAS and RESPES spectra of $\text{EuN}_{1/2}(\text{Si}_{0.2}\text{Ge}_{0.8})_2$ at 120 K and 40 K, across the MV transition at $T_v = 80$ K are consistent with bulk sensitive measurements. The experimental spectra correspond nicely with calculated spectra for the Eu^{2+} and Eu^{3+} free ion configurations in an atomic model. The mean valence was estimated to be 2.35 ± 0.03 at 120 K and 2.70 ± 0.03 at 40 K. The redistribution between $\text{Eu}^{2+} 4f^7 + [\text{spd}]^0$ and $\text{Eu}^{3+} 4f^6 + [\text{spd}]^1$ states is attributed to a hybridization change coupled to a Kondo-like volume collapse. Eu 3d-4f XAS is very useful for studying the bulk intrinsic ES of strongly correlated rare earth compounds undergoing a MV transition.

Acknowledgments The authors thank Prof. T. Kinoshita, Dr. Y. Taguchi, Prof. K. Ichikawa and Prof. O. Aita for very valuable discussions.

-
- ¹ For early developments see : C.M. Varma, Rev. Mod. Phys. 48, 219 (1976); Valence Fluctuations in Solids, ed. L.M. Falicov, W. Hanke, and M.B. Maple (North-Holland, Amsterdam, 1981); Theoretical and Experimental Aspects of Valence Fluctuations and Heavy Fermions, ed. L.C. Gupta and S.K. Malik (Plenum, New York, 1987).
 - ² J.K. Freericks and V. Zlatić, Rev. Mod. Phys. 75, 1333 (2003).
 - ³ C.Dallera et al., Phys. Rev. Lett. 88, 196403 (2002); C.Dallera et al., Phys. Rev. B 70, 085112 (2004).
 - ⁴ J.-P. Rue et al., Phys. Rev. Lett. 93, 067402 (2004).
 - ⁵ K. Haulke, V. Odovenko, S. Y. Savrasov, and G. Kotliar, Phys. Rev. Lett. 94, 036401 (2005).
 - ⁶ A. Jayaraman, V. Narayanamurti, E. Bucher, and R.G. Maines, Phys. Rev. Lett. 25, 368 (1970).
 - ⁷ M. Croff, J.A. Hodges, E. Kemly, A. Krishnan, V. Murgai, and L.C. Gupta, Phys. Rev. Lett. 48, 826 (1982); J. Rohler, D. Wohlleben, G. Kaindl, and H. Balster, Phys. Rev. Lett. 49, 65 (1982).
 - ⁸ C. Felser et al., Europhys. Lett. 40, 85 (1997).
 - ⁹ T. Matsumura et al., Phys. Rev. Lett. 78, 1138 (1997).
 - ¹⁰ I. Felner and I. Nowik, Phys. Rev. B 33, 617 (1986).
 - ¹¹ B.P. Clayman, R. Ward, and J.P. Tidman, Phys. Rev. B 16, 3734 (1977).
 - ¹² E.V. Sampathkumaran, L.C. Gupta, R. Vijayaraghavan, K.V. Gopalakrishnan, R.G. Pillay, and H.G. Devare, J. Phys. C 14, L237 (1981).
 - ¹³ C.U. Segre, M. Croff, J.A. Hodges, V. Murgai, L.C. Gupta, and R.D. Parks, Phys. Rev. Lett. 49, 1947 (1982).
 - ¹⁴ G. Wortmann, I. Nowik, B. Perscheid, G. Kaindl, and I. Felner, Phys. Rev. B 43, 5261 (1991).
 - ¹⁵ H. Wada et al., J. Phys.: Condens. Matter 9, 7913 (1997).
 - ¹⁶ H. Wada, M.F. Hundley, R. Movshovich, and J.D. Thompson, Phys. Rev. B 59, 1141 (1999).
 - ¹⁷ H. Wada et al., J. Phys. Soc. Jpn. 68, 950 (1999).
 - ¹⁸ O. Gunnarsson and K. Schonhammer, Phys. Rev. B 28, 4315 (1983).
 - ¹⁹ J.C. Fuggle, F.U. Hillebrecht, J.-M. Esteve, R.C. Karnatak, O. Gunnarsson, and K. Schonhammer Phys. Rev. B 27, 4637-4643 (1983).
 - ²⁰ J.W. Allen, in Synchrotron Radiation Research: Advances in Surface and Interface Science, ed. R.Z. Bachrach, pg. 253 (Plenum, New York, 1992).
 - ²¹ F. de Groot, Chemical Reviews 101, 1779 (2001).
 - ²² F. Reinert et al., Phys. Rev. B 58, 12808 (1998); S. Schmidt, S. Hüfner, F. Reinert, and W. Asmus Phys. Rev. B 71, 195110 (2005).
 - ²³ D.P. Moore et al., Phys. Rev. B 62, 16492 (2000).
 - ²⁴ P.A. Rayjada et al., Phys. Rev. B 70, 235105 (2004).
 - ²⁵ L.B. Raicovich, N.B. Brookes, C.Dallera, M. Salvietti, and G.L. O'Leary, Phys. Rev. B 56, 15047 (1997).
 - ²⁶ K. Kobayashi et al., Appl. Phys. Lett. 83, 1005 (2003).
 - ²⁷ Y. Takata et al., Appl. Phys. Lett. 84, 4310 (2004).
 - ²⁸ W. D. Nube, T. Eickho, H. Schulte-Schrepping, and J. Heuer, AIP Conference Proceedings 705, 1130 (2004).
 - ²⁹ C.Dallera et al., Appl. Phys. Lett. 85, 4532 (2004).
 - ³⁰ P. Torelli et al., Rev. Sci. Instrum. 76, 023909 (2005).
 - ³¹ H. Sato et al., Phys. Rev. Lett. 93, 246404 (2004).
 - ³² A. Sekiyama, T. Iwasaki, K. Matsuda, Y. Saitoh, Y. Onuki, and S. Suga, Nature 403, 396 (2000).
 - ³³ E.-J. Cho et al., Phys. Rev. B 67, 155107 (2003).
 - ³⁴ R. Cowan, The Theory of Atomic Structure and Spectra (University of California Press, Berkeley, 1981).
 - ³⁵ K. Yamamoto et al., J. Phys. Soc. Jpn. 73, 2616 (2004).
 - ³⁶ T. Kinoshita et al., J. Phys. Soc. Jpn. 71, 148 (2002).
 - ³⁷ N. Martensson, B. Reihl, W.-D. Schneider, V. Murgai, L.C. Gupta, and R.D. Parks, Phys. Rev. B, 25, R1446 (1982).
 - ³⁸ W. Lenth, F. Lutz, J. Barth, G. Kalkonen, and C. Kunz, Phys. Rev. Lett. 41, 1185 (1978).
 - ³⁹ F. Gerken, J. Barth, and C. Kunz, Phys. Rev. Lett. 47, 993 (1981).