## D istortion-D ependent R am an Spectra and M ode M ixing in RM nO $_3$ Perovskites

M.N. Iliev<sup>1</sup>, M.V. Abrashev<sup>2</sup>, J. Laverdiere<sup>3</sup>, S. Jandl<sup>3</sup>, M.M. Gospodinov<sup>4</sup>, Y.-Q. W ang<sup>1</sup>, and Y.-Y. Sun<sup>1</sup>

<sup>1</sup> Texas Center for Superconductivity and Department of Physics, University of Houston, Texas 77204-5002, USA

<sup>2</sup>Faculty of Physics, University of So a, 1164 So a, Bulgaria

<sup>3</sup>Departem ent de Physique, Universite de Sherbrooke, Sherbrooke, Canada J1K 2R1 and

<sup>4</sup> Institute of Solid State Physics, Bulgarian Academy of Sciences, 1184 So a, Bulgaria

(D ated: A pril 14, 2024)

The polarized R am an spectra of orthorhom bic RM nO 3 series  $(R = La_P r_N d_S m_E u_G d_T b_D y_H o_Y)$  were studied at room temperature. The variation of phonon frequencies with R ionic radius  $r_R$  as a whole con rms the commonly accepted Raman line assignments with two noticeable exceptions: (1) with decreasing  $r_R$  the stretching A<sub>q</sub> (1) and bending  $A_{\alpha}$  (3) modes strongly mix for R = Sm to Tb, while for further decrease or  $r_{R}$  (R = D y, H o, Y) the  $A_{q}$  (3) mode is observed at higher frequency than  $A_{q}$  (1) mode; (2) similar distortion-dependent m ode m ixing takes place for the rotational  $A_q$  (2) and O1(x)  $A_q$  (7)] m odes. The m ode m ixing is particularly strong for the RM nO  $_3$  compounds with  $r_R$  values close to the transition from A-type to incommensurate sinusoidal antiferrom agnetic ordering at low temperatures. The frequency of rotational  $A_q$  (2) and  $A_q$  (4) modes scales to the angles of M nO  $_6$  [101] and [010] rotations, respectively, and could be used as a measure of their value.

PACS num bers: 78.30.-j, 63.20 D j, 75.47 Lx

#### I. IN TRODUCTION

Until recently the RM nO<sub>3</sub> perovskites (R = rareearth, Y, Sc) have been object of research mainly as parent materials of mixed valence manganites exhibiting colossalm agnetoresistivity (CMR).[1, 2, 3, 4] In the past few years, how ever, there is an increased interest in the com plex relationships among the lattice distortions, magnetism, dielectric and transport properties of undoped RM nO<sub>3</sub>. [5, 6, 7, 8, 9, 10] In particular, it has been found that with decreasing radius  $(r_R)$  of R (R = La toEu) the transition temperature  $T_N$  to A-type antiferromagnetic (A-AFM) structure also decreases. W ith further decrease of  $r_R$  (R = G d to H o) the magnetic structure below T<sub>N</sub> changes from A-AFM to incommensurate antiferrom agnetic one (IC - A FM ) with sine-wave ordering of the M n m om ents with tem perature-dependent wave vector  $\tilde{K}_s = (k_s; 0; 0)$  along the a-axis (in P nm a notations). At  $T_{lock} < T_N$  an incommensurate-to-commensurate (IC -CM ) transition takes place and  $k_{\rm s}$  locks at a value < 0:4.[8] A transition to com m ensurate E -type antiferrom agnetic structure (E-AFM ,  $k_s = 0.5$ ) has been observed below  $T_{lock} = 26K$  only for HoM nO<sub>3</sub>. [6] For TbM nO<sub>3</sub> and DyMnO3 it was found that the IC-CM transition is accompanied by a ferroelectric transition, associated with lattice modulation in the CM phase. [7, 9]. Large magnetodielectric e ects have also been reported for orthorhom bic HoM nO  $_3$ , and YM nO  $_3$ .[11]

A lthough the role of lattice distortions in the interplay of magnetic, dielectric and transport properties of RM nO<sub>3</sub> perovskites is widely recognized, there are relatively few studies on the variations of these distortions with R .[10, 12] R am an spectroscopy can provide signicant additional information on the distortions and their variations with both R and temperature. The R am an active modes in RM nO<sub>3</sub> (7A<sub>g</sub> + 5B<sub>1g</sub> + 7B<sub>2g</sub> + 5B<sub>3g</sub>)

are activated exclusively due to the deviations from ideal perovskite structure and in principle the activation of each Raman line can with de nite certainty be assigned to the value of one or two types of basic distortion (rotations of M nO 6 octahedra around [101] or [010] directions, Jahn-Teller distortion, or shift of R atom s).[13] The rst assignment of the Raman lines in the spectra of RM nO<sub>3</sub> to de nite atom ic vibrations has been done by comparison of experim entally obtained Ram an phonon frequencies of LaM nO  $_3$  and YM nO  $_3$  with those predicted by lattice dynam ical calculations (LDC). [14] Although for most of the experim entally observed Ram an lines the frequencies have been in good agreem ent with those predicted by LDC, som e uncertainties about the phonon line assignm ent rem ained. Indeed, som e R am an lines of same symmetry have close frequencies and due to the approximations of the LDC model one reasonably expects som e di erence between m easured and calculated values. The assignment of the two  $A_{g}$  R am an lines between 450 and 520 cm  $^{1}$  , where are the A  $_{\rm q}$  m odes corresponding to anti-stretching (AS) and bendings (B) of M nO<sub>6</sub> octahedra, has been challenged by M artin-C arron et al.[15] in a R am an study of several RM nO 3 perovskites  $(R = La_{P}r_{N}Nd_{T}b_{H}o_{E}r_{Y})$ . Based on the fact that the Mn-O distances exhibit only small changes within the RM nO<sub>3</sub> series, they assigned the AS band observed near 480-490 cm  $^1$  to the anti-stretching mode, while the 450 cm  $^{1}$  in LaM nO  $_{3}$  to B band which shifts from 530 cm  $^{1}$  in ErM nO  $_{3}$  has been assigned to bending mode(s). An obvious problem of this re-assignment is the "crossing" of the AS and B modes, which are of the

In this work we present results of a detailed study of polarized Raman spectra of RM nO<sub>3</sub> ( $R = La_P r_N d_r Sm , Eu, G d_r Tb_P y_H o_r Y$ ) at room temperature. The comparison of variations with R of phonon

sam e  $A_{q}$  sym m etry.

frequencies and relative intensities of most pronounced  $A_g$  and  $B_{2g}$  modes shows that some corrections of previous phonon mode assignment are needed. The strong mixing and spectral weight transfer between  $A_g$  anti-stretching (AS) and bending (B) modes in the 500 cm<sup>-1</sup> region, most clearly observed for R = Eu,Gd and Tb, correlates with changes of magnetic structure. Similar distortion-dependent mode mixing is observed for the rotational  $A_g$  (2) and O1(x)  $A_g$  (7)] modes.

## II. SAMPLES AND EXPERIMENTAL

P rM nO  $_3$  , N dM nO  $_3$  and Sm M nO  $_3$  sam ples were grow n by the oating zone method described in Ref.[16]. Single crystals of D yM nO  $_3$  of average sizes 1 2 m m <sup>3</sup> 1 were prepared following a procedure to be described elsewhere [17]. Orthorhom bic YM nO $_3$ , HoM nO $_3$  sam ples were prepared under pressure as described in Ref.[11]. For R = Eu,Gd,Tb the precursor powders were heated at 1130-1160 C in O $_2$  for 24 hours. A lthough the sam ples (except for DyM nO<sub>3</sub>) were polycrystalline, the size of the constituting m icrocrystals was larger than the laser spot. It was possible to select m icrocrystals with crystallographic orientation such that the spectra in paralleland crossed scattering con gurations were dom inated by Ag or B<sub>2g</sub> contributions, respectively. For exact separation of the  $A_{\alpha}$  and  $B_{2\alpha}$  spectra the SPECTRA SUBTRACT program of the GRAMSAI software package was used.

The Ram an spectra were measured at room temperature in backscattering con guration using two di erent spectrom eters: Labram -800 and Jobin Y von HR 640, both equipped with microscope and liquid-nitrogencooled CCD detector. The spectra obtained with 514.5 nm (Ar<sup>+</sup>) and 632.8 nm (He-Ne) were practically identical.

#### III. RESULTS AND DISCUSSION

The A<sub>g</sub> and B<sub>2g</sub> spectra of RM nO<sub>3</sub> as obtained at room temperature are shown in Figure 1. W ith same scattering conguration the absolute value of Raman intensities were increasing with decreasing R ionic radius ( $r_R$ ). For better comparison the A<sub>g</sub> and B<sub>2g</sub> spectra were normalized to the integrated intensities of A<sub>g</sub> (1) + A<sub>g</sub> (3) and B<sub>2g</sub> (1) lines, respectively. At least we A<sub>g</sub> and four B<sub>2g</sub> lines are clearly pronounced and the variations of their parameters with R can be followed with a good accuracy. The phonon line frequencies are given in Table I.

The correlation between structural and physical param eters of RM nO<sub>3</sub> perovskites m ay be described as a function of di erent param eters, such as the ionic radius  $r_{\rm R}$ , tolerance factor t or the averaged tilt angle  $\,$ . The relation between these param eters, how ever, is close to linear[10] and any one of them can be used for characterization of phonon m ode frequency variations. Figure 2 shows the dependence of R am an phonon frequencies



FIG.1:  $A_g$  and  $B_{2g}$  Ram an spectra of RM nO<sub>3</sub> at room temperature. The phonon mode notations correspond to those of Refs.[13, 14]. The  $A_g$  and  $B_{2g}$  spectra are normalized to the integrated intensity of  $A_g$  (1) +  $A_g$  (3) and  $B_{2g}$  (1) lines, respectively.



FIG.2: Variations of phonon m ode frequencies with R ionic radius  $r_{\!R}$  .

TABLE I: Frequencies (in cm  $^{1}$ ) of the experimentally observed A<sub>g</sub> and B<sub>2g</sub> Ram an lines of RM nO<sub>3</sub> at room temperature.

M ode	M ain atom ic m otions	La	Ρr	Nd	Sm	Εu	Gd	Τb	Dу	Ηо	Y	Basic distortion	
A <sub>g</sub> (1) ! A <sub>g</sub> (3	) 02 anti-stretchng ! M n0 <sub>6</sub> bending	490.7	491.2	491.7	496.1	501.0	506.0	509.0	513.4	520.0	520.6	JT,[010]!	[101]
A <sub>g</sub> (3) ! A <sub>g</sub> (1	) M nO 6 bending ! 02 anti-stretching	444.8	461.8	465.6	476.7	479.0	486.4	488.8	492.1	498.9	496.7	[101]! JT	,[010]
A <sub>g</sub> (4)	out-of-phase M nO 6 x-rotations	283.6	323.7	331.8	352.9	360.8	370.5	378,2	386.0	395.9	398.1	[101]	
A <sub>g</sub> (2) ! A <sub>g</sub> (7	) in-phase M nO $_6$ y-rotations! 01(x)	256.8					309.8	314.6	319.5	323.8	325.3	[010]! R	-shift
Ag(7)! Ag(2	) 01(x) ! in-phase M n0 <sub>6</sub> y-rotations	198.1	231.8	245.0	266.1		276.1	280.5		287.8	289.4	R-shift !	[010]
B <sub>2g</sub> (1)	in-plane 0.2 stretching	612.3	606.7	606,2	606.6	609.5	611.7	612,2	613.5	615.0	617.3	JT	
B <sub>2g</sub> (2)	in-phase 0 2 "scissors'-like	482.5	495.7	502.6	513.1	518.4	525.0	528.4	533.6	537.0	539.2	[010]	
B <sub>2g</sub> (3)	out-of-phase M nO 6 bending	430.0	444.8	449.1	460.9	464.6	468.9	473.7	477.5	481.1	481.5	[101]	
B <sub>2g</sub> (7)	O1(z)	309.7	311.5	313,2		323.8	329.2	330.9	335.6		342.0	R-shift	

on  $r_R$ . M ost R am an frequencies  $!_i$  exhibit nearly linear increase with  $r_R$ , but the slope  $!_i = r_R$  depends mainly on the type of the mode (stretching,bending or rotational) as well on the type of distortion that has activated the corresponding mode in the R am an spectrum (M nO  $_6$  rotations around [010]<sub>c</sub> or [101]<sub>c</sub> cubic axes, Janh-Teller(JT) distortion, and R-shift).[13]

#### A . Basic distortions and R am an m odes in RM nO $_{\rm 3}$

In the ideal cubic ABO3 perovskite (space group P m 3m, Z = 1) all atom s are at centrosym m etrical sites with xed coordinates and there are no Ram an allowed modes. The structure of stoichiom etric RM nO<sub>3</sub>, described at room temperature by the Pnm a space group (Z = 4), can be considered as orthorhom bically distorted superstructure of the ideal perovskite with [100], [010], and [001], directions coinciding with the [101], [010], and [101] directions of the parent cubic structure. In the P nm a structure the atom s occupy four non-equivalent atom ic sites (R,Mn,O1,O2), of them only the Mn site is a center of sym m etry. From sym m etry considerations only 5 of the 12 atom ic coordinates are xed [R-1,M n-3,01-1], while the remaining 7 variable coordinates can be considered as the lattice degrees of freedom producing the above m entioned lattice distortion. These distortions give rise to 24 (7A  $_{g}$  + 5B  $_{1g}$  + 7B  $_{2g}$  + 5B  $_{3g}$ ) R am an-allow ed phonon modes, which in turn can be assigned to their distortions of origin ([010]-, [101]-rotation, JT, or R-shift). W ith decreasing  $r_R$  the distortions increase and most of the bond lengths shorten, which reasonably results in twofold e ect: enhanced R am an intensity and hardening of Ram an frequencies.

At rst sight the [010] and [101] rotations can directly be obtained from the 0.2-M n-0.2 and 0.1-M n-0.1 angles, which practically have equal values.[10, 12] As shown by Abrashev et al.[13], however, even in the case of equal 0-M n-0 angles, the [010] and [101] rotation angles will be di erent. They are related to the deviations ( $x_i; y_i; z_i$ , i-atom ic index) of P nm a atom ic coordinates from those in a hypothetical undistorted perovskite structure as

$$[010] = \arctan(2jx_{02} - z_{02})$$

$$[101] = \arctan(2^{5-2} \mathbf{j}_{02}) \quad \arctan(2^{3-2} \mathbf{j}_{01})$$

The so de ned atom ic deviations can also be used to describe the other two basic distortions, namely, the JT distortion, characterized by the relative di erence  $D_{JT} = j d_{M n \ 0.2} \neq d_{M n \ 0.2} > of the two pairs of M n-0.2 distances, and the shift <math>D_R(x)$  of the R-atom s in x-direction from their positions in an undistorted perovskite. In the case of sm all distortions:

$$D_{JT} = 2jx_{02} + z_{02}j$$
  
 $D_{R(x)} = 2x_{R}$ 

The variations of the basic distortions, calculated using the available data for atom ic positions in RM nO  $_3$  [10, 12] are given in Table II.

### B. Pure and m ixed stretching (Jahn-Teller) m odes

The frequency of a mode involving mainly stretching vibrations of 0.2 atoms in the xz planes is determined by the Mn-O.2 distances. The short and long Mn-O.2 bond lengths vary with  $r_R$  within 0.5% and 1.1%, respectively [10, 12] and therefore one expects that  $!_{stretch} / d_{Mn \ O.2}^{3=2}$  will change by no more than 1.5%. As illustrated in Figure 3, this is exactly the case for the  $B_{2g}$  (1) mode at 606-617 cm<sup>-1</sup>, which has been assigned to the in-phase O.2 stretching.[14]. The minimum of  $B_{2g}$  (1) frequency near R=N d,Sm re exts the fact that for these R's the averaged Mn-O distance has a maximum.

Based on the same bond-length considerations, one could expect that the R am an line of  $A_g$  sym m etry at 490-495 cm<sup>-1</sup>, corresponding to the in-phase anti-stretching vibrations of 0.2 in the xz plane, [14] would behave in a similar way and its frequency would remain nearly constant through the whole RM nO<sub>3</sub> series. As seen from Fig.4, this is obviously not the case. The data of Figs. 1 and 4 clearly show a classic example for m ixing of m odes of same sym m etries and close frequencies. For large  $r_R$  ( $R = La_r P r_N d$ ) the lines at 490-492 and 445-465 cm<sup>-1</sup> can be considered as pure stretching ( $A_q$  (1))

TABLE II: Variations with R of the four basic distortions of the P nm a structure. The data for Sm M nO $_3$  and G dM nO $_3$  have been obtained by the t of corresponding experimental data for rest R M nO $_3$  com pounds.[10, 12]

D istortion	M easure	La	Рr	Nd	Sm	Eu	Gd	Тb	Dу	Но	Y
[010]	<sub>[010]</sub> [deg]	9.23	11.43	12.11	13.07	13.35	13.60	13.81	14.00	14.16	14.11
[101]	<sub>[101]</sub> [deg]	12.17	13.53	14.08	15.10	15.49	15.86	16.24	16.59	16.90	16.82
JT	jd <sub>M n 02</sub> j= < d <sub>M n 02</sub> >	0.0647	0.0665	0.0652	0.0612	0.0597	0.0582	0.0574	0.0571	0.0575	0.0573
R-shift	2x <sub>R</sub>	0.097	0.129	0.138	0.151	0.155	0.159	0.166	0.167	0.169	0.168
<mn-02> Refs.[10]</mn-02>	A	2.044	2.063	2.067		2.066			2.065		
<mn-02> Refs.[12]</mn-02>	A	2.043	2.059	2.062				2.063	2.063	2.064	2.052

and bending (A<sub>g</sub> (3)) m odes, respectively. W ith decreasing  $r_R$  the A<sub>g</sub> (3) frequency increases and approaches that of A<sub>g</sub> (1), resulting in strong m ode m ixing evidenced by m ode repulsion and transfer of intensity. The m ixing is m ost strongly pronounced for R = Sm to Tb where the twom odes are of comparable intensities and involve both stretching and bending atom icm otions. W ith further decrease of  $r_R$  (R = Dy,Ho,Y) the m odes become less m ixed but now the higherm ode is dom inated by M nO<sub>6</sub> bending [A<sub>g</sub> (3)-type] m otions and the lower one is A<sub>g</sub> (1)-type.

Two phonon modes of same symmetries and close frequencies can be considered as coupled quantum oscillators. In a good approximation their frequencies are given by

$$!_{1,2} = \frac{!^{0} + !^{0}}{2} \qquad \frac{r}{(!^{0} - !^{0})^{2}} + \frac{V^{2}}{4}$$

where  $!^{0}$  and  $!^{0}$  are the mode frequencies without coupling and V is the coupling constant. It is reasonable to assume that without coupling the  $A_q$  (1) and  $A_q$  (3) mode frequencies would depend on  $r_R$  in the same way as the  $B_{2q}$  (1) and  $B_{3q}$  (3) modes, respectively, as both m odes of the  $A_q$  (1)- $B_{2q}$  (1) (stretching) and  $A_q$  (3)- $B_{2q}$  (3) (bending) pairs are activated by the same basic distortion and have sim ilar shape. Therefore, as shown with dash lines in F ig.4, the  $!^{0}(r_{R})$  dependence for the uncoupled  $A_{\alpha}$  (1) mode can be approximated by scaling the experim ental  $B_{2q}$  values, whereas that of uncoupled  $A_q$  (3) m ode [!<sup>(0)</sup>(r<sub>R</sub>)], like in the case of B<sub>2g</sub>(3), can be approxim ated by a linear dependence. At the crossing point 1:125 A),  $!^{0}(1:125) = !^{0}(1:125)$ , which gives (r<sub>R</sub>  $V = !_1 (1:125) !_2 (1:125) 20 \text{ cm}^{-1}$ .

# C. Pure and m ixed rotational ("soft") m odes

The frequency vs  $_{[101]}$  dependence for the A<sub>g</sub>(4) m ode involving mainly M nO<sub>6</sub> x-rotations, shown in Fig.4 with full circles, is close to proportionality. Expectedly, this mode exhibits "soft mode" behavior with !()! 0 for ! 0, the slope of ! A<sub>g</sub>(4) ( $_{[101]}$ ) being 23.5 cm <sup>1</sup>/deg. Calculations of lattice dynamics for the two end compounds LaM nO<sub>3</sub> and YM nO<sub>3</sub> have shown that the two weak A<sub>g</sub> modes at low er frequencies are strongly mixed and involve both in-phase M nO<sub>6</sub> yrotations A<sub>g</sub>(2)] and O1(x)-motions A<sub>g</sub>(7)]. The higher



FIG.3: Variations with  $r_R$  of the frequencies of B<sub>2g</sub>(1), A<sub>g</sub>(3) and A<sub>g</sub>(1) modes. The dashed curves show the expected  $!^{0}(r_R)$  and  $!^{0}(r_R)$  dependences for pure stretching and bending modes.

of these m odes is  $A_g$  (7)-like in LaM nO<sub>3</sub>, but  $A_g$  (2)-like in YM nO<sub>3</sub>. A ssum ing that the higher m ode remains  $A_g$  (2)-like in other compounds with small  $r_R$  (H oM nO<sub>3</sub>, D yM nO<sub>3</sub>, TbM nO<sub>3</sub>, G dM nO<sub>3</sub>), one nds that the frequency vs <sub>[010]</sub> dependence for the partly m ixed  $A_g$  (2) m ode (shown with empty squares) is practically the same as that for the pure  $A_g$  (4) m ode. Interestingly, the frequencies of [111]-rotationalm odes of structurally di erent rhom bohedral LaM nO<sub>3</sub> and LaA D<sub>3</sub> to these dependences, which is an indication for a quite general relationship between the angle of rotation and frequency of the rotational "soft" m odes in perovskitelike com pounds, independent on the direction of the rotational axis.

## D. R-shift modes

The weak  $A_g$  (7) and  $B_{2g}$  (7) involvem ainly 01m otions in the xz plane, activated in the Raman spectrum due to the shift of R<sup>3+</sup> ions from their positions in an ideal



FIG. 4: Variations with the tilt angle  $_{[101]}$  or  $_{[010]}$  of the frequencies of  $A_g$  (4) and  $A_g$  (2) modes, involving mainly M nO  $_6$  rotations.

perovskite. It follows from Fig2, Table I and Table II that in the case of pure R-shift mode  $[B_{2g}(7)]$ , despite of strongly increasing R-shift distortion between R = La and Y, the corresponding increase of mode frequency is

- [1] R M. Kusters, J. Singleton, D A. Keen, R. McG reevy, and W. Hayes, Physica B 155, 362 (1989).
- [2] R. von Helmolt, J.W ecker, B.Holzapfel, L.Schultz, and K.Samwer, Phys. Rev. Lett. 71, 2331 (1993).
- [3] S.Jin, T.H.Tiefel, M.McComack, R.A.Fastnacht, R. Ramesh, and L.H.Chen, Science 64,413 (1994).
- [4] Y. Tokura, A. Urushibara, Y. Moritomo, T. Arima, A. Asamitsu, G. Kido, and N. Furukawa, Science 63, 3931 (1994).
- [5] A.Munoz, M.T.Casais, J.A.Alonso, M.J.Martinez-Lope, J.L.Martinez, and M.T.Fernandez-Diaz, Inorg. Chem. 40, 1020 (2001).
- [6] A. Munoz, J. A. Alonso, M. T. Casais, M. J. Martinez-Lope, J. L. Martinez, and M. T. Fernandez-Diaz, J. Phys.: Condens. Matter 14, 3285 (2002).
- [7] T.K im ura, T.G oto, H.Shintani, K.Ishizaka, T.A rim a, and Y.Tokura, Nature 426, 55 (2003).
- [8] T. Kimura, S. Ishihara, H. Shintani, T. Arima, K. T. Takahashi, K. Ishizaka, and Y. Tokura, Phys. Rev. B 68, 060403 (R) (2003).
- [9] T.Goto, T.Kimura, G.Lawes, A.P.Ramirez, and Y.

relatively modest (see Table II). It is plausible to expect similar dependence on  $r_R$  for the  $A_g$  (7) mode, which explains the above discussed observation that the frequency vs  $r_R$  dependence of the mixed  $A_g$  (2) +  $A_g$  (7) modes is governed mainly by their rotational  $[A_g$  (2)] component.

### IV. CONCLUSION

The com parative study of polarized Ram an spectra of orthorhom bic RM nO 3 series  $(R = La_{P}r_{N}Nd_{r}Sm_{E}u_{r}Gd_{r}Tb_{r}Dy_{r}Ho_{r}Y)$ show s that the variations of lattice distortions with r<sub>R</sub> a ect signi cantly both the phonon frequencies and the shape of some Raman phonon modes. The strong mixing of phonon modes involving in-plane and out-of-plane oxygen motions may become a clue for understanding the change with  $r_R$  of magnetic ordering at low tem peratures. The established proportionality between the frequency of a rotational mode and the angle of corresponding rotational distortion may be used for m aterial characterization.

## A cknow ledgm ents

This work is supported in part by the State of Texas through the Texas C enter for Superconductivity and the N ational Science and Engineering R essarch C ouncil of C anada. The work of M M G is supported by the Bulgarian N ational R essarch Fund (P roject F-1207).

Tokura, Phys. Rev. Lett. 92, 257201 (2004).

- [10] B.Dabrowski, S.Kolesnik, A.Baszczuk, O.Chmaissen, T.Maxwell, and J.Mais, J.Solid State Chem. 178, 629 (2005).
- [11] B.Lorenz, Y.Q.W ang, Y.Y.Sun, and C.W.Chu, Phys. Rev.B 70, 212412 (2004).
- [12] J. A. Alonso, M. J. Martinez-Lope, M. T. Casais, and M. T. Fernandez-Diaz, Inorg. Chem 39, 917 (2000).
- [13] M. V. Abrashev, J. Backstrom, L. Borjesson, V.N.Popov, R.A. Chakalov, N. Kolev, R.-L. Meng, and M.N. Iliev, Phys. Rev. B 65, 184301 (2002).
- [14] M.N.Iliev, M.V.Abrashev, H.G.Lee, V.N.Popov, Y. Y.Sun, C.Thom sen, R.L.Meng, and C.W.Chu, Phys. Rev.B 57, 2872 (1998).
- [15] L. Martin-Carron, A. de Andres, M. J. Martinez-Lope, M. T. Casais, and J. A. Alonso, Phys. Rev. B 66, 174303 (2002).
- [16] A.M. Balbashov, S.G. Karabashev, Y.A.M. Mukovskii, and S.A. Zverkov, J.Cryst.Growth 167, 365 (1996).
- [17] M.M.Gospodinov et al, unpublished results.