Upper critical field H_{c2} in $PrOs_4Sb_{12}$

D. PARKER^{1,2}, K. MAKI^{1,2} and H. WON^{1,3}

¹ Max-Planck Institute for the Physics of Complex Systems, Nöthnitzer Str. 38 D-01187, Dresden, Germany

² Department of Physics and Astronomy, University of Southern California, Los Angeles, CA 90089-0484 USA

³ Department of Physics, Hallym University, Chuncheon 200-702, South Korea

PACS. 74.70.Tx – Heavy-fermion superconductors. PACS. 74.25.Qt – Vortex lattices, flux pinning, flux creep. PACS. 74.20.Rp – Pairing symmetries (other than s-wave).

Abstract. – We study the upper critical field of the A and B phases in the triplet superconductor $PrOs_4Sb_{12}$ within the p+h-wave superconductivity proposed recently for this material. The present result is compared with $H_{c2}(t)$ and $H^*(t)$, the boundary between the A and B phase in $PrOs_4Sb_{12}$, reported earlier and with more recent data of $H_{c2}(t)$ for the single phase crystal. We find $H_{c2}(t)$'s for both the two phase crystal and the single phase crystal are described by the model for the A phase. From this fitting one can deduce the Fermi velocity as $v = 2.5 \times 10^6$ cm/s. On the other hand $H_{c2}(t)$ for the B phase is found to be somewhat smaller than $H^*(t)$, which is rather puzzling.

Introduction. – Superconductivity in the filled skutterudite $PrOs_4Sb_{12}$ discovered in 2002 by Bauer et al [1–3] has generated a big sensation. First the presence of at least two distinct phases (A and B phases) in a magnetic field, with both gap functions having point nodes is surprising. Further these superconductors belong to the triplet pairing with broken chiral symmetry [4–6]. However, the exact location of the A-B phase boundary is still controversial [7]. More recently Measson et al [8,9] have discovered many $PrOs_4Sb_{12}$ crystals with only a single phase. Therefore the nature of this single phase has to be addressed. In this paper we assume that the gap functions of the A and B phases of $PrOs_4Sb_{12}$ are given as [6]

$$\mathbf{\Delta}_{A}(\mathbf{k}) = \mathbf{d}_{\mathbf{k}} e^{\pm i\phi_{i}} \frac{3}{2} (1 - \hat{k}_{x}^{4} - \hat{k}_{y}^{4} - \hat{k}_{z}^{4})).$$
(1)

$$\mathbf{\Delta}_B(\mathbf{k}) = \mathbf{d}_{\mathbf{B}} e^{\pm i\phi_3} (1 - \hat{k}_z^4) \tag{2}$$

Here $e^{\pm i\phi_i}$ is one of $e^{i\phi_1} = (\hat{k}_y + i\hat{k}_z)/\sqrt{\hat{k}_y^2 + \hat{k}_z^2}$, $e^{i\phi_2} = (\hat{k}_z + i\hat{k}_x)/\sqrt{\hat{k}_z^2 + \hat{k}_x^2}$, $e^{i\phi_3} = (\hat{k}_x + i\hat{k}_y)/\sqrt{\hat{k}_x^2 + \hat{k}_y^2}$. The factor of 3/2 ensures proper normalization of the angular dependence of the order parameter. In Eq.(2) the nodal direction is chosen to be parallel to (001). We note that $|\Delta_A(\mathbf{k})|$ retains the cubic symmetry while $|\Delta_B(\mathbf{k})|$ has only the axial symmetry. In the absence of an external perturbation, we assume that the nodal direction of $|\Delta_B(\mathbf{k})|$ is

EUROPHYSICS LETTERS

parallel to \mathbf{H} , the magnetic field, when \mathbf{H} is parallel to one of the crystal axes. Although many other gap functions for $\text{PrOs}_4\text{Sb}_{12}$ have been proposed so far, none can describe the thermal conductivity data of Izawa et al as discussed in [4,6]. For a discussion of our methodology for determining the gap functions of nodal superconductors please see Ref. [10].

In the following we study the upper critical field $H_{c2}(T)$ of the A and B phases of $PrOs_4Sb_{12}$ in terms of the linearized gap equation [11]. For unconventional superconductors Gor'kov's original formulation must be modified as shown by Luk'yanchuck and Mineev [12]. The upper critical field thus obtained for the A phase describes consistently H_{c2} of the A phase as obtained by Measson et al [7]. On the other hand $H^*(T)$ is somewhat larger than $H_{c2}(T)$ in the B phase at low temperatures.

Of course $H^*(T)$ is not exactly equal to $H_{c2}(T)$ of the B phase. But it is rather puzzling that $H^*(T)$ is larger than the predicted $H_{c2}(T)$ of the B phase. Meanwhile, some of the single crystals exhibit only a single phase transition. Measson has reported $H_{c2}(T)$ of the single phase system at SCES05 in Vienna [8]. The observed $H_{c2}(T)$ is practically the same as $H^*(T)$, and consistent with the one for the A phase. This, perhaps, implies that the A phase is more robust than the B phase. Also, perhaps $H^*(T)$ is associated with the A phase.

From the spatial configuration of $\Delta(\mathbf{r}, \mathbf{k})$ at $\mathrm{H}=\mathrm{H}_{c2}(\mathrm{T})$, we can deduce the stable vortex lattice structure as in [13, 14]. Except in the immediate vicinity of the superconducting transitions $(T < 0.95T_c)$ we find the square vortex lattice is more stable than the hexagonal one for $\mathbf{H} \parallel [001]$ or any of the cubic axes, while the hexagonal lattice is more stable for $\mathbf{H} \parallel [111]$ for example. Recently the vortex lattice in $\mathrm{PrOs}_4\mathrm{Sb}_{12}$ was studied via small angle neutron scattering (SANS) by Huxley et al [15]. They find only a distorted hexagonal lattice at T=100 mK and H =0.1 T, most likely due to poor sample quality.

Upper critical field. – As in the chiral p-wave superconductor the upper critical field is determined from the linearized gap equation for $\Delta(\mathbf{r}, \mathbf{k})$:

$$\Delta(\mathbf{r}, \mathbf{k}) \sim (e^{i\phi} + Ce^{-i\phi} (a^{\dagger})^2) |0\rangle$$
(3)

where $|0\rangle$ is the Abrikosov state [16]:

$$|0> = \sum_{n} c_{n} e^{-eBx^{2} - nk(x+iy) - \frac{(kn)^{2}}{4eB}}$$
(4)

and $a^{\dagger} = \frac{1}{\sqrt{2eB}}(-i\partial_x - \partial_y + 2ieBx)$ is the raising operator and we have assumed $\mathbf{H} \parallel \mathbf{c}$. Then following Refs. [13, 14] the upper critical field is determined by

$$-\ln t = \int_0^\infty \frac{du}{\sinh u} (1 - \langle f^2 \rangle^{-1} \langle f^2 e^{-\rho u^2 (1 - z^2)} \times (1 + 2C\rho u^2 (1 - z^2)) \rangle)$$
(5)

$$-C\ln t = \int_0^\infty \frac{du}{\sinh u} (1 - \langle f^2 \rangle^{-1} \langle f^2 e^{-\rho u^2 (1 - z^2)} \times (\rho u^2 (1 - z^2) + C(1 - 4\rho u^2 (1 - z^2) + 2\rho^2 u^4 (1 - z^2)^2))))$$
(6)

where $t = \frac{T}{T_c}$, $\rho = \frac{v^2 e H_{c2}(t)}{2(2\pi T)^2}$, where v is the Fermi velocity and

$$f = 1 - \cos^4 \theta - \sin^4 \theta (\sin^4 \phi + \cos^4 \phi), \quad (A - \text{phase}) \tag{7}$$

$$= 1 - \cos^4 \theta, \quad (B - phase) \tag{8}$$

and $\langle \ldots \rangle$ means $\int d\Omega/(4\pi) \ldots$ Also $\langle f^2 \rangle = \frac{4}{21}$ and $\frac{32}{45}$ for the A and B phases respectively. Then for the A phase we obtain the following asymptotics for $t \simeq 1$:

$$-\ln t = \frac{3\zeta(3)}{7}\rho(1-2C)$$
 and (9)

$$-C\ln t = \frac{3\zeta(3)}{7}\rho(-1+5C)$$
(10)

where $\zeta(3) = 1.202...$ From this we find $C = \sqrt{\frac{3}{2}} - 1$ and $\rho = \frac{3}{7\zeta(3)}(1 + \sqrt{\frac{2}{3}})(-\ln t) = 0.5942(-\ln t)$. On the other hand, for t=0 we find

$$0 = \ln(4\gamma\rho_0) + \langle f^2 \rangle^{-1} \langle f^2 \ln(1-z^2) \rangle - 2C \text{ and}$$
(11)

$$0 = C(\ln(4\gamma\rho_0) + \langle f^2 \rangle^{-1} \langle f^2 \ln(1-z^2) + 2 \rangle - 1$$
(12)

where $\gamma = 1.780...$ is the Euler constant and $\langle f^2 \rangle^{-1} \langle f^2 \ln(1-z^2) \rangle = -0.40104$. These yield $C = \frac{1}{2}(\sqrt{3}-1)$ and

$$\rho_0 \equiv \frac{v^2 e H_{c2}(0)}{2(2\pi T_c)^2} = \frac{1}{4\gamma} \exp[1.2295] = 0.4795$$
(13)

From this we obtain

$$h(0) = \frac{H_{c2}(0)}{-\frac{dH_{c2}(t)}{dt}|_{t=1}} = 0.80696$$
(14)

 $H_{c2}(t)$ and C(t) are evaluated numerically and shown in Fig. 1 and Fig. 2 respectively. Also in Fig. 1 $H_{c2}(t)$ from the A phase is compared with the data from Ref. [7]. As is readily seen, we have an excellent fit, where we used $v = 2.45 \times 10^6$ cm/sec which is very reasonable. This v is somewhat smaller than the one deduced from the thermal conductivity data [6]. However, it is known that the thermal conductivity data in the clean limit (and not in the superclean limit) is less sensitive to the actual value of v. In the same way v is smaller than that deduced from de Haas-van Alphen data [17]. But in heavy-fermion systems such as UPt₃, it is well known that dHvA gives a lighter effective mass than that deduced via the specific heat.

For the B phase we find for $t\simeq 1$

$$-\ln t = \frac{31\zeta(3)}{11}\rho(1-2C) \text{ and }$$
(15)

$$-C\ln t = \frac{31\zeta(3)}{11}\rho(-1+5C)$$
(16)

which give $C = \sqrt{\frac{3}{2}} - 1$ and $\rho = \frac{11}{31\zeta(3)}(1 + \sqrt{\frac{2}{3}})(-\ln t) \simeq 0.5362(-\ln t)$. For $t \simeq 0$, on the other hand, we have the same set of equations as in Eqs.(10) and (11), where

$$\langle f^2 \rangle^{-1} \langle f^2 \ln(1-z^2) \rangle = -0.25973$$
 (17)

This gives $C = \frac{1}{2}(\sqrt{3}-1)$ and

$$\rho_0 = \frac{1}{4\gamma} \exp[1.2295025] = 0.3786 \tag{18}$$



Fig. 1 – $H_{c2}(T)$ for the A and B phases is compared with the experimental data for $H_{c2}(T)$ and $H^*(T)$. The triangles indicate the single phase data.

We then find

$$h(0) = \frac{H_{c2}(0)}{-\frac{dH_{c2}(t)}{dt}|_{t=1}} = 0.7062115$$
(19)

Both $H_{c2}(t)$ and C(t) for the B phase are obtained numerically and shown in Fig. 1 and Fig. 2 respectively as before. Also $H^*(t)$ from Ref. [7] is shown in Fig. 1 as well, though there is no reason that $H^*(t)$ should correspond to $H_{c2}(t)$ of the B phase. Indeed we see that $H_{c2}(t)$ for the B phase is substantially smaller than the observed $H^*(t)$, especially at low temperatures.

We also compare in Fig. 1 the observed $H_{c2}(t)$ of the single phase crystal with previous data, as well as our predictions for the A and B phases. The single phase data appears essentially identical to $H^*(t)$ of the two phase data, suggesting that the single-phase crystals have only the A phase. $H^*(t)$ and $H_{c2}(t)$ of the single phase crystal are fully consistent with $H_{c2}(t)$ of the A phase, if T_c is taken as 1.72 K, as indicated by the middle fit line in Fig. 1. Such a reduction in T_c is readily reproduced in the presence of impurity scattering [12]. Also we recall the scaling of $H_{c2}(T/T_c, \Gamma)/H_{c2}(0, \Gamma)$ in the presence of impurity scattering. These strongly suggest that both $H^*(t)$ and $H_{c2}(t)$ of the single phase system should be associated with the A phase. As we have mentioned earlier the actual A-B phase boundary is still controversial; below in Fig. 3 we show a measurement [4,6] indicating a phase boundary lying much lower in the H-T plane, and hence more consistent with our preduction for $H_{c2}(t)$ of the B phase. Clearly experiments with cleaner crystals are desirable.

Also from Fig. 2 we notice that C(t) for the B phase is practically the same as the one obtained for the A phase. Further the present C(t) is practically the same as C(t) obtained for the chiral p-wave superconductor [13]. We believe there should be an analytical reason that C(t) is universal for the class of chiral superconductors. This means that the Abrikosov state consists of the n=0 Landau wave function with an admixture of the n=2 Landau wave



Fig. 2 - C(T) for the A and B phases.



Fig. 3 – Alternate phase diagram of $PrOs_4Sb_{12}$

functions with opposite chirality. Further the coefficient of the n=2 Landau wave function is a universal function of $t = T/T_c$.

Vortex lattice. – A relatively large C (i.e. $C > \sqrt{\frac{3}{2}} - 1 \simeq 0.22474$) appears to be characteristic of triplet superconductivity with chirality ± 1 , as observed in Sr₂RuO₄. This suggests strongly that the square vortex lattice is more stable than the usual hexagonal lattice except in the immediate vicinity of the superconducting transitions at T_{cA} and T_{cB} .

In order to examine the vortex lattice structure we calculate the Abrikosov parameter [13,14]

$$\beta_A = \frac{\langle |\Delta(\mathbf{r})|^4 \rangle}{(\langle |\Delta(\mathbf{r})|^2 \rangle)^2} \tag{20}$$

For both the A and B phases in a magnetic field $\mathbf{H} \parallel \mathbf{c}$, we obtain

$$\beta_A = \sqrt{\frac{R}{2\pi}} \sum_{n,m} (-1)^{nm} e^{-\frac{\pi}{2}R(n^2 + m^2)} \times (1 + 2C)^{-2} \times \int_{-\infty}^{\infty} dx e^{-x^2} (1 + C^2(f(x + x_1) + f(x - x_1))) \times (f(x + x_2) + f(x - x_2)) + C^4 f(x + x_1) f(x - x_1) f(x + x_2) f(x - x_2))$$

where $f(x) = x^2 - 1$, $R = \tan(\frac{\theta_0}{2})$, $x_1 = \sqrt{\frac{\pi R}{2}}(n-m)$, $x_2 = \sqrt{\frac{\pi R}{2}}(n+m)$ and θ_0 is the apex angle of the vortex lattice. Here $R = \sqrt{3}$ corresponds to the regular hexagonal lattice, while R = 1 is the square lattice. The above expression is the same as in the chiral p-wave superconductor discussed in [13]. As is well known, for the most stable lattice β_A takes the minimum value. From the analysis of the chiral p-wave superconductor [13] we conclude that the square vortex lattice is the most stable for $T < 0.95T_{cA}$ and $T < 0.95T_{cB}$ in the A and B phase respectively.

Of course the present analysis applies only in the vicinity of $H = H_{c2}(T)$. In order to find the phase boundary between the square vortex and the hexagonal vortex lattice a parallel analysis, as was done for the vortex lattice for d-wave superconductivity by Shiraishi et al [18], is required. But we expect the transition line should be around $\kappa^{-1}H_{c2}(T)$ where κ is the Ginzburg-Landau parameter of PrOs₄Sb₁₂. Making use of the magnetic penetration depth determined by Chia et al [19] we can extract $\kappa \simeq 30.0$. This means that the square vortex lattice should be visible for H= 0.1 T in an ideal crystal. As already mentioned Huxley et al [15] studied the vortex lattice via small angle neutron scattering (SANS), but saw only a distorted hexagonal lattice. In a magnetic field **H** || [001], most of the nodal excitations in both the A and B phases of PrOs₄Sb₁₂ are moving parallel to the [100] and [010] directions. Hence a square vortex lattice aligned parallel to the crystal axis will minimize the quasi-particle energy in the vortex state.

Concluding Remarks. – We have analyzed the upper critical field H_{c2} for the proposed p+h-wave superconductor $PrOs_4Sb_{12}$ [6] and compared with the observed $H_{c2}(t)$ and $H^*(t)$. The present model reproduces H_{c2} without any adjustable parameters. Also the $H_{c2}(t)$ observed in the single phase crystals indicates the single phase is most likely the A phase. Also $H^*(t)$ appears to belong to the A phase. Does this suggest inhomogeneity? Also the present analysis predicts that the square vortex lattice is favored when the magnetic field is parallel to one of the crystal axes. So far no strong correlation between the superconducting transition temperature T_{cA} and T_{cB} and RRR [8] has been observed. This could be interpreted as meaning that disorder has little effect. However, from the early analysis of chiral p-wave superconductivity, we conclude that $H_{c2}(T, \Gamma)/H_{c2}(0, \Gamma)$ is rather universal. An open question is whether a high-quality single crystal with RRR > 100 would show a single or double phase transition. Clearly such a study is highly desirable.

Acknowledgements

We thank Marie-Aude Measson for her generosity in sharing with us her unpublished experimental data [8,9] and wealth of new ideas. Without her help this paper would not be completed in the present form. We have also benefitted from discussions with Stephan Haas and Koichi Izawa. One of us (HW) acknowledges support from the Korean Research Foundation through grant No. R05-2004-000-10814.

REFERENCES

- E.D. BAUER, N.A. FREDERICK, P.-C. HO, V.S. ZAPF, AND M.B. MAPLE, *Phys. Rev. B*, 65 (2002) R100506.
- [2] R. VOLLMER, A. FAIβT, C. PFLEIDERER, H. V. LÖHNEYSEN, E. D. BAUER, P.-C. HO, V. ZAPF, AND M. B. MAPLE, Phys. Rev. Lett, 90 (2003) 57001.
- [3] H. KOTEGAWA, M. YOGI, Y. IMAMURA, Y. KAWASAKI, G.-Q. ZHENG, K. KITAOKA, S. OHSAKI, H. SUGAWARA, Y. AOKI, and H. SATO, *Phys. Rev. Lett.*, **90** (2003) 027001.
- [4] K. IZAWA, Y. NAKAJIMA, J. GORYO, Y. MATSUDA, S. OSAKI, H. SUGAWARA, H. SATO, P. THALMEIER, and K. MAKI, Phys. Rev. Lett., 90 (2003) 117001.
- [5] Y. AOKI, A. TSUCHIYA, T. KANAYAMA, S.R. SAHA, H. SUGAWARA, H. SATO, W. HIGEMOTO, A. KODA, K. OHISHI, K. NISHIYAMA, and R. KADONO, *Phys. Rev. Lett.*, **91** (2003) 067003.
- [6] K. MAKI, S. HAAS, D. PARKER, H. WON, K. IZAWA and Y. MATSUDA, Europhys. Lett., 68 (2004) 720.
- [7] M.-A. MEASSON, D. BRATHWAITE, J. FLOUQUET, G. SEYFARTH, J.P. BRISON, E. LHOTEL, C. PAULSEN, H. SUGAWARA, and H. SATO, *Phys. Rev. B*, **70** (2004) 064516.
- [8] M.-A. MEASSON, D. BRATHWAITE, B. SALCE, J. FLOUQUET, G. LAPERTAT, J. PÉCANT, G. SEYFARTH, J.-P. BRISON, H. SUGAWARA and H. SATO, in SCES'05 proceeding.
- [9] M.-A. MEASSON ET AL, to be published; M.-A MEASSON, PhD thesis, University Joseph Fourier, Grenoble I (2005).
- [10] H. WON, S. HAAS, D. PARKER, S. TELANG, A. VÀNYOLOS and K. MAKI, in "Lectures on the physics of highly correlated electron systems IX", AIP conference proceedings 789 (Melville 2005), pp. 3-43.
- [11] L.P. GOR'KOV, Sov.-Phys. JETP, 10 (1960) 59.
- [12] I. LUK'YANCHUK and V.P. MINEEV, Sov. Phys. JETP, 66 (1987) 1168.
- [13] G.F. WANG and K. MAKI, Europhys. Lett., 45 (1999) 71.
- [14] G. YANG and K. MAKI, Europhys. Lett., 48 (1999) 208.
- [15] A. D. HUXLEY, M.-A. MEASSON, K. IZAWA, C. D. DEWHURST, R. CUBITT, B. GRENIER, H. SUGAWARA, J. FLOUQUET, Y. MATSUDA, and H. SATO, *Phys. Rev. Lett.*, **93** (2004) 187005.
- [16] A.A. ABRIKOSOV, Soviet Phys. JETP, 5 (1957) 1774.
- [17] H. SUGAWARA, S. OSAKI, S.R. SAHA, Y. AOKI, H. SATO, Y. INADA, H. SHISHIDO, R. SETTAI, Y. ONUKI, H. HARIMA and K. OIKAWA, *Phys. Rev. B*, 66 (2002) 220504(R).
- [18] J. SHIRAISHI, M. KOHMOTO and K. MAKI, Europhys. Lett., 44 (1998) 367; Phys. Rev. B, 59 (1999) 4497.
- [19] E.E.M. CHIA, M.B. SALAMON, H. SUGAWARA AND H. SATO, Phys. Rev. Lett., 91 (2003) 247003.