

Superconducting Pairing Amplitude and Local Density of States in Presence of Repulsive Centers

Grzegorz Litak^a; Mariusz Krawiec^b

^a Department of Mechanics, Technical University of Lublin, Nadbystrzycka 36, PL-20-618 Lublin, Poland

^b Institute of Physics and Nanotechnology Center, Marie Curie-Skłodowska University, pl. M. Curie-Skłodowskiej 1, PL-20-031 Lublin, Poland

Abstract

We study the properties of superconductor in presence of a finite concentration of repulsive centers. The superconductor is described by the negative U Hubbard model while repulsive centers are treated as randomly distributed impurities with repulsive interaction. Analyzing the pairing potential and local density of states at impurity sites we find a wide range of the system parameters where the d -like state could possibly be realized. Comparison of our results to the single repulsive center case is also given.

Key words: superconductivity, non-magnetic impurities, tunneling

PACS: 74.20.-z; 74.25.-q; 74.40.+k; 74.50.+r

A superconducting system is regarded as in the d -phase if there is a sign change of the order parameter between two subsystems. The simplest example is the junction made from two superconductors with the phase of the order parameter equal to π [1,2]. In this case Josephson current becomes negative in contrast to the usual 0-phase junction. Another example are granular high- T_c materials which can likely form network of microscopic π -junctions [3] between small regions with different phases of the order parameter. In such systems the zero-energy Andreev bound states, zero-bias conductance peaks, paramagnetic Meissner effect and spontaneously generated currents take place [1,2]. In our recent report [4] we have considered a single impurity with repulsive interaction embedded in a s -wave superconductor on two dimensional lattice showing conditions which should be fulfilled to obtain the d -state. For a uniform embedding system such a state has been found in the limit of very strong repulsion at the impurity site. In the present paper we discuss an-

other possibility. Our superconductor possesses a finite concentration of repulsive centers with random distribution. With such assumptions d -states could appear for moderate values of repulsive interactions at impurities due to additional disorder in pairing potential Δ_i .

The system is described by random U Hubbard model [5] with the Hamiltonian

$$H = \sum_{ij} (t_{ij} - \mu_{ij}) c_i^\dagger c_j + \frac{1}{2} \sum_i U_i n_i n_i; \quad (1)$$

where i, j label sites on a square lattice, $t_{ij} = t$ is the hopping integral between nearest neighbor sites and μ is the chemical potential. Disorder is introduced through the random site interaction U_i . Depending on site i ($i = A$ or B with binary alloy distribution $A_1 c B_c$) U_i describes attraction ($U_A < 0$) or repulsion ($U_B > 0$) between electrons with opposite spins occupying the same site. In the Hartree-Fock approximation [6] (we dropped the Hartree terms $U_i n_i n_i$, and considered only the half filled system $n = 1$, for simplicity) the corresponding Gorkov equation at zero temperature ($T = 0$) has the following form

Corresponding author. Tel: + 48-81-5381573; Fax: + 48-81-5241004

Email address: g.litak@pollub.pl (Grzegorz Litak).

- [5] G. L. Litak, B. L. Gyory, Phys. Rev. B 62 (2000) 6629.
- [6] R. M. McNas et al., Rev. Mod. Phys. 62 (1991) 113.