Anomalous charge transport in dodecaborides RB₁₂ (R- Ho, Er, Tm, Lu)

N. Sluchanko^{1*}, L. Bogomolov^{1,2}, V. Glushkov^{1,2}, S. Demishev^{1,2}, M. Ignatov^{1,2}, N. Samarin¹,

D. Sluchanko¹, A. Levchenko³, N. Shitsevalova³, K. Flachbart⁴

¹A.M.Prokhorov General Physics Institute of RAS, 38, Vavilov str., Moscow, 119991, Russia ²Moscow Institute of Physics and Technology, 9, Institutskii per., Dolgoprudny, Moscow region, 141700, Russia

³Institute for Problems of Materials Science, 03680, Kiev, Ukraine

⁴Centre of Low Temperature Physics, IEP SAS and IPS FS UPJS, SK-04001Košice, Slovakia

PACS: 72.15.Qm.

High precision measurements of Hall $R_H(T)$ and Seebeck S(T) coefficients have been carried out for the first time on single crystals of rare earth dodecaborides RB₁₂ (R - Ho, Er, Tm, Lu) at temperatures 1.8 - 300K. Low temperature anomalies associated with antiferromagnetic phase transitions in HoB₁₂, ErB₁₂ and TmB₁₂ compounds have been detected on the temperature dependencies of $R_H(T)$ and S(T). The estimated values of charge carriers' mobility allowed us to conclude about the appreciable influence of spin fluctuations on the charge transport in these compounds with B₁₂ atomic clusters.

1. In the family of rare earth and transition metal borides a growing interest of researchers is attracted to the study of compounds with framework structural units - boron nanoclusters B_6 and B_{12} . Depending on the cubic crystal structure parameters and the filling of internal 4f- and

^{*} E-mail: <u>nes@lt.gpi.ru</u>

valence 5d, 6s-shells of rare earth ions, these compounds reveal dielectric (SmB₆ and YbB₁₂) or metallic (R³⁺B₆, R³⁺B₁₂) types of conductivity at low temperatures with superconducting (YB₆, ZrB₁₂, LuB₁₂ *et al.*) and various magnetic (para-, dia-, ferro- and antiferromagnetic) ground states. Similar to the intensively studied perovskites as well as molybdates and tungstates, these "framework structures" are characterized by a cooperative motion of connected polyhedral boron units, and seem to be perspective model objects for studying the nature of magnetic interactions and the peculiarities of ground state formation in 3D systems with nanoclusters and localized magnetic moments due to their simple crystal structure (*bcc* for hexaborides RB₆ and *fcc* for dodecaborides RB₁₂). In this respect one of the most important and fundamental problems is connected with the identification of the interplay between phonon spectra and electronic band structures of these crystals, their magnetic properties, and the features of charge transport in these strongly correlated metallic systems.

As far as we know, there are no trustworthy data of Hall and Seebeck coefficients behaviour in rare earth dodecaborides at present time. The current status of experimental studies is given mainly by considerable obstacles which result from (i) particular complications of the growth of RB₁₂ single crystals due to high melting temperatures ($T_m \ge 2300$ K) and (ii) due to high conductivities, which impede precision measurements of transport coefficients in these metallic compounds.

2. The aim of the experimental study was to investigate in details the behaviour of Hall (R_H) and Seebeck (*S*) coefficients as well as the resistivity (ρ) in paramagnetic and antiferromagnetic phases of rare earth dodecaborides RB₁₂ (R - Ho, Er, Tm, Lu) at helium and intermediate temperatures (1.8 – 300 K). Single crystals of RB₁₂ grown by the crucible-less inductive zone melting in argon gas atmosphere [1, 2] have been used for measurements. The Hall coefficient $R_H(H,T)$ has been measured by the sample rotation technique with the step-by-step fixation of the sample's position in steady magnetic field $H \sim 3-4$ kOe using the

experimental setup described in [3]. The original four-probe technique with the variation of temperature gradient on the sample [4] was applied to study the thermopower. All the measurements have been performed with temperature gradient ∇T in (110) plane and sample current $I \parallel < 110 > \perp H$.

3. The angular dependencies of Hall resistivity $\rho_{\rm H}(\varphi)$ measured for some RB₁₂ compounds are presented in fig.1. It was found that in the whole temperature interval corresponding to the paramagnetic state of rare-earth dodecaborides the $\rho_{\rm H}(\varphi)$ dependence can be well described by the cosine law $\rho_{\rm H}(\varphi) \sim \rho_{\rm H1} \cos\varphi$. Results of straightforward fitting have been used to estimate the absolute value of Hall coefficient from the simple relation $\rho_{\rm H1}=R_{\rm H}d$ (d – the sample's thickness). The calculated values of Hall coefficient measured in the paramagnetic phase of RB₁₂ (R- Ho, Er, Tm, Lu) turn out to be rather small ($R_H(T) \sim 2.8 \pm 4.5 \cdot 10^4$ cm³/Coul, see also fig. 2) with a relative changes of $R_H(T)/R_H(300\text{K})$ not exceeding the maximal value of ~30% estimated for HoB₁₂. However, the onset of antiferromagnetic (AF) ordering below Nèel temperature T_N is accompanied by considerable distortions of the $\rho_{\rm H}(\varphi)$ dependencies that is shown by Hall effect data obtained for ErB₁₂ (fig.1). The appearance of even (second $\rho_{\rm H}(\varphi) \sim \rho_{\rm H2} \cos 2\varphi$ and forth $\rho_{\rm H}(\varphi) \sim \rho_{\rm H4} \cos 4\varphi$) harmonics, which are similar to those earlier observed in antiferromagnetic state of CeAl₂ [3], seriously complicates the analysis of $R_H(T)$ dependence at $T < T_N$ (fig.1) The discussion of even Hall effect harmonics occurring in these strongly correlated electron systems is outside the scope of this paper and will be presented in details elsewhere.

The temperature dependencies of Hall coefficient $R_H(T)$ obtained in this study for RB₁₂ compounds (R - Ho, Er, Tm, Lu) are presented in fig. 2. As seen from data of fig. 2, the behaviour of $R_H(T)$ for some magnetic (HoB₁₂, ErB₁₂) dodecaborides in general is roughly similar to that of non-magnetic (LuB₁₂) compound at intermediate temperatures (20 K $\leq T \leq$ 300 K). A wide maximum of $R_H(T)$ observed at temperatures 20 \div 50K is evolved to the minimum

detected in the range of 100÷300K. In the case of TmB₁₂, the observed feature is transformed in the sequence of three extremas (see the lowest curve in fig. 2). However, the temperature independent behaviour of the Hall coefficient, which is observed in non-magnetic metal LuB₁₂ at low temperatures T < 20K (fig. 2), is not specific for the magnetic dodecaborides under investigation. Particularly, distinct maxima of $R_H(T)$ are observed at $T = T_{max} \sim 10-12$ K for HoB₁₂ and TmB₁₂. Additionally, the pronounced anomalies of Hall coefficient associated with AF transitions for all magnetic compounds RB₁₂ can be clearly seen on the temperature dependences of $R_H(T)$ in the vicinity of Neel temperatures T_N . The estimated values of T_N , which are equal to 7.4 K, 6.7 K and 3.3 K for HoB₁₂, ErB₁₂ and TmB₁₂, respectively, agree very well to the results of magnetic and thermodynamic measurements of RB₁₂ [5-7]. Note also that the drastic increase of Hall coefficient observed for the first time in AF phase of ErB₁₂ (fig. 2) requires further investigation of Hall effect in the magnetic phase of this compound.

The temperature dependencies of Seebeck coefficient S(T) as measured for magnetic and non-magnetic compounds RB₁₂ (R - Ho, Er, Tm, Lu) also demonstrate the consistent behaviour (fig. 3). A pronounced feature of Seebeck coefficient at intermediate temperatures (100 – 300 K) is observed for all dodecaborides under investigation, the amplitude of the negative minimum of S(T) being the largest one for non-magnetic lutetium dodecaboride (fig. 3). When lowering temperature, the thermopower of all magnetic dodecaborides changes the sign. In the case of HoB₁₂ and TmB₁₂, a wide positive maximum of relatively small amplitude $S \le 0.5 \,\mu$ V/K is detected on S(T) curves in the temperature interval of 10÷20 K (inset of fig. 3). For ErB₁₂, the sign inversion and the maximum of S(T) are observed at temperatures 10.5 K and 8 K, respectively (fig. 3). The transition into AF state in RB₁₂ is accompanied by the appearance of an additional positive contribution to Seebeck coefficient (inset of fig. 3). The values of Nèel temperature for ErB₁₂ and HoB₁₂ found from the approximation of S(T) curves in AF-phase to temperature axis (see inset of fig. 3) are in good consistence to the T_N values estimated from Hall effect (fig. 2), and magnetic [5] and thermal [6] measurements. In the case of TmB₁₂, the vicinity of $T_N \approx 3.3$ K is characterized by a very small amplitude maximum on the S(T) curve. The value of T_N^S determined by the mentioned approximation procedure is lower than $T_N - T_N^S$ (TmB₁₂) \approx 2.7 K (inset of fig. 3).

To receive additional information about the transport properties of RB₁₂ single crystals the temperature dependencies of resistivity $\rho(T)$ have been measured for all the samples under investigation. The results of the $\rho(T)$ study (see fig. 4a) allowed us to estimate the values of T_N , which agree with previous results [5-7] within the experimental accuracy.

4. When analysing the temperature behaviour of transport coefficients in RB_{12} compounds, it should be taken into account that trivalent rare earth dodecaborides in the paramagnetic phase are metals having a rather complicated Fermi surface (FS) consisting of two parts. The first part is multiply connected in the <111> directions and topologically similar to the FS of copper, the second one forms pancake-like electron surfaces centred at the X point [8]. Band structure calculations and quantum oscillations studies performed on LuB₁₂ [8] allowed to conclude that the conduction band of LuB₁₂ is mainly formed by the *5d*-states of rare earth ions hybridised with boron *2p*-states. According to the current conception trivalent rare earth compounds RB₁₂ are one-electron metals [5-8], the change of *4f*-state configuration in the sequence of Ho - Tm, Lu having only weak influence on the conduction band structure.

In this respect it is reasonable to estimate the behaviour of Hall mobility in RB₁₂ using the common expression for one type of charge carriers $\mu_H(T) = R_H(T)/\rho(T)$. The data of fig. 4b presented for temperatures 1.8 – 300 K demonstrate that the charge carriers mobility reaches its maximum value (~2500 cm²/(V·s)) for the non-magnetic metal LuB₁₂ with fully filled 4*f*-states of rare earth ions (4*f*ⁿ, *n* = 14). Additionally, the change of 4*f*-shell configuration in the sequence HoB₁₂ - LuB₁₂ starting from HoB₁₂ (4*f*ⁿ, *n* = 10) induces a significant decrease of μ_H which depends monotonously on the filling number *n* in the range 10 < *n* < 13 (fig. 4b). Note that the

de-Gennes factor $(g-1)^2 J(J+1)$ (*J* - full magnetic moment of the 4*f*-shell), which characterizes the magnetic scattering of charge carriers, is also reduced dramatically with the increase *n* in the range 10 < n < 13. It is of special interest to accent here that the intermediate valence state of rare earth ions in dodecaborides ($v(Yb) \approx 2.9$ [9]) realized in YbB_{12} (4*f*ⁿ, *n* = 13) results to the unusual semiconducting ground state [10].

To explain the anomalous behaviour of transport coefficients in the sequence of HoB₁₂ -YbB₁₂, it is necessary to propose that the decrease of charge carriers mobility with the increase of *n* in the range n = 10-13 seems to be connected with the enhancement of spin (and charge- in case of YbB₁₂) fluctuations in these compounds. As a result, the natural explanation can be also provided for (i) the decrease of the S(T) absolute value, which is observed at intermediate temperatures 50-300 K (fig. 3) and accompanies the mobility lowering between HoB12 and TmB₁₂ (fig. 4b), as well as for (ii) the reduction of Néel temperature from 7.4 K (HoB₁₂) down to 3.3 K (TmB₁₂) with the increase of n, which is, however, much faster than expected for these magnetic dodecaborides (see [2, 5]). Besides, within the framework of the spin fluctuation approach the similar behaviour of $R_H(T)$ curves detected for various compounds RB₁₂ in the temperature interval 50÷300 K (fig. 2) as well as that of S(T) dependencies for magnetic and non-magnetic dodecaborides in this range of temperatures (fig. 3) could be associated with the absence of noticeable changes in the structure of 5d-2p-states forming the conduction band in these rare earth dodecaborides. However, to check the approach proposed in the present work in detail, a comprehensive study of transport, magnetic and thermodynamic characteristics should be performed for RB_{12} in a wide range of temperatures and magnetic fields.

This work was performed in framework of RFBR 04-02-16721 and INTAS 03-51-3036 projects, as well as under the financial support of the RAS Program "Strongly Correlated Electrons in Semiconductors, Metals, Superconductors and Magnetic Materials" and Russian Science Support Foundation. Acknowledged is also the support of Slovak Scientific Grant

Agencies VEGA, contract 4061, and APVT, contract 0317, and by the contract I/2/2003 of the Slovak Academy of Sciences for the Centres of Excellence.

* e-mail: nes@lt.gpi.ru

- Yu. Paderno, V. Filippov, and N. Shitsevalova. The study of RE dodecaborides zone melting process. In: Boron-Rich Solids, AIP Conference Proc., Eds. D. Emin, T.L. Aselage et al. (Eds.), Vol. 230, Albuquerque, 1991, p. 460;
- [2] N.Yu. Shitsevalova, PhD. Thesis, Wroclaw, 2001 (in Russian).
- [3] N.E. Sluchanko et al., JETP, **98**, 793 (2004)
- [4] N.E. Sluchanko et al., JETP, **86**, 190 (1998)
- [5] S. Gabani, I. Bat'ko, K. Flachbart et al., J. Magn. Magn. Mat., 207, 131 (1999)
- [6] A. Czopnik, N. Shitsevalova, A. Krivchikov et al., J. Sol. State Chem., 177, 507 (2004)
- [7] A. Kohout, I. Bat'ko, A. Czopnik et al., Phys. Rev. B, **70**, 224416 (2004)
- [8] M. Heinecke et al., Z. Phys. B, 98, 231 (1995); N. Okuda, T. Suzuki, I. Ishii et al., Physica B, 281-282, 756 (2000)
- [9] T. Susaki, A. Sekiyama, K. Kobayashi et al., Phys. Rev. Lett., 77, 4269 (1996)
- [10] F. Iga, N. Shimizu, T. Takabatake, J. Magn. Magn. Mat., 177-181, 337 (1998)

Figure captions

- **Fig. 1.** Angular dependencies of Hall resistivity $\rho_{\rm H}(\varphi)$ for LuB₁₂ (left panel) and ErB₁₂ (right panel). Solid lines present the results of harmonic analysis (see text).
- **Fig. 2.** Temperature dependencies of Hall coefficient $R_H(T)$ for RB₁₂ compounds (R Ho, Er, Tm, Lu).
- **Fig. 3.** Temperature dependencies of Seebeck coefficient S(T) for RB₁₂ compounds (R Ho, Er, Tm, Lu). T^* corresponds to the peculiarity observed on S(T) curves at intermediate temperatures. The temperature interval in the vicinity of magnetic transitions is presented in the inset in larger scale.
- **Fig. 4.** Temperature dependencies of (a) resistivity $\rho(T)$ and (b) Hall mobility $\mu_H(T) = R_H(T)/\rho(T)$ for RB₁₂ compounds (R Ho, Er, Tm, Lu). The numbers on $\mu_H(T)$ curves correspond to the exponents α of the power law dependencies $\mu_H(T) \sim T^{-\alpha}$ fitted in the temperature range 50 300 K.



Fig.1



Fig.2



Fig.3



Fig.4