

# Theoretical Analysis of the Reduction of Neel Temperature in $\text{La}_2(\text{Cu}_{1-x}\text{Zn (or Mg)}_x)\text{O}_4$

T. Edagawa<sup>a</sup>, Y. Fukumoto and A. Oguchi

<sup>a</sup>Department of Physics, Faculty of Science and Technology, Tokyo University of Science, 2641 Yamazaki, Noda, Chiba 278-8510, Japan

## Abstract

Using Tyablikov's decoupling approximation, we calculate the initial suppression rate of the Neel temperature,  $R_{\text{IS}} = \lim_{x \rightarrow 0} T_N^{-1} dT_N/dx$ , in a quasi two-dimensional diluted Heisenberg antiferromagnet with nonmagnetic impurities of concentration  $x$ . In order to explain an experimental fact that  $R_{\text{IS}}^{(\text{Zn})} = 3.4$  of the Zn-substitution is different from  $R_{\text{IS}}^{(\text{Mg})} = 3.0$  of the Mg-substitution, we propose a model in which impurity substitution reduces the intra-plane exchange couplings surrounding impurities, as well as dilution of spin systems. The decrease of 12% in exchange coupling constants by Zn substitution and decrease of 6% by Mg substitution explain those two experimental results, when an appropriate value of the interplane coupling is used.

© 2021 Elsevier B.V. All rights reserved.

PACS: 75.10.Jm; 75.10.Nr; 74.72.Dn

Keywords: diluted Heisenberg antiferromagnets; Neel Temperature;  $\text{La}_2\text{CuO}_4$

The discovery of high- $T_c$  compounds renewed interests in quasi two-dimensional quantum antiferromagnets. The site dilution problem of two-dimensional quantum antiferromagnets has been extensively studied. [1,2,3,4,5] In this paper, we treat a problem of the difference between Zn and Mg substitutions in  $\text{La}_2\text{CuO}_4$ . [1]

As far as the present authors know, on the impurity problem of square-lattice Heisenberg antiferromagnets nonmagnetic impurities have been treated just as static vacancies in spin systems in all previous theoretical studies. However, in an experiment on  $\text{La}_2(\text{Cu}_{1-x}\text{Zn (or Mg)}_x)\text{O}_4$ , Cheong et al. reported that the initial suppression rate of Neel temperature

$$R_{\text{IS}} = \lim_{x \rightarrow 0} \frac{1}{T_N} \frac{dT_N}{dx} \quad (1)$$

shows impurity ion dependence, i.e.,  $R_{\text{IS}}^{(\text{Zn})} = 3.4$  for Zn substitution and  $R_{\text{IS}}^{(\text{Mg})} = 3.0$  for Mg substitution. [1] This result indicates that the nonmagnetic impurities are not a role of static vacancies in the spin system. Cheong et al. also measured the orthorhombic-to-tetragonal transition temperature  $T_{\text{O} \rightarrow \text{T}}$  of  $\text{La}_2(\text{Cu}_{1-x}\text{Zn (or Mg)}_x)\text{O}_4$ , and found a faster increase of  $T_{\text{O} \rightarrow \text{T}}$  of Zn substitution than Mg substitution. On the basis of this observation, they concluded

that Mg is a better substitutional ion than Zn for realizing spin dilution systems. [1]

We write the Hamiltonian of the parent compound without impurities as

$$H = \sum_{\langle ij \rangle_k} J S_i \cdot S_j + J_z \sum_{\langle ij \rangle_z} S_i \cdot S_j; \quad (2)$$

where  $i$  and  $j$  denote lattice points on a simple cubic lattice,  $\langle ij \rangle_k$  are nearest-neighbor pairs of sites on a square-lattice plane, and  $\langle ij \rangle_z$  are inter-plane nearest neighbor pairs. Although inter-plane exchange couplings in  $\text{La}_2\text{CuO}_4$  are more complex than those in the above model, we simply treat the three dimensionality within the form of the above Hamiltonian. An "ideal" nonmagnetic impurity is introduced at site  $O$ , then the spin system is perturbed by

$$H_O^0 = \sum_{\langle iO \rangle_k} J S_O \cdot S_i + \sum_{\langle iO \rangle_z} J_z S_O \cdot S_i; \quad (3)$$

The Hamiltonian of the diluted spin system is given by  $H_{\text{tot}} = H + \sum_O H_O^0$ , where the sum runs over  $N \times N$  lattice points chosen at random from the total  $N$  lattice points. On the basis of the Tyablikov decoupling approximation, MaGum calculated conformation averaged Green's functions with self-energy corrections within first order in  $x$ , and estimated  $R_{\text{IS}}$  for a square lattice case,  $J_z \neq 0$ , and for an isotropic simple cubic lattice case,  $J_z = J$ . [6] MaGum's results are  $R_{\text{IS}}(J_z \neq 0) = \frac{1}{2}$  and  $R_{\text{IS}}(J_z = J) = 1.68$ . The

<sup>a</sup>Corresponding author.

E-mail address: oguchi@rs.noda.tus.ac.jp (T. Edagawa).




Fig. 1. Initial suppression rate  $R_{IS}$  as a function of interplane coupling  $J_{\perp}$ .

former value for the square lattice is close to the experimental values for  $\text{La}_2(\text{Cu}_{1-x}\text{Zn}(\text{Mg})_x)\text{O}_4$ , but other mechanisms are needed to get a quantitative agreement between theory and experiment. One of such mechanisms is a weak inter-plane coupling.

We begin with extending MacGum's calculation to study how  $R_{IS}$  depends on  $J_{\perp}$ . The result is shown in Fig. 1. We find that  $R_{IS}$  decreases monotonically as  $J_{\perp}$  increases. This behavior is reasonable because the three dimensionality is expected to stabilize antiferromagnetic ordering. If we assume  $J_{\perp} = 5.0 \times 10^{-5} J$  in  $\text{La}_2\text{CuO}_4$ , [7] then we obtain  $R_{IS} = 2.67$ . This value is much smaller than  $R_{IS}^{(Zn)} = 3.4$  and  $R_{IS}^{(Mg)} = 3.0$ , and thus we have to search for an additional mechanism which destabilizes the antiferromagnetic ordering and makes  $R_{IS}$  increase.

The experimental result of  $R_{IS}^{(Zn)} \notin R_{IS}^{(Mg)}$  gives us a hint in searching for the additional mechanism. A natural way to understand this experimental result is that the exchange couplings around nonmagnetic impurities are changed depending on the ion radius of the impurities. The ion radii of Zn, Cu, Mg are, respectively, 0.74, 0.73, 0.72 [Å]. When a Cu ion substitutes for a Zn ion, then the four nearest neighbor Cu ions of the impurity move away from the impurity and in the case of Mg they approach the impurity, as shown in Fig. 2. (We neglect smaller displacements of other Cu ions.) Then, for eight exchange bonds surrounding the impurity ion, the linear arrangement of lobes of two  $d_{x^2-y^2}$  orbitals and a p orbital is changed to a distorted one, which leads to the reduction of overlap integral between such two Cu sites, i.e.,  $t \neq t'$ . The reduction of the overlap integral




Fig. 2. Schematic representations of (a) a  $\text{CuO}_2$  plane, where the small closed circles represent positions of oxygens, (b) a  $\text{CuO}_2$  plane with Zn-substitution, and (c) a  $\text{CuO}_2$  plane with Mg-substitution.




Fig. 3. Initial suppression rate  $R_{IS}$  as a function of  $\alpha$  for  $J_{\perp} = J = 5.0 \times 10^{-5}$ .

also gives  $J \neq J^0 = J(1 - 2t/t')$  for small  $t/t'$ .

In order to incorporate this effect, we write the perturbation due to an impurity at site 0 as

$$H_0^0 = H_0^0 + \sum_{\langle ij \rangle \ni 0} X_{ij} S_i \cdot S_j; \quad (4)$$

where  $\langle ij \rangle = 2t/t'$ , and the sum runs over eight intra-plane nearest-neighbor pairs surrounding the impurity site 0. Following MacGum's procedure, we calculate  $R_{IS}$  for the Hamiltonian  $H_{\text{tot}} = H + \sum_0 H_0^0$ . In the limit  $J_{\perp} \rightarrow 0$ , we obtain  $R_{IS} = A' + A$  with a rather large coefficient  $A = 32/16 + 5/2 = 2'6.4$ . The calculated result for  $J_{\perp} = 5.0 \times 10^{-5} J$ , which corresponds to  $\text{La}_2\text{CuO}_4$ , is shown in Fig. 3. Using this result and experimental results of  $R_{IS}^{(Mg)} = 3.0$  and  $R_{IS}^{(Zn)} = 3.4$ , we obtain  $\alpha^{(Zn)} = 0.12$  and  $\alpha^{(Mg)} = 0.06$  for  $\text{La}_2(\text{Cu}_{1-x}\text{Zn}(\text{Mg})_x)\text{O}_4$ , which means that reductions of the overlap integral due to Zn and Mg substitutions are, respectively, 6% and 3%. The result of  $\alpha^{(Zn)} > \alpha^{(Mg)}$  shows that Mg is a better substitution than Zn, which is consistent with the experimental finding by Cheong et al. mentioned before. [1]

In summary, we conclude that the reduction of intra-plane exchange couplings around impurities causes a rather fast increase of  $R_{IS}$  and gives the origin of the difference in  $R_{IS}$  between  $\text{La}_2(\text{Cu}_{1-x}\text{Zn})\text{O}_4$  and  $\text{La}_2(\text{Cu}_{1-x}\text{Mg})\text{O}_4$ . As a future problem, it is also interesting to incorporate four-spin ring-exchange terms into our model, [8] which is expected to get the estimations of  $R_{IS}$  to decrease more or less because of frustration effects. [9]

## References

- [1] S.-W. Cheong et al.: Phys. Rev. B 44 (1991), p. 9739.
- [2] K. Kato et al.: Phys. Rev. Lett. 84 (2000), p. 4204.
- [3] A. L. Chemyshv et al.: Phys. Rev. B 65 (2002), p. 104407.
- [4] E. R. Mucciolo et al.: Phys. Rev. B 69 (2004), p. 214424.
- [5] E. V. Castro et al.: Phys. Rev. B 73 (2006), p. 054422.
- [6] R. MacGum: J. Phys. C 27 (1979), p. 3523.
- [7] M. Hucker et al.: Phys. Rev. B 59 (1999) p. 725.
- [8] R. Coldea et al.: Phys. Rev. Lett. 86 (2001) p. 5377.
- [9] A. Lauchli et al.: Phys. Rev. Lett. 95 (2005) p. 137206.