

Journal of M agnetism and M agnetic M aterials 0 (2024) 1{0



www.elsevier.com/locate/jnmm

# M icroscopicA spects of Multipole Properties of Filed Skutterudites

TakashiHotta

A dvanæd Scienæ Research Center, Japan A tom ic Energy Agency, Tokai, Ibaraki 319–1195, Japan Received 15 April 2024

A bstract

We discuss low-temperature multipole states of Nd-based lled skuttenudites by analyzing a multiorbital Anderson model with the use of a numerical renormalization group method. In order to determ ine the multipole state, we take a procedure to maximize the multipole susceptibility matrix. Then, it is found that the dominant multipole state is characterized by the mixture of 4u magnetic and 5u octupole moments. The secondary state is specified by 2u octupole. When we further take into account the coupling between f electrons in degenerate  $_{67}$  (eu) orbitals and dynamical Jahn-Teller phonons with Eg symmetry, quadrupole uctuations become e signi cant at low temperatures in the mixed multipole state with 4u magnetic and 5u octupole moments. Finally, we brie y discuss possible relevance of the present results to actual Nd-based lled skutterudite compounds. c 2024 E lsevier B.V. All rights reserved.

PACS: 75.20 Hr; 71.27.+ a; 75.10 Dg; 71.10.-w

Keywords: Multipole; Filled Skutterudites; Dynamical Jahn-Teller E ect

### 1. Introduction

Recently, magnetism and superconductivity of rare-earth and actinide compounds have attracted renewed attention in the research eld of condensed matter physics [1]. In particular, lled skutterudites, expressed as  $RT_4X_{12}$  with rare-earth atom R, transition m etalatom T, and pnictogen X, provide us a platform for system atic research of m agnetism and superconductivity of f<sup>n</sup>-electron systems with n 2 [2,3], where n denotes the number of f electrons.

Since  $RT_4X_{12}$  crystallizes in the cubic structure with high symmetry of  $T_h$  point group [4], orbital degeneracy remains in general. Due to the strong spin-orbit coupling in f electrons, spin-orbital complex degrees of freedom, i.e., multipoles, become active in led skuttenudites. For instance, a second-order phase transition at 6.5K in PrFe<sub>4</sub>P<sub>12</sub> [5] has been considered to be due to antiferro quadrupole ordering [6]. Note that a possibility of antiferro hexadecapole order has been also suggested in PrFe<sub>4</sub>P<sub>12</sub> [7]. In NdFe<sub>4</sub>P<sub>12</sub>, a signi cant role of quadrupole at low temperatures has been suggested from the measurement of elastic constant [8]. A possibility of octupole ordering in Sm Ru<sub>4</sub>P<sub>12</sub> has been also pointed out from the elastic constant measurement [9]. Note that the octupole scenario in Sm Ru<sub>4</sub>P<sub>12</sub> has been supported by muon spin relaxation [10] and  $^{31}P$  NMR experiments [11].Quite recently, a possibility of antiferro hexadecapole order has been proposed to understand metal-insulator transition of PrR u<sub>4</sub>P<sub>12</sub> [12].

A nother characteristic issue of led skuttenudites is rattling, i.e., anharm onic vibrations of rare-earth atom around the o -center position inside the pnictogen cage. E ffects of rattling on low-tem perature f-electron states have been recently discussed actively, in particular, with relevance to m agnetically robust heavy-ferm ion phenom enon observed in Sm  $0 s_4 Sb_{12}$  [13,14]. Concerning the symm etry of vibrations, a possibility of degenerate  $E_g$  m ode has been suggested in PrO  $s_4 Sb_{12}$  [15]. Since there exists linear coupling between f electrons in degenerate  $_{67}$  ( $e_u$ ) orbitals and vibration m ode with  $E_g$  symm etry, the present author has pointed out quasi-K ondo phenom enon due to dynam ical Jahn-Teller (JT) phonons [16,17].

In this paper, we focus on the case of n= 3 as typicalexample to study low-tem perature multipole properties and thee ect of JT phonons on themultipole state of lled skutterudites. The multiorbital Anderson model constructed based on a j-j coupling scheme is analyzed by a numericalrenorm alization group method. Note that the multipole state is determined by the maximization of the multipole susceptibility. It is found that the primary multipole state is characterized by the mixture of 4u magnetic and 5u octupole moments, while the secondary state is specified by

Corresponding author.

Em ailaddress: hotta.takashi@jaea.go.jp (TakashiHotta).

2u octupole.W hen we further include the coupling between f electrons and JT phonons, we nd that quadrupole uctuations are signi cant at low tem peratures in the 4u-5u coupled multipole state.Finally, we brie y discuss possible relevance of our results to actual N d-based led skutterudite com pounds.

## 2. M ultiorbitalAnderson M odel

The local f-electron state is described by [18,19]

$$H_{loc} = \begin{pmatrix} X \\ B_{m,m} \circ \circ + m; m \circ; \circ \end{pmatrix} f_{m}^{y} f_{m} \circ \circ \\ + X \\ X \\ + I_{m_{1},m_{2},m_{3},m_{4}} f_{m_{1}}^{y} f_{m_{2}}^{y} f_{m_{3},2} f_{m_{4},1}; (1) \\ + I_{m_{1},m_{4},1;2} \\ \end{pmatrix}$$

where  $f_m$  is the annihilation operator for f electrons with spin and angularmomentum m (= 3, ..., 3), = +1 (for up (down) spin,  $B_{m,m^{\circ}}$  is the crystalline electric eld (CEF) potential for angular momentum  $=3, \circ$  is the K ronecker's delta, and is the spin-orbit coupling. The matrix element  $m; m^{\circ}; \circ$  is given by

and zero for the other cases. The Coulomb integral  $I_{m_1m_2m_3m_4}$  is expressed by the combination of four Slater-Condon parameters,  $F^0$ ,  $F^2$ ,  $F^4$ , and  $F^6$  [19]. In this paper, we set  $F^{0}$ = 10,  $F^2$ = 5,  $F^4$ = 3, and  $F^6$ = 1 in the unit ofeV. For the  $T_h$  point group,  $B_{m,m^0}$  is given by three CEF parameters,  $B_4^0$ ,  $B_6^0$ , and  $B_6^2$  [4,18]. In the traditional notations [20,21], they are expressed as

$$B_4^0 = W x=15; B_6^0 = W (1 jx)=180; B_6^2 = W y=24:$$
 (3)

where x and y specify the CEF scheme for  $T_h$  point group, while W determ ines an energy scale for the CEF potential.

The local H am iltonian H  $_{\rm loc}$  can provide us exact inform m ation on local f-electron states, irrespective of the values of C oulom b interactions and spin-orbit coupling [18]. How – ever, since H  $_{\rm loc}$  includes seven orbitals, we are im m ediately faced with di culties for further study of m any-body phenom ena in f-electron system s. Thus, it is natural to consider the e ective m odel which describes well low -energy states of H  $_{\rm loc}$ . For the purpose, we have proposed to exploit a j-j coupling scheme [22,23]. W e set the spin-orbit coupling term as an unperturbed part, while the CEF potential and C oulom b interaction terms as perturbations. Then, we obtain the e ective m odel of H<sub>loc</sub> as [23]

$$H_{e} = {\begin{array}{*{20}c} X \\ H_{e} \end{array}} {\begin{array}{*{20}c} X \\ F \end{array}} {\begin{array}{*{20}c} Y \\ F \end{array}} {\begin{array}{*{20}c} F \\ F \end{array}} {\begin{array}{*{20}c} Y \\ F \end{array}} {\begin{array}{*{20}c} F F$$

where f is the annihilation operator for f electron with angularm om entum (= 5/2, ,5/2) in the j= 5/2 sex. The modi ed CEF potential is expressed as

$$\vec{B}_{i} = \vec{B}_{i}^{(0)} + \vec{B}_{i}^{(1)}; \qquad (5)$$

where  $B''^{(0)}$  denotes the CEF potential for J = 5/2 and  $B''^{(1)}$ ; is the correction in the order of  $W^2 = .$  The e ective interaction in eq. (4) is given by

$$\Gamma_{1;2;3;4} = \Gamma_{1;2;3;4}^{(0)} + \Gamma_{1;2;3;4}^{(1)};$$
(6)

where  $\Gamma_{1;2;3;4}^{(0)}$  is expressed by three R acah param eters,  $E_0, E_1$ , and  $E_2$ , which are related to the Slater-C ondon param eters. Explicit expressions of  $\Gamma^{(0)}$  by using  $E_0, E_1$ , and  $E_2$  are shown in Ref. [22].

On the other hand,  $\Gamma_{1;2;3;4}^{(1)}$  is the correction term in the order of 1= .Details on this term have been discussed in Ref. [23].Here, three comments are in order. (i) E ectsofB<sub>0</sub><sup>6</sup> and B<sub>6</sub><sup>2</sup> are included as two-body potentials in  $\Gamma^{(1)}$ . (ii) The lowest-order energy of  $\Gamma^{(1)}$  is  $j_{N}$   $j_{H}$ = , where  $J_{H}$  denotes the original H und's rule interaction among f electrons. (iii) The parameter space in which H<sub>e</sub> works 1s determ ined by the conditions for the weak CEF, i.e.,  $j_{N}$   $j_{=}J_{H}$  1 and  $j_{N}$   $j_{H}$ = E<sub>2</sub>. Since E<sub>2</sub> is the e ective H und's rule interaction in the j-j coupling scheme, estim ated as E<sub>2</sub>  $J_{H}$  =49 [22], we obtain  $j_{N}$   $j_{=}$  0.02. Thus, it is allowed to use H<sub>e</sub> even for in the order of 0.1 eV [23], when  $j_{N}$  j is set as a realistic value in the order of 10 <sup>4</sup> eV for actual f-electron m aterials.

Now we consider the hybridization between f and conduction electrons. From the band-structure calculations, it has been revealed that the main conduction band of led skutterudites is  $a_u$  with xyz symmetry [24], which is hybridized with f electrons in the  $_5$  state with  $a_u$  symmetry. In order to specify the f-electron state, we introduce <code>\orbital"</code> index which distinguishes three kinds of the K ram ers doublets, two  $_{67}$  and one  $_5$ . Here <code>\a"</code> and <code>\b"</code> denote the two  $_{67}$  's and <code>\c"</code> indicates the  $_5$ .

Then, the multiorbital Anderson model is given by

$$H = \bigvee_{k}^{X} c_{k}^{y} c_{k} + \bigvee_{k}^{X} (V c_{k}^{y} f_{c} + h c) + H_{e} + H_{eph}; (7)$$

where " $_{\rm k}$  is the dispersion of  $a_{\rm u}$  conduction electrons with  $_5$  sym m etry, f is the annihilation operator of f electrons on the in purity site with pseudospin and orbital , q is the annihilation operator for conduction electrons with m om entum k and pseudo-spin , and V is the hybridization between conduction and f electrons with  $a_{\rm u}$  sym m etry. Throughout this paper, we set V = 0.05 eV . Note that the energy unit of H is half of the bandwidth of the conduction band, which is considered to be in the order of 1 eV, since the bandwidth has been typically estimated as 2.7 eV for PrRu<sub>4</sub>P<sub>12</sub> [25]. Thus, the energy unit of H is taken as eV. To set the local f-electron number as n= 3, we adjust the f-electron chemical potential.

The last term in eq. (7) denotes the electron-phonon coupling. Here, the e ect of  $E_g$  rattling is included as relative vibration of surrounding atom s. W e rem ark that localized  $_{67}$  orbitals with  $e_u$  sym m etry have linear coupling with used as  $_{67}$  orbitals with  $E_g$  sym m etry, since the sym m etric representation of  $e_u$   $e_g$  includes  $E_g$ . Then,  $H_{eph}$  is given by

$$H_{eph} = g(Q_{2x} + Q_{3z}) + (P_{2}^{2} + P_{3}^{2}) = 2$$
  
+ (!<sup>2</sup>=2)(Q\_{2}^{2} + Q\_{3}^{2}) + b(Q\_{3}^{3} - 2Q\_{2}^{2}Q\_{3}); (8)

where g is the electron-phonon coupling constant,  $Q_2$  and  $Q_3$  are normal coordinates for  $(x^2 \quad y^2)$ -and  $(3z^2 \quad r^2)$ -type JT phonons, respectively  $pP_2$  and  $P_3$  are corresponding canonical momenta,  $_x = (f_a^y f_b + f_b^y f_a)$ ,  $_z = (f_a^y f_a \quad f_b^y f_b)$ , ! is the frequency of local JT phonons, and b indicates the cubic anharm onicity. Note that the reduced m ass of JT modes is set as unity. Here we introduce non-dimensional electron-phonon coupling constant and the anharm onic energy as  $= g^2 = (2!^3)$  and  $= b = (2!)^{3=2}$ , respectively.

## 3. M ultipole Susceptibility

In order to clarify the magnetic properties at low tem peratures, we usually discuss the magnetic susceptibility, but in more general, it is necessary to consider the susceptibility of multipole moments such as dipole, quadrupole, and octupole. The multipole operator is given in the secondquantized form as

$$X = (X) f^{y}f; \qquad (9)$$

where X denotes the sym bolofmultipole with the symmetry of and indicates a set of indices for the irreducible representation. For j=5/2, we can de nemultipole operators up to rank 5 in general, but we are primarily interested in multipole properties from the  $_{67}$  quartet. Thus, we consider multipole moments up to rank 3 in O<sub>h</sub> symmetry.

Now we show explicit forms of multipole operators [26,27]. As for dipole moments with  $_{4u}$  symmetry, the operators are expressed as

$$J_{4ux} = J_x; J_{4uy} = J_y; J_{4uz} = J_z;$$
 (10)

where  $J_x$ ,  $J_y$ , and  $J_z$  are three angular momentum operators for j= 5/2, respectively. Concerning quadrupole moments, they are classified into  $_{3g}$  and  $_{5g}$ . We express the  $_{3g}$  quadrupole operators as

$$O_{3gu} = (2J_z^2 \quad J_x^2 \quad J_y^2) = 2; O_{3gv} = \frac{p}{3} (J_x^2 \quad J_y^2) = 2: (11)$$

For the 5q quadrupole, we have the three operators

$$O_{5g} = {}^{p} \frac{1}{3} \overline{J_{y} J_{z}} = 2;$$

$$O_{5g} = {}^{p} \frac{1}{3} \overline{J_{z} J_{x}} = 2;$$

$$O_{5g} = {}^{p} \frac{1}{3} \overline{J_{x} J_{y}} = 2;$$
(12)

where the bar denotes the operation of taking all possible permutations in terms of cartesian components.

O ctupole mom ents are classied into three types as  $_{2u}$  ,  $_{4u}$  , and  $_{5u}$  . A mong them ,  $_{2u}$  octupole is written as

$$T_{2u} = {}^{p} \overline{15} \overline{J_{x}} J_{y} J_{z} = 6:$$
(13)

For the  $_{4u}$  octupole, we express the operators as

$$T_{4ux} = (2J_x^3 \quad \overline{J_x J_y^2} \quad \overline{J_x J_z^2}) = 2;$$
  

$$T_{4uy} = (2J_y^3 \quad \overline{J_y J_z^2} \quad \overline{J_y J_x^2}) = 2;$$
  

$$T_{4uz} = (2J_z^3 \quad \overline{J_z J_x^2} \quad \overline{J_z J_y^2}) = 2;$$
(14)

while <sub>5u</sub> octupole operators are given by

Note that we rede not the multipole moments so as to satisfy the orthonorm alcondition  $Tr(X \times 0) = 0$  [28].

In principle, the multipole susceptibility can be evaluated in the linear response theory [27], but we should note that the multipole moments belonging to the same symmetry can be mixed. In order to determ ine the coe cient of such a mixed multipole moment, it is necessary to nd the optimized multipole state which maximizes the susceptibility. Namely, we de ne the multipole operator as

$$M = \begin{array}{c} X \\ p X ; \end{array}$$
(16)

where the coe cient p is determined by the eigenstate with the maximum eigenvalue of the susceptibility matrix, given by

$$O = \frac{1}{Z} \sum_{n,m}^{X} \frac{e^{E_n = T} e^{E_m = T}}{E_m E_n} \ln \frac{1}{X} \text{ jn ihm } \frac{1}{X} \text{ opi: (17)}$$

Here  $E_n$  is the eigenenergy for the n-th eigenstate jni, T is a temperature, and Z is the partition function given by  $Z = \sum_{n} e^{E_n = T}$ .

In order to evaluate • as well as an entropy  $S_{im\,p}$  and a speci c heat  $C_{im\,p}$  off electrons, we resort to the num erical renorm alization group (NRG) method [29,30], in which m om entum space is logarithm ically discretized to include e ciently the conduction electrons near the Ferm i energy. In actual calculations, we introduce a cut-o for the logarithm ic discretization of the conduction band. D ue to the limitation of computer resources, we keep m low energy states. In this paper, we set = 5 and m = 3000. N ote that the tem perature T is de ned as  $T = (N - 1)^{-2}$  in the NRG calculation, where N is the num ber of the renorm alization step. The phonon basis for each JT m ode is truncated at a nite num ber  $N_{ph}$ , which is set as N  $_{ph} = 20$  in this paper.

#### 4. Results

First let us discuss the CEF states on the basis of H<sub>e</sub>. In Figs.1 (a) and 1 (b), we show the CEF energy levels for n = 2 and 3, respectively. Here we set = 0.1 eV,  $W = 6 10^4 \text{ eV}$ , and y = 0.3. Since the e ects of B<sub>6</sub><sup>0</sup> and B<sub>6</sub><sup>2</sup> are included in H<sub>e</sub> as two-body potentials, H<sub>e</sub> can reproduce well the



Fig.1.CEF energy levels of H  $_{\rm e}~$  for (a) n= 2 and (b) n= 3.W e set = 0.1eV, W =  $~6~~10^{~4}{\rm eV}$  , and y= 0.3.

CEF energy levels of the local H am iltonian H in the realistic interm ediate coupling region with  $=J_H$  in the order of 0.1.As for details, see R ef. [23].

In order to determ ine the value of x for Nd-based led skutterudites, here we recall that in PrOs<sub>4</sub>Sb<sub>12</sub>, the ground state is  $\frac{1}{1}$  singlet and the excited state is  $\frac{4}{4}$  triplet with sm all excitation energy as large as 10 K [B1{35}]. Such a situation is well reproduced by choosing x= 0.4 for n= 2 in F ig.1(a). Now we change rare-earth ion from P r<sup>3+</sup> (n= 2) to N d<sup>3+</sup> (n= 3). In principle, it is not necessary to modify the CEF parameters even if rare-earth ion is changed, since the CEF potential is given by the sum of electrostatic potentials from ligand anions. Note, however, that the CEF potentials may be changed due to the substitution of T and/or X in RT<sub>4</sub>X<sub>12</sub>.

W hen we set x=0.4 for n=3 in Fig. 1(b), it is observed that the ground state for n = 3 at x = 0.4 is <sub>67</sub> quartet and the state is 5 doublet with the excitation energy of 0.02 eV .E xperim ents for N dO s4 Sb12 have suggested 67 ground and 5 excited states with the excitation energy of 220K [36]. It should be rem arked that the theoreticalCEF energy levels for n = 3 agree wellw ith experim ental results for NdO s4Sb12, by using the CEF parameters deduced from the CEF energy levels for P rO  $s_4 \, {\rm Sb}_{12}\, . \, W$  e note that in NdFe<sub>4</sub>P<sub>12</sub>, both the ground and states have been found to be 67 quartet with the excitation energy of 222 K [8]. However, in any case, the ground state quartet is well separated from the rst excited state both for N dO s4 Sb12 and N dFe4 P 12. In such a situation, it is considered that low -tem perature multipole properties are not sensitive to the rst excited state. Thus, in the following discussion, we x = 0.4.

For the purpose to understand the CEF energy lev-els of N dFe<sub>4</sub>P<sub>12</sub>, it is necessary to consider st those of P rFe<sub>4</sub>P<sub>12</sub>. Here we note that the hybridization e ect has been considered to play an important role to understand the di erence in the CEF energy states among P r-based

led skuttenudites [37{39]. In order to determ ine the CEF energy levels of  $N dFe_4P_{12}$ , it is also in portant to include the e ect of hybridization for the case of n= 3. Such calculations can be done, in principle, by using the e ective m odel H<sub>e</sub> on the basis of the j-j coupling scheme. It is one of future problem s.

Now we proceed to the NRG results of H. First let us consider the case without the coupling between f electrons



Fig. 2. (a) T and (b)  $S_{\mbox{im}\mbox{p}}$  and  $C_{\mbox{im}\mbox{p}}$  vs. temperature for n=3 without JT phonons.

and JT phonons. In Fig. 2 (a), we show the multipole susceptibility . The dom inant multipole moment in the lowtem perature region is the mixture of 4u m agnetic and 5u octupole, given by

$$M_{a} = p_{a}J_{4ua} + q_{a}T_{4ua} + r_{a}T_{5ua};$$
(18)

where we nd that p = 0.989,  $q_a = 0.0258$ , and  $r_a = 0.0258$ 0:146 for a= x, y, and z. The m ixture of 4u and 5u m om ents is characteristic of T<sub>h</sub> sym m etry. In fact, when we calculate the multipole susceptibility for  $O_h$  symmetry (y= 0) using the same parameters except for y, we actually nd that  $r_a = 0.$  It is one of in portant features of led skutterudites with T<sub>h</sub> symmetry that 4u magnetic moment is accompanied with 5u octupole. Note that the magnitude of  $r_a$ depends on param eters. The secondary multipole state is given by 2u octupole. We also nd another mixture of 4u m agnetic and 5u octupole m om ents, with reduced m agnitude of susceptibility. In Fig. 2(b), we show entropy and speci c heat. At low tem peratures, there rem ains an entropy of log 4, originating from localized 67 quartet, since we consider the hybridization between au conduction band and 5 state. In actuality, there should exist a nite hybridization between eu conduction bands and 67 states, even if the value is not large com pared with that between  $a_u$  conduction and  $_5$  electrons. Thus, the entropy of log 4 should be eventually released.

Next we include the e ect of dynam ical JT phonons, but before proceeding to the num erical results, let us consider intuitively what happens. In the j-j coupling picture, we accommodate three electrons into the one-electron levels with 5 and 67. Note that 5 is lower than 67, since the ground state of n=2 is  $\frac{1}{1}$  singlet, which is mainly composed of doubly occupied 5. When we accommodate one more electron, it should be put into 67. Thus, the 67 quartet ground state is obtained. Intuitively, the 4-fold degeneracy is understood by the combination of spin and orbital degrees of freedom.

Here we consider the JT potential in the adiabatic approximation. Note that in actuality, the potential is not static, but it dynamically changes to follow the electron motion. For = 0, the potential is continuously degenerate along the circle of the bottom of the M exican-hat potential. Thus, we obtain double degeneracy in the vibronic state concerning the rotational JT modes along clockwise and anti-clockwise directions. When a temperature becomes



Fig. 3. (a) T , (b)  $S_{imp}$  and  $C_{imp}$ , and (c)  $M_{i}i$  and  $M_{i}^{2}i$  (i= 2 and 3) vs temperature for = 0. (d) T , (e)  $S_{imp}$  and  $C_{imp}$ , and (f)  $M_{i}^{2}i$  (i= 2 and 3) vs. temperature for = 0.002.

lower than a characteristic energy T , which is related to a time scale to turn the direction of rotational JT m odes, the entropy of log 2 should be eventually released, leading to K ondo-like behavior [16], since the speci c rotational direction disappears due to the average over the long enough time.

In Figs. 3(a) and 3(b), we show multipole susceptibilities, entropy, and speci c heat for !=0.1, =0.5, and = 0.0. Note that we suppress the cubic anham onicity. We nd that the results do not seem to be qualitatively changed from Figs. 2 (a) and 2 (b), in spite of the JT active situation. For the dom inant m ixed multipole m om ent, we nd p = 0.902,  $q_a = 0.412$ , and  $r_a = 0.127$  for a = x, y, and z in eq. (18). In Fig. 3(c), we show the temperature dependence of average displacements, At relatively high tem perature, we nd nite values of  $hQ_2^2i$  and hQ 3i, while  $hQ_2 i = hQ_3 i = 0$ . Namely, JT vibrations occur around the origin without displacem ents. As the tem perature is decreased, such vibrations are also suppressed and the situation in the low-tem perature region is well described by the electronic model, leading to the sim ilarity between Figs. 2 (a) and 3 (a) at low tem peratures.

However, when we include the e ect of anham onicity, three potentialm inim a appear in the bottom of the JT potential in the adiabatic approxim ation. Since the rotational mode should be changed to the quantum tunneling am ong three potentialm inim a at low tem peratures, the frequency is e ectively reduced in the factor of  $E^{=!}$ , where E is the potential barrier. Then, we expect to observe the quasi-K ondo behavior even in the present tem perature range, when we include the e ect of cubic anharm onicity.

In Figs. 3 (d) and 3 (e), we show multipole susceptibilities, entropy, and speci cheat for ! = 0.1, = 0.5, and = 0.002. For T > 10<sup>4</sup>, susceptibilities for both 3g quadrupole moments are signi cant, suggesting that quadrupole uctuations are dominant in this temperature region. However, when the temperature is decreased,  $_{3gv}$  is suppressed, while  $_{3gu}$  remains at low temperatures. Instead, them ixed multipole with 4u m agnetic and 5u octupole moments becomes dominant. Note that for M<sub>z</sub> is slightly larger than those for M<sub>x</sub> and M<sub>y</sub>.

A round at  $T = 10^{-3}$ , we nd a peak in the speci c heat, since an entropy of log 2 is released. A s m entioned above, this is considered to be quasi-K ondo behavior, originating from the suppression of the rotationalm ode of dynam ical JT phonons [16]. In this case, the entropy of log 2 concerning orbital degree of freedom coupled with JT phonons is released, while there still remains spin degree of freedom in the localized <sub>67</sub> quartet. In fact, at low temperatures, m agnetic susceptibility becom es dom inant.

In Fig. 3 (f), we show the tem perature dependence of average displacements. For T > 10<sup>5</sup>, we nd  $M_2^2$  if 0 and  $M_2^2$  if 0, suggesting that both Q<sub>2</sub> and Q<sub>3</sub> modes are active. This is consistent with the nite values of susceptibilities for 0<sub>3gu</sub> and 0<sub>3gv</sub>. Note that the Q<sub>3</sub>-type displacement is considered to occur, since  $M_2^2$  i = 0 and  $M_3$  if 0. In the low-temperature region, we nd  $M_2^2$  i =  $M_2$  i = 0, while  $M_3^2$  i =  $M_3$  i f 0, indicating that only Q<sub>3</sub>-type JT vibration is active with nite displacement. This is also consistent with the result that  $_{3gu}$  remains at low temperatures, since the vibration mode is xed as Q<sub>3</sub>-type after the quasi-K ondo phenomenon occurs.

## 5. D iscussion and Sum m ary

In this paper, we have clari ed that the magnetic state with active quadrupole uctuations appears in Nd-based

led skuttenudites, when we consider the e ect of dynamical JT phonons. In fact, the existence of degenerate quadrupolem om ents has been suggested from the experim ent of elastic constant [8]. In Fig. 3 (d), in the tem perature region of  $T > 10^{-4}$ , we have observed that both O<sub>3gu</sub> and O<sub>3gv</sub> become e active, although they are not exactly degenerate due to the e ect of JT phonons. How ever, the idea of the magnetic state with active quadrupole uctuations seems to be consistent with actual Nd-based led skuttenudites. Note that in the present NRG calculations, we cannot conclude the nature of intersite magnetic interaction, ferrom agnetic or antiferrom agnetic, although Nd-based led skutterudites are ferrom agnets.

In Nd-based led skutterudites such as NdFqP<sub>12</sub> [40] and NdRu<sub>4</sub>Sb<sub>12</sub> [41], peculiar behavior of a resistance m in-

in um in the tem perature region higher than a C unie tem – perature  $T_C$  has been pointed out. Quite recently, N p-based lled skutterudite NpFqP<sub>12</sub> has been synthesized [42]. Since actinide ion is considered to take a tetravalent state in the lled skutterudite structure, NpFqP<sub>12</sub> is also classi ed into the case of n= 3, except for the di erence between 4f and 5f electrons states. In fact, NpFe<sub>4</sub>P<sub>12</sub> is also a ferrom agnet with  $T_C = 23$  K and a sim ilar resistance m in-im um has been observed above  $T_C$  [42].

In the present paper, we have observed the quasi-K ondo behavior for the case of n=3.W hen the tem perature is decreased, an entropy log2 originating from the double degeneracy of the vibronic state is released. In other word, thism ay be quadrupole K ondo phenom enon, since quadruple (orbital) degrees of freedom are tightly coupled with JT phonons, as understood from Figs. 3(d) and 3(f). It seems to be premature to conclude the mechanism only from the present num erical results, but the quasi-K ondo behavior due to dynam ical JT phonons coupled with orbital (quadrupole) degrees of freedom may explain qualitatively the resistance minim um phenom enon in N d-based

lled skutterudites. Further investigations are required.

A sm entioned in the introduction, concerning them echanism of magnetically robust heavy-ferm ion phenom ena observed in Sm O  $s_4$ Sb<sub>12</sub> [13], a potential role of phonons has been pointed out from the view point of the K ondo e ect with non-magnetic origin [14]. In this context, the quasi-K ondo behavior due to the dynam ical JT phonons may be a possible candidate to understand magnetically robust heavy-ferm ion phenom enon. In fact, we have found the quasi-K ondo behavior also for the case of n= 5, but the details of the results on Sm -based led skuttenudites will be discussed elsewhere [43]. Here we emphasize the common feature between N d-and Sm -based led skuttenudites with the same  $_{67}$  quartet ground states. From this view point, itm ay be interesting to design the experiment to detect the e ect of rattling in N d-based led skuttenudites.

In sum mary, we have discussed the multipole state for n=3 by analyzing the multipole Anderson model with the use of the NRG method. When we do not consider the coupling between JT phonons and f electrons in  $_{67}$  quartet, we have found that the dominant multipole moment is the mixture of 4u magnetic and 5u octupole. The secondary multipole state is 2u octupole. When the coupling with JT phonons is switched and the cubic anharm onicity is included, the magnetic ground state includes signi – cant quadrupole uctuations and we have found the quasi-K ondo behavior due to the entropy release concerning the rotational JT mode.

## A cknow ledgm ent

The author thanks H. Harima, K. Kubo, T. D. Matsuda, Y. Nakanishi, H. Onishi, and M. Yoshizawa for discussions and comments. This work has been supported by a Grant-in-Aid for Scienti cResearch in Priority Area \Skuttenudites" under the contract No. 18027016 from the Ministry of E ducation, C ulture, Sports, Science, and Technology of Japan. The author has been also supported by a G rant-in-A id for Scienti c R esearch (C) under the contract N 0.18540361 from Japan Society for the P rom otion of Science. The computation of this work has been done using the facilities of the Supercomputer C enter of Institute for Solid State P hysics, U niversity of Tokyo.

## References

- [1] See, for instance, J. Phys. Soc. Jpn. Suppl. 75 (2006).
- [2] H.Sato et al.: J.Phys.: Condens. M atter 15 (2002) S2063.
- [3] Y.Aokietal: J.Phys.Soc.Jpn.74 (2005) 209.
- [4] K. Takegahara, H. Harim a and A. Yanase: J. Phys. Soc. Jpn.
   70 (2001) 1190; ibid. 70 (2001) 3468; ibid. 71 (2002) 372.
- [5] Y.Aokietal: Phys. Rev. B 65 (2002) 064446.
- [6] K.Iwasa et al: Physica B 312-313 (2002) 834.
- [7] Y.Nakanishietal:preprint.
- [8] Y.Nakanishietal: Phys.Rev.B 69 (2004) 064409.
- [9] M.Yoshizawa et al.: J.Phys.Soc.Jpn. 74 (2005) 2141.
- [10] K.Hachitanietal: Phys.Rev.B 73 (2006) 052408.
- [11] S.M asakiet al.: J. Phys. Soc. Jpn. 75 (2006) 053708.
- [12] T. Takim oto: J. Phys. Soc. Jpn. 75 (2005) 034714.
- [13] S. Sanada et al: J. Phys. Soc. Jpn. 74 (2005) 246.
- [14] S.Yotsuhashi et al.: J.Phys.Soc.Jpn.74 (2005) 49.
- [15] T.Goto et al: Phys. Rev. B 69 (2004) 180511 (R).
- [16] T.Hotta: Phys.Rev.Lett. 95 (2006) 197201.
- [17] T. Hotta: Physica B 378-380 (2006) 51.
- [18] T.Hotta: J.Phys.Soc.Jpn.74 (2005) 1275.
- [19] T.Hotta: Rep. Prog. Phys. 69 (2006) 2061.
- [20] K.R. Lea, M. J.M. Leask and W. P.W olf: J. Phys. Chem. Solids 23 (1962) 1381.
- [21] M.T.Hutchings: Solid State Phys. 16 (1964) 227.
- [22] T.Hotta and K.Ueda: Phys.Rev.B 67 (2003) 104518.
- [23] T. Hotta and H. Harim a: J. Phys. Soc. Jpn. 75 (2006) No. 12, in press. See also cond-m at/0602646.
- [24] H. Harim a and K. Takegahara: J. Phys.: Condens. M atter 15 (2003) S2081.
- [25] H.Harim a et al.: J. Phys. Soc. Jpn. Suppl. 71 (2002) 70.
- [26] R. Shiina, H. Shiba and P. Thalm eier: J. Phys. Soc. Jpn. 66 (1997) 1741.
- [27] T.Hotta: J.Phys.Soc.Jpn.74 (2005) 2425.
- [28] K.Kubo and T.Hotta: J.Phys.Soc.Jpn.75 (2006) 013702.
- [29] K.G.W ilson: Rev. M od. Phys. 47 (1975) 773.
- [30] H.R.Krishna-murthy, J.W. W ilkins and K.G.W ilson: Phys. Rev.B 21 (1980) 1003.
- [31] Y.Aokietal: J.Phys.Soc.Jpn.71 (2002) 2098.
- [32] M.Kohgietal: J.Phys.Soc. Jpn. 72 (2003) 1002.
- [33] T. Tayam a et al: J. Phys. Soc. Jpn. 72 (2003) 1516.
- [34] K.Kuwahara et al: J.Phys.Soc.Jpn.73 (2004) 1438.
- [35] E.A.Gorem ychkin et al.: Phys. Rev. Lett. 93 (2004) 157003.
- [36] P.-C. Ho et al: Phys. Rev. B 72 (2005) 094410.
- [37] J. O tsuki, H. K usunose and Y. K uram oto: J. Phys. Soc. Jpn. 74 (2005) 200.
- [38] Y.Kuram oto et al.: Prog. Theor. Phys. Suppl. 160 (2005) 134.
- [39] Y.Kuram oto et al.: J.Phys. Soc. Jpn. Suppl. 75 (2006) 209.
- [40] H.Sato et al: Phys. Rev. B 62 (2000) 15125.
- [41] K.Abe et al.: J. Phys.: Condens. M atter 14 (2002) 11757.
- [42] D.Aokietal: J.Phys.Soc.Jpn.75 (2006) 073703.
- [43] T.Hotta:preprint.