

Soft quasicrystals – Why are they stable?

Ron Lifshitz^y and Haim Diamant

^ySchool of Physics & Astronomy and School of Chemistry

Raymond and Beverly Sackler Faculty of Exact Sciences

Tel Aviv University, Tel Aviv 69978, Israel

October 31, 2006

Abstract

In the last two years we have witnessed the exciting experimental discovery of soft matter with nontrivial quasiperiodic long-range order – a new form of matter termed a soft quasicrystal. Two groups have independently discovered such order in soft matter: Zeng et al. [Nature 428 (2004) 157] in a system of dendrimer liquid crystals; and Takano et al. [J. Polym. Sci. Polym. Phys. 43 (2005) 2427] in a system of ABC star-shaped polymers. These newly discovered soft quasicrystals not only provide exciting platforms for the fundamental study of both quasicrystals and of soft matter, but also hold the promise for new applications based on self-assembled nanomaterials with unique physical properties that take advantage of the quasiperiodicity, such as complete and isotropic photonic band-gap materials. Here we provide a concise review of the emerging field of soft quasicrystals, suggesting that the existence of two natural length-scales, along with 3-body interactions, may constitute the underlying source of their stability.

1 Background

The discovery of quasicrystals by Shechtman more than two decades ago [1] signaled the beginning of a remarkable scientific revolution [2], in which some of the most basic notions of condensed matter physics have undergone a thorough reexamination. Today, the science of quasicrystals, with its growing number of textbooks [3{10], is in its adolescence. Old paradigms are being carefully transformed into new ones [11]; definitions are being changed [12]; space-group theory has been generalized to quasicrystals using two alternative approaches [13{16], and even extended to treat novel long-range order possessing color [17] or magnetic symmetry [18,19]); and many fundamental problems – including Bak's famous question: "Where are the atoms?" [20] – are gradually finding their solutions. Nevertheless, other questions that are equally important have remained unanswered to this day. Some of these – such as the stabilization of quasicrystals, the role of clusters, and the importance of the phason degree of freedom – were hotly debated at a recent International Conference on Quasicrystals [21].

We know today that quasicrystals are more common than one had originally expected. Scores of binary and ternary metallic alloys are known to form quasicrystalline phases [22] – mostly with icosahedral or decagonal point-group symmetry – and more are being discovered all the time. Nevertheless, it is only in the last couple of years that quasicrystals have been discovered (independently) in two

different soft-matter systems: dendrimers [23–25] and star block copolymers [26–28]. These newly discovered soft quasicrystals not only provide exciting alternative experimental platforms for the basic study of quasiperiodic long-range order, but also hold the promise for new applications based on self-assembled nanomaterials [29–31], with unique electronic or photonic properties that take advantage of the quasiperiodicity. One example is the isotropic photonic band gaps that have been demonstrated in artificially-constructed octagonal [32] and dodecagonal [33] quasicrystals.

The first step in a theoretical study of soft quasicrystals would be to provide an explanation for their thermodynamic stability. To this date, soft quasicrystals have been observed only with dodecagonal point-group symmetry. Their source of stability is therefore likely to be different from their solid-state siblings, yet a good understanding of the stability of one quasiperiodic system may help to understand the stability of the other. The purpose of this article is to propose initial suggestions as to the source of stability of soft quasicrystals, while providing a concise background on the subject.

2 Quasicrystals | Terminology and general framework

Let us consider a scalar function $\rho(\mathbf{r})$ that describes the electronic density or the ionic potential of a material. The Fourier transform of a quasiperiodic density $\rho(\mathbf{r})$ (we shall assume here that the transform always exists) has the form

$$\rho(\mathbf{r}) = \sum_{\mathbf{k} \in L} \rho(\mathbf{k}) e^{i\mathbf{k} \cdot \mathbf{r}}, \quad (1)$$

where the (reciprocal) lattice L is a finitely generated \mathbb{Z} -module, i.e. it can be expressed as the set of all integral linear combinations of a finite number D of d -dimensional wave vectors, $\mathbf{b}^{(1)}; \dots; \mathbf{b}^{(D)}$. In the special case where $D = d$, called the rank of the crystal, is equal to the physical dimension d , the crystal is periodic. We refer to all quasiperiodic crystals that are not periodic as "quasicrystals".¹

It is useful to introduce a physical setting based on the notion of symmetry breaking [35–37]. Let us assume that the quasiperiodically-ordered state, described by $\rho(\mathbf{r})$, is a symmetry-broken stable ground state of some generic free energy F , invariant under all translations and rotations in \mathbb{R}^d . This is the same as saying that the physical interactions giving rise to the quasicrystal are themselves translationally and rotationally invariant, and that the ground state breaks this symmetry. The free energy F is a functional of $\rho(\mathbf{r})$, which in Fourier space takes the general form

$$F[\rho] = \sum_{\mathbf{n} \in L} A(\mathbf{k}_1; \dots; \mathbf{k}_n) \rho(\mathbf{k}_1) \dots \rho(\mathbf{k}_n) \quad (2)$$

Based on the idea of such a generic free energy, Rokhsar, Wright, and Mermin [13] introduced the notion of indistinguishability, namely that two functions $\rho(\mathbf{r})$ and $\rho^0(\mathbf{r})$ are indistinguishable if a generic free energy cannot distinguish between them and assigns them both the same value. It then follows

¹ Some older texts require crystals to possess so-called "forbidden symmetries" in order to be regarded as quasicrystals. It is now understood that such a requirement is inappropriate. See Ref. [12] for details, and Ref. [34] for examples of square and cubic quasicrystals.

that $\psi(\mathbf{r})$ and $\psi^0(\mathbf{r})$ are indistinguishable if and only if

$$\forall \mathbf{k} \in L : \psi^0(\mathbf{k}) = e^{2\pi i \phi(\mathbf{k})} \psi(\mathbf{k}); \quad (3)$$

where $\phi(\mathbf{k})$, called a gauge function, has the property that $\phi(\mathbf{k}_1 + \mathbf{k}_2) = \phi(\mathbf{k}_1) + \phi(\mathbf{k}_2)$ whenever \mathbf{k}_1 and \mathbf{k}_2 are in L , where \equiv denotes equality to within an additive integer.

Gauge functions are useful in describing the relations between the different symmetry-broken ground states of F . D rager and M erm in [38] showed that gauge functions form a vector space V of all real-valued linear functions on the lattice L , and because L has rank D , V is a D -dimensional vector space over the real numbers. The space V contains, as a subspace, all the integral-valued linear functions on L . This subset, which has the algebraic structure of a rank- D \mathbb{Z} -module (just like L itself) is denoted by L . Gauge functions in L leave the ground-state density invariant. Gauge functions that belong to the quotient space V/L take the ground state described by ψ into a different, yet indistinguishable, ground state described by some other density function ψ^0 . Thus, one can parameterize all the related symmetry-broken ground states of F on a simple D -torus | the order parameter space V/L .

Different, yet indistinguishable, ground states may also be related by rotations $g \in O(d)$. In this case ψ^0 in (3) is simply a rotated version of ψ , and for each such rotation g there is a special gauge function ϕ_g , called a phase function, satisfying

$$\forall \mathbf{k} \in L : \psi(g\mathbf{k}) = e^{2\pi i \phi_g(\mathbf{k})} \psi(\mathbf{k}); \quad (4)$$

The set of all rotations satisfying (4) forms the point group of the crystal, and along with the corresponding phase functions completely characterizes its space group [13{15,17{19].

3 Ordered soft matter

A wide variety of materials in physical-chemical and biological systems lie in the intermediate region between simple liquids and crystalline solids. Examples include liquid crystals, suspensions, emulsions, polymer solutions or melts, surfactant solutions, and biomaterials [39]. These materials, termed complex fluids, structured fluids, or soft condensed matter, are mostly viscoelastic liquids, which contain a certain degree of inner structure. Unlike simple fluids or solids, where either entropy (in the former) or interactions (in the latter) dominate, the behavior of soft matter is determined by an intricate interplay between interactions and thermal fluctuations. Consequently, soft-matter systems exhibit remarkably rich structures and dynamics, which have been the subject of extensive experimental and theoretical research during the past several decades [39{43].

Soft materials may possess long-range or quasi-long-range order [44,45]. As was first demonstrated by Onsager [46], such liquid-crystalline phases can be obtained in systems as simple as molecular liquids whose molecules have anisotropic shapes. In more complex, self-assembling systems, liquid-crystalline phases are usually made of intermediate structures, which form as a result of incompatible molecular groups linked together by chemical bonds. For example, amphiphilic molecules (surfactants) are composed of hydrophilic and hydrophobic groups, leading, in aqueous solution, to the formation

of mesoscopic structures such as micelles or fluid membranes [40{42]. These structures, at sufficiently high concentration, organize into various ordered phases [42,43]. Another important example is block copolymers| macromolecules composed of two or more chemically bonded, chain-like blocks [47{51]. The incompatibility of the different blocks gives rise to a variety of ordered structures in melts and in solutions. The main advantage of block copolymers as self-assembling systems is the relative ease at which the sizes and properties of the different blocks (and, thus, the resulting mesoscopic structures) can be controlled. Block copolymers, like homopolymers, can be linear or branched. Two branched architectures which can be well controlled, and thus have been drawing considerable attention recently, are star polymers [52{62], where the chains are joined in one point, and dendrimers [60,63{66], having a tree-like structure.

Phenomenological models based on generic free energies similar to (2) have been very successful in describing phase diagrams and transitions in soft matter [43{45,50,51,67,68]. In such models one identifies an order parameter, which may be a scalar function| as in Eq. (2)| or a vector function, and formulates, based on symmetry, a free-energy functional as an expansion in the order parameter and its gradients. Such an expansion is generally expected to become a good approximation close to a continuous phase transition, where variations in the order parameter occur over large length scales. The reason for the success of this approach for soft systems, in particular, lies in their intermediate, mesoscopic building blocks, which are significantly larger than the atomic scale. For example, spatial variations of the order parameter in block copolymer phases must occur over lengths larger than a polymer block, which may be many nanometers. As a result, composition variations and interfaces are smoother in soft materials than in crystalline solids, rendering a long-wavelength gradient expansion a much better approximation. The situation becomes even better in the case of flexible star polymers and dendrimers| which are of particular relevance here| as the effective pair potentials in these systems have an "ultra-soft" short-range repulsion [54{57,60,62,66].

4 Recent discovery of soft-matter quasicrystals

Our current discussion is motivated by the recent experimental discovery that soft matter can self-assemble into structures with quasiperiodic long-range order.² In one case, dendrimers that assume a conical shape assemble into micelles, which then pack to form a perfect dodecagonal (12-fold) quasicrystal [23{25]. In another case, ABC star-shaped block terpolymers| in which the length ratios of the three arms, B/A and C/A , can be chemically-controlled| assemble into a host of 2-dimensional columnar structures. One of these, composed of square and triangle motifs (tiles), is suspected as being a dodecagonal quasicrystal, or at least a periodic approximant of such a quasicrystal, which under minor parameter tweaking may indeed form a perfect quasicrystal [26{28]. This phase has also been reproduced numerically using lattice Monte Carlo simulations by D'otera and Gemma [75]. A similar square-triangle tiling has also been observed in a liquid crystal composed of T-shaped molecules [76], which forms yet a third soft system which may potentially self-assemble into a dodecagonal qua-

²For the sake of historical accuracy, it should be noted that at some point the blue phase III of liquid crystals, also known as the "blue fog", was thought to have icosahedral quasicrystalline order [69,70], but this eventually turned out not to be the case [71,72]. Also, incommensurate helical twist-grain-boundary phases are known to exist in smectic liquid crystals [73,74], but the quasiperiodic order in this case is essentially only along the 1-dimensional screw axis.

quasicrystal. The characteristic length of the basic building blocks ranges in these systems from 10 to 100 nanometers [2 to 3 orders of magnitude greater than the atomic length scales found in hard quasicrystals. This property of soft quasicrystals is what will potentially make them useful as functional self-assembled nanomaterials, and at the same time as a new experimental platform for detailed real-space and real-time study of quasiperiodic long-range order.

Very little is known at this point about these soft quasicrystals. For example, even the space groups of the observed phases have not been determined, although from the diffraction patterns of the dendrimer liquid crystals given by Zeng et al. [23,24] it seems that they have a 12-fold screw axis, and therefore, most likely, the nonsymmorphic space group $P12_1/m$ [14]. More generally, the same questions [21] concerning the mechanism of stabilization, the role of clusters in formation and dynamics, and the importance of phasons, apply to soft quasicrystals as they do to hard quasicrystals. Yet the answers may be more tractable (albeit possibly different as the systems are quite different). Thus, the study of soft quasicrystals will clearly have implications well beyond the limits of the specific soft systems that have been discovered so far, and is likely to promote the fundamental understanding of quasicrystals in general.

5 Why are soft quasicrystals stable? { Insight from the Lifshitz-Petrich equation

Motivated by experiments with parametrically-excited surface waves (Faraday waves), exhibiting dodecagonal quasiperiodic order [77], Lifshitz and Petrich [78] developed a model for describing the pattern-forming dynamics of a two-dimensional field in which two length scales undergo a simultaneous instability. This model is an extension of the Swift-Hohenberg equation [79], which is used for describing a variety of different pattern-forming systems [80]. Its dynamics is relaxational, $\partial_t = -F =$, driving a 2-dimensional field $(x,y;t)$ towards the minimum of an effective free energy" (2),

$$F_{LP}[\phi] = \int dx dy \left[\frac{1}{2} |\nabla^2 \phi|^2 + \frac{1}{2} [(r^2 + 1)(r^2 + q^2) \phi]^2 - \frac{1}{3} \phi^3 + \frac{1}{4} \phi^4 \right]; \quad (5)$$

yielding a dynamical equation of the form

$$\partial_t \phi = - \left[(r^2 + 1)^2 (r^2 + q^2)^2 \phi + \phi^2 - \phi^3 \right]; \quad (6)$$

It essentially mimics the dynamics of a generic 2-dimensional material in search of its ground state, and therefore offers us important insight and a good starting point for our current investigation of soft quasicrystals.

The Lifshitz-Petrich free energy F_{LP} is indeed generic, imposing only two requirements on a material, described by a 2-dimensional density $(x,y;t)$: (a) The existence of two characteristic length scales, whose ratio is given by the parameter q ; and (b) The existence of effective 3-body interactions, whose importance is given by the relative strength of the parameter β . In [78] we were able to show analytically (using standard methods [44, ch. 4.7] and [81]), and demonstrate numerically, that if q is chosen around $2 \cos(\pi/12) = \sqrt{2 + \frac{2}{3}}$, 1.932 one can obtain a ground state with quasiperiodic

long-range order and dodecagonal symmetry,³ yet no choice of q yields globally-stable ground states with octagonal or decagonal symmetry. The latter two have insufficient triplets of wave vectors in the Fourier Lattice L [Eq. (1)] that add up to zero to overcome the cost of additional density modes, as compared with the hexagonal state. Thus, in two dimensions, the requirements of two length scales and 3-body interactions are sufficient to stabilize dodecagonal quasicrystals, but insufficient to stabilize octagonal or decagonal quasicrystals. This raises the possibility that the fact that the soft quasicrystals discovered to date are all dodecagonal, may be accounted for using a free energy similar to F_{LP} . Note that for hard quasicrystals the situation is different| decagonal quasicrystals are thermodynamically stable whereas octagonal and dodecagonal quasicrystals are believed to be metastable| indicating that the stabilization mechanism for soft quasicrystals might be quite different from that of hard quasicrystals.

6 Future directions

6.1 Free-energy functionals and stability analysis

At the outset, the experimental soft systems in which quasicrystalline order has been observed seem to satisfy the basic assumptions of the Lifshitz-Petrich theory described in Sec. 5. The asymmetric and heterogeneous structure of the star polymers and dendrimers will most likely require more than one length scale for an appropriate coarse-grained description. Their ultra-soft repulsion and resulting strong inter-penetration [54{57,60,62,66] imply that 3-body interactions should be significant [59]. Thus, we expect that studies that we are currently undertaking will yield functionals similar in nature to F_{LP} of Eq. (5). Significant differences may emerge, nonetheless, as the systems considered here are 3-dimensional and differ in their microscopic structure. For instance, two order parameters rather than one might be required [28], which could potentially allow point-group symmetries other than dodecagonal to be observed.⁴

A 3-dimensional version of an LP-like free energy may remind the reader of the early attempts by Kalugin, Kitaev, and Levitov [84, KKL], who extended the model of Alexander and McTague [85], to establish that the icosahedral quasicrystal has lower free energy than the competing bcc phase. Narasimhan and Ho [86, NH] managed to show in their model that there are regions in parameter space in which a dodecagonal quasicrystal is favored and other regions in which a decagonal quasicrystal is favored. These attempts were eventually discontinued after it was shown by Gronlund and Mermin [81] that the addition of a quartic term to the cubic free energy of KKL reverses the outcome of the calculation, establishing the bcc phase as the favored one. For hard crystals it is unclear where to truncate the expansion of the free energy and whether such a truncation is fully justified. As has been mentioned in Sec. 3, for the soft systems considered here the truncation of the expansion should be more valid. We therefore intend to reexamine some of the old conclusions when considering the stability of soft quasicrystals based on generic free energy considerations. Roan and Shakhnovich [87] performed such a study for the case of icosahedral order in diblock copolymers and concluded that such

³Note the seeming coincidence that the star-shaped polymers, giving rise to the approximant dodecagonal quasicrystal, have ratios $B/A = 1$ and $C/A = 1:9$ [27,28].

⁴Models with two order parameters were suggested also for hard quasicrystals [82] and pattern-forming systems [83], yielding additional ground-state symmetries.

order is only metastable. Nevertheless, we are encouraged by the old results of NH who established the stability of dodecagonal, as well as decagonal, quasicrystals within the same model.

Another key insight can be drawn from a recent theoretical observation, according to which dispersions of soft, fuzzy, particles are essentially different in their thermodynamics from those of hard particles [88, 89]. The overlap of the soft "coronas" surrounding the particles leads to a driving force acting to minimize their interfacial area, in analogy with foams. Consequently, unusual liquid-crystalline structures can be stabilized in systems of soft spheres [88–91]. Both star polymers and flexible dendrimers fall into this fuzzy category, yet they may be highly aspherical. Likos et al. [66] have also shown that stars and flexible dendrimers have the same kind of soft pair potentials. We thus expect such considerations of interfacial-area minimization to become highly relevant in the upcoming study of soft quasicrystals.

6.2 Dislocation and phason dynamics

Valuable knowledge about the nature of quasiperiodic order can be obtained by studying its topological defects [35, 37, 92], and its low-energy collective excitations—in particular those associated with the phason degrees of freedom. Much like phonons, phasons are low-energy excitations of the quasicrystal, only that instead of slightly shifting the atoms away from their equilibrium positions, the relative positions of atoms are changed. Their existence stems directly from the fact that the dimension D of the order parameter space $V = L$ is greater than the physical dimension d . Thus, in addition to d independent (acoustic) phonon modes there are $D - d$ independent phason modes. The exact role of phasons in the stabilization and the dynamics of quasicrystals is not fully-understood [21], yet their presence is unequivocally-detected in numerous types of experiments. Edagawa et al. [93] have recently managed to observe the real-time thermal fluctuations of single phason-ips in a solid-state quasicrystal—a remarkable achievement that requires a very sophisticated experiment. Soft quasicrystals, with their larger length scales, may be much better suited for real-time investigation of phason dynamics.

We have recently begun investigating the motion of dislocations and the dynamics of phasons in the dodecagonal ground state of the LP equation [94, 95]. We are studying, both analytically and numerically, such questions as the climb velocity of dislocations under strain, the pinning of dislocations by the underlying quasiperiodic structure under conditions of weak diffusion, and the relaxation of phason strain as two dislocations of opposite topological sign merge and annihilate each other. We have also used similar theoretical procedures in the analysis of defect dynamics in a real experimental nonlinear photonic quasicrystal [96]. Similar investigations of more realistic models of soft quasicrystals, or on the soft systems themselves, should provide valuable insight into their physical nature.

Acknowledgments

One of the authors (RL) thanks X. Zeng and T. Døstera for fruitful discussions while attending "Aperiodic 2006" in Zao, Japan. This research is funded by the Israel Science Foundation through grant number 684/06.

References

- [1] D. Shechtman, I. Blech, D. Gratias, and J.W. Cahn, "Metallic phase with long-range orientational order and no translational symmetry," *Phys. Rev. Lett.* 53 (1984) 1951.
- [2] J.W. Cahn, "Epilogue," *Proceedings of the 5th International Conference on Quasicrystals*, Ed. C. Janot and R. Mosseri, (World Scientific, Singapore, 1996) 807.
- [3] Early papers in the field were collected by P.J. Steinhardt and S. Ostlund (Ed.), *The physics of quasicrystals*, (World Scientific, Singapore, 1987).
- [4] For an introductory textbook on quasicrystals, see C. Janot, *Quasicrystals: A Primer*, Second Edition (Clarendon Press, Oxford, 1994).
- [5] For collections of reviews on the physical properties of quasicrystals, see Z.M. Stadnik (Ed.), *Physical Properties of Quasicrystals*, (Springer-Verlag, Berlin Heidelberg, 1999).
- [6] and J.B. Suck, M. Schreiber, and P. Haussler (Eds.), *Quasicrystals: An Introduction to Structure, Physical Properties, and Applications*, (Springer-Verlag, Berlin Heidelberg, 2002).
- [7] For an introductory textbook on the mathematics of quasicrystals, see M. Senechal, *Quasicrystals and Geometry* (Cambridge University Press, Cambridge, 1995).
- [8] For detailed reviews on the mathematics of quasicrystals, see R.V. Moody (Ed.), *The Mathematics of Long-Range Aperiodic Order*, (Kluwer, Dordrecht, 1997).
- [9] and M. Baake and R.V. Moody (Eds.), *Directions in Mathematical Quasicrystals*, (American Mathematical Society, Providence, 2000).
- [10] For a detailed overview on the applications of quasicrystals, see J.M. Dubois, *Useful quasicrystals*, (World Scientific, Singapore, 2005).
- [11] R. Lifshitz, "The rebirth of crystallography," *Zeit. Krist.* 217 (2002) 432.
- [12] R. Lifshitz, "Quasicrystals: A matter of definition," *Foundations of Physics* 33 (2003) 1703.
- [13] N.D. Mermin, "The space groups of icosahedral quasicrystals and cubic, orthorhombic, monoclinic, and triclinic crystals," *Revs. Mod. Phys.* 64 (1992) 3.
- [14] D.A. Rabson, N.D. Mermin, D.S. Rokhsar, and D.C. Wright, "The space groups of axial crystals and quasicrystals," *Rev. Mod. Phys.* 63 (1991) 699.
- [15] R. Lifshitz, "The symmetry of quasiperiodic crystals," *Physica A* 232 (1996) 633.
- [16] T. Janssen, A. Janner, A. Looijenga-Vos, and P.M. de Wöl, "Incommensurate and commensurate modulated structures," in *International Tables for Crystallography, Volume C*, Ed. A.J.C. Wilson, (Kluwer Academic, Dordrecht, 1992) 797.
- [17] R. Lifshitz, "Theory of color symmetry for periodic and quasiperiodic crystals," *Rev. Mod. Phys.* 69 (1997) 1181.
- [18] R. Lifshitz, "Symmetry of magnetically ordered quasicrystals," *Phys. Rev. Lett.* 80 (1998) 2717.
- [19] R. Lifshitz and S. Even-Dar Mandel, "Magnetically-ordered quasicrystals: Enumeration of spin groups and calculation of magnetic selection rules," *Acta Cryst. A* 60 (2004) 167.
- [20] P. Bak, "Icosahedral crystals: Where are the atoms?" *Phys. Rev. Lett.* 56 (1986) 861.
- [21] C.L. Henley, M. de Boissieu, and W. Steurer, "Discussion on clusters, phasons, and quasicrystal stabilization," *Phil. Mag.* 86 (2006) 1131.
- [22] A.-P. Tsai, "Metallurgy of quasicrystals," *Ref. [5], Chap. 2*.
- [23] X. Zeng, G. Ungar, Y. Liu, V. Percec, A.E. Dulcey, and J.K. Hobbs, "Supramolecular dendritic liquid quasicrystals," *Nature* 428 (2004) 157.
- [24] X. Zeng, "Liquid quasicrystals," *Current Op. in Colloid and Interface Sci.* 9 (2005) 384.
- [25] G.H. Mehl, "Quasiperiodic organization in soft self-assembling matter," *Angew. Chem. Int. Ed.* 44 (2005) 672.
- [26] A. Takano, S. Wada, S. Sato, T. Arai, K. Hirahara, T. Kazama, S. Kawahara, Y. Isono, A. Ohno, N. Tanaka, and Y. Matsushita, "Observation of cylinder-based microphase-separated structures from ABC star-shaped terpolymers investigated by electron computerized tomography," *Macromolecules* 37 (2004) 9941.

- [27] Y. Matsushita, W. Kawashima, A. Noro, A. Takano, N. Tanaka, T. Doteru, "Mesoscopic Archimedean tilings in polymeric stars," *Acta Cryst. A* 61 (2005) C38.
- [28] A. Takano, W. Kawashima, A. Noro, Y. Isono, N. Tanaka, T. Doteru, Y. Matsushita, "A mesoscopic Archimedean tiling having a new complexity in polymeric stars," *J. Polym. Sci. Polym. Phys.* 43 (2005) 2427.
- [29] W. A. Lopes and H. M. Jaeger, "Hierarchical self-assembly of metal nanostructures on diblock copolymer scaffolds," *Nature* 414 (2001) 735.
- [30] V. Percec, M. G. Lodge, T. K. Bera, Y. Miura, I. Shiyankovskaya, K. D. Singer, V. S. K. Balagurusamy, P. A. Heiney, I. Schnell, A. Rapp, H.-W. Spiess, S. D. Hudson, and H. Duan, "Self-organization of supramolecular helical dendrimers into complex electronic materials," *Nature* 419 (2002) 384.
- [31] D. K. Smith, A. R. Hirst, C. S. Love, J. G. Hardy, S. V. Bignell, and B. Huang, "Self-assembly using dendritic building blocks | Towards controllable nanomaterials," *Prog. Polym. Sci.* 30 (2005) 220.
- [32] C. Jin, B. Cheng, B. Man, Z. Li, D. Zhang, S. Ban, and B. Sun, "Band gap and wave guiding effect in a quasiperiodic photonic crystal," *Appl. Phys. Lett.* 75 (1999) 1848.
- [33] M. E. Zoorob, M. D. B. Charlton, G. J. Parker, J. J. Baumberg, M. C. Netti, "Complete photonic bandgaps in 12-fold symmetric quasicrystals," *Nature* 404 (2000) 740.
- [34] R. Lifshitz, "The square Fibonacci tiling," *J. of Alloys and Comp.* 342 (2002) 186.
- [35] P. W. Anderson, *Basic notions of condensed matter physics* (Addison Wesley, Reading MA, 1997), Chap. 2.
- [36] P. C. Martin, O. Parodi, and P. S. Pershan, "Unified hydrodynamic theory for crystals, liquid crystals, and normal fluids," *Phys. Rev. A* 6 (1972) 2401.
- [37] J. P. Sethna, *Entropy, order parameters, and complexity* (Clarendon Press, Oxford, 2006), Chap. 9.
- [38] J. Dager and N. D. Mermin, "Superspace groups without the embedding: The link between superspace and Fourier-space crystallography," *Phys. Rev. Lett.* 76 (1996) 1489.
- [39] T. A. Witten, *Structured Fluids* (Oxford University Press, Oxford, 2004).
- [40] D. F. Evans and H. Wennerstrom, *The Colloidal Domain*, 2nd ed. (Wiley, New York, 1999).
- [41] *Micelles, Membranes, Microemulsions, and Monolayers*, Eds. W. M. Gelbart, A. Ben-Shaul, and D. Roux (Springer, New York, 1994).
- [42] S. A. Safran, *Statistical Thermodynamics of Surfaces, Interfaces, and Membranes*, 2nd ed. (Wiley, Boulder, 2003).
- [43] G. Gompper and M. Schick, *Self-Assembling Amphiphilic Systems*, in *Phase Transitions & Critical Phenomena*, Ed. C. Domb and J. L. Lebowitz (Academic Press, London, 1994).
- [44] P. M. Chaikin and T. C. Lubensky, *Principles of Condensed Matter Physics* (Cambridge University Press, New York, 1995).
- [45] P.-G. de Gennes and J. Prost, *The Physics of Liquid Crystals*, 2nd ed. (Oxford University Press, New York, 1993).
- [46] L. Onsager, "The effects of shapes on the interaction of colloidal particles," *Ann. N.Y. Acad. Sci.* 51 (1949) 627.
- [47] I. W. Hamley, *The Physics of Block Copolymers* (Oxford University Press, Oxford, 1998).
- [48] I. W. Hamley, *Block Copolymers in Solution: Fundamentals and Applications* (Wiley, New York, 2005).
- [49] F. S. Bates and G. H. Fredrickson, "Block copolymers | designer soft materials," *Phys. Today* 52 (1999) 32.
- [50] F. S. Bates and G. H. Fredrickson, "Block copolymer thermodynamics | theory and experiment," *Annu. Rev. Phys. Chem.* 41 (1990) 525.

- [51] G. H. Fredrickson and F. S. Bates, "Dynamics of block copolymers: theory and experiment", *Annu. Rev. Mat. Sci.* 26 (1996) 501.
- [52] G. S. Grest, L. J. Fetters, J. S. Huang, and D. R. Richter, "Star polymers: experiment, theory, and simulation", *Adv. Chem. Phys.* 94 (1996) 67.
- [53] N. Hadjichristidis, S. Pispas, M. Pitsikalis, H. Iatrou, and C. Vlahos, "Asymmetric star polymers: synthesis and properties", *Adv. Polymer Sci.* 142 (1999) 71.
- [54] C. N. Likos, H. Lowen, M. Watzlawek, B. Abbas, O. Jucknischke, J. Allgaier, and D. R. Richter, "Star polymers viewed as ultrasoft colloidal particles", *Phys. Rev. Lett.* 80 (1998) 4450.
- [55] M. Watzlawek, H. Lowen, and C. N. Likos, "The anomalous structure factor of dense star polymer solutions", *J. Phys. Condens. Matter* 10 (1998) 8189.
- [56] M. Watzlawek, C. N. Likos, and H. Lowen, "Phase diagram of star polymer solutions", *Phys. Rev. Lett.* 82 (1999) 5289.
- [57] A. Jusu, M. Watzlawek, and H. Lowen, "Effective interaction between star polymers", *Macromolecules* 32 (1999) 4470.
- [58] C. von Ferber, A. Jusu, M. Watzlawek, C. N. Likos, and H. Lowen, "Polydisperse star polymer solutions", *Phys. Rev. E* 62 (2000) 6949.
- [59] C. von Ferber, A. Jusu, C. N. Likos, H. Lowen, and M. Watzlawek, "Triplet interactions in star polymer solutions", *Eur. Phys. J. E* 2 (2000) 311.
- [60] C. N. Likos, N. Homann, H. Lowen, and A. A. Louis, "Exotic fluids and crystals of soft polymeric colloids", *J. Phys. Condens. Matter* 14 (2002) 7681.
- [61] C. Mayer, C. N. Likos, and H. Lowen, "Equilibrium properties of highly asymmetric star-polymer mixtures", *Phys. Rev. E* 70 (2004) 041402.
- [62] G. M. Gration and R. D. Kamien, "Interfaces in diblocks: a study of miktoarm star copolymers", *Macromolecules* 37 (2004) 7371; 38 (2005) 2022.
- [63] T. H. Mourey, S. R. Turner, M. Rubinstein, J. M. J. Frechet, C. J. Hawker, and K. L. Wooley, "Unique behavior of dendritic macromolecules | intrinsic viscosity of polyether dendrimers", *Macromolecules* 25 (1992) 2401.
- [64] D. Boris and M. Rubinstein, "A self-consistent mean field model of a starburst dendrimer: dense core vs. dense shell", *Macromolecules* 29 (1996) 7251.
- [65] V. Percec, C. H. Ahn, G. Ungar, D. J. P. Yearley, M. Moller, and S. S. Sheiko, "Controlling polymer shape through the self-assembly of dendritic side-groups", *Nature* 391 (1998) 161.
- [66] C. N. Likos, M. Schmidt, H. Lowen, M. Ballau, D. Potschke, and P. Lindner, "Soft interaction between dissolved flexible dendrimers: theory and experiment", *Macromolecules* 34 (2001) 2914.
- [67] H. Diamant, G. Ariel, and D. Andelman, "Kinetics of surfactant adsorption: the free energy approach", *Colloids & Surfaces A* 183 (2001) 259.
- [68] H. Diamant and M. E. Cates, "Swelling kinetics of the onion phase", *European Physical Journal E* 4 (2001) 223.
- [69] R. M. Homreich and S. Shtrikman, "Broken icosahedral symmetry: A quasicrystalline structure for cholesteric blue phase III", *Phys. Rev. Lett.* 56 (1986) 1723.
- [70] D. S. Rokhsar and J. P. Sethna, "Quasicrystalline textures of cholesteric liquid crystals: Blue phase III?" *Phys. Rev. Lett.* 56 (1986) 1727.
- [71] D. C. Wright and N. D. Mermin, "Crystalline liquids: The blue phases", *Rev. Mod. Phys.* 61 (1989) 385.
- [72] T. C. Lubensky and H. Stark, "Theory of a critical point in the blue-phase-III isotropic phase diagram", *Phys. Rev. E* 53 (1996) 714.
- [73] S. R. Renn and T. C. Lubensky, "Abrikosov dislocation lattice in a model of the cholesteric-smectic-A transition", *Phys. Rev. A* 38 (1988) 2132.
- [74] J. W. Goodby, M. A. Wagh, S. M. Stein, E. Chin, R. Pindak and J. S. Patel, "Characterization of a new helical smectic liquid crystal", *Nature* 337 (1989) 449.

- [75] T. D. Otera and T. G. Mason, "Dodecagonal quasicrystal in a polymeric alloy," *Phil. Mag.* 86 (2006) 1085.
- [76] B. Chen, X. Zeng, U. Baumeister, G. Ungar, C. T. Schierske, "Liquid crystalline networks composed of pentagonal, square, and triangular cylinders," *Science* 307 (2005) 96.
- [77] W. S. Edwards and S. Fauve, "Parametrically excited quasicrystalline surface waves," *Phys. Rev. E* 47 (1993) R788.
- [78] R. Lifshitz and D. M. Petrich, "Theoretical model for Faraday waves with multiple-frequency forcing," *Phys. Rev. Lett.* 79 (1997) 1261.
- [79] J. B. Swift and P. C. Hohenberg, "Hydrodynamic fluctuations at the convective instability," *Phys. Rev. A* 15 (1977) 319.
- [80] For a review, see M. C. Cross and P. C. Hohenberg, "Pattern formation outside of equilibrium," *Rev. Mod. Phys.* 65 (1993) 851.
- [81] For more detail, see L. Gronlund and N. D. Mermin, "Instability of quasicrystalline order in the local Kalugin-Kitaev-Levitov model," *Phys. Rev. B* 38 (1988) 3699.
- [82] N. D. Mermin and S. M. Troian, "Mean-field theory of quasicrystalline order," *Phys. Rev. Lett.* 54 (1985) 1524.
- [83] H. W. Müller, "Model equations for two-dimensional quasipatterns," *Phys. Rev. E* 49 (1994) 1273.
- [84] P. A. Kalugin, A. Yu. Kitaev, and L. C. Levitov, "Al₁₃Si₁₄: a six-dimensional crystal," *JETP Lett.* 41 (1985) 145.
- [85] S. Alexander and J. M. C. Laguerre, "Should all crystals be bcc? Landau theory of solidification and crystal nucleation," *Phys. Rev. Lett.* 41 (1984) 702.
- [86] S. Narasimhan and T. L. Ho, "Mean-field-theory study of the energetics of icosahedral, decagonal, and dodecagonal quasicrystals," *Phys. Rev. B* 37 (1988) 800.
- [87] J. R. Roan and E. I. Shakhnovich, "Stability study of icosahedral phases in diblock copolymer melt," *J. Chem. Phys.* 109 (1998) 7591.
- [88] P. Zifferland and R. D. Kamien, "Maximizing entropy by minimizing area: Towards a new principle of self-organization," *J. Phys. Chem. B* 105 (2001) 10147.
- [89] W. Kung, P. Zifferland, and R. D. Kamien, "The foam analogy: from phases to elasticity," *J. Colloid Interface Sci.* 275 (2004) 539.
- [90] Y. Li, S.-T. Lin, and W. A. Goddard III, "Efficiency of various lattices from hard ball to soft ball: Theoretical study of thermodynamic properties of dendrimer liquid crystal from atomistic simulation," *J. Am. Chem. Soc.* 126 (2004) 1872.
- [91] M. A. Glaser, G. M. Gerson, R. D. Kamien, A. Kosmrlj, C. D. Santangelo, and P. Zifferland, "Soft spheres make more mesophases," preprint, (cond-mat/0609570).
- [92] N. D. Mermin, "The topological theory of defects in ordered media," *Rev. Mod. Phys.* 51 (1979) 591.
- [93] K. Edagawa, K. Suzuki, and S. Takeuchi, "High resolution transmission electron microscopy observation of thermally fluctuating phasons in decagonal Al-Cu-Co," *Phys. Rev. Lett.* 85 (2000) 1674; and "HRTEM observation of phason flips in Al-Cu-Co decagonal quasicrystal," *J. Alloys and Compounds* 342 (2002) 271.
- [94] G. Barak, "Dislocation dynamics in quasiperiodic patterns," M.Sc. Thesis, (Tel Aviv University, 2005).
- [95] G. Barak and R. Lifshitz, "Dislocation dynamics in a dodecagonal quasiperiodic structure," *Phil. Mag.* 86 (2006) 1059.
- [96] B. Freedman, G. Bartal, M. Segev, R. Lifshitz, D. N. Christodoulides, and J. W. Fleischer, "Observation of wave and defect dynamics in nonlinear photonic quasicrystals," *Nature* 440 (2006) 1166.