Evidence of Strong-Coupled Superconductivity in CaC₆ from Tunneling Spectroscopy

C. Kurter,^{1,2,*} L. Ozyuzer,^{1,3} Daniel Mazur,^{1,2} J. F. Zasadzinski,²

D. Rosenmann,¹ H. Claus,¹ D. G. Hinks,¹ and K. E. Gray¹

¹Materials Science Division, Argonne National Laboratory, Argonne IL 60439

²Physics Division, Illinois Institute of Technology, Chicago, IL 60616

³Department of Physics, Izmir Institute of Technology, Izmir, Turkey

(Dated: December 23, 2021)

Point-contact tunneling on CaC₆ crystals reproducibly reveals superconducting gaps, Δ , of 2.3±0.2 meV which are ~ 40% larger than earlier reports. That puts CaC₆ into the class of very strong-coupled superconductors since $2\Delta/kT_c \sim 4.6$. Thus soft Ca phonons will be primarily involved in the superconductivity, a conclusion that explains the large Ca isotope effect found recently for CaC₆. Consistency among superconductor-insulator-normal metal (SIN), SIS and Andreev reflection (SN) junctions reinforces the intrinsic nature of this result.

PACS numbers: 74.50.+r, 74.70.-b

The discovery of superconductivity at 11.6 K in CaC₆ at ambient pressures [1] and up to 15.1 K at 8 GPa[2]has reinvigorated interest in graphite intercalated compounds. While the possibility of unconventional superconductivity had been suggested [3], the collective experimental data on CaC_6 are consistent with weaklycoupled, electron-phonon driven superconductivity with a nearly isotropic energy gap. The recent scanning tunneling spectroscopy [4], specific heat [5] and penetration depth measurements[6] all indicate BCS weak-coupled superconductivity that is consistent with linear response theory[7]. However, Mazin et al.[8] have pointed out several outstanding problems with the above picture including its inconsistency with recent data[9] showing a large isotope effect for Ca and the less than perfect agreement with theory for the temperature dependence of the specific heat and the upper critical field, $H_{c2}(T)$, data. The isotope effect and $H_{c2}(T)$ dilemmas would disappear and the specific heat data might be better fit if CaC_6 were a strong-coupled superconductor.

Here we report evidence for strong coupling in CaC₆ based on point-contact tunneling (PCT) from both superconductor-insulator-normal metal (SIN) junctions and SIS junctions. Both junction types reveal a gap parameter significantly larger than previously reported, yielding a strong coupling ratio, $2\Delta/kT_c \sim 4.6$. Andreev reflection spectroscopy (SN junctions) on the same crystals support this large ratio. We will show that such a large strong coupling ratio, along with the modest T_c , indicates that soft phonon modes must dominate the pairing of electrons. Low frequency modes in CaC₆ only involve Ca and, therefore, our results lead to a natural explanation of the large Ca isotope effect. This result may have broader implications by constraining the band structure and/or the calculation of gap anisotropy[10].

Preparation of CaC_6 used the alloy method as described by Emery et al.[11]. A stainless steel (SS) tube is cleaned, baked at 900 °C in vacuum and loaded with lithium and calcium in a 3:1 atomic ratio. Natural,



FIG. 1: The (00ℓ) diffraction peaks using Cu-K_{α} radiation. Inset: Normalized magnetization in a field of 0.1 G.

single-crystal graphite flakes are added and then the SS ampoule is mechanically sealed and placed inside a onezone furnace, evacuated to 2×10^{-7} Torr, and then filled with argon gas. The reaction takes place in an argon atmosphere for 10 days at 350 °C. The ampoule is then transferred to an argon glove bag where the alloy is remelted and the Ca intercalated graphite crystals are extracted.

Figure 1 displays the x-ray diffraction pattern of a typical CaC₆ crystal showing the (00ℓ) diffraction peaks obtained using Cu- K_{α} radiation taken in the Bragg-Brentano geometry. No lines corresponding to hexagonal graphite are present within our detection limits confirming the bulk nature of the samples. Magnetization data, shown in the inset of Fig. 1, were taken in a μ -metal-shielded, non-commercial SQUID magnetometer on warming in a field of 0.1 G parallel to the *c*-axis of the sample after zero-field cooling. They reveal a sharp, ultra-low-field superconducting transition onset at 11.6 K.

Tunnel junctions were obtained at T=1.65 K usi a PCT method described in detail elsewhere[12]. T CaC_6 samples (and CaC_6 tips for SIS junctions) we mounted on a point contact tunneling system in a N₂ : mosphere and immediately cooled down to 4.2 K. For S. junctions, CaC_6 crystal flakes were oriented such that t vertical motion of the gold tip was nominally along the axis. For SIS junctions a tip was fabricated from anoth CaC_6 crystal and aligned such that the tip and substra crystals had similar *c*-axis orientations. Initial contacts the tips in both configurations led to junctions of varyi quality but with typical gap parameters, Δ , smaller th 1.7 meV. The relative ease of forming SIN and SIS tu nel junctions indicates that there is an insulating surfa layer on CaC_6 , which is presumably the high band-g CaO. After repeated contacts of tip and sample, like resulting in some mechanical cleaning of the CaC_6 su face, junctions were found which had higher quality cha acteristics and gap parameters > 2 meV. The proof this low-temperature, effective-ultra-high-vacuum clea ing of the surface was the fairly common appearance Andreev reflection spectra (SN junctions) indicating clean superconductor-Au junction.

Figure 2 shows I-V and dI/dV vs. V for some of t high quality tunnel junctions (two SIN and one SIS) a one SN Andreev contact. The well-defined conductar peaks for the SIS junctions are seen at twice the volta of the SIN peaks as expected. The large peak-height to-high-voltage-background ratio as well as the relative low zero-bias conductance (near zero for the SIS jur tion) attest to the high quality of the junctions. Th far we have never observed the flat sub-gap conductance expected for an isotropic s-wave energy gap, which may be an indication of gap anisotropy [10]. For convenience, fits of the raw conductance data to a BCS density-ofstates modified (as in Ref. [4]) with an empirical scattering rate [13], Γ , are shown as dashed lines in Figs. 2a and 2b. The gaps for these SIN and SIS junctions are 2.3 and 2.4 meV respectively. The Andreev reflection data (Fig. 2a, left inset) show the expected factor-of-two enhancement of the conductance below the energy-gap voltage for a clean metal-to-metal contact. The SN energy gap can only be estimated to be 2.1-2.6 meV as there is no rigorous fitting procedure available for the entire spectrum.

Figure 3 displays a set of SIN tunneling data obtained on three different CaC_6 crystals. As in previous reports[4], the tunneling conductance shows no evidence of multiband superconductivity like the distinct energy gaps observed in MgB₂ (for a review see Ref. [14]). While the numerous junctions analyzed after initial surface cleaning exhibit a varying degree of quality, fits to all such SIN and SIS data lead to a range of gaps from 2.1 to 2.5 meV, with an average value of 2.3 meV.

We can easily rule out the possibility of extrinsic factors emulating the large gap we observe in this work.



FIG. 2: (Color online) (a) Two SIN dI/dV(V) are shown for different junctions at 1.65 K, each fit with an identical BCS curve. (b) One dI/dV(V) of an SIS junction at 1.65 K, along with the BCS fit. Fits are using the parameters shown in respective plots. Right-hand insets: Corresponding I(V) data, the I(V) curve in (a) corresponds to the lower dI/dV. Lefthand inset in (a): An example of measured Andreev reflection characteristics, I(V) and corresponding dI/dV(V) shown. All insets: Horizontal axis are voltages in mV, left vertical axis are currents in μ A, right vertical axis, when present, is conductance in mS.

For example, the SIN data could be from an inadvertent SIS break-junction caused by a piece of the CaC₆ crystal sticking to the Au tip. In such a case, the peak at 2.3 mV would be the result of two pieces with an average Δ =1.15 meV, a value much smaller than published range of 1.6–1.8 meV. This is unlikely. Furthermore the temperature dependencies of SIN and SIS junctions are very different, e.g., as T increases, SIS junctions reveal a closing of the 2 Δ conductance peak, as well as the development of a conductance peak at zero bias due to thermally created quasiparticles. The temperature dependence of one SIN junction with Δ =2.3 meV is shown in Fig. 4. Although not as high a quality junction, the



FIG. 3: (Color online) A variety of SIN junctions made on three different crystals of CaC_6 showing consistent gap values of 2.1-2.5 meV.



FIG. 4: Temperature dependence of dI/dV is shown for one SIN junction.

data show typical SIN behavior without any evidence for a zero-bias peak developing at higher T.

It is also possible that the SIS junctions, as in Fig. 2b, are multiple junctions, e.g., two independent SIS junctions in series. But in this case the observation of a

single conductance peak would require that the two independent junctions have identical resistances, a highly unlikely scenario. No such multiple-junction structure can be conceived for the Andreev reflection (SN) data.

Continuing this critical examination of the data, the increase in T_c from 11.5 K to ~15.1 K at a pressure of 8 GPa[2] in CaC₆ forces us to consider the possibility that the larger Δ results from a larger T_c brought about by local tip pressure. Noting that the yield stress of high purity Au at 4.2 K is less than 100 MPa readily dispels this possibility[15]. In addition, we find similar large gaps for SIS junctions without the soft Au tip. Therefore we conclude that the common observation of $\Delta \sim 2.3$ meV for SIN, SIS and SN junctions are not consequences of extrinsic factors.

The importance of this result is that it puts CaC_6 in the class of very strongly coupled superconductors $(2\Delta/kT_c \sim 4.6)$, which implies that the electron-phonon coupling strength, λ , is significantly larger than the theoretical result [7] of 0.83. Here λ is an integral over $\alpha^2 F(\omega)/\omega$, where α is the electron-phonon matrix element and $F(\omega)$ is the density of phonon states of frequency ω . Clearly, λ is heavily weighted by the low-frequency contributions, so the combination of large λ and modest T_c can only occur within standard strong-coupling theory of Allen and Dynes [16] if their T_c -equation prefactor, ω_{log} , defined therein, is very small. It is useful to remember another strong-coupled superconductor, Pb, where the origins of the large strong coupling ratio and similar T_c of 7.2 K are its low-energy (4-8 meV) phonons [17]. Using the empirical results on conventional superconductors [18], a strong coupling ratio of 4.6 and T_c of 11.6 K leads to a characteristic phonon energy, $\omega_{log} \sim 5-7$ meV. In the case of CaC₆, such soft modes are a characteristic of the Ca intercalant only[7, 8]. This would then suggest that Ca phonons are primarily involved in the pairing of electrons, a result which is quite different from the weak-coupling picture, but which would readily explain the nearly full isotope coefficient found with Ca isotopic substitution[9].

To date, the phonon density of states in CaC_6 has not been measured but phonon dispersions determined from band structure and linear response theory[7, 8] show inplane zone boundary Ca modes near 10 meV. It is possible that such modes could be renormalized to even lower frequencies due to strong electron-phonon coupling. Such renormalization is not included in linear response theory. The present work would argue that $\alpha^2 F(\omega)$ is large at low frequencies and relatively small for higher phonon frequencies. It would then imply that linear response theory[7] is underestimating the strength of coupling to the low-frequency Ca modes.

Our proposed strong-coupled, low-frequency peak in $\alpha^2 F(\omega)$ should be observable in the tunneling conductance, as for the classic case of Pb[16]. We see a noticeable and reproducible negative deviation of the raw SIN data (Fig. 2a) in high-quality junctions from the smeared BCS fit for $|eV| > \Delta$. The characteristic energy expected from strong coupling to phonons is where this feature crosses over from a negative to positive deviation, and it is measured with respect to Δ . That energy is at most 5 meV, and although it would appropriately agree with the range of $\omega_{log} \sim 5-7$ meV estimated above, the present quality of tunneling data and our understanding of the normal state background are insufficient to confirm it or rule it out.

In summary, the superconducting gap of CaC_6 is found to be 2.3 meV. This gap exceeds the previously reported value by approximately 40%. Noting the consistency of SIN, SIS and SN junction configurations, and ruling out possible extrinsic causes, we conclude that this value is representative of the intrinsic energy gap of CaC_6 . The resulting strong coupling ratio of ~ 4.6 changes considerably the current understanding of superconducting pairing in CaC_6 . While this is a radical departure from the present consensus of weak coupling [4, 5, 6, 7], it provides a direct explanation for the nearly full isotope effect found with Ca substitution[9] and may help resolve the linear temperature dependance of $H_{c2}(T)$. This result may have a broader impact on band structure and electron-phonon calculations[8]. Our result argues for intercalant-driven superconductivity with electron pairing dominated by the low-frequency Ca phonons; an idea that was proposed earlier [19].

This research was supported by the US Department of Energy, Basic Energy Sciences-Materials Sciences under Contract No. DE-AC02-06CH11357 at the Argonne National Laboratory operated by UChicago Argonne, LLC.

* Corresponding author: kurter@anl.gov

- T. E. Weller, M. Ellerby, S. S. Saxena, R. P. Smith, and N. T. Skipper, Nature Phys. 1, 39 (2005).
- [2] A. Gauzzi, S. Takashima, N. Takeshita, C. Terkura, H. Takagi, N. Emery, C. Hérold, P. Lagrange, and G. Loupias, Phys. Rev. Lett. 98, 067002 (2007).
- [3] G. Csányi, P. B. Littlewood, A. H. Nevidomskyy, C. J. Pickard, and B. D. Simons, Nature Phys. 1, 42 (2005).
- [4] N. Bergeal, V. Dubost, Y. Noat, W. Sacks, D. Roditchev, N. Emery, C. Hérold, J.-F. Marêché, P. Lagrange, and G. Loupias, Phys. Rev. Lett. 97, 077003 (2006).

- [5] J. S. Kim, R. K. Kremer, L. Boeri, and F. S. Razavi, Phys. Rev. Lett. 96, 217002 (2006).
- [6] G. Lamura, M. Aurino, G. Cifariello, E. Di Gennaro, A. Andreone, N. Emery, C. Hérold, J.-F. Marêché, and P. Lagrange, Phys. Rev. Lett. 96, 107008 (2006).
- [7] M. Calandra and F. Mauri, Phys. Rev. Lett. 95, 237002 (2005).
- [8] I. I. Mazin, L. Boeri, O. V. Dolgov, A. A. Golubov, G. B. Bachelet, M. Giantomassi, and O. K. Andersen, (Proceedings of the M2S Conference in Dresden, 2006), cond-mat/0606404. (to be published in Physica C) (2006).
- [9] D. G. Hinks, D. Rosenmann, H. Claus, M. S. Bailey, and J. D. Jorgensen, Phys. Rev. B 75, 014509 (2007).
- [10] A. Sanna, G. Profeta, A. Floris, A. Marini, E. K. U. Gross, and S. Massidda, Phys. Rev. B 75, 020511(R) (2007).
- [11] N. Emery, C. Hérold, M. d'Astuto, V. Garcia, C. Bellin, J. F. Marêché, P. Lagrange, and G. Loupias, Phys. Rev. Lett. 95, 111801 (2005).
- [12] L. Ozyuzer, J. F. Zasadzinski, and K. E. Gray, Cryogenics 38, 911 (1998).
- [13] For the SIN junctions in Fig. 2 the ratio, Γ/Δ , is less than 9% which is sufficiently small to give confidence in the determined gap value. However, we stress that there is no *a-priori* reason to suspect that such a large scattering rate is intrinsic to CaC₆. In conventional superconductors large scattering rates consistent with strongcoupling effects occur only near T_c. Note especially for the SIS junction in Fig. 2b that the shoulder at eV ~ Δ predicted by the smeared BCS model is not observed. This suggests that the non-BCS nature of the sub-gaptunneling conductance is arising from factors other than simple quasiparticle scattering effects in the DOS.
- [14] H. Schmidt, J. F. Zasadzinski, K. E. Gray, and D. G. Hinks, Physica C 385, 221 (2003).
- [15] The room temperature value of the yield stress of high purity Au is about 40 MPa. Using the temperature dependence of the tensile stress[20], we estimate a yield stress of about 80 MPa at 4.2 K. This is two-orders-ofmagnitude lower than the 8 GPa needed to raise T_c to 15.1 K.
- [16] P. B. Allen and R. C. Dynes, Phys. Rev. B 12, 905 (1975), eq. 30.
- [17] W. L. McMillan and J. M. Rowell, Phys. Rev. Lett. 14, 108 (1965).
- [18] J. P. Carbotte, Rev. Mod. Phys. 62, 1027 (1990).
- [19] I. I. Mazin, Phys. Rev. Lett. 95, 227001 (2005).
- [20] R. D. McCammon and H. M. Rosenberg, Proc. R. Soc. London A 242, 203 (1957).