## A ngular dependence of the melting of the porous vortex matter in $B_{2}Sr_{2}CaCu_{2}O_{8}$

Nurit Avraham, 1 Y.Y.Goldschmidt, J.T.Liu, Y.M yasoedov, M.Rappaport,

E. Zeldov,  $^{1}$  C. J. van der Beek,  $^{3}$  M. Konczykowski,  $^{3}$  and T. Tam egai<sup>4</sup>

<sup>1</sup>D epartm ent of Condensed M atter Physics, The W eizm ann Institute of Science, Rehovot 76100, Israel

<sup>2</sup>D epartm ent of Physics and Astronom y, University of Pittsburgh, Pittsburgh, Pennsylvania 15260, USA

<sup>3</sup>Laboratoire des Solides Irradies, CNRS UMR 7642 and CEA-CMS-DRECAM, Ecole Polytechnique, 91128 Palaiseau, France

<sup>4</sup> Department of Applied Physics, The University of Tokyo, Hongo, Bunkyo-ku, Tokyo 113-8656, Japan

(D ated: M arch 23, 2024)

Vortex matter in  $B_{12}Sr_2CaCu_2O_8$  with a low concentration of tilted columnar defects (CDs) was studied using magneto-optical measurements and molecular dynamics simulations. It is found that while the dynamic properties are signicantly a ected by tilting the magnetic eld away from the CDs, the thermodynamic transitions are angle independent. The simulations indicate that vortex pancakes remain localized on the CDs even at large tilting angles. This preserves the vortex thermodynamics, while vortex pinning is considerably weakened due to kink sliding.

The dynam ic and therm odynam ic properties of vortex m atter in high  $T_c$  superconductors are strongly a ected by the introduction of correlated disorder in the form of columnar defects (CDs). In the presence of a low concentration of CDs, experimental [1, 2, 3] and theoretical results [4, 5, 6, 7, 8, 9] indicate the presence of two vortex subsystem s: vortices localized on pinning centers and interstitial vortices between them . At low temperature, a porous vortex solid phase is created. A rigid matrix of vortices, strongly pinned on a network of random CDs, is form ed, while the interstitial vortices create relatively ordered nanocrystals within the pores of the matrix. When the tem perature is increased, the interstitial vortices melt while the rigid matrix remains localized, form ing a nanoliquid phase in which nanodroplets of liquid are weakly con ned within the pores of the matrix. When the tem perature is increased further, the matrix delocalizes at the delocalization transition, and the liquid becom es homogeneous. Above this transition the elect of the CDs on vortex dynam ics becom es indiscernible.

This picture holds when the angle between the average induction B and the CDs is zero. According to theoreticalm odels [10, 11], for sm all , the localized vortices on CDs remain completely trapped along the CDs. At larger , the vortices form a staircase structure with segments trapped on dierent CDs connected by weakly pinned kinks. At still larger angles, the vortices follow the eld direction and are not a ected by the correlated nature of the CDs. In general, one expects the e ect of the correlated nature of the CD s to decrease as increases, and to vanish at = 90. In more isotropic materials such as YBa<sub>2</sub>Cu<sub>3</sub>O<sub>7</sub>, this picture is supported by various experiments, showing an angle dependent behavior in both dynam ic [12] and therm odynam ic [13] properties. In layered materials such as  $B_{12}Sr_2CaCu_2O_8$  (BSCCO), vortices consist of stacks of two-dim ensional pancake vortices (PVs) de ned in the superconducting CuO<sub>2</sub> layers only. M easurem ents of the equilibrium torque and m aqnetization in BSCCO [14] have shown that the CD occupation by PVs in the liquid phase is angle independent.

In contrast, Josephson plasm a resonance m easurements [15] show that the PV alignment in the liquid is signi – cantly a ected by CDs. The corresponding equilibrium properties of the solid phase have not been studied. Since the melting transition depends on the dierence in the behavior of the free energies of the solid and liquid, it is very interesting to study the angular dependence of the melting in the presence of CDs. Moreover, CDs are known to shift the melting line upward [1] and point disorder was found to shift it downward [16]. One might expect, therefore, that tilting B away from the CDs would shift them elting line continuously from above the pristine melting line to below it, reaching the lowest position at = 90, where CDs act like point defects.

Here, we study the angular dependence of the dynam ic and therm odynam ic properties of porous vortex m atter in BSCCO.Ourm easurements show that the irreversibility line shifts to low erT when the ekd is tilted away from the CDs, as expected [12, 17]. However, the therm odynam ic melting and delocalization lines have no angular dependence.Our simulations show that even at large angles the PV s are electively pinned by the CD s and therefore the therm odynam ic features remain una ected.On the other hand, the form ation of a kink structure of the PV stacks increases their mobility due to kink sliding, therefore suppressing the irreversible properties.

For the m easurem ents, BSCCO crystals ( $T_c$  90 K) were irradiated, at GAN IL, with 1 GeV Pb ions, through stainless steel masks with triangular arrays of 90 m holes. This produces am orphous colum nar tracks, with density  $n_d$  equal to the ion dose, only in those parts of the crystals situated under the holes. Crystals A and B, irradiated at 45 with respect to the c-axis, have matching elds B =  $n_d$  0 of 20 G and 30 G respectively. The m easurem ents were perform ed using di erential m agneto-optical im aging (DMO) [18] with a vector m agnet that allows application of a DC m agnetic eld in any direction, so that the local m agnetic response can be im aged over the full range of angles from B k CDs



FIG.1: (color online) (a) The inveversibility line  $H_{irr}^{cd}(T)$  of crystal A, mapped for ve angles between B and the CDs, from = 0 to 90 .  $H_m^p$  is the pristine melting line. (b) DMO in age of part of the sample at T = 79 K and H<sub>z</sub> = 35 Oe. (c) Flux pro les across the invadiated region [dashed line in (b)], at 67 K and H<sub>z</sub> = 22 Oe, for = 0 and 90.

(= 0) to B ? CDs (= 90).

Figure 1 (a) shows the irreversibility line of the irradiated regions H  $_{\rm irr}^{\rm cd}$  (T) on an H  $_{\rm z}$  T plane, where H  $_{\rm z}$  is the c-axis component of the applied eld, for di erent angles of B with respect to the CD s [19]. The curves were obtained using DMO with eld modulation of 1 O e, upon sweeping the temperature. Below H  $_{\rm irr}^{\rm cd}$  (T), the external eld modulation is shielded in the irradiated regions due to enhanced pinning [1]. Hence, the dark regions in the DMO im age (Fig. 1(b)) are the irradiated regions, while the bright background is the reversible pristine region. Upon increasing T, these dark regions gradually fade until they disappear com pletely at H  $_{\rm irr}^{\rm cd}$  (T), where the screening current drops to an unobservably low level.

Figure 1 (a) shows that upon tilting the eld away from the CDs (changing from 0 to 90), the irreversibility line shifts to lower tem peratures. For example, at H  $_z = 70$ O e the irreversibility tem perature at 90 is 2.5 K lower than at = 0. Even at = 90,  $H_{irr}^{cd}$  (T) rem ains slightly above the melting line of the vortex lattice in the pristine crystal, H  $_{\rm m}^{\rm p}$  (T). This is at odds with the expectation that at = 90 the CD s act as weak point disorder; then, the m elting and irreversibility lines are expected to lie below H  $_{\rm m}^{\rm p}$  (T ) [16]. The angular dependence of H  $_{\rm irr}^{\rm cd}$  (T ) is more pronounced at lower tem peratures. It decreases upon increasing T until it disappears completely at 82 K, above which all lines coincide with H  $_{m}^{p}$  (T). This behavior was observed for dierent samples with B of 20, 30 and 40 G.The relative shift in H  $_{\rm irr}^{\rm cd}$  (T) between = 0 to 90 was found to increase with  ${\tt B}$  .

To exam ine the vortex behavior below H  $_{\rm irr}^{\rm cd}$  (T), within the vortex solid phase, we perform ed conventional M O m easurements, in which a sequence of images is taken

while the applied eld H<sub>a</sub> is swept. Figure 1 (c) shows ux pro les across the irradiated regions. These have a linear (Bean-like) shape due to the enhanced pinning in these regions. The pro les were taken at H<sub>z</sub> = 220 e and T = 67 K, well below H<sup>cd</sup><sub>irr</sub>(T). At = 90, the pro le is very shallow. In contrast, at = 0, a clear sharp pro le is observed. The critical current, estim ated from the ux gradient, is 3.5 tim es higher at = 0 than at 90.



FIG.2: (color online) The melting transition in crystalB.(a) DMO image of part of the sample at H  $_z$  = 350e, T = 81 K. (b) LocalDMO intensity versus T for di errent angles . The peak around 80.4 K corresponds to the melting transition. The curves are vertically displaced for clarity.

The angular dependence of the melting transition was studied using DMO upon temperature sweeps with T modulation [1, 18]. The rst-order melting transition is characterized by a step in the equilibrium ux density, and appears as a bright signal in the DMO im ages. For example, the bright circular regions in Fig. 2 (a) are the irradiated areas that undergo melting, while the surrounding pristine regions are already in the liquid phase and hence appear as a darker background.

Figure 2 (b) shows the local DMO intensity, averaged over a region of 15 15 m<sup>2</sup> in one of the irradiated regions (red square in Fig. 2 (a)). The melting transition manifests itself as a peak in the local intensity as T is swept. Each curve corresponds to a di erent , while H<sub>z</sub> = 350 e was kept constant. In contrast to the irreversibility line that shifts to lower T upon increasing , the melting temperature remains una ected, even when B is perpendicular to the CDs. Moreover, the transition width, determ ined from the width of the peak, appears to be the same for all measured angles. Sim ilar results were obtained for di erent H<sub>z</sub> values. Note that the pristine melting line was found to have a weak linear dependence on the in-plane eld [20] which cannot be detected within our experimental resolution for our low in-plane elds.

Fig. 3 (a) gathers the melting lines obtained at di erent angles . They all fall on a single line,  $H_m^{cd}$  (T), that term inates at a critical point (CP) below which the transition becomes continuous in nature. The CP occurs at the same tem perature of 77 K at all angles. The width of



FIG.3: (color online) (a) The melting line H $_{\rm m}^{\rm cd}$  (T) and the delocalization line H $_{\rm dl}$ (T) in crystal A, m apped for di erent : 0(+), 25 (), 45 (), 65 (N) and 90 (). (b) DMO selfeld in age of part of sam ple A at 400e, 75 K, 20 m A.

the transition, denoted by the horizontal right-pointing arrows, is broadened on approaching the CP, but remains independent of angle, as was already shown in Fig. 2 for  $H_z = 35$  Oe. In Fig. 3, we also plot the delocalization line  $H_{d1}(T)$  [2], which separates the nanoliquid from the hom ogeneous liquid. H<sub>d1</sub>(T) was determined using MO visualization of the self- eld induced by a transport current applied to the sample. DMO im age of the self-eld allows one to visualize the transport current density distribution within the sample. Below H<sub>dl</sub>(T), the current ow is highly nonuniform due to enhanced pinning in the irradiated regions [2], and the DMO im age shows significant spatial variations (Fig. 3(b)). These disappear at H  $_{\rm dl}$ , when the network of pinned vortices is delocalized, and a hom ogeneous liquid is form ed. As H  $_{\rm m}^{\rm cd}\left(T\right.$  ), the  $H_{dl}(T)$  does not depend on the eld angle (Fig. 3(a)). On approaching  $T_{c}$ , vortex pinning by CD sbecom esweak and hence all the transition lines coincide.

The experim ental observations show that the dynam ic properties of porous vortex matter are strongly dependent on the angle between B and the CDs, while the therm odynam ic melting and delocalization lines are angleindependent. In order to understand these observations, we have carried m olecular dynam ics sim ulations of a rectangular parallelepiped model system of 36 PV stacks and 200 layers. As shown in [9, 21], such system size is sufcient for observing the various phase transitions. Periodic boundary conditions (PBC) were in plem ented in all directions. The intraplane PV interaction was modeled by the repulsion of their screening currents, while the interplane PV interaction is described by their mutual electrom agnetic attraction. For details see Refs. [9, 22]. W e also included the attractive Josephson interaction between pairs of pancakes in adjacent planes, but belonging

to the same stack [22]. We keep track of pancakes belonging to a vortex stack and allow for ux cutting and recombination [22]. The average vortex direction (i.e. H<sub>a</sub>) was kept parallel to the z axis, while tilted CDs of radius  $r_r = 30 \text{ nm}$  were introduced at random positions. The interaction between a pancake and a CD in the same plane is given by an attractive potential [9, 11], which has  $_0 dr_r^2 = R^2$ , due mainly a long range tail contribution to the electrom agnetic pinning, and a short range at region of depth  $_{0}$ d due to the combined e ects of electrom agnetic and core pinning. Here,  $_{0} = (_{0}=4)^{2}$ , =  $(0)=(1 T=T_c)^{1=2}$  is the penetration depth, R is the distance between a pancake and a CD and d is the layer separation. The interaction B = H = (4) is implemented by the PBC, since the electrom agnetic interaction between a tilted stack and the stacks of in ages, positioned above (and below) its center of mass, pull the tilted stack in the z direction. Tem perature e ects are im plem ented in the simulation by using a white therm al noise whose variance is proportional to the tem perature.

Figure 4 shows projections of the vortices onto the xy plane (top view) and the xz plane (side view), with CDs tilted by 45  $\,$  and 80  $\,$  . The main observation is that, for B > B, the CD s are alm ost fully decorated by pancakes both in the solid and nanoliquid phases. This means that the matrix of pinned PVs is preserved even when the eld is tilted away from the CDs, and as a result the interstitial PVs remain caged in the surrounding xed matrix. The interstitial PV stacks are even found to be tilted to som e extent in the direction of CDs, in the solid phase. A nother in portant observation is that the vortices adopt a structure featuring kinks between the layers, as shown by the side views in Figs. 4(c) and 4(d). Kinks of different vortices tend to align, form ing a structure which resembles the Josephson and Abrikosov crossing lattices [23] in BSCCO at tilted eld. Here, how ever, the Josephson vortices (JV) are formed when tilting the eld away from CDs rather than from the c-axis. For example, when B is parallel to the CD s but at 45 with respect to c-axis, no JV s are present, while for B k c-axis JV s segments appear, as shown in Figs. 4 (c) and 4 (d).

To further interpret the results we consider the energies involved: The binding energy of a vortex to a CD is of the order of  $_{0}d$  per layer. For angles less than about 75 this gain exceeds the electrom agnetic energy loss. For an in nitely long stack tilted at angle , the later is given by  $_0$ dln((1 + cos())=2cos()) per layer 24]. In addition, the energy B H = (4) tends to align the average vortex orientation with H. The contradicting requirements imposed by the need to m in imize all these energies are optim ized by the creation of kinks. The Josephson energy cost of the kinks is negligible com pared to the total energy of the vortex system in a highly anisotropic material like BSCCO [25]. Indeed, for 375, the total energy measured in the simulations for non tilted CDs and for CDs tilted at 45 is the same, in the vicinity of



FIG. 4: (color online) Snapshots of vortex stacks and CDs tilted at 45 (a, b and c) and 80 (d) for B = 100 G and  $B^{\text{eff}} = 35$  G.Pancakes in the same stack are connected. Free pancakes are in blue, trapped ones in red. Only CDs at the bottom layer are shown (green). (a) (b) Projection onto the a-b plane (top view). (a) Nanosolid phase. (b) Nanoliquid phase. (c) Projection of (a) onto the a-c plane (side view), rst row is shown. (d) Side view with CDs at 80.

the melting transition (T = 73 K to 77 K), within the simulation's error bars. The comparison was done for the same value of  $B^{eff} = B \cos in order to m atch the ex$ perim ental situation where the ratio of vortices to CDs remains xed as changes. Our simulations show that the rigid matrix of pancakes pinned on CDs is preserved up to very large angles in both the solid and nanoliquid vortex phases. This means that the enhanced caging potential created by the CDs, that was found to shift the melting line upwards, [1] is negligibly a ected by increasing the angle between B and the CDs. Consequently, the therm odynam ic properties, in particular the melting and delocalization lines, are angle independent. This was veri ed in our simulations for B = 100 G, where the melting and delocalization transitions occur at 74 K and 76 K respectively, both for nontilted and tilted CDs, as evidenced by m easurem ents of the m ean square deviation of the ux lines, the amount of their entanglem ent and other m easurem ents [26].

These observations can resolve the apparent discrepancy between the dynam ic and therm odynam ic properties. The kinks developed by the vortices have a negligible e ect on the therm odynam ics but a large e ect on the dynam ics. As demonstrated by our simulations, the kinks slide along the CD s due to the Lorentz force exerted by in-plane current, see also [10, 27]. Consequently, they transfer PVs between segments, thus producing an e ective transverse drift of the whole pancake stack. Upon increasing , the am ount of kinks increases and the ux creep becom es more e ective. This process decreases the critical current and shifts the irreversibility line to lower tem peratures. This is consistent with [14], which concluded that CD s' pinning anisotropy commonly measured in BSCCO [17] must be a dynamic e ect.

In sum m ary, the porous vortex m atter in BSCCO is shown to preserve its therm odynam ic properties even when the eld is tilted away from the CDs. W hile the irreversibility line shifts to low ertem peratures upon tilting the eld, the therm odynam ic m elting and delocalization lines rem ain constant. Num erical simulation shows that increasing the angle between the eld and the CDs leads to form ation of weakly pinned vortex kinks, while preserving the basic structure of a rigid m atrix of pancake stacks residing along the CDs with nanocrystals of interstitial vortices embedded within the pores of the m atrix.

We thank S. Goldberg and Ady Stem for stimulating discussions, D. Linsky for technical help. This work was supported by the ISF Center of Excellence, Germ an-Israeli Foundation (GIF), US-Israel BSF and Grant-inaid from the M inistry of Education, Culture, Sports, Science, and Technology, Japan. The work of YYG and JTL was supported by the USD epartment of Energy (DOE-DE-FG 02-98ER 45686), NERSC program and the Pittsburgh Supercom puting center. YYG thanks the W eston Visiting Professors program of the WIS for support.

- [1] S.S.Banerjee et al, Phys.Rev.Lett. 90, 087004 (2003).
- [2] S.S.Banerjee et al, Phys.Rev.Lett. 93, 097002 (2004).
- [3] M. Menghiniet al, Phys. Rev. Lett. 90, 147001 (2003).
- [4] L.Radzihovsky, Phys.Rev.Lett. 74, 4923 (1995).
- [5] S. Tyagi and Y. Y. Goldschm idt, Phys. Rev. B. 67, 214501 (2003).
- [6] C.Dasgupta et al, Phys.Rev.Lett. 91, 127002 (2003).
- [7] Y.Nonom ura and X.Hu, Europhys.Lett. 65, 533 (2004).
- [8] A.V. Lopatin and V.M. Vinokur, Phys. Rev. Lett. 92, 067008 (2004).
- [9] Y.Y.Goldschm idt and E.Cuansing, Phys. Rev. Lett. 95, 177004 (2005).
- [10] D.R.Nelson and V.M.Vinokur, Phys. Rev. B 48, 13060 (1993).
- [11] G.Blatter et al, Rev.M od.Phys. 66, 1125 (1994).
- [12] L.Civale et al, Phys. Rev. Lett. 67, 648 (1991); A.Silhanek et al, Phys. Rev. B 59, 13620 (1999).
- [13] B.Hayanietal, Phys.Rev.B 61, 717 (2000).
- [14] R.J.D rost et al, Phys. Rev. B 58, R615 (1998).
- [15] N.Kameda et al., Phys.Rev.B 72, 064501 (2005).
- [16] B.Khaykovich et al, Phys. Rev. B 56, R 517 (1997).
- [17] C. J. van der Beek et al, Phys. Rev. Lett. 74, 1214
  (1995); W. S. Seow et al, Phys. Rev. B 53, 14611 (1996);
  V. Hardy et al, Phys. Rev. B 54, 656 (1996).
- [18] A. Soibelet al, Nature (London) 406, 282 (2000).
- [19] Tilting B by 45 requires tilting  $H_a$  by 40 (found experim entally) since  $H_z$  is screened more e ciently by in-plane equilibrium shielding currents, compared to  $H_{ab}$ .
- [20] B.Schm idt et al, Phys.Rev.B 55, R8705 (1997); S.Ooi et al, Phys.Rev.Lett.82, 4308 (1999).
- [21] H. Nordborg and G. Blatter, Phys. Rev. B 58, 14556 (1998).
- [22] S.Tyagiand Y.Y.Goldschm idt, Phys.Rev.B 70,024501

(2004); Y.Y.Goldschm idt, Phys.Rev.B 72, 064518 (2005); Y.Y.Goldschm idt and S.Tyagi, Phys.Rev.B 71,014503 (2005).

- [23] A.E.Koshelev, Phys.Rev.Lett.83,187 (1999).
- [24] J.R.Clem, Phys.Rev.B 43, 7837 (1991).
- [25] L.N.Bulaevskiietal, Phys.Rev.Lett. 77, 936 (1996).
- [26] Y.Y.Goldschm idt and J.T.Liu, to be published.
- [27] D. R. Nelson and V. M. Vinokur, Phys. Rev. Lett. 68, 2398 (1992); M. V. Indenbom et al., Phys. Rev. Lett. 84, 1792 (2000).