M.D.Stiles^z, W.M.Saslow^x, M.J.Donahue^y, and A.Zangwill[{]

²C enter for Nanoscale Science and Technology, National Institute of Standards and Technology, Gaithersburg, MD 20899-8412

^xD epartm ent of Physics, Texas A & M University, College Station, TX 77843-4242

^yM athem atical and C om putational Sciences D ivision,

National Institute of Standards and Technology, Gaithersburg, MD 20899-8910 and

¹ School of Physics, Georgia Institute of Technology, Atlanta, GA 30332-0430

(D ated: D ecem ber 29, 2021)

Recent theory and measurements of the velocity of current-driven domain walls in magnetic nanowires have re-opened the unresolved question of whether Landau-Lifshitz damping or G ilbert damping provides the more natural description of dissipative magnetization dynamics. In this paper, we argue that (as in the past) experiment cannot distinguish the two, but that Landau-Lifshitz damping nevertheless provides the most physically sensible interpretation of the equation of motion. From this perspective, (i) adiabatic spin-transfer torque dominates the dynamics with small corrections from non-adiabatic e ects; (ii) the damping always decreases the magnetic free energy, and (iii) microscopic calculations of damping become consistent with general statistical and therm odynamic considerations.

I. BACKGROUND

Experiments designed to study the e ect of electric current on domain wall motion in magnetic nanowires show that domain walls move over large distances with a velocity proportional to the applied current.^{1,2,3,4,5,6,7,8,9,10} M ost theories ascribe this behavior to the interplay between spin-transfer (the quantum mechanical transfer of spin angular momentum between conduction electrons and the sam ple m agnetization) and m agnetization dam ping of the G ilbert type.¹¹ Contrary to the second point, we argue in this paper that Landau-Lifshitz dam ping¹² provides the most natural description of the dynamics. This conclusion is based on the premises that damping should always reduce magnetic free energy and that m icroscopic calculations must be consistent with statistical and therm odynam ic considerations.

Theoretical studies of current-induced domain wall motion typically focus on one-dimensionalmodels where current ows in the x-direction through a magnetization $M(x) = M \hat{M}(x)$. When M is constant, the equation of motion is

$$M_{-} = M H + N_{ST} + D$$
: (1)

The precession torque M H depends on the gyromagnetic ratio and an elective eld $_0H = F = M$ which accounts for external elds, anisotropies, and any other elects that can be modelled by a free energy F M] ($_0$ is the magnetic constant). The spin-transfer torque N_{ST} is not derivable from a potential, but its form is xed by symmetry arguments and model calculations.^{13,14,15,16,17,18,19,20,21} A local approximation²² (for current in the x-direction) is

$$\begin{array}{c} h \\ N_{ST} = \\ 0_{x}M \\ M \\ 0_{x}M \\ \end{array}$$

The rst term in (2) occurs when the spin current follows the dom ain wall magnetization adiabatically, i.e., when the electron spins remain largely aligned (or antialigned) with the magnetization as they propagate through the wall. The constant is a velocity. If P is the spin polarization of the current, j is the current density, and $_{\rm B}$ is the B ohr magneton,

$$= \frac{P j_{B}}{eM} :$$
 (3)

The second term in (2) arises from non-adiabatic e ects. The constant is model dependent.

The damping torque D in (1) accounts for dissipative processes, see 23 for a review. Two phenom enological forms for D are employed commonly: the Landau-Lifshitz form 12 with damping constant ,

$$D_{L} = \hat{M} (M H); \qquad (4)$$

and the G ilbert form 11 with damping constant ,

$$D_{G} = \hat{M} M_{-} :$$
 (5)

The di erence between the two is usually very small and almost all theoretical and simulation studies of current-induced domain wall motion solve (1) with the G ilbert form of dam ping.^{18,19,20,24,25,26,27,28} This is signi cant because, as we now discuss, G ilbert dam ping and Landau-Lifshitz dam ping produce quite di erent results for this problem when the same spin transfer torque is used.

Consider a Neelwallwhere M lies entirely in the plane of a thin lm when the current is zero. By de nition, $\hat{M} = 0$ if we choose M (x) as the equilibrium structure which m in in izes the free energy F M]. The wall distorts if $\hat{M} = 0$ for any reason. The theoretical literature cited above shows that, with damping om itted, the Neel wallm oves undistorted at the speed [see (3)] when = 0 in (2). G ilbert damping brings this motion to a stop because D_G rotates M (x) out-of-plane until the torque from magnetostatic shape anisotropy cancels the spintransfer torque. However, if the non-adiabatic term in (2) is non-zero, steady wall otion occurs at speed = .

U sing this information, two recent experiments^{9,10} used their observations of average domain wall velocities very near to infer that for permalloy nanow ires. This is consistent with m icroscopic calculations (which include disorder-induced spin- ip scattering) that report $= {}^{29}$ or 30 for realistic band m odels of an itinerant ferrom agnet. On the other hand, calculations for \sd" m odels of ferrom agnets with localized m om ents nd little num erical relationship between and 30,31 .

A rather di erent interpretation of the data follows from a discussion of current-driven dom ain wall motion in the s-d m odelo ered by B arnes and M aekawa.³² T hese authors argue that there should be no dam ping of the m agnetization when a wall which corresponds to a m inim um of the free energy F M] sim ply translates at constant speed. This is true of D_L in (4) because M H = 0 but it is not true of D_G in (5) because M- € 0 when N_{ST} € 0. From this point of view, the \correct" equation of motion is

 $M_{-} = M H (Q_{x}M M (M H); (6)$

because it reduces (for energy-m in im izing walls) to

$$\mathbf{M}_{-} = \mathbf{Q}_{\mathbf{X}}\mathbf{M} : \tag{7}$$

In the absence of extrinsic pinning, this argument identi es the experimental observation of long-distance wall motion with a uniform ly translating solution M (x t) of (7) with minimum energy.

A swe discuss below, it is possible to convert between descriptions with Landau-Lifshitz and G ilbert dampings by concurrently changing the value of the non-adiabatic spin-transfer torque. The Landau-Lifshitz description in Eq. 6 is equivalent to one with G ilbert damping with = . The goal of this paper is to argue that there are conceptual reasons to prefer the description with Landau-

Lifshitz dam ping even when $\frac{1}{2}$.

Section II presents m icrom agnetic simulations that con m the discussion above and describes further details. Then, the remainder of this paper provides three theoretical arguments which support the use Landau-Lifshitz damping for current-driven domain wall motion (in particular) and for other magnetization dynamics problems (in general). First, we reconcile our preference for Landau-Lifshitz damping with the explicit m icroscopic calculations of G ilbert damping and non-adiabatic spin torque reported in Refs. 29,30,31. Second, we show that G ilbert damping can increase the magnetic free energy in the presence of spin-transfer torques. Finally, we show that Landau-Lifshitz damping is uniquely selected form agnetization dynamics when the assumptions of non-equilibrium therm odynamics are valid.



FIG.1: Position versus time for a transverse dom ain walland several values of the applied current density computed with adiabatic spin torques (= 0) and the two form s of dam ping in (4) and (5).

II. M ICROMAGNETICS

Our analysis begins with a check on the robustness of the foregoing model predictions using full threedim ensionalm icrom agnetic sim ulations of current-driven dom ain wallm otion.³³ W e studied nanow ires 12 nm thick and 100 nm wide with material parameters chosen to sim ulate N igoFe20. At zero current, this geometry and m aterial system support in-plane magnetization with stable dom ain walls of transverse type.³⁴ Figure 1 shows the wall position as a function of time for a transverse domain wall for several values of applied current density j. The curves labelled Gilbert (= 0.02) show that wallm otion com es quickly to a halt. Exam ination of the m agnetization patterns con m s the torque cancellation mechanism outlined above. The curves labelled Landau-Lifshitz show that the wallm oves uniform ly with the velocity given by (3) which is independent of the dam ping parameter .35

The sudden turn-on of the current and hence O ersted m agnetic eld at t = 0 generates the sm all am plitude undulations of the curves in F igure 1 but otherw ise has little e ect on the dynam ics. An initial state of a stable vortex wall in a 300 nm wide wire produces sim ilar results, except that under the G ilbert form ulation the vortex wall m oves about twenty times farther before stopping as com pared to the transverse wall in the 100 nm wire. We conclude from these simulations that the basic picture of dom ain wall dynam ics gleaned from one-dimensional m odels is correct.

The magnetic free energy behaves di erently in simulations depending on whether Landau-Lifshitz or G ilbert dam ping is used. B efore the current is turned on, the domain wall is in a con guration that is a local minimum in the energy. For Landau-Lifshitz dam ping, the energy remains largely constant near this minimum and is exactly

constant if the O ersted elds are ignored. For G ilbert dam ping, the energy increases when the current is turned on and the walls distort. For a transverse wall, the distortion is largely an out of plane tilting. Initially, the energy increases at a rate proportional to the dam ping param – eter (ignoring higher order corrections discussed in the next section). The details of this behavior are som ew hat obscured by the oscillations due to the O ersted m agnetic eld, but are quite apparent in simulations in which this eld is om itted. A s the wall tilts out of plane, the torque due to the m agnetostatic eld opposes the wall m otion and the wall slow s dow n. E ventually the torque balances the adiabatic spin transfer torque and the wall stops.

In simulations using Gilbert damping, the change in magnetic free energy between the initial and nalcon gurations is independent of the dam ping param eter as it is determ ined by the balance between the magnetostatic torque and the adiabatic spin transfer torque. However, the am ount of time before the wall stops and the distance the wallm oves are inversely proportional to the dam ping param eter. The Gilbert damping torque is responsible for this increase in energy as can be seen from analyzing the directions of the other torques. P recessional torques, like those due to the exchange and the magnetostatic interactions that are important in these simulations, by their nature are directed in constant energy directions and do not change the magnetic free energy. The adiabatic spin transfer torque is in a direction that translates the dom ain wall and does not change the energy in system swhere the energy does not depend on the position of the wall. Thus, in simulations of ideal dom ain wall motion without 0 ersted elds, the Gilbert damping torque is the only torque that changes the energy. Throughout these simulations, the Gilbert damping torque is in a direction that increases rather than decreases the magnetic free energy.

III. MAGNETIC DAMPING W ITH SPIN-TRANSFER TORQUE

W hen N_{ST} = 0, it is well known that a few lines of algebra converts the equation of motion (1) with G ilbert damping into (1) with Landau-Lifshitz damping (and vice-versa) with suitable rede nitions of the precession constant and the damping constants and $.^{36}$ The same algebraic manipulations²⁹ show that (6) is mathematically equivalent to a G ilbert-type equation with = = :

$$M_{-} = (1 + {}^{2})M H + M M_{-}$$

$$h i (8)$$

$$@_{x}M M @_{x}M :$$

To analyze (8), we rst ignore spin-transfer (put = 0) and note that this re-written Landau-Lifshitz equation di ers from the conventional Gilbert equation only by an O (²) renorm alization of the gyrom agnetic ratio. Consequently, rst-principles derivations of any equation of motion for the magnetization must be carried to second order in the putative damping parameter if one hopes to distinguish Landau-Lifshitz damping from G ilbert damping. This observation shows that papers that derive G ilbert damping^{29,30,31,37,38,39} or Landau-Lifshitz damping^{40,41} from m icroscopic calculations carried out only to rst order in cannot be used to justify one form of damping over the other.

Now restore the spin-transfer terms in (8) and note that the transform ation to this equation from (6) automatically generates a non-adiabatic torque with =. This transform ation means that to low est order in and , an equation of motion with G ilbert damping and a non-adiabatic coe cient $_{G}$ is equivalent to an equation of motion with Landau-Lifshitz damping with non-adiabatic coe cient $_{LL} = _{G}$. This shows that equivalent equations of motion can be made using either form of damping, albeit with rather di erent descriptions of current induced dom ain wallm otion. Nevertheless, as we argue below, there are conceptual advantages to the Landau-Lifshitz form.

IV. LANDAU-LIFSHITZ DAM PING UN IQUELY REDUCES MAGNETIC FREE ENERGY

Landau-Lifshitz damping inveversibly reduces magnetic free energy when spin-transfer torque is present. The same statement is not true for G ilbert damping. This can be seen from the situation described in Section II where G ilbert damping causes a minimum energy domain wallcon guration to distort and tilt out of plane. Nothing prevents an increase in magnetic free energy for this open system, but it is clearly preferable if changes magnetic con gurations that increase F M] come from the elects of spin-transfer torque rather than from the effects of a torque intended to model dissipative processes. This is an important reason to prefer D $_{\rm L}$ in (4) to D $_{\rm G}$ in (5). This argument depends crucially on the fact that the adiabatic spin-transfer torque is not derivable from a free energy as we discuss henceforth.

The eld H in Eq. (1) is the (negative) gradient of the magnetic free energy. The component of this gradient in the direction that does not change the size of the magnetization is \hat{M} М H]. Since this direction is exactly that of the Landau-Lifshitz form of the dam ping, Eq. (4), it follows that this form of the dam ping always reduces this magnetic free energy. When the Gilbert form of the damping, Eq. (5), is used in Eq. (1), it is possible to rewrite the damping term as $D_G =$ м М H $(1 =)N_{ST}] + O(^{2})$. Further, one can always write $N_{ST} =$ М H_{ST} where H_{ST} is an elective \spin transfer magnetic eld". However, unlike the eld $_{0}H = F = M$ in (1), there is no \spin transfer free energy" F_{ST} which gives H_{ST} as its gradient:

$$_{0}H_{ST} = \frac{F_{ST}}{M}$$
 (not correct): (9)



FIG.2: A one-dimensional N eel dom ain wall with magnetization M (\boldsymbol{x}) .

If (9) were true, the lowest order (in) G ilbert dam ping term \hat{M} [M (H + H_{ST})] would indeed always lower the sum F + F_{ST}. Unfortunately, a clear and convincing demonstration of the non-conservative nature of the spintransfer torque is not easy to nd. Therefore, in what follows, we focus on the adiabatic contribution to (2) and show that a contradiction arises if (9) and its equivalent,

$$dF_{ST} = {}_{0}H_{ST} \quad dM ; \qquad (10)$$

are true.

For this argument we consider a simpler model than that discussed in Section II. Figure 2 shows the magnetization M (x) for a one dimensional Neelwall in a system with uniaxial anisotropy along the x-direction. The domain wall of width w is centered at x = 0 and the plane of the magnetization is tilted out of the x-y plane by an angle . A convenient parameterization of the in-plane rotation angle (x) is

$$(x) = =2 + \sin^{1} [\tanh(x=w)];$$
 (11)

Therefore,

 $M = M [\cos (x); \sin (x) \cos ; \sin (x) \sin]; \quad (12)$

where $\cos(x) = \tanh(x=w)$ and

$$\sin (x) = \operatorname{sech}(x=w):$$
(13)

The magnetic free energy of this dom ain wall is independent of both its position and its orientation (angle).

For electron ow in the x-direction, (2) shows that the adiabatic piece of the spin-transfer torque lies entirely in the plane of the m agnetization:

$$N_{ST}^{ad}$$
 / ⁰(x)(sin ; cos cos ; cos sin): (14)

This torque rotates the magnetization in a manner which produces uniform translation of the wall in the x-direction with no change in $\$. Since

$$^{0}(x) = (1=w) \operatorname{sech} (x=w);$$
 (15)

com parison with (13) shows that N $_{ST}^{ad} = 0$ outside the wallas expected. The magnetic free energy of the dom ain wall does not change as the wall is translated.

Now, as indicated above (9), we are free to interpret the foregoing wall translation as resulting from local precession of M (x) around an elective eld H $_{\rm ST}$ (x) directed perpendicular to the plane of the domain wall. Speci – cally,

$$H_{ST}(x) / (x) (0; sin ; cos):$$
 (16)

However, if (9) and thus (10) are assumed to be correct, the magnitude and direction of H $_{\rm ST}$ imply that the putative free energy $F_{\rm ST}$ decreases when M (x) rotates rigidly around the x-axis in the direction of increasing 42 On the other hand, the free energy must return to its original value when rotates through 2 . Since the gradient (9) can never increase the free energy, we are forced to conclude that our assumption that $F_{\rm ST}$ exists is incorrect.

V. A LANGEV IN EQUATION FOR THE MAGNET IZATION

N eglected work by Iwata⁴³ treats m agnetization dynam ics from the point of view of the therm odynam ics of irreversible processes.⁴⁴ H is non-perturbative calculations uniquely generates the Landau-Lifshitz form of dam ping. In this section, we make equivalent assum ptions but go farther and derive an expression for the dam ping constant. M ori and co-workers did this using a projection operator m ethod.⁴⁵ O ur m ore accessible discussion follows R eif's derivation of a Langevin equation for B row nian m otion.⁴⁶

We begin by taking the energy change in a unit volum e

$$dE = _{0}H \quad dM ; \qquad (17)$$

where the repeated index in plies a sum over Cartesian coordinates. It is crucial to note that the magnitude M j= M is xed so only rotations of M toward the e ective eld H change the energy of the system. The interaction with the environm ententers the equation of m otion for the magnetization through a uctuating torque N⁰:

$$\frac{\mathrm{d}M}{\mathrm{d}t} = (M + 1) + N^{0}; \qquad (18)$$

The torque N⁰ is perpendicular to M since M = M.

We consider the evolution of the m agnetization over a time interval twhich is much less than the precession period, but much greater than the characteristic time scale for the uctuations . A fler this time interval, the statistical average of the change in m agnetization M = M (t+t) M (t) is

$$M = (M H) (t) + dt^{0} < N^{0} (t^{0}) > :$$

The equilibrium Boltzmann weighting factor W $_0$ gives $< N^0(t^0) >_0 = 0$. However, $< N^0(t^0) > 6 0$ when the magnetization is out of equilibrium. Indeed, this method derives the damping term precisely from the bias

built into the uctuations due to the changes $E = {}_0H M$ in the energy of the magnetic system .

The Boltzm ann weight used to calculate $< N^{0} (t^{0}) >$ is $W = W_{0} \exp(E = (k_{B}T))$ where (assuming that H does not change much over the integration interval),

$$E(t^{0}) = {}_{0}H(t^{0})^{Z}{}_{t^{0}}^{t}\frac{dM(t^{0})}{dt^{0}}dt^{0}$$

$${}_{0}H(t) N^{0}(t^{0})dt^{0}: (20)$$

Note that precession does not contribute to $E(t^{0})$. Only motions of the magnetization that change the energy of the magnetic subsystem produce bias in the torque uctuations. Therefore, since $W = W_{0}(1 = E = (k_{B}T))$ for small $E = (k_{B}T)$, the last term in (19) now involves only an average over the equilibrium ensemble:

$$+ \frac{{}_{0}H}{k_{B}T} t dt^{0} t dt^{0} < N^{0}(t^{0})N^{0}(t^{0}) >_{0}:$$

(21)

We recall now that the torque uctuations are correlated over a microscopic time that is much shorter than the smallbut macroscopic time-interval over which we integrate. Therefore, to the extent that memory effects are negligible, we de ne the damping constant (a type of uctuation-dissipation result) from

$$Z_{t^{0}}$$

dt⁰⁰ < N⁰ (t⁰)N⁰ (t⁰⁰) > (k_B T M = ₀)[?]; (22)

for t^0 tj and with $? = \hat{M} \cdot \hat{M}$, which restricts the uctuations to be transverse to the magnetization, but otherwise uncorrelated. This approximation reduces the last term in (21) to $M \cdot H_2$ t, where $H_2 = \hat{M} \cdot \hat{M} \cdot H$, is the piece of H which is perpendicular to M. Substituting (22) into (21) gives the nal result in the form,

$$\frac{dM}{dt} \qquad (M H) \qquad M (M H): (23)$$

E quation (23) is the Landau-Lifshitz equation for the statistically averaged m agnetization. It becomes a Langevin equation when we add a (now) unbiased random torque to the right hand side.

The procedure outlined above generates higher order term sin from the expansion of the therm alw eighting to higher order in E. The second order terms involve an equilibrium average of three powers of N 0 . These are zero for G aussian uctuations. The third order terms involve an average of four powers of N 0 , and are non-zero. They lead to a term proportional to $^2{\rm H}_2$ H $_2$, which we expect to be sm alland to modify only large-anglem otions of the m agnetization.

In this paper, we analyzed current-driven dom ain wall motion using both Gilbert-type and Landau-Lifshitztype damping of the magnetization motion. Equivalent equations of motion can be written with either type of damping, but the implied description of the dynam ics (and the relative importance of adiabatic and nonadiabatic e ects) is very di erent in the two cases.

W ith Landau-Lifshitz damping assumed, adiabatic spin transfer torque dominates and produces uniform translation of the wall. Non-adiabatic contributions to the spin transfer torque distort the wall, raise its magnetic energy, and thus produce a magnetostatic torque which perturbs the wallvelocity. D amping always acts to reduce the distortion back towards the originalm inim um energy wall con guration. W ith G ilbert damping assumed, the damping torque itself distorts and thereby raises the magnetic energy of the moving wall. The distortion-induced magnetostatic torque stops domain wall motion altogether. A dditional wall distortions produced by non-adiabatic spin-transfer torque are needed to produce wall motion.

In our view, Landau-Lifshitz dam ping is always preferable to G ilbert dam ping. When spin-transfer torque is present, this form of dam ping inexorably moves the magnetic free energy toward a local minimum. G ilbert dam ping does not. Even in the absence of spin-transfer torque, arguments based on irreversible therm odynam ics show that the Landau-Lifshitz form of dam ping is uniquely selected for a macroscopic description.⁴³ Here, we proceeded equivalently and derived the Landau-Lifshitz equation of motion as the unique Langevin equation for the statistical average of a uctuating magnetization with xed spin length.

A Z.and W M S.gratefully acknow ledge support from the U S. Department of Energy under contracts DE-FG 02-04ER 46170 and DE-FG 02-06ER 46278. We thank R.A.Duine, H.Kohno, R.D.M cM ichael, J.Sinova, N. Sm ith, G.Tatara, and Y.T serkovnyak for useful discussions.

¹ H.Koo, C.Kra t, and R D.G om ez, ApplPhys.Lett.83, 105 (2003).

Fainini, E. Cambril, and L.J. Heyderman, Appl. Phys. Lett. 83, 105 (2003).
⁴ J.G rollier, P.Boulenc, V.Cros, A.Ham zic, A.Vaures, A.

- ² M. Tsoi, R.E. Fontana, and S.S.P. Parkin, Appl. Phys. Lett. 83, 2617 (2003).
- 3 M . K laui, C A F . Vaz, JA C . B land, W $\,$ W emsdorfer, G .
- J.G rollier, P.Boulenc, V.Cros, A.Ham zic, A.Vaures, A. Fert, and G.Faini, Appl.Phys.Lett. 83, 509 (2003).
- ⁵ N.Vemier, D.A.Allwood, M.D.Cooke, and R.P.Cowburn,

Europhys.Lett.65,526 (2004).

- ⁶ A.Yam aguchi, T.O no, S.N asu, K.M iyake, K.M ibu, and T.Shinjo, Phys. Rev. Lett. 92 077205 (2004).
- ⁷ C K. Lim, T. Devolder, C. Chappert, J. G rollier, V. Cros, A Naures, A. Fert, and G. Faini, Appl. Phys. Lett. 84 2820 (2004).
- ⁸ M.Klaui, P.O.Jubert, R.Allenspach, A.Bischof, JAC. Bland, G.Faini, U.Rudiger, CAF.Vaz, L.Vila, and C. Vouille, Phys. Rev. Lett. 95, 026601 (2005).
- ⁹ M. Hayashi, L. Thomas, Ya. B Bazaliy, C. Rettner, R. Moriya, X. Jiang, and S.S.P. Parkin, Phys. Rev. Lett. 96, 197207 (2006).
- ¹⁰ G.S.D.Beach, C.Knutson, C.Nistor, M.Tsoi, and J.L. Erskine Phys. Rev. Lett. 97, 057203 (2006).
- ¹¹ T L. G ilbert, A m our Research Foundation Project No. A 059, Supplem entary Report, M ay 1, 1956 (unpublished). See also T L.G ilbert, IEEE Trans.m agn.40, 3443 (2004).
- ¹² L.Landau and E.Lifshitz, Phys.Z.Sow jet. 8, 153 (1935).
- ¹³ L.Berger, J.Appl.Phys.49, 2156 (1978). Recent reviews of spin-transfer e ects in spin-valve and tunnel junction heterostructures are JZ.Sun, IBM J.Res. & Dev.50, 81 (2006); and M D.Stiles and J.M iltat in Spin Dynam ics in C on ned M agnetic Structures III, edited by B.H illebrands and A. Thiaville (Springer, Berlin, 2006).pp.225-308.
- ¹⁴ Ya.B.Bazaliy, BA. Jones, and S.-C. Zhang, Phys. Rev. B 57, R 3213 (1998).
- ¹⁵ J.P.Anserm et, IEEE Trans.M agn.40, 358 (2004).
- ¹⁶ G. Tatara and H. Kohno, Phys. Rev. Lett. 92, 086601 (2004).
- 17 X W aintal and M .V iret, Europhys.Lett. 65, 427 (2004).
- ¹⁸ S. Zhang and Z. Li, Phys. Rev. Lett. 93, 127204 (2004).
- ¹⁹ A.Thiaville, Y.Nakatani, J.M iltat, and Y.Suzuki, Europhys.Lett. 69, 990 (2005).
- ²⁰ V K. Dugaev, V R. Vieira, P D. Sacram ento, J. Barnas, M A N. A raujo, and J. Berakdar, Phys. Rev. B 74, 054403 (2006).
- ²¹ J. X iao, A. Zangwill, and M D. Stiles, Phys. Rev. B 73, 054428 (2006).
- ²² N on-local contributions to the non-adiabatic spin-transfer torque are known to exist. See Refs. 17 and 21 and also G. Tatara, H. Kohno, J. Shibata, and K.-J. Lee, cond-m at/0612275.
- ²³ B.Heinrich, in Ulbrathin M agnetic Structures III, edited by J.A.C.Bland and B.Heinrich (Springer-Verlag, Berlin, 2005), p.143.
- ²⁴ Z.Liand S.Zhang, Phys. Rev. B 70, 024417 (2004).
- ²⁵ A. Thiaville, Y. Nakatani, J. M iltat, and N. Vernier, J. Appl. Phys. 95, 7049 (2004).
- ²⁶ J. He, Z. Li, and S. Zhang, J. Appl. Phys. 99, 08G 509 (2006).
- ²⁷ G. Tatara, T. Takayam a, H. Kohno, J. Shibata, Y. Nakatani, and H. Fukuyam a, J. Phys. Soc. Jpn. 75, 064708

(2006).

- ²⁸ J.He, Z.Li, and S.Zhang, Phys. Rev. B 73, 184408 (2006).
- ²⁹ Y. Tserkovnyak, H.J. Skadsem, A. Brataas, and G E W. Bauer, Phys. Rev. B 74, 144405 (2006). See also H.J. Skadsem, Y. Tserkovnyak, A. Brataas, and G E W. Bauer, cond-m at/0611588.
- ³⁰ H.Kohno, G. Tatara, and J. Shibata, J. Phys. Soc. Jpn. 75, 113706 (2006).
- ³¹ R.A.Duine.A.S.Numez, J.Sinova, and A.H.M acDonald, condm at-0703414.
- ³² S E . B ames and S . M aekawa, Phys. Rev. Lett. 95, 107204 (2005). See also S E . B ames, Phys. Rev. Lett. 96, 189701 (2006).
- ³³ M. J. Donahue and D. G. Porter, \OOM M.F. User's Guide, Version 1.0", Interagency Report N ISTIR 6376, National Institute of Standards and Technology, Gaithersburg, M.D. (Sept. 1999). Sim ilar simulations with the Gilbert form ulation were reported in Ref25.
- ³⁴ R D . M cM ichael and M J. D onahue, EEE Trans. M agn. 33, 41678 (1997).
- ³⁵ R ef. 24 is an extensive study of current-driven dom ain wall m otion with G ilbert dam ping. In the \N um erical R esults" section, there is an unelaborated rem ark to the e ect that the replacement of G ilbert dam ping by Landau-Lifshitz dam ping leads to \a nite velocity independent of the dam ping parameter."
- ³⁶ See, for exam ple, J.C. M allinson, IEEE Trans. M agn. 23, 2003 (1987) and G. Bertotti, ID. M ayerogyz, and C. Serpico, Physica B 306, 102 (2001).
- ³⁷ V.Kambersky, Can. J. Phys. 48, 2906 (1970).
- ³⁸ Y. Tserkovnyak, A. Brataas, and G E W. Bauer, Phys. Rev.Lett.88,117601 (2002); D L.M ills, Phys.Rev.B 68, 014419 (2003).
- ³⁹ B.Koopmans, JJM Ruigrok, F.Dalla Longa, and W JM. de Jonge, Phys. Rev. Lett. 95, 267207 (2005).
- ⁴⁰ H B.Callen, J.Phys.Chem.Solids 4, 256 (1958).
- ⁴¹ D R.Fredkin and A.Ron, Phys. Rev. B 61, 8654 (2000).
- ⁴² N st in (14) is proportional to ⁰(x) and thus [from (13) and (15)] it is proportial to sin , the projection of the magnetization on the in-plane hard axis. This guarantees that the entire magnetization pattern rotates rigidly around the x-axis without distortion.
- ⁴³ T. Iwata, J.M agn.M agn.M at. 31-34, 1013 (1983); ibid., 59, 215 (1986).
- ⁴⁴ See, for example, I. Prigogine, Introduction to the Thermodynamics of Interversible Processes, 3rd edition (Interscience, New York, 1967).
- ⁴⁵ T.Yam ada, H.Fujisaka, and H.M ori, Prog. Theor. Phys. 49, 1062 (1973).
- ⁴⁶ F.Reif, Fundam entals of Statistical and Therm alPhysics, (M cG raw H ill, New York, 1965), Section 15.7.