arXiv:cond-mat/9207021v1 17 Jul 1992

Nonlinear Meissner E ect in CuO Superconductors

S.K.Yip and J.A. Sauls

Department of Physics & Astronom y, Northwestern University, Evanston, IL 60208 (Received M ay 8, 1992, revised June 17)

Recent theories of the NMR in the CuO superconductors are based on a spin-singlet $d_{x^2 \ y^2}$ order parameter. Since this state has nodal lines on the Ferm i surface, nonlinear e ects associated with low-energy quasiparticles become important, particularly at low temperatures. We show that the eld-dependence of the supercurrent, below the nucleation eld for vortices, can be used to locate the positions of the nodal lines of an unconventional gap in momentum space, and hence test the proposed $d_{x^2 \ y^2}$ state.

PACS numbers: 74.30 Ci, 74.30 Gn, 74.65.+ n

M uch of the interest in the CuO high T_c superconductors is due to the belief by m any theoreticians that these m aterials represent new, or at least novel, form s of superconductivity. Theories based on very di erent excitations (e.g. spinless ferm ions, anyons, and traditional charged ferm ions) have been proposed to explain the norm al and superconducting properties of these m aterials. Superconductivity from anyons has received considerable attention. Sim ilarly, several theories based on BCS-like pairing, either of novel excitations or of novel pair states of conventional charged ferm ions have been proposed [[1]]. All of the theories of the superconducting state, except the conventional BCS pairing state, have the property that they break at least one additional sym metry of the norm all state besides gauge symmetry. While there has been little compelling evidence to identify the order parameter of the high T_c superconductors with any of these unconventional states, recent theories, based largely on interpretations of NMR in both the norm all and superconductors [[2,3]]. In this letter we show that the eld dependence of the supercurrent can be used to locate the positions of the nodal lines of the gap in momentum space; we suggest new experiments to resolve the gap structure of the $d_{x^2 - y^2}$ state, or other unconventional BCS states.

B ased on ideas from H am m el, et al. and Shastry [[4]], a sem iphenom enological model of a nearly AFM Fermi liquid that accounts for the anom alous NMR properties of the CuO superconductors has been proposed [[5,6]]. M onthoux, et al. [[2]] recently argued that the same AFM spin uctuations that are responsible for the anom alous norm all state m agnetic properties are also responsible for superconductivity in the layered CuO system s. These authors exam ine the weak-coupling gap equation with a pairing interaction given by the exchange of a single spin- uctuation, and nd that the superconducting state with $d_{x^2 y^2}$ symmetry is the preferred solution.

Several authors [3]] have extended the nearly AFM Fermi liquid into the superconducting state, and have concluded that the K night shift and anisotropy of the spin-lattice relaxation rates in YBCO are most reasonably twith a singlet, $d_{x^2 \ y^2}$ order parameter. Since the arguments put forward in favor of a $d_{x^2 \ y^2}$ order parameter are connected with the spin excitation spectrum, independent tests of the $d_{x^2 \ y^2}$ state based on the orbital structure of the gap or its excitation spectrum are needed to identify the order parameter.

The important feature of the quasiparticle excitation spectrum, which is required by symmetry for a clean superconductor with a $d_{x^2-y^2}$ order parameter, is that the excitation gap vanishes along four lines (hodal lines') located at the postions $\hat{f}_x j = \hat{f}_y j$ in the 2D plane and running along the length of the Ferm i tube [see cross-section in Fig. 1]. These nodal lines in ply low-energy excitations, at all temperatures, that give rise to power law deviations of the penetration depth from its zero-temperature limit; i.e. 1 = (0) = (T) = (T) (T = T) for $T = T_c$ and a gap with line nodes, while deviations proportional to higher powers are obtained from gaps with point nodes [[7]]. At present there is no consensus 'for' or 'against' a true gap in the spectrum from penetration depth measurements. Several measurements of the penetration depth in CuO superconductors are interpreted as supporting the predictions of BCS theory with a true gap, while the analysis by Annett, et al. [[8]] of those same measurements [see also [[8]] for original references] suggests deviations from a true gap, but gives no indication of a linear temperature dependence that would be consistent with a $d_{x^2-y^2}$ state.

The main idea of this paper is that the eld-dependence of the supercurrent may be used to locate the positions of the nodal lines (or points) of an unconventional gap in momentum space. This is a stronger test of the symmetry of the superconducting state than power law behavior for the penetration length. This gap spectroscopy is possible at low

tem peratures, T T_c , and is based on features which are intrinsic to nearly all possible unconventional BCS states in tetragonal or orthorhom bic structures. The constitutive equation relating the supercurrent, j_s , to the velocity, $\mathbf{v}_s = \frac{1}{2} \left(\mathbf{0} + \frac{2e}{c} \mathbf{A} \right)$ (this de nition avoids the introduction of an arbitrary mass scale), is linear only for velocities sm all compared with the critical velocity, $\mathbf{v}_c = = \mathbf{v}_f$. Since the unconventional gaps of interest have nodal lines on the Ferm i surface [9], nonlinear corrections to the constitutive equations become in portant, particularly at low tem peratures. The low-energy states near the nodes of the gap lead to a quasiparticle contribution to the current that (i) persists at zero tem perature, (ii) is a nonanalytic function of the velocity and (iii) exhibits a large anisotropy at low tem perature that is determined by the positions of the nodes on the Ferm i surface. We discuss the theory of the nonlinear current/velocity relation at low tem perature, and then show how the nonlinearity in the current leads to a novel basal plane anisotropy of the screening length and magnetization energy (or magnetic torque), for the d_{x^2} y^2 state when the eld is parallel to the CuO planes.

Consider a superconductor-vacuum interface which is parallel to the magnetic eld, and assume the penetration length is large compared to the in-plane coherence length, . The important spatial variations are then contained in the local value for the super uid velocity, which is eld, and escale of . The order parameter achieves its equilibrium value for the local value of the velocity, and the resulting current is [10]],

$$eN_{f} d^{2}sn(s) v_{f}(s) T \sum_{n}^{X} \frac{v(s) i_{n}}{(n + i_{v}(s))^{2} + j(s)^{2}};$$

where $v = v_f(s)$ svis the shift in the quasiparticle energy due to the super ow, N_f is the total density of states at the Ferm i level, n (s) is the angle-resolved density of states normalized to unity, $v_f(s)$ is the quasiparticle velocity at the points on the Ferm i surface, and $E = \frac{p}{2} + j(s)f$. The nst line of eq.(1) is useful for calculating the current in the low-temperature limit. The nst term represents the supercurrent obtained from an unperturbed condensate, i.e. $j_s = e v_s$, where is the total density ($= \frac{1}{2}N_fv_f^2$ for a cylindrical Ferm i surface). The term involving the Ferm i functions is the current from the equilibrium population of quasiparticles. This form ula shows clearly that the quasiparticles do not contribute to the current at T = 0 for a superconductor with a true gap over the entire Ferm i surface, provided the velocity is below the critical velocity, $m_i = v_f$. At nite temperature, the excitation term is responsible for the reduction in the super uid density from to s(T) in the linear response limit. In addition, the quasiparticles give rise to a nonlinear reduction in the supercurrent.

In order to motivate the proposal for detecting the nodal structure of the gap in an unconventional superconductor consider the elect of a magnetic eld on the penetration depth in a conventional, isotropic superconductor. For a eld parallel to the surface, the screening current is proportional to the applied eld, i.e. j(0) cH = . This linear relation breaks down because of pairbreaking induced by the velocity eld,

$$J_{s} = {}_{s}(T) *_{s} [1 (T) \frac{V_{s}}{V_{c}}^{2}];$$
 (2)

for $(v_s=v_c)$ 1, where (T) 0 and v_c = (T)= v_f is the critical velocity. One important point to note is that (T) ! 0 for T ! 0, since the quasiparticle occupation is zero for all quasiparticles states with velocity below the critical velocity. The importance of the nonlinear current/velocity constitutive equation to the penetration of m agnetic elds into a superconductor is qualitatively clear. The reduction of the current by the pair-breaking e ect reduces the e ective super uid density, and, therefore, increases the e ective penetration length. Since the current is proportional to the eld in linear order, the correction to the eld in length is quadratic in the surface eld [[11]],

$${}_{eff}(T; H)^{1} = (T)^{1} 1 \frac{1}{3}(T) \frac{H}{H_{o}(T)}^{2};$$
 (3)

where $H_{\circ}(T) = (3=4)$ (c $v_{c}(T)=e$ (T)) is of order the therm odynamic critical eld.

Now consider the $d_{x^2 y^2}$ order parameter, $(s) = {}_{\circ}(\hat{k}_x^2 \quad \hat{k}_y^2)$. The nodes in the gap in ply that there is a quasiparticle contribution to the supercurrent even at T = 0, which is easily calculated in terms of the phase space of occupied quasiparticle states. Consider the case where the velocity is directed along the nodal line $k_x = k_y; v_s = v_s \hat{x}^0$ as shown in Fig. 1. For any non-zero v_s there is a wedge of occupied states near the node opposite to the ow velocity. For a cylindrical Ferm i surface the quasiparticle current is

$$\tilde{J}_{qp} = 2eN_{f} (2_{o}v_{f}) \int_{c}^{Z} \frac{d}{2} \cos^{2}(1)^{p} \frac{1}{\sin^{2}(c_{c})} \sin^{2}(c_{c});$$
 (4)

where is the angle measured relative to the node at x^0 and $c = \sin^{-1}(\frac{v_f v_s}{2})$ is the maximum angle for which the quasiparticle states near the node are occupied. To leading order in $(\frac{v_f v_s}{2})$ we obtain a total supercurrent of

$$\tilde{J}_{s} = \left(\frac{e}{2}N_{f}v_{f}^{2}\right)v_{s} fl \frac{jv_{s}j}{2_{o}=v_{f}}g;$$
(5)

for v_s directed along any of the four nodes. Note that the current is parallel to the velocity, and that the occupied quasiparticle states reduce the supercurrent, as expected. A loo the nonlinear correction is quadratic rather than cubic, as is obtained for the conventional gap, and with the characteristic scale determ ined by $v_o = 2_o = v_f$. Furtherm ore, the quasiparticle contribution to the current is a nonanalytic function of v_s [[12]].

Unlike the linear response current, the nonlinear quasiparticle current is an isotropic in the basal plane. A velocity eld directed along the maximum direction of the gap, $v_s = v_s x$, produces two groups of occupied states, albeit with reduced populations because the projection of v_s along the nodal lines is reduced by 1 = 2. The resulting current is easily calculated to be

$$\tilde{j}_{s} = \left(\frac{e}{2}N_{f}v_{f}^{2}\right)v_{s}f1 + \frac{1}{2}\frac{jv_{s}j}{2_{o}=v_{f}}g;$$
 (6)

which is again parallel to the yelocity and has a quadratic nonlinear correction. However, the magnitude of the nonlinear term is reduced by 1 = 2. This anisotropy is due to the relative positions of the nodal lines and is insensitive to the anisotropy of the the Ferm i surface or Ferm i velocity because the quasiparticle states that contribute to the current, for either orientation of the velocity, are located in a narrow angle, $c'(v_s=v_o)$ 1, near the nodal lines. Thus, the occupied quasiparticle states near the nodes have essentially the same Ferm i velocity and density of states; only the relative occupation of the states is modil ed by changing the direction of the velocity.

The dependence of the supercurrent on the positions of the nodal lines in momentum space suggests that the anisotropy can be used to distinguish di erent unconventional gaps with nodes located in di erent directions in momentum space. For example, the d_{xy} state, $\hat{k}_x \hat{k}_y$, would also exhibit a four-fold anisotropy, but the nodal lines are rotated by =4 relative to those of the d_{x^2} y^2 state, while the state $\hat{k}_x \hat{k}_y (\hat{k}_x^2 - \hat{k}_y^2)$ corresponding to the A_{2q} representation would exhibit an 8 fold anisotropy.

This anisotropy in the current in plies a similar anisotropy in the eld dependence of the penetration length, which can be calculated from eqs.(5)-(6) and M axwell's equation; in the gauge, $\mathcal{C} = 0$, and for surface elds parallel to a nodal line the equations reduce to,

$$\frac{\theta^2 v_s}{\theta z^2} = \frac{4}{c^2} \dot{j}_s [v_s] = \frac{v_s}{2} \quad 1 \quad \frac{\dot{j} v_s \dot{j}}{v_o} \quad : \tag{7}$$

The magnetic eld in the superconductor, $\tilde{b} = (c=e)$ (v_s , is also parallel to a node, and has magnitude b = (c=e) ($v_s=0$ x) with b(0) = H. For eld penetration into a bulk superconductor we de ne the elective screening length in terms of the surface in pedance, $1 = e_{ff} = (1=H)$ (0 = 0 x) $j_{=0}$. We obtain

$$\frac{1}{\text{eff}} = \frac{1}{2} \quad 1 \quad \frac{2}{3} \frac{\text{H}}{\text{H}_{\circ}} \quad ; \text{ ff jjnode } ; \quad \frac{1}{\text{eff}} = \frac{1}{2} \quad 1 \quad \frac{1}{p} \frac{2}{2} \frac{2}{3} \frac{\text{H}}{\text{H}_{\circ}} \quad ; \text{ ff jjantinode } ; \tag{8}$$

to leading order in $H = H_{o}$, where $H_{o} = (v_{o} =)$ (c=e) $_{o} = ($) H_{c} . Observation of this anisotropy and linear eld dependence would be strong indication of a $d_{x^{2}} = \frac{1}{y^{2}}$ order parameter.

Sridhar et al. [[13]] have measured the eld dependence of the penetration length for if parallel to the a and baxes of single crystals of YBCO. These authors report an in-plane penetration depth which obeys $(H;T) = (T) + (T)H^2$. At intermediate temperatures, T' 80 K, they measure $(80)' 1A = G^2$, which drops by three orders of magnitude by T' 10 K; $(4)' 10^3 A = G^2$. The simplest interpretation is that the data is in good agreement with a fullgap on the Ferm i surface, in which case the $d_{x^2} = y^2$ state is not the order parameter of YBCO. However, we can ask if the data, so far, forces this conclusion. First of all, the $d_{x^2} = y^2$ state will also show a quadratic eld correction to the elective penetration depth at intermediate and high temperatures, with a coelectent that is similar in magnitude to that of the conventional BCS prediction, and also drops rapidly with temperature. The question is, at what temperatures and elds does the elective penetration depth exhibit a linear eld dependence?' The linear eld regime is inferred from eq.(1). The linear behavior arises from the nonanalytic dependence of γ_s on v_s at T = 0 for the nodal directions

where (s) = 0. Non-zero temperature removes the singularity. For su ciently small elds an expansion in v_s is valid; however, the cross-over eld is determined when the smallest M atsubara frequency becomes comparable to the super ow kinetic energy shift per particle, i.e. T ' $v_F v_s$ ' 2 $_{\circ}$ (H = H $_{\circ}$). This implies a cross-over eld, H $_x$ ' H $_{\circ}$ (T = T_c). Thus, to obtain a signi cant linear eld regime down to H ' H_{cl}=10' 25 G requires temperatures T 2 K. Thus, the experiments of ref.[[13]], which are reported down to 10 K, are apparently at the high end of the temperature regime where a linear term m ight become observable.

We also consider the elect of in purity scattering on the linear eld dependence of the elective penetration length. Quasiparticle scattering from in purities plays a similar role to that of temperature; the in purity lifetime removes the singular behavior of the current at su ciently low velocities. The cross-over eld due to impurity scattering can be obtained by including the impurity scattering selfenergy. The resulting current is given by eq.(1) with the replacement of $n ! r_n = n + (r_n=2) < 1 = \frac{1}{r_n^2 + j} (s)f >$, where is the s-wave scattering rate in the Born approximation, and the average is over the Fermi surface. At zero temperature, impurity scattering leads to a new low energy scale [14]], $r_n = 4$ oe r_n , which smooths out the linear behavior of the elective penetration length below the crossover eld, $H = 2H_0e^{-1}$ of H_{cl} . This condition is considerably less restrictive than that for the temperature. For YBCO with a mean-free path of $H_{res} = r_0 + 10$ the crossover eld is of order $2H_0e^{-10} = H_{cl}$. Thus, there should be no di culty from in purity scattering in observing the linear behavior in the elective penetration length form oderately clean YBCO crystals.

A nother test of the presence of nodal lines associated with a $d_{x^2 \ y^2}$ order parameter would be to measure the magnetic anisotropy energy, or magnetization torque, for in-plane elds. Consider a velocity eld $y = v_{x^0} \hat{x}^0 + v_{y^0} \hat{y}^0$. The projections of the velocity along the nodal lines \hat{x}^0 and \hat{y}^0 in ply two occupations of quasiparticle states of di ering magnitudes, which generate the current,

$$\hat{J}_{\rm qp} = \left(\begin{array}{cc} \frac{e}{2} N_{\rm f} v_{\rm f}^2 \right) & \frac{v_{\rm x^0}^2}{v_{\rm o}} & (x^0) + \frac{v_{\rm y^0}^2}{v_{\rm o}} & (y^0) \end{array} \right)$$
(9)

The important feature is that the current is not parallel to the velocity eld, except for the special directions along the nodes or anti-nodes; neither is the magnetic eld parallel to the applied eld \mathcal{H} . This implies that the magnetic energy, $U = \frac{1}{8}^{R} \mathcal{B} + \mathcal{H} d^{3}x$, is an isotropic in the ab-plane. For a lm in a parallel eld $\mathcal{H} = H$ ($\sin \# x^{0} + \cos \# y^{0}$), the magnetic anisotropy energy to leading order in $H = H_{\circ}$ is [[11]],

$$U_{an}(\#) = \frac{H^2}{2} \frac{H}{H_o} A [sin^3 \# + cos^3 \#] ; 0 \# =2;$$
(10)

where A is the surface area of the lm and $=\frac{8}{3}\left(1+\frac{1}{2}\cosh\left(\frac{d}{2}\right)\right) \sinh^4\left(\frac{d}{4}\right) = \cosh^3\left(\frac{d}{2}\right)$, which is constant equal to

1=3 for d , and varies as $(\frac{1}{4})^4$ for very thin lm s. The anisotropy energy is minimized for eld directions along the nodal lines, and is maximum for elds along the anti-nodes. In order to suppress vortex nucleation, thin lm s with dimensions d are desirable; the lower critical eld for vortex nucleation is increased by roughly (=d) in a thin lm. The optimum geometry might be a superlattice of superconducting/normal layers with an S-layer thickness, d < . In this case the eld at each SN interface is essentially the external eld, and the anisotropy energy is enhanced by the number of S-layers.

Torque magnetom etry has proven extrem ely useful for measuring the anisotropy of the penetration lengths for current ow along the c-axis compared to the basal plane [[15]]. In the linear response limit we do not expect anisotropy of the penetration depth for current ow in di erent directions in the basal plane; how ever, in-plane anisotropy of the current arising from nonlinear eld corrections should be observable at low temperatures, if the superconducting state has an unconventional order param eter. For comparison, the maximum magnetic torque from eq.(10) is ' $(1=6\frac{5}{3})H^2$ (H =H_o)A 10³ dyne cm =rad, for H = H_{c1} = 250 G, A = (2;000 m)² and

= 1;400A, which is small, but comparable to the smallest values of torque reported in [[15]].

In sum m ary, we suggest that m easurements of the eld dependence of the penetration depth for elds parallel to the CuO layers at tem peratures wellbelow 4 K should provide an answer to the question of whether or not the gap in the CuO superconductors has a line of nodes. If so, torque m agnetom etry and/or the anisotropy of the low tem perature penetration length could be used to locate the nodal lines on the Ferm i surface, thus providing direct evidence for or against a d_{x^2} y² order parameter for the CuO superconductors.

This research is supported by the Science and Technology Center for Superconductivity through NSF grant number DMR 88-09854.

- [1] Bedell, K., et al., eds., H igh Tem perature Superconductivity Addison-Weseley Pub.Co., 1989.
- [2] M onthoux, P., et al. Phys. Rev. Lett., 67, 3448, 1991.
- [3] Bulut, N. and Scalapino, D. Phys. Rev. Lett., 68, 706, 1992; J. P. Liu, unpublished, 1992.
- [4] Hammel, P.C., et al. Phys. Rev. Lett., 63, 1992, 1989; Shastry, B.S., Phys. Rev. Lett., 63, 1288, 1989.
- [5] Bulut, N., et al. Phys. Rev., B 41, 1797, 1990.
- [6] M illis, A.J., et al. Phys. Rev., B 42, 167, 1990.
- [7] Gross, F., et al. Z. Phys., B 64, 175, 1986.
- [8] Annett, J., et al. Phys. Rev., B 43, 2778, 1991.
- [9] Volovik, G. Physica Scripta, 38, 502, 1988.
- [10] Bardeen, J. Phys. Rev. Lett., 1, 399, 1958.
- [11] The details of this calculation are given elsewhere [Y ip, S., and Sauls, J.A. unpublished, 1992].
- [12] Nonanlytic behavior of the supercurrent at T = 0 was rst pointed out by Volovik and M ineev Sov. Phys. JETP, 54, 524, 1981.] in the context of super uid ³H e A, and is discussed in careful detail by M uzikar and Rainer Phys. Rev., B 27, 4243, 1983]. These latter authors also calculated the nonanalytic supercurrent for a p-wave polar state which has a line of nodes.
- [13] Sridhar, S., et al. Phys. Rev. Lett., 63, 1873, 1989.
- [14] Gorkov, L., and Kalugin, P. Sov. JETP Lett., 41, 254, 1985.
- [15] Farrell, D.E., et al. Phys. Rev. Lett., 61, 2805, 1988.

Figure Caption

Figure 1. Phase space for $\mathbf{v}_s \mathbf{j} \mathbf{\hat{x}}^0$