

Feedback Effects in Superconductors

Tony Gherghetta and Yoichiro Nambu

Enrico Fermi Institute and Department of Physics
University of Chicago, Chicago, IL 60637

We calculate corrections to the BCS gap equation caused by the interaction of electrons with the collective phase and amplitude modes in the superconducting state. This feedback reduces the BCS gap parameter, Δ , and leaves the critical temperature, T_c , unchanged. The feedback effect is proportional to $(\Delta/E_F)^2$, where E_F is the Fermi energy. This is a negligible correction for type-I superconductors. However in type-II superconductors the feedback effect is greatly enhanced due to smaller Fermi velocities, v_F , and may be responsible for effects seen in recent experimental data on organic superconductors.

June 93

e-mail : tonyg@yukawa.uchicago.edu

In the BCS theory of superconductivity [1], there exist two distinct collective modes corresponding to the fluctuations of the phase and amplitude of the superconducting gap. The phase or Anderson-Bogoliubov mode [2] has been known for a very long time to be important in maintaining gauge invariance in the BCS theory [3]. In the presence of a Coulomb field, the phase mode, (ϕ) interacts strongly with the Coulomb field to become the plasmon mode. On the other hand the amplitude mode, (Δ) is unaffected by Coulomb interactions, so that this mode remains intact. This decoupling feature of the amplitude mode means that it is not easily observable and it was only recently that such a mode was discovered in the charge density wave compound NbSe₂ through the coupling to long-wavelength phonons [4{5].

In this Letter we wish to consider the effects of these collective modes back on the superconducting state. In the effective four-Fermi interaction BCS theory, an effective coupling between the collective modes and the quasiparticles induces self-energy corrections to the quasiparticle propagator. These corrections can either enhance the attraction between Cooper pairs and so contribute positively to the superconducting state, or they can act negatively on the superconducting state and reduce the gap parameter Δ . The magnitude of these corrections is proportional to $(\Delta/E_F)^2$. These are negligible corrections for type-I superconductors where typically $\Delta/E_F \sim 10^{-3}$. However the feedback effects may become important if the typical Fermi energies are much smaller. This is the case in type-II superconductors where $v_F \sim 10^6 \text{ cm s}^{-1}$. Recent experiments in organic superconductors [6], where typical Fermi energies are small, hint at the possibility that such a scenario may be at work. We will now present a calculation of these corrections and show how the superconducting state is affected.

Let us first recall some basic features of the field theoretic formulation of BCS superconductivity [7{8]. In the BCS ansatz [1] the Frohlich effective electron-electron interaction [9] is replaced by a contact potential

$$V(\mathbf{x}, \mathbf{x}') = -V \delta^3(\mathbf{x} - \mathbf{x}') \quad (1)$$

where $V > 0$. The effective Lagrangian is given by

$$L = i \sum_{\mathbf{r}} \psi_{\mathbf{r}}^\dagger \psi_{\mathbf{r}} - \sum_{\mathbf{r}} \psi_{\mathbf{r}}^\dagger \psi_{\mathbf{r}} + \frac{1}{2} V \sum_{\mathbf{r}} \psi_{\mathbf{r}}^\dagger \psi_{\mathbf{r}} \psi_{\mathbf{r}}^\dagger \psi_{\mathbf{r}} \quad (2)$$

where E is the electron kinetic energy measured from the Fermi energy and we have used the two-component notation [3]

$$\psi = \begin{pmatrix} \psi_1 \\ \psi_2 \end{pmatrix} \quad (3)$$

to represent the Bogoliubov-Valatin fermionic quasiparticle modes. In the superconducting state the Lagrangian (2) is written as a sum of a free term L_0 plus an interaction piece L_I

$$\begin{aligned} L_0 &= i \bar{\psi} \gamma_0 \psi - \sum_{\mathbf{p}} \bar{\psi}_{\mathbf{p}} \gamma_0 \psi_{\mathbf{p}} \\ L_I &= \frac{1}{2} V \sum_{\mathbf{p}} \bar{\psi}_{\mathbf{p}} \gamma_0 \psi_{\mathbf{p}} + \sum_{\mathbf{p}} \bar{\psi}_{\mathbf{p}} \gamma_0 \psi_{\mathbf{p}} \end{aligned} \quad (4)$$

where we have introduced the mass gap Δ . The bare quasiparticle Green's function corresponding to L_0 is

$$G(\mathbf{k}) = i \frac{k_0 + \Delta}{(k_0)^2 - E^2 + i\epsilon} \quad (5)$$

where $E^2 = E^2 + \Delta^2$ is the quasiparticle excitation energy. In L_I we have to ensure that there are no selfenergy corrections proportional to Δ in order to maintain consistency with the ansatz that L_0 describes the superconducting ground state with mass gap Δ . Using a Fierz identity for the Pauli matrices, [8] this leads directly to the BCS gap equation [1]

$$1 = \frac{1}{2} V \int_0^{\Lambda_D} \frac{d^3 p}{(2\pi)^3} \frac{1}{E_p^2 + \Delta^2} \quad (6)$$

where the integral is cut off at the Debye energy, Λ_D .

To exhibit the collective modes of the superconducting state, let us examine the quasiparticle-quasiparticle scattering amplitude generated by the infinite sum of bubble diagrams, as shown in fig. 1. The scattering amplitude is a simple geometric series and is easily summed to give

$$A_{\mathbf{k}}(\mathbf{k}) = \frac{\frac{1}{2} V}{1 - I_{\mathbf{k}}(\mathbf{k})} \quad (7)$$

where

$$I_{\mathbf{k}}(\mathbf{k}) = \frac{1}{2} V \int_0^{\Lambda_D} \frac{d^4 p}{(2\pi)^4} \text{Tr} \left[\gamma_0 G(\mathbf{p} + \frac{\mathbf{k}}{2}) \gamma_0 G(\mathbf{p} - \frac{\mathbf{k}}{2}) \right] \quad (8)$$

and

$$I_{\mathbf{k}}(\mathbf{k}) = \frac{1}{2} V \int_0^{\Lambda_D} \frac{d^4 p}{(2\pi)^4} \text{Tr} \left[\gamma_1 G(\mathbf{p} + \frac{\mathbf{k}}{2}) \gamma_1 G(\mathbf{p} - \frac{\mathbf{k}}{2}) \right] \quad (9)$$

are the integrals for the two types of single bubble diagrams. The poles of the scattering amplitude (7) occur when $I_{\mathbf{k}}(\mathbf{k}) = 1$. At zero momentum transfer ($\mathbf{k} = 0$), the integrals (8) and (9) can be written in the form

$$I_{\mathbf{k}}(k_0^2 = \Delta^2) = 1 - \frac{1}{2} V \int_0^{\Lambda_D} \frac{d^3 p}{(2\pi)^3} \frac{1}{E_p} \frac{\Delta^2}{\Delta^2 + 4E_p^2} \quad (10)$$

$$I_{\mathbf{k}}(k_0^2 = \Delta^2) = 1 - \frac{1}{2} V \int_0^{\Lambda_D} \frac{d^3 p}{(2\pi)^3} \frac{1}{E_p} \frac{\Delta^2 + 4E_p^2}{\Delta^2 + 4E_p^2} \quad (11)$$

where we have used the BCS gap equation (6). It is then obvious that $I(\omega^2 = 0) = I(\omega^2 = 4\epsilon^2) = 1$ and the quasiparticle-quasiparticle scattering amplitude has poles at $\omega^2 = 0$ and $\omega^2 = 4\epsilon^2$ which represent the phase (ϕ) and amplitude (α) modes respectively [10]. For nonzero momentum transfers \mathbf{k} , we can Taylor expand the integrands in (8) and (9) to obtain the dispersion relations for the collective modes [5]

$$E^2(\mathbf{k}) = \frac{1}{3}v_F^2 \mathbf{k}^2 \quad (12)$$

$$E^2(\mathbf{k}) = 4\epsilon^2 + \frac{1}{3}v_F^2 \mathbf{k}^2 \quad (13)$$

where v_F is the Fermi velocity.

The effective quasiparticle-collective mode coupling is obtained from the residue at the pole of the scattering amplitude (7). Using (10), the quasiparticle-mode coupling is

$$f^2 = \frac{1}{2}V \frac{dI}{d\omega^2} \Big|_{\omega^2=0} = \frac{4\epsilon^2}{N(\epsilon_F)} \quad (14)$$

where $N(\epsilon_F) = \frac{m k_F}{2}$ is the density of states at the Fermi surface. If we attempt a similar procedure for the ϕ mode then it turns out that the corresponding integral in (14) is divergent, because the pole coincides with the two-particle threshold. This is the inadequacy of modelling the BCS theory by the ϕ model. We will simply circumvent this problem by assuming $f = f_\phi$ as in the Ginzburg-Landau theory. This is a good approximation in the weak coupling limit.

What are the effects of the collective modes on the quasiparticle self-energy? First, we assume that a Coulomb field is present, so that the Goldstone ϕ mode turns into the massive plasmon mode [7]. In order to correctly take into account the plasmon mode, we need to start with the original Coulomb and phonon interactions instead of the effective four-Fermi interaction, V . This is beyond the scope of this Letter, so we will ignore its effects on the quasiparticle self-energy. However we expect this contribution to be small because the plasmon mass is large compared to ϵ and the Debye energy, ω_D .

For the massive ϕ mode there will be two contributions to the quasiparticle self-energy. The first contribution comes from the tadpole term shown in Fig. 2. It is given by

$$\Sigma_t = \frac{i J(\omega)}{1 - I(0)} \quad (15)$$

However this term is already implicitly included in the BCS gap equation and its inclusion would amount to a double counting of diagrams. To see this more clearly, consider the effect of adding a small bare term Δ_0 to the gap equation (6)

$$\Delta = \Delta_0 + J(\Delta) \quad (16)$$

If we now seek a perturbative solution of (16) of the form $\Delta = \Delta_0 + \delta\Delta$ then we obtain

$$\begin{aligned} \Delta &= \Delta_0 + \frac{\partial(J(\Delta))}{\partial\Delta} \delta\Delta \\ &= \frac{\Delta_0}{1 - I'(0)} \end{aligned} \quad (17)$$

Thus comparing (15) and (17) we see that the tadpole term appears only as the response of Δ to a nonzero Δ_0 .

The second contribution results from contracting the crossed tree diagram, leading to the "Weisskopf term" shown in fig. 2. This contribution will act negatively on the superconducting state because contracting the crossed diagram involves a sign change. Hence the Weisskopf term will act to reduce the gap. In order to calculate the Weisskopf term we reinterpret the quasiparticle-quasiparticle scattering amplitude, A as arising from the exchange of the m mode with propagator

$$G_m(k) = i \frac{1}{(k^0)^2 - E^2(k)} \quad (18)$$

where we have approximated the continuum cut solely by the m mode pole. This considerably simplifies the equations and the corrections arising from the continuum contribution in (7) do not affect the qualitative behaviour. The Weisskopf self-energy term may now be written as

$$\Sigma_W(k) = if^2 \int \frac{d^4p}{(2\pi)^4} G_1(p) G_m(p-k) G_1(k) \quad (19)$$

and we will evaluate it at the Fermi surface: $k_0 = \epsilon_F$, $|\mathbf{k}| = k_F$. The term proportional to G_1 which gives a contribution to the gap in the limit $E_F \rightarrow 0$ is

$$\begin{aligned} \Sigma_W &= \frac{3}{8} \frac{1}{E_F} \int_0^{2\pi} d\theta \int_0^{2\pi} d\phi \int_0^{2\pi} d\psi \int_0^{2\pi} d\chi \frac{1}{E^2 + \frac{1}{2}} \\ &\quad \ln \frac{1}{4} \frac{E}{E_F} + \frac{3}{8E_F^2} \frac{1}{(E^2 + \frac{1}{2})} \frac{1}{3E^2 + 4} + \frac{3}{4} \frac{1}{E_F} \end{aligned} \quad (20)$$

where ω_D is the Debye frequency cut-off.

The Weisskopf term will also give corrections to the λ and μ terms in L_0 . The corrections to λ will renormalize the chemical potential and the electron mass and give rise to an effective electron mass, m^* . The term proportional to the identity matrix, 1 , adds a contribution $k_0(\omega_D)$ to the energy k_0 . Defining $Z = 1 + \lambda$, this corresponds to a wavefunction renormalization $\psi \rightarrow Z^{-1/2} \psi$ and modifies the mass gap term by Z^{-1} . Evaluating the wavefunction renormalization constant at the Fermi surface in the limit $E_F \gg \omega_D$ gives

$$Z = 1 + \frac{3}{8} \left(\frac{\omega_D}{E_F} \right)^2 \left[3 - \frac{\pi}{3} \ln \frac{2\omega_D}{E_F} \right] = 0.844 + O\left(\frac{\omega_D}{E_F}\right) \quad (21)$$

Thus the total self-energy contributions to the gap arising from the Weisskopf term will be $\Delta_W = (\lambda + \mu)$ where we have kept terms to lowest order in the correction parameter $(\omega_D/E_F)^2$. Thus the BCS gap equation with the Weisskopf corrections in the limit $E_F \gg \omega_D$ is

$$1 = \frac{1}{2} V N(E_F) \ln \frac{2\omega_D}{E_F} + \frac{3}{8} \left(\frac{\omega_D}{E_F} \right)^2 \left[\ln \frac{2\omega_D}{E_F} + \ln \frac{2\omega_D}{E_F} - 2 \ln \frac{E_F}{\omega_D} + 0.762 \right] + 0.389 \frac{\omega_D}{E_F} \quad (22)$$

where we have evaluated the integral in (20) to $O(\ln x = x^2)$ where $x = \omega_D/E_F$. In normal type-I superconductors $(\omega_D/E_F)^2 \approx 10^{-6}$ because $v_F \approx 10^8 \text{ cm s}^{-1}$. This is quite a small correction compared to $V N(E_F) \approx 0.25$. However in type-II superconductors the Fermi velocity is smaller: $v_F \approx 10^6 \text{ cm s}^{-1}$, and the gap parameter is larger, so that the correction, $(\omega_D/E_F)^2 \approx 10^{-2}$. Note that this does not contradict the fact that we assumed $E_F \gg \omega_D$, because the corrections are always proportional to $(\omega_D/E_F)^2$. However we need to obtain the coefficients of $(\omega_D/E_F)^2$ in the limit $E_F > \omega_D$. We present the full exact expressions for λ and μ below.

All the above results are for $T = 0$. The results at finite temperature are obtained by using the imaginary time formalism. The quasiparticle-mode coupling constant (14) at finite T becomes

$$\frac{1}{f^2(T)} = \frac{N(E_F)}{8\pi^2 E_F} \int_0^{\omega_D} \frac{dE}{E^3} \frac{1}{E + E_F} \tanh \frac{E}{2T} \quad (23)$$

where $\beta = 1/k_B T$. It is interesting to note that in the limit $E_F \gg \omega_D$ the coupling (23) is simply $f^2(T) = 4\pi^2(T)N(E_F)$ as $T \rightarrow 0$. One immediate consequence of (23)

is that at $T = T_c$ the integral is divergent and so the coupling constant vanishes, i.e., $f(T_c) = 0$. Hence the determination of T_c remains unaffected by the amplitude mode correction.

Similarly we can obtain the finite temperature expressions for Z_1 and Z_2 . At the Fermi surface we have

$$Z_1(T) = f^2(T) \frac{N(E_F)}{8E_F} \int_{-1}^1 d\cos\theta \frac{1}{(E + E_F)^2} \frac{1}{(E - E_F)^2} \frac{1}{E^2 + E_F^2 - E^2} \tanh \frac{E}{2} + \frac{1}{E} (E^2 - E_F^2 + E^2) \coth \frac{E}{2} \quad (24)$$

$$Z_2(T) = f^2(T) \frac{N(E_F)}{8E_F} \int_{-1}^1 d\cos\theta \frac{1}{(E + E_F)^2} \frac{1}{(E - E_F)^2} \frac{1}{E^2 - 2EE_F \tanh \frac{E}{2} + (E^2 - E_F^2 + E^2) \coth \frac{E}{2}} \quad (25)$$

where the coupling $f(T)$ is determined from (23) and

$$E^2 = E_F^2 + \frac{r}{3E_F^2} \left(1 + \frac{1}{2} \frac{E}{E_F}\right) \left(1 + \frac{E}{E_F} \cos\theta + 4\right)^{-2} \quad (26)$$

In the limit $E_F \rightarrow \infty$ and $T = 0$ the expressions (24) and (25) reduce to (20) and (21). Combining these corrections with the finite temperature BCS gap equation, [7] we obtain the complete finite temperature equation for $f(T)$:

$$1 = \frac{1}{4E_F} V N(E_F) \int_{-1}^1 d\cos\theta \frac{dE}{E} \frac{1}{E + E_F} \tanh \frac{E}{2} + Z_1(T) + Z_2(T) \quad (27)$$

The solution of (27) is shown in Fig. 3 for typical values of the parameters in a type-II superconductor. The biggest deviation is at $T = 0$ and decreases until $T = T_c$, where there is no change from the BCS result. Such a scenario may be occurring in the organic superconductor $(BEDT-TTF)_2I_3$ where a proposal, [6] to place the gap at 6 cm^{-1} may be consistent with the observation that the gap below T_c is reduced from the BCS value ($2(T = 0) = 20 \text{ cm}^{-1}$), while T_c remains unchanged.

For a thorough discussion of the realistic cases, however, one has to take into account the complexities of the electronic band structure and phonon spectra. One of the important effects is the mixing of the amplitude mode with the original Coulomb and phonon interactions [5]. This mixing is proportional to $\propto E_F$ and occurs because of the intrinsic

particle-hole asymmetry relative to the Fermi surface. It again results in a reduction of the pairing forces and is most significant in type-II or organic superconductors.

It should be noted that if one considers so called 'neutral' superconductors and includes the effect of the pure Goldstone ω_2 mode then one finds that the feedback is positive for the ω_1 term. This will almost cancel against the negative feedback of the amplitude mode (20). However the contribution to the ω_1 term is the same sign as for the amplitude mode and will add to the amplitude correction to give $\omega_w^2 = 2 \omega_Z^2$.

The feedback effects of the collective bosonic modes on the superconducting state may also be relevant for the recent high T_c superconductors where $\omega_F/\omega_D \approx 0.1$ [11]. However without a complete understanding of the mechanism involved in high T_c materials at present, we can only but speculate on these effects.

We would like to thank M. Weger, whose correspondence initiated this work. This work was supported in part by NSF contract PHY-91-23780.


References

- [1] J. Bardeen, L. N. Cooper and J. R. Schrieffer, Phys. Rev. 108, 1175 (1957).
- [2] P. W. Anderson, Phys. Rev. 110, 827 (1958); 112, 1900 (1958) ;
N. N. Bogoliubov, Nuovo Cimento, 7, 794 (1958).
- [3] Y. Nambu, Phys. Rev. 117, 648 (1960).
- [4] R. Sooryakumar and M. V. Klein, Phys. Rev. Lett. 45, 660 (1980) ;
Phys. Rev. B 23, 3213 (1981); B 23, 3223 (1981).
- [5] P. B. Littlewood and C. M. Varma, Phys. Rev. B 26, 4883 (1982) ;
C. A. Balseiro and L. M. Falicov, Phys. Rev. Lett. 45, 662 (1980).
- [6] K. I. Pokhodnia, A. G. Raj, M. Weger and D. Schweitzer, Z. Phys. B, 90, 127 (1993).
- [7] J. R. Schrieffer, Theory of Superconductivity, W. A. Benjamin Inc, New York, 1964.
- [8] S. Cramer, M. Sapiro and D. Lurie, Nuovo Cimento, B 6, 179 (1971).
- [9] H. Frohlich, Phys. Rev. 79, 845 (1950).
- [10] Y. Nambu and G. Jona-Lasinio Phys. Rev. 122, 345 (1961).
- [11] V. Z. Kresin and S. A. Wolf, Fundamentals of Superconductivity, Plenum Press, New York, 1990


Figure Captions

- Fig. 1. The infinite sum of bubble diagrams for the quasiparticle-quasiparticle scattering amplitude. The ϵ_i represents either ϵ_1 (mode) or ϵ_2 (mode).
- Fig. 2. The quasiparticle self-energy diagrams arising from the ϵ mode coupling, where (a) depicts the tadpole diagram and (b) shows the Weisskopf term.
- Fig. 3. Comparison of the solution of the gap equation with feedback effect (dashed line) with the normal BCS result (solid line) for typical type-II superconductor parameter values.

$$\begin{array}{c} \diagup \bullet \tau_i \diagdown \end{array} \cdots \begin{array}{c} \diagdown \bullet \tau_i \diagup \end{array} = \begin{array}{c} \diagup \bullet \bullet \tau_i \diagdown \end{array} + \begin{array}{c} \diagup \bullet \bullet \tau_i \tau_i \bullet \tau_i \diagdown \end{array} + \begin{array}{c} \diagup \bullet \bullet \tau_i \tau_i \bullet \bullet \tau_i \tau_i \tau_i \diagdown \end{array} + \cdots$$



(a)



(b)

