

# OPTICAL ABSORPTION IN $C_{70}$ AND $C_{76}$ : EFFECTS OF SYMMETRY REDUCTION

Kikuo Harigaya and Shuji Abe

Fundamental Physics Section, Electrotechnical Laboratory,

Umezono 1-1-4, Tsukuba 305, Japan

## Abstract

Optical absorption spectra of  $C_{70}$  and  $C_{76}$  are calculated by a tight binding model with a long ranged Coulomb interaction. The spectrum of  $C_{70}$  is in overall agreement with the experiment of molecules in a solution. The variations of the spectral shape are discussed relating with the symmetry reduction from  $C_{70}$  to  $C_{76}$ .

## 1. Introduction

Recently, fullerenes  $C_N$  with hollow cage structures have been intensively investigated. Many optical experiments have been performed, and interesting properties due to  $\pi$  electrons delocalized on molecule surfaces have been revealed. They include the optical absorption spectra of  $C_{60}$  and  $C_{70}$  [1], and the large optical nonlinearity of  $C_{60}$  [2,3]. In order to analyze the optical prop-

---

To whom correspondence should be addressed; E-mail address: harigaya@etlgo.jp.

erties, we have studied the linear absorption and third harmonic generation of  $C_{60}$  by using a tight binding model [4] and a model with a long range Coulomb interaction [5].

The purpose of this paper is to extend the calculation of  $C_{60}$  [5] to higher fullerenes:  $C_{70}$  and  $C_{76}$ . The main purpose is to look at how the optical absorption changes as the symmetry of the molecule reduces from  $C_{60}$  and  $C_{70}$  to  $C_{76}$ . We start from a tight binding model with a long ranged Coulomb interaction. The Coulomb interaction is the form of the Ohno potential with the onsite and long range interaction strengths. We also consider the broadening of the optical spectra due to lattice fluctuations by using the bond disorder model.

We shall report calculations in the following way. In the next section, our model and its meaning are explained. Calculation method is also described shortly. In §3, we report about  $C_{70}$ . The calculated absorption spectrum is shown, and comparison with experiments in a solution is made. We will conclude that there is an overall agreement. Then, in §4, we turn to  $C_{76}$ . We will discuss how the symmetry reduction appears in the spectrum. The summary is given in the last section.

## 2. Model and formalism

We use the following hamiltonian to consider optical spectra of  $C_{70}$  and  $C_{76}$ :

$$H = H_0 + H_{\text{bond}} + H_{\text{int}}: \quad (1)$$

The first term of Eq. (2.1) is the tight binding model:

$$H_0 = -t \sum_{\langle i,j \rangle} c_{i\uparrow}^\dagger c_{j\uparrow} \quad (2)$$

where  $t$  is the hopping integral;  $c_{i\uparrow}$  is an annihilation operator of a  $\uparrow$ -electron with spin  $\uparrow$ . If  $t$  depends on the bond length, the results do not change so strongly, because main contributions come from the strong Coulomb potential. Effects of zero point vibrations and thermal fluctuation of the lattice are described by the bond disorder model which is the second term of Eq. (2.1):

$$H_{\text{bond}} = \sum_{\langle i,j \rangle} t_{ij} c_{i\uparrow}^\dagger c_{j\uparrow} \quad (3)$$

Here,  $t_{ij}$  is the Gaussian disorder potential at the bond  $\langle i,j \rangle$ . We can estimate the strength of the disorder (standard deviation)  $t_s$  from the results by the extended Su-Schrieffer-Heeger model [6]. The value would be  $t_s = 0.05 - 0.1t$ . This is of the similar magnitude as in the fullerene tubules and conjugated polymers. We shall treat interactions among  $\uparrow$ -electrons by the following model:

$$H_{\text{int}} = U \sum_i (c_{i\uparrow}^\dagger c_{i\uparrow} - \frac{1}{2}) (c_{i\downarrow}^\dagger c_{i\downarrow} - \frac{1}{2}) + \sum_{i \neq j} W(r_{ij}) (c_{i\uparrow}^\dagger c_{i\uparrow} - \frac{1}{2}) (c_{j\uparrow}^\dagger c_{j\uparrow} - \frac{1}{2}); \quad (4)$$

where  $r_{ij}$  is the distance between the  $i$ th and  $j$ th sites and

$$W(r) = \frac{1}{(1+U)^2 + (r-r_0/V)^2} \quad (5)$$

is the Ono potential. The quantity  $U$  is the strength of the onsite interaction,  $V$  means the strength of the long range Coulomb interaction, and  $r_0$  is the average bond length.

The model is treated by the Hartree-Fock approximation and the single excitation configuration interaction method (single CI), as we used in the previous paper [5]. All the quantities of the energy dimension are shown in the units of  $t$ . Parameters of the Coulomb interaction are changed within  $0 \leq V \leq U \leq 5t$ , and we search for the data which reproduce overall features of experiments of  $C_{60}$  (shown in Ref. [5,7]) and  $C_{70}$ . The absorption spectra become anisotropic with respect to the orientation of the molecule against the electric field as reported in the free electron model (Huckel theory) of  $C_{70}$  [8]. We average the anisotropy by rotating the molecule. The averaged data can be compared with experiments of molecules in solutions [1]. We also include the lattice fluctuation effects by averaging over bond disorder potentials as well. Samples of the orientation of the molecule and the disorder potential are changed 100 times. The good convergence is checked by comparing with the results of the sample number 50.

### 3. Optical absorption in $C_{70}$

Fig. 1(a) shows the molecular structure of the  $C_{70}$ . It has the rugbyball structure with the  $D_{5h}$  symmetry. The absorption spectrum is calculated for the Coulomb potential strengths  $U = 4t$  and  $V = 2t$ , and the bond disorder  $t_s = 0.09t$ . The same parameter set has been successful for  $C_{60}$  when the calculation is compared with the experiment [7].

Fig. 2(a) shows the calculated optical absorption. Fig. 2(b) shows the experimental data of  $C_{70}$  in a solution taken from [1]. The abscissa is scaled

by using  $t = 1.9\text{eV}$ . The optical gap near  $1.0t$  accords well with the experiment. The small peaks around  $1.8t$  may correspond to those of the experiment in the similar energy region. Commonly, there is a dip of the optical absorption at about  $2.0t$  in the calculation and experiment. There is a maximum at  $2.8t$  in the two data. Therefore, we conclude that there is an overall agreement between the calculation and the experiment. We note that the quantum lattice fluctuation effects are also simulated well by the bond disorder model.

## 4. Optical absorption in $C_{76}$

There have been two possible structures for  $C_{76}$  which satisfy the isolated pentagon rule [9]. They have  $D_2$  and  $T_d$  symmetries. Owing to the NMR experiment [10], the molecular structure has been identified. There is only the molecule with  $D_2$  symmetry. The structure is shown in Fig. 1 (b). We calculate the optical absorption taking account of the bond disorder  $t_s = 0.09t$ , and Coulomb interaction strengths  $U = 4t$  and  $V = 2t$ . As far as the authors know at present, there are not detailed experimental data which can be compared with the calculation. However, the calculation will be helpful for experimental developments.

Fig. 3 shows the calculated results. The average by the rotation has been performed. The optical gap is about  $0.7t$  and this is smaller than  $1.8t$  of  $C_{60}$  and that of  $C_{70}$ . There are two broad large features around  $1.5t$  and  $2.5t$  with the structures. We could say that several small peaks around  $1.5t$  and  $2.6t$  in the  $C_{70}$  data become fragmented to form the two wide features in the  $C_{76}$

data. There is still a dip near 2.0t as in  $C_{70}$ . The position of the dip does not change so much. These variations could be regarded as owing to the symmetry reduction from  $C_{60}$  and  $C_{70}$  to  $C_{76}$ .

## 5. Summary

We have considered optical spectra of higher fullerenes:  $C_{70}$  and  $C_{76}$ . We have mainly looked at how the optical absorption changes as the symmetry of the molecule reduces from  $C_{60}$  and  $C_{70}$  to  $C_{76}$ . In the report about  $C_{70}$ , we compared the data averaged over the molecule orientation with experiments in a solution. We have concluded that there is an overall agreement about the energy dependence in the optical spectrum. In the report of  $C_{76}$ , we have discussed how the symmetry reduction appears in the spectrum. As we proceed from  $C_{60}$  and  $C_{70}$  to  $C_{76}$ , several peaks merge into two large broad peaks owing to the symmetry reduction.

## Acknowledgements

The authors acknowledge helpful correspondence with Dr. Mitsutaka Fujita. They also thank Mr. Mitsuho Yoshida for providing them with molecular coordinates of  $C_{70}$  and  $C_{76}$  which are generated by the program [11] based on the projection method on the honeycomb lattice [12].

## References

- [1] Hare, J.P., Kuroto, H.W., and Taylor, R., Chem. Phys. Lett., 1991, 177, 394.
- [2] Meth, J.S., Vanherzeele, H., and Wang, Y., Chem. Phys. Lett., 1992, 197, 26.
- [3] Kafa, Z.H., Lindle, J.R., Pong, R.G.S., Bartoli, F.J., Lingg, L.J., and Milliken, J., Chem. Phys. Lett., 1992, 188, 492.
- [4] Harigaya, K. and Abe, S., Jpn. J. Appl. Phys., 1992, 31, L887.
- [5] Harigaya, K. and Abe, S., J. Lum in., (to be published).
- [6] Friedman, B. and Harigaya, K., Phys. Rev. B, 1993, 47, 3975; Harigaya, K., Phys. Rev. B, 1993, 48, 2765.
- [7] Harigaya, K. and Abe, S., Phys. Rev. B, (preprint).
- [8] Shumway, J. and Satpathy, S., Chem. Phys. Lett., 1993, 211, 595.
- [9] Manolopoulos, D.E., J. Chem. Soc. Faraday Trans., 1991, 87, 2861.
- [10] Ettl, R., Chao, I., Diederich, F., and Robert, L.W., Nature, 1991, 352, 149.
- [11] Yoshida, M. and O sawa, E., (preprint).
- [12] Fujita, M., Saito, R., Dresselhaus, G., and Dresselhaus, M.S., Phys. Rev. B, 1992, 45, 13834.

Figure captions

FIG. 1. Molecular structures for (a)  $C_{70}$  with  $D_{5h}$  symmetry and (b)  $C_{76}$  with  $D_2$  symmetry.

FIG. 2. Optical absorption spectra for  $C_{70}$  shown in the arbitrary units. The abscissa is scaled by  $t$ . (a) The calculated spectrum with the parameters  $U = 4t$  and  $V = 2t$ . (b) The experimental spectrum (Ref. [1]) of molecules in a solution. We use  $t = 1.9\text{eV}$ .

FIG. 3. Optical absorption spectrum for  $C_{76}$  shown in the arbitrary units. The abscissa is scaled by  $t$ . Parameters in the Coulomb potential are  $U = 4t$  and  $V = 2t$ .