

# Temperature induced transitions between insulator, metal, and quantum Hall states

S.V.Kravchenko, Whitney Mason, and J.E.Fumeaux

Laboratory for Electronic Properties of Materials and Department of Physics and Astronomy,  
University of Oklahoma, Norman, Oklahoma 73019

J.M.Caulfield and J.Singleton

Clarendon Laboratory, Department of Physics, University of Oxford, Parks Road, Oxford  
OX1 3PU, United Kingdom

V.M.Pudalov

Institute for High Pressure Physics, Troitsk, 142092 Moscow district, Russia

## Abstract

We report the observation of temperature induced transitions between insulator, metal, and quantum Hall behaviors for transport coefficients in the very dilute high mobility two-dimensional electron system in silicon at a magnetic field corresponding to Landau level filling factor  $\nu = 1$ . Our data show that as the temperature decreases, the extended states at  $\nu = 1$  (above the Fermi level at higher temperature so that the system is insulating) sink below the Fermi energy, so that the quantum Hall effect occurs. As the extended states cross the Fermi level, the conductivity has a temperature dependence characteristic of a metallic system.

PACS 73.40.Hm, 73.40.Qv, 71.30.+h

Typeset using REVTeX

In the study of two dimensional electron systems (2DES), there have been considerable interest in transitions between insulating and quantum Hall (QH) states. Thus far such transitions have only been observed as the magnetic field and/or the electron density are changed. However, in this paper we present experimental evidence that transitions between insulator, metal, and QH-like behaviors for transport coefficients can also be observed at fixed field and carrier density as the temperature is decreased. In particular, we have observed 2DES delocalization (insulator to metal transition) with decreasing temperature, whereas increasing localization is the usual consequence of lowering the temperature for a 2DES.

It was reported recently both for high-mobility silicon inversion layers [1] and for low-mobility GaAs/AlGaAs heterostructures [2,3] that 2DES, strongly localized in zero magnetic field ( $B = 0$ ), can nevertheless manifest the integer QH effect. References [4-6] discuss this magnetic-field-induced transition from a many-body point of view, whereas Refs. [2,3] ignore the effects of electron-electron interactions and consider the arguments of Kohn and Laughlin [7] and Laughlin [8] along with the global phase diagram proposed by Kivelson, Lee, and Zhang [9] as the basis for the insulator-QH transition. According to Refs. [7,8], extended states, which lie above the Fermi energy ( $E_F$ ) at  $B = 0$  (i.e. making the system insulating) decrease in energy as  $B$  is increased [see inset in Fig. 1 (a)] and may sink below  $E_F$  [10]. At zero temperature, the diagonal conductivity ( $\sigma_{xx}$ ) is zero except when extended states are at  $E_F$ . As long as  $E_F$  lies below the lowest extended state, the Hall conductivity ( $\sigma_{xy}$ ) is also zero and the system is insulating. For each band of extended states below  $E_F$ ,  $\sigma_{xy}$  increases by  $e^2/h$ , providing the next integer QH state. In high magnetic fields, the extended states approximately follow half-filled Landau levels with filling factors  $\nu = n_s/(eB/h) = 1/2, 3/2, 5/2$  etc (here  $n_s$  is the electron density,  $e$  is the electron charge,  $c$  is the speed of light, and  $h$  is the Planck constant). If temperature is not zero,  $\sigma_{xx}$  usually displays activated behavior except when there are extended states at  $E_F$  with the activation energy equal to the energy difference between  $E_F$  and the nearest extended state.

Magnetic-field-induced transitions between insulating and QH groundstates have also been investigated in very dilute high-mobility GaAs/AlGaAs heterostructures in the ex-

transverse quantum limit (see, e.g., Ref. [12] and references therein) and in Si inversion layers around  $\nu = 1, 2$ , and 6 (Ref. [5,6]). In some papers [4,6,13-15] the fact that the insulating state can be disrupted by integer or fractional QH resistivity minima was discussed in terms of the formation of a pinned electron solid melting at integer or fractional  $\nu$ . However, the global phase diagram [9] can also explain magnetic-field-induced transitions between QH (at  $\nu = 1, 1/3$ , or  $1/5$ ) and insulating groundstates without invoking collective effects; though, recently observed direct transitions from  $\nu = 2=7$  and  $2/5$  (Refs. [15,16]) and  $\nu = 6$  (Ref. [6]) to insulating states are contradictions of the global phase diagram. At very low  $n_s$ , the QH effect breaks down even at integer or fractional  $\nu$  [1,15]; nevertheless  $\rho_{xx}$  still has minima at these filling factors.

Here we consider the  $\nu = 1$  integer QH effect at the border of its existence, at very low  $n_s$ . There is definitely no electron solid for these conditions. We report experimental evidence for transitions from insulating to metallic and QH types of behavior of transport coefficients at constant filling factor  $\nu = 1$  as the temperature is varied. We will define a system as insulating if its conductivities exhibit insulator-like temperature behavior, i.e.,  $d\rho_{xx}/dT, d\rho_{xy}/dT > 0$  with  $\rho_{xy} < \rho_{xx} < e^2/h$ . Similarly we define "metallic" behavior as  $d\rho_{xx}/dT, d\rho_{xy}/dT < 0$ . Finally, a QH state is characterized by  $\rho_{xy} \rightarrow e^2/h$  and  $\rho_{xx} \rightarrow 0$  as the temperature is lowered. The observed transitions from insulating behavior can be explained by assuming that at  $\nu = 1$ , the lowest band of extended states, which lies above the Fermi energy at high temperature as expected for an insulator, drops as the temperature is lowered. The system behaves as a metal as it passes through the Fermi level, and finally displays the QH effect after the band of extended states sinks below  $E_F$ .

Two samples from wafers with different mobilities have been studied: Si-14, which has a maximum mobility ( $\mu_{max}$ ) of  $1.9 \times 10^4 \text{ cm}^2/\text{Vs}$ , and Si-22, which has  $\mu_{max} = 3.5 \times 10^4 \text{ cm}^2/\text{Vs}$ . The samples are rectangular with a source to drain length of 5 mm, a width of 0.8 mm, and an intercontact distance of 1.25 mm. Resistances were measured using a four-terminal low-frequency (typically 8 Hz) AC technique using cold amplifiers with input resistances  $> 10^{14} \Omega$  installed inside the cryostat. The output of these amplifiers was connected to a

standard lock-in amplifier. Great care was taken to ensure that all data discussed here were obtained where the  $I-V$  characteristics are linear.

The dependencies of  $\rho_{xx}$  and  $\rho_{xy}$  (both are in units of  $h/e^2$ ) on magnetic field for three different temperatures are shown in Fig. 1 (a). At the highest temperature,  $\rho_{xx}(B)$  is flat up to  $B = 4$  T and lies well above  $h/e^2$ . As the temperature decreases, minima near integer filling factors  $\nu = 1$  and 2 and maxima at intermediate filling factors  $\nu = 1.5$  and 2.7 appear. The Hall resistance is almost  $T$ -independent; at low temperature, narrow QH plateaux start to develop near  $\nu = 1$  and 2 [17]. Note that as the temperature is decreased from 1.82 K to 942 mK,  $\rho_{xx}$  at  $\nu = 1$  decreases while remaining larger than  $\rho_{xy} = h/e^2$ ; this corresponds to  $d\rho_{xx}/dT < 0$  characteristic of a metallic state and reflects delocalization with decreasing temperature, whereas  $\rho_{xx}$  increases at  $B = 0$ , indicating an insulating groundstate. At still lower temperature,  $\rho_{xx}$  at  $\nu = 1$  sinks below  $\rho_{xy} = h/e^2$  penetrating into the QH region.

Before proceeding further, we must demonstrate that the observed metallic-like decrease in  $\rho_{xx}$  near  $\nu = 1$  is a fundamental effect of the whole 2DES and not an artifact of special current paths such as, e.g., edge currents [18]. Furthermore, in principle the current distribution in a 2DES at low temperatures can be inhomogeneous. If this is the case, it is difficult to draw conclusions about the behavior of  $\rho_{xx}$  using  $\rho_{xx}$  data. To check these points and to obtain information about  $\rho_{xx}$  directly, we have measured the impedance between the 2D channel and the metallic gate using an RC bridge. The real part of the bridge balance signal is proportional to inverse  $\rho_{xx}$  averaged over the sample area. The magnetic field dependence of the signal proportional to  $\rho_{xx}^{-1}$  is shown in Fig. 1 (b). One can see that it is qualitatively similar to  $\rho_{xx}(B)$  as expected for the case of  $\rho_{xx} > \rho_{xy}$ . For "normal", high- $n_s$  QH effect, where  $\rho_{xx} < \rho_{xy}$ , the dependence is qualitatively different: at integer filling factors  $\nu = 1$  and 2,  $\rho_{xx}^{-1}$  has extreme maxima instead of minima, see Fig. 1 (b) inset]. Again, as the temperature is lowered,  $\rho_{xx}$  increases at  $\nu = 1$ , showing metallic behavior, and decreases at  $B = 0$ , showing insulating behavior. The similarity of the independently determined  $\rho_{xx}(B)$  and  $\rho_{xx}^{-1}(B)$  shows that the current distribution can be considered homogeneous and that we can therefore calculate  $\rho_{xx}$  and  $\rho_{xy}$  from the data for  $\rho_{xx}$  and  $\rho_{xy}$ .

Figure 2 shows the temperature dependence of  $\sigma_{xx}$  at  $\nu = 1$  for four different electron densities. For the lowest  $n_s$ ,  $\sigma_{xx}(T)$  always lies above  $h/e^2$  and monotonically increases as the temperature is decreased showing an activated temperature behavior (see inset). On the other hand, for the highest electron density,  $\sigma_{xx}$  always lies below  $h/e^2$  and monotonically decreases as the temperature is decreased below  $T \approx 3$  K showing QH type of behavior. But for the two middle  $n_s$ ,  $\sigma_{xx}(T)$  are nonmonotonic, increasing exponentially at high temperatures (see inset) and decreasing at lower ones. This nonmonotonic behavior implies, as shown below, temperature induced transitions from insulator-like to metallic and QH types of behavior.

The temperature dependencies of  $\sigma_{xx}$  and  $\sigma_{xy}$ , computed from the data for  $\sigma_{xx}$  and  $\sigma_{xy}$ , are shown in Fig. 3. Figure 3 (a) shows temperature behavior of  $\sigma_{xx}$  and  $\sigma_{xy}$  for the case of "ordinary", "high- $n_s$ " QH effect. Diagonal conductivity, which is always less than  $e^2=2h$ , monotonically decreases, and  $\sigma_{xy}$ , which is always higher than  $e^2=2h$ , monotonically increases as the temperature is decreased. Neither metallic nor insulator-like behavior is observed at  $n_s > 1.3 \times 10^{11} \text{ cm}^{-2}$  for any temperature. However, at slightly lower electron density [Fig. 3 (b)], both components of conductivity are no longer monotonic functions of  $T$ :

(i) at  $T > 2.5$  K (to the left of the first vertical dotted line),  $\sigma_{xy} < \sigma_{xx} < e^2=h$  and both diminish with diminishing  $T$  which is characteristic for an insulating state. Furthermore, according to Khlentzskii [7],  $\sigma_{xy}$  in units of  $e^2=h$  is a "counter" of the number of bands of extended states below  $E_F$ , and because  $\sigma_{xy} < e^2=h$  at  $T > 2.5$  K, there are no extended states below  $E_F$  which confirms an insulating state in this temperature region.

(ii) at  $1 < T < 2.5$  K (between the two vertical dotted lines), both  $\sigma_{xx}$  and  $\sigma_{xy}$  increase with decreasing  $T$ , indicating "metallic" behavior. Both also reach  $e^2=2h$ , the value expected for an extended state ( $\sigma_{xx}^0 = \sigma_{xy}^0 = e^2=2h$  at  $\nu = 1=2$  and  $T = 0$  [19]).

(iii) below  $T \approx 1$  K (to the right of the second dotted line),  $\sigma_{xx}$  again tends to zero as  $T \rightarrow 0$  while  $\sigma_{xy}$  approaches  $e^2=h$ . The value of  $\sigma_{xy}$  now corresponds to one band of extended states below  $E_F$ ; this is a QH state.

At even lower  $n_s$  [Fig. 3 (c)], both  $\sigma_{xx}(T)$  and  $\sigma_{xy}(T)$  change their slope from "insulator-like" to the "metallic" at  $T \approx 1$  K but  $\sigma_{xy}$  always remains  $< e^2=2h$  and the QH conditions are never obtained for this  $n_s$ . Finally, for the lowest  $n_s$  [Fig. 3 (d)], both  $\sigma(T)$  decrease monotonically down to the lowest temperatures while  $\sigma_{xy} < \sigma_{xx} < e^2=h$ ; for this  $n_s$ , the system always remains insulating. In summary, for  $n_s > 1.3 \cdot 10^{11} \text{ cm}^{-2}$  we have observed that the system remains in the QH state regardless of temperature. For  $n_s = 9.5 \cdot 10^{10} \text{ cm}^{-2}$ , we have observed three different types of behavior at  $\nu = 1$ : insulator-like at higher temperatures, metallic at intermediate, and QH at  $T \rightarrow 0$ . For lower  $n_s = 8.6 \cdot 10^{10} \text{ cm}^{-2}$ , we have observed a transition from insulating to metallic types of behavior without a further transition to QH behavior. For even lower  $n_s = 8.1 \cdot 10^{10} \text{ cm}^{-2}$ , the system remains insulating.

We can understand this effect phenomenologically by examining the position of the energy of the lowest extended state at  $T = 0$ . According to Refs. [7,8], this is

$$E_c = \frac{1}{2} \hbar \omega_c \left( 1 + \left( \frac{\tau}{\tau_c} \right)^2 \right)^{1/2}; \quad (1)$$

where  $\omega_c$  is the cyclotron frequency and  $\tau$  is the relaxation time. Therefore, at constant  $B$  ( $\omega_c = \text{const}$ ),  $E_c$  increases with decreasing  $\tau$ , i.e., with increasing disorder. Our data show that at  $\nu = 1$ , the effect of temperature is qualitatively similar to the effect of disorder: with decreasing temperature, the energy of the lowest band of extended states decreases. At high  $T$ , there are no extended states below the Fermi energy, and conductivity is due to temperature activation to the nearest extended state. At lower temperatures, the band of extended states crosses the Fermi level, and we observe a metallic state with characteristic metallic temperature dependencies for both diagonal and Hall conductivities. At still lower temperatures, the band of extended states sinks below the Fermi energy,  $\sigma_{xy}$  approaches  $e^2=h$ , and the system enters the QH regime.

Summarizing, we have studied the temperature dependent behavior of the very dilute 2D electron system in silicon at fixed filling factor  $\nu = 1$ . We have obtained experimental evidence that at  $\nu = 1$ , the energy of the lowest band of extended states decreases relative

to the Fermi energy as the temperature is decreased. As a result, this band passes through the Fermi energy, causing transitions from insulator-like to metal-like and metal to QH-like temperature dependencies of transport coefficients. The first of these transitions reflects delocalization with decreasing temperature; this is in sharp contrast to "normal" situation in which lowering the temperature makes a 2DES more localized.

We acknowledge useful discussions with E. I. Rashba, L. Zhang, B. A. Mason, X. C. Xie, and D. Shahar. This work was supported by grants from the National Science Foundation, DMR 89-22222 and Oklahoma EPSCoR via the LEPM, and the SERC (UK).

## REFERENCES

- [1] M .D 'Torio, V .M .Pudalov, and S .G .Sem enchinsky, Phys. Lett. A 150, 422 (1990).
- [2] H .W .Jiang, C .E .Johnson, K .L .W ang, and S .T .H annahs, Phys. Rev. Lett. 71, 1439 (1993).
- [3] T .W ang, K .P .C lark, G .F .Spencer, A .M .M ack, and W .P .K irk, Phys. Rev. Lett. 72, 709 (1994).
- [4] S .V .K ravchenko, J .A .A .J .Perenboom , and V .M .Pudalov, Phys. Rev. B 44, 13513 (1991).
- [5] M .D 'Torio, V .M .Pudalov, and S .G .Sem enchinsky, Phys. Rev. B 46, 15992 (1992).
- [6] V .M .Pudalov, M .D 'Torio, and J .W .C ampbell, P is'm a Zh. Eksp. Teor. F iz. 57, 592 (1993) [JETP Lett. 57, 608 (1993)].
- [7] D .E .K hm elitskii, Phys. Lett. 106A , 182 (1984); Helvetica Physica Acta 65, 164 (1992).
- [8] R .B .Laughlin, Phys. Rev. Lett. 52, 2304 (1984).
- [9] S .K ivelson, D .H .Lee, and S .C .Zhang, Phys. Rev. B 46, 2223 (1992).
- [10] Experiments which are consistent with this behavior were reported recently in Ref. [11].
- [11] A .A .Shashkin, G .V .K ravchenko, and V .T .D olgoplov, P is'm a Zh. Eksp. Teor. F iz. 58, 215 (1993) [JETP Lett. 58, 220 (1993)].
- [12] H .W .Jiang, H .L .Storm er, D .C .T sui, L .N .P fei er, and K .W .W est, Phys. Rev. B 44, 8107 (1991).
- [13] H .W .Jiang, R .L .W illett, H .L .Storm er, D .C .T sui, L .N .P fei er, and K .W .W est, Phys. Rev. Lett. 65, 633 (1990).
- [14] V .J .G oldm an, M .Santos, M .Shayegan, and J .E .C unningham , Phys. Rev. Lett. 65,



2189 (1990).

[15] M . B . Santos, J. Jo, Y . W . Suen, L . W . Engel, and M . Shayegan, Phys. Rev. B 46, 13639 (1992)

[16] H . C . M anoharan and M . Shayegan, Bull. Am er. Phys. Soc. 39, 486 (1994).

[17] Hall resistivity in the presence of the reentrant insulating phase in 2D system in silicon has been studied extensively in Refs. [4,6] so we will not repeat the details here.

[18] P . L . M cEuen, A . Szafer, C . A . Richter, B . W . Alphenaar, J . K . Jain, A . D . Stone, R . G . Wheeler, and R . N . Sacks, Phys. Rev. Lett. 64, 2062 (1990).

[19] T . Ando, A . B . Fowler, and F . Stern, Rev. Mod. Phys. 54, 437 (1982).

## FIGURES

FIG .1. (a) Diagonal and Hall resistivity of sample Si-14 in units of  $h/e^2$  vs magnetic field at three temperatures and  $n_s = 9.1 \cdot 10^{10} \text{ cm}^{-2}$ . The inset schematically shows the expected behavior of extended states in a magnetic field [7,8]; (b) Inverse  $\rho_{xx}$  of sample Si-22 obtained by impedance measurements vs magnetic field at two temperatures and  $n_s = 7.8 \cdot 10^{10} \text{ cm}^{-2}$ . The inset shows a "conventional"  $\rho_{xx}(B)$  for higher electron density,  $n_s = 1.56 \cdot 10^{11} \text{ cm}^{-2}$ .

FIG .2. Temperature dependence of diagonal resistivity of Si-14 at  $\omega = 1$  for four electron densities. Inset shows activated temperature dependence of  $\rho_{xx}$  at higher temperatures for the same sample.

FIG .3. Temperature dependence of diagonal and Hall conductivities for sample Si-14 at  $\omega = 1$  for four different  $n_s$ . Open symbols correspond to  $\sigma_{xy}$ , closed - to  $\sigma_{xx}$ . Vertical dotted lines approximately separate different kinds of temperature behavior.