

Knight Shift Anomalies in Heavy Electron Materials

E. Kim¹, M. Makivic^{1,2} and D. L. Cox¹

¹Department of Physics, Ohio State University, Columbus, OH 43210

²Northeast Parallel Architectures Center, Syracuse, NY 13244

(December 31, 2021)

We calculate non-linear Knight Shift K vs. susceptibility anomalies for Ce ions possessing local moments in metals. The ions are modeled with the Anderson Hamiltonian and studied within the non-crossing approximation (NCA). The K vs. non-linearity diminishes with decreasing Kondo temperature T_0 and nuclear spin-local moment separation. Treating the Ce ions as an incoherent array in CeSn_3 , we find excellent agreement with the observed $\text{Sn } K(T)$ data.

PACS Nos. 74.70.Vy, 74.65.+n, 74.70.Tx

The origin of Knight shift anomalies in metals with localized moments that undergo the Kondo effect has been a subject of great interest in the condensed matter community over a period of nearly twenty five years [11]. The central physical concept is that the many body screening cloud surrounding a Kondo impurity site should give rise to an anomalous temperature dependent Knight shift at nuclear sites due to the coupling of the local moment to the nuclear spin through the screening cloud [1,3{5,9,10]. This would be manifest in a deviation from a linear relation of the Knight shift K to the magnetic susceptibility below the Kondo temperature T_0 . Another way to say this is that in the absence of an anomaly, the contribution $K(\mathbf{r};T)$ from a local moment at distance \mathbf{r} from the nucleus can be written as $f(\mathbf{r})(T)$. This factorization does not hold if there is an anomaly (instead $K(\mathbf{r};T) = f(\mathbf{r};T)(T)$ due to the temperature dependent polarization cloud). The classic experiments by Boyce and Slichter [2] on the low Kondo temperature ($T_0 \sim 10\text{K}$) alloy FeCu displayed no evidence for this anomalous Knight shift behavior. In contrast, pronounced Knight shift anomalies have been observed in the concentrated heavy electron materials CeSn_3 [6,8] and YbCuAl [7,8], which have been described as Kondo lattice systems with $T_0 \sim 400\text{K}$. In view of the Boyce-Slichter result, the question is raised whether these anomalies represent a coherent effect of the periodic lattice rather than a single ion effect. However, recent experiments on the proposed quadrupolar Kondo alloy [12,13] $\text{Y}_{1-x}\text{U}_x\text{Pd}_3$ demonstrate that for concentrations of 0.1-0.2 there are pronounced non-linearities in the Y Knight shift for sufficiently large distances away from the U ion [11].

In this paper, we present some results from our systematic theoretical studies of the Knight shift in heavy electron materials. We find, as expected from earlier analytic theories, that the magnitude of the Knight shift anomaly is reduced with decreasing Kondo temperature and decreasing distance between local moment and im-

urity sites. Ours is the first study to display this effect in a realistic model calculation. We find that the Knight shift anomaly of CeSn_3 can be accounted for by incoherent, single ion physics. In particular, by carrying out a full lattice sum on CeSn_3 , we obtain an excellent one parameter fit of the calculated Knight shift to the experimental one, with a small low temperature deviation possibly due to the oversimplifications of our model. We conjecture that coherence effects may explain some of the small numerical disagreement.

The application of NMR in Kondo systems received impetus from Heeger [1] who suggested that the anomalous cloud was detectable in Knight shift measurements. Essentially, the oscillatory conduction spin density $s(\mathbf{r})$ induces a local moment-nuclear moment interaction. In the limit $T_0 \rightarrow 0$, this interaction $I(\mathbf{r})$ is well described by the second order perturbation theory Ruderman-Kittel-Kasuya-Yosida expression $(s(\mathbf{r}) \cdot \mathbf{I}(\mathbf{r}) \cos(2k_F r) = r^3)$. Ishii [4,5] conjectured that for an $S_I = 1/2$ pure-spin Kondo impurity (with no charge fluctuations) an anomalous conduction spin density cloud sets in beyond the Kondo screening length $\xi_K = \hbar v_F / k_B T_0$, where v_F is the Fermi velocity. Inside this radius, conventional temperature independent RKKY oscillations dominate of the kind observed by Boyce and Slichter. Outside the screening length, at $T = 0$, the anomalous term will dominate also with an RKKY form but an amplitude of order D , the conduction bandwidth, compared with $D(N(0)J)^2$ for the Ruderman-Kittel term, where $N(0)$ is the conduction electron density of states at the Fermi energy and J the conduction electron-local moment exchange coupling. Ishii did not calculate the explicit temperature dependence of this structure, but did anticipate that it would vanish above the Kondo scale. Scaling analysis conjectured the asymptotic factorization of the Knight shift for short distance and low temperature [9]. A possible understanding of the Boyce and Slichter results, then, is the Cu nuclei they sampled were at distances $r \ll \xi_K$.

from the Fe ions.

In an Anderson model treatment of the problem, charge fluctuations are allowed. Consider, for example, a Ce ion with nominally one f electron giving rise to the local moment. The ensuing Kondo effect is best understood in terms of a mixing of the empty conduction with one in which the Ce moment is screened by a superposition of conduction hole states. This opens up new possibilities for detecting the anomalous screening cloud. One interpretation of the Boyce-Slichter results is that due to subtleties of spin conservation in the singlet ground state the spin cloud is unobservable, while the anomalous charge cloud is observable through electronic field gradient measurements at atomic nuclei [3].

We shall focus on the second possibility, that the anomalous spin cloud now has a finite amplitude within $r < r_K$ which is proportional to the weight of f^0 in the ground state. This anomaly scales approximately linearly with T_0 , so the cloud will be virtually undetectable in small T_0 systems, but may be observable in high T_0 systems. Our results support this picture as we shall explain in more detail.

Our starting point is an Anderson model Hamiltonian. We shall first discuss the situation for Ce^{3+} and Yb^{3+} ions, and write down the model only for the Ce case. For a single Ce site at the origin, the model is

$$H = H_c + H_f + H_{cf} + H_z \quad (1)$$

with

$$H_c = \sum_k \epsilon_k C_k^\dagger C_k \quad (2)$$

the conduction band term for electrons with a broad featureless density of states of width D , taken to be Lorentzian here for convenience; with

$$H_f = \sum_{jm} \epsilon_{fjm} f_{jm}^\dagger f_{jm} \quad (3)$$

where $j = 5/2; 7/2$ indexes the angular momentum multiplets of the Ce ion having azimuthal quantum numbers m , with $\epsilon_{f5/2} = 2\text{eV}$, $\epsilon_{f7/2} = \epsilon_{f5/2} + \epsilon_{so} = 1.7\text{eV}$ (we take the f^0 configuration at zero energy); with

$$H_{cf} = \sum_{kjm} V_{kjm} C_k^\dagger f_{jm}^0 + \text{h.c.} \quad (4)$$

where $V_{kjm} = V Y_{3m}(\hat{k}) < 3m < j < 7/2 > = \frac{1}{N_s} \overline{N_s}$, V being the one particle hybridization strength and N_s the number of sites; with

$$H_z = \sum_k B_k H_z \sum_{jm} n_{kjm} + \sum_{jm} g_{jm} f_{jm}^\dagger f_{jm} \quad (5)$$

being the Zeeman energy of the electronic system for a magnetic field H_z applied along the z -axis. In addition to this, we must add a term coupling the nuclear spin system to the conduction electrons, which we take to be of a simple contact form $\text{vec} I(\mathbf{r}) \cdot S(\mathbf{r})$ for each nuclear spin $I(\mathbf{r})$ at position \mathbf{r} with $S(\mathbf{r})$ the conduction spin density at the nuclear site, and a nuclear Zeeman term. In terms of the parameters, the Kondo scale characterizing the low energy physics is given by

$$k_B T_0 = D \left(\frac{D}{\epsilon_{so}} \right)^{4/3} \left(\frac{1}{\sum_{f5/2} S(f5/2)} \right)^{1/6} \exp \left(-\frac{\epsilon_{f5/2}}{6} \right) \quad (6)$$

where the hybridization width $D = N(0)V^2$.

We treat the Anderson Hamiltonian with the non-crossing approximation (NCA), a self-consistent diagrammatic perturbation theory discussed at length in the paper of Bickers et al. [14]. This approximation is controlled by the large orbital degeneracy of the Ce ground state. It does show pathological behavior (due to the truncation of the diagrammatic expansion) for a temperature scale $T_p \ll T_0$ in this conventional Anderson model, provided the f^1 occupancy $n_{f^1} \approx 0.7$. In practice, this is not a problem for $N = 4$ as shown in Ref. [14], in that comparison of NCA results with exact thermodynamics from the Bethe-Ansatz shows agreement at the few percent level above T_p . Hence, this is a reliable method for our purposes.

The approach in the NCA is to write a propagator for each ionic state of the Ce site (i.e., $f^1 j = 5/2; 7/2$ and f^0 in the present model), solve self-consistent integral equations to second order in the hybridization for the ionic propagator self-energies, and then to calculate physical properties as convolutions of these propagators. To evaluate the Knight shift we employ the lowest order diagram coupling nuclear spin to Ce magnetic moment, as shown in Fig. 1. The full expression corresponding to this diagram is cumbersome and shall be presented in detail elsewhere. To the extent that the dynamics of the empty orbital can be neglected, this expression factorizes into a nearly temperature independent RKKY interaction (modified due to the spin-orbit coupling and anisotropic hybridization from the original form) times the f -electron susceptibility. Thus, no anomaly results from the diagram in this limit. In this limit, the susceptibility in the diagram corresponds to the leading order estimate used in Ref. [14] to compare with exact Bethe-Ansatz results.

However, for $T = 0$, the empty orbital propagator may be written in an approximate two-pole form, one with amplitude $1/Z$, $Z = k_B T_0/6$, centered near zero energy, and one with amplitude Z centered at $\epsilon_{f5/2} = k_B T_0$ which reflects the anomalous ground state mixing due to the Kondo effect. The first term gives conventional RKKY oscillations modulo the anisotropy and altered range dependence induced by the m, \hat{k} dependence of the

hybridization. The amplitude of the second term goes to zero above the Kondo temperature. It is this term which may be traced to the anticipated anomalous Knight shift, and within such a two-pole approximation may be seen to be finite within r_K , have a stronger distance dependence in that regime, but possess an amplitude of order Z only within this distance regime. Beyond r_K , the amplitude is of order $1/N$ and the shape of the spin oscillations is the same as that found from the high frequency pole of the empty orbital propagator.

The diagram of Fig. 1 has been studied with the NCA previously [10], but only for the spin $1/2$ model with infinite Coulomb repulsion, and for a limited parameter regime (very low T_0 values) and short distances ($r < r_K$). In consequence, no strong evidence was found for a Knight shift anomaly in this previous work.

Our numerical procedure, briefly, consists of solving the NCA integral for the Anderson Hamiltonian specified above on a logarithmic mesh with order 600 points chosen to be centered about the singular structures near the ground state energy E_0 [15]. We then feed the self-consistent propagators for the empty and doubly occupied orbitals into the convolution integrals obtained from the diagram of Fig. 1, which allows for evaluation of the Knight shift at arbitrary angle and distance from the nuclear site. It is convenient to take the nuclear site as the origin in this case leading to phase factors $e^{i\mathbf{k}\cdot\mathbf{R}}$ in the hybridization Hamiltonian H_{cf} , where \mathbf{r} is the nuclear-Ce site separation. These factors give the oscillations and position space angular dependence in χ . All contributions from the Ce susceptibility are included.

To demonstrate the dependence of the χ vs: anomaly as a function of Kondo scale T_0 , we have evaluated the diagram of Fig. 1 for a single local moment placed at a fixed distance $r = 3.3k_F^{-1} = 3.3A$ for our choice of $k_F = 1A^{-1}$ and angle of 0° with respect to the quantization axis. We have tuned the Kondo scale by holding fixed all parameters except the hybridization. The Knight shift is scaled to a susceptibility by matching at high temperatures, and the susceptibility units are scaled by a factor of one calculation to the data for $CeSn_3$ assuming $D = 3eV$. The results are shown in Fig. 2(a). Clearly, as the Kondo scale is reduced, the magnitude of the deviation between a linear χ vs: relation is systematically reduced. Also, as the separation r is decreased (c.f., Fig. 2(b)) the magnitude of the χ vs: non-linearity diminishes. Very similar results are obtained for Yb compounds (the Yb^{3+} ion has a lone 4f hole and our procedure describes these with a simple particle hole transformation, which we shall discuss in detail in a subsequent publication).

To assess the relevance of this single site physics to the periodic compound $CeSn_3$ we have performed a lattice sum about a given Sn nucleus from all surrounding Ce ions. We assume the Knight shift contribution of each ion

to be described by this single site physics, known to be a good approximation at high temperatures where the ions are incoherent with one another, and known to provide a very accurate description of the thermodynamics in many cases. We carried out the sum to several hundred shells about the Sn site, obtaining good convergence at all calculated temperatures. We fixed the parameters by fitting the susceptibility data of $CeSn_3$. The result is shown in Fig. 3, where we have scaled the Knight shift by an intermediate range temperature match to the susceptibility (note that the NMR data of Ref. [6] extends only to room temperature). There are several notable features here: (i) the calculated amplitude of our Knight shift prior to scaling is actually negative, which implies that the shift is sensible only if the assumed contact coupling between conduction and nuclear spins is negative, which actually makes sense because the Sn nucleus should dominantly couple through core polarization; (ii) the magnitude of the anomaly goes in the right direction and begins at the right temperature to agree with the experimental anomaly [6], though the quantitative value is slightly too high (given the highly oversimplified conduction band we are employing, we don't regard this as a serious defect in the calculation; (iii) the magnitude of the anomalous contribution from the Ce sites does go down with distance from the Sn nucleus (the theoretical data which most closely match those of experiment are taken at the fixed distance $r = 3k_F^{-1} = 3A$ and angle of 0°). However, the anomaly is then still surprisingly large even at this short distance. While we cannot rule out that the discrepancy reflects our oversimplified band structure, we conjecture that lattice coherence effects may drive our calculated lattice sum in this direction, because the repeated scattering of conduction electrons off of the Ce ions (now in every unit cell) has the effect of reducing the screening length [15]. We intend to study this idea further within a local approximation ($d=1$ expansion) to the lattice model. We note that the high temperature deviation of Knight shift and susceptibility may be realistic and is related to the different couplings to ground and excited spin orbit multiplets.

In summary, we have computed Knight shift anomalies within a realistic model for Ce ions in metals for the first time. We find that the magnitude of the non-linearity scales down in size as the Kondo scale is diminished or the nuclear moment-local moment separation is reduced. Modeling the Ce ions incoherently in $CeSn_3$, we find that summing over all lattice sites the resulting Sn Knight shift agrees quite well with experiment. The remaining quantitative discrepancies may be due to a combination of our oversimplified band structure for the conduction states together with lattice coherence effects.

This research was supported by a grant from the U.S. Department of Energy, Office of Basic Energy Sciences, Division of Materials Research. We acknowledge many

useful conversations over the years with D. E. M. acLaughlin and H. Lukefahr.

-
- [1] A. J. Heeger, in *Sol. St. Physics*, Vol. 23, ed. F. Seitz, D. Turnbull, and H. Ehrenreich (Academic Press, New York, 1969), p. 283.
 - [2] J. B. Boyce and C. P. Slichter, *Phys. Rev. Lett.* 32, 62 (1974).
 - [3] G. G. Giner and A. Zawadowski, *Rep. Prog. Phys.* 37, 1497 (1974), and in *Prog. in Low Temp. Physics V IIB*, ed. D. F. Brewer (North-Holland, Amsterdam, 1978), p. 591.
 - [4] H. Ishii, *Progr. Theor. Phys.* 55, 1373 (1976).
 - [5] H. Ishii, *J. Low Temp. Phys.* 32, 457 (1978).
 - [6] S. K. Malik, et al., *Phys. Stat. Sol. (b)* 68, 399 (1975).
 - [7] D. E. M. acLaughlin, F. R. de Boer, J. Bijvoet, P. E. de Châtel and W. C. M. Matens, *J. Appl. Phys.* 50, 2094 (1979).
 - [8] D. E. M. acLaughlin, *J. Mag. Mag. Materials* 47 & 48, 121 (1985).
 - [9] K. Chen, C. Jayaprakash, and H. R. Krishna-Murthy, *Phys. Rev. Lett.* 58, 2833 (1987).
 - [10] W. Pollwein, T. Hohn, and J. Keller, *Z. Phys. B* 73, 219 (1988).
 - [11] H. Lukefahr, et al., *Physica B* 199-200, 413 (1994).
 - [12] D. L. Cox, *Phys. Rev. Lett.* 59, 1240 (1987).
 - [13] C. L. Seaman, et al., *Phys. Rev. Lett.* 67, 2882 (1991).
 - [14] N. E. Bickers, D. L. Cox and J. W. Wilkins, *Phys. Rev B* 36, 2036 (1987).
 - [15] A. J. Millis and P. A. Lee, *Phys. Rev. B* 35, 3394 (1987).
 - [16] H. Mook, et al., *Physica B* 186-188, 341 (1993).
 - [17] D. L. Cox and A. Ruckenstein, *Phys. Rev. Lett.* 71, 1613 (1993).
 - [18] D. L. Cox and A. Zawadowski, to be published (1994).
 - [19] J. Han et al., to be published (1994).

Figure 1. Feynman diagram of coupling between Ce local moment and nuclear spin in the infinite U Anderson model. The dashed line represents the singly occupied (f^1) state and wavy line the empty orbital (f^0) state. The solid line represents the conduction electron. The dot-dashed line is a propagator for the nuclear spin states and H' is the external magnetic field.

Figure 2 (a) Calculated Knight shift $K(T)$ vs. susceptibility $\chi(T)$ for a single Ce site at $k_F r = 3.33$ from a nuclear moment and angle $\theta = 0$. Fixing the f -level energy $\epsilon_{5/2} = -2\text{eV}$, and the spin orbit splitting $\epsilon_{so} = 0.3\text{eV}$, the hybridization is varied to illustrate the dependence of the nonlinearity on the magnitude of T_0 . The diagram of Fig. 1 is used to calculate $K(T)$. The magnitude of the non-linearity diminishes as T_0 is reduced. The theoretical Knight shift has been shifted by a common offset and scale factor to match the susceptibility. (b) Calculated Knight shift $K(T)$ for a single Ce site vs. susceptibility $\chi(T)$ for varying separation with the Kondo scale used to

the CeSn_3 (T) (see Fig. 3). For each plot the angle is held at θ with respect to the nuclear moment-Ce axis. The magnitude of the non-linearity diminishes as $k_F r$ is reduced. The theoretical Knight shifts have been shifted by offset and scale factors to match the susceptibilities; this does not affect the relative size of the anomaly.

Figure 3 Temperature dependence of Sn Knight Shift $K(T)$ and Ce (T) (both calculated and experimental results [6]) for CeSn_3 . The theoretical $K(T)$ is calculated using the diagram of Fig. 1 and with T_0 chosen to fit the experimental (T) data. A full (incoherent) lattice sum is carried out over several hundred shells of atoms.