

# Superconducting Coherence in a Vortex Line Liquid; Simulations with Finite

Tao Chen and S. Teitel

Department of Physics and Astronomy, University of Rochester, Rochester, New York 14627

(December 31, 2021)

## Abstract

We carry out simulations of a lattice London superconductor in a magnetic field  $B$ , with a finite magnetic penetration length  $\lambda$ . We find that superconducting coherence parallel to  $B$  persists into the vortex line liquid. We argue that the length scale relevant to this effect is  $\xi = \frac{2}{\sqrt{3}} \lambda = 8 T_m$ .  
74.60.Ge, 64.60.-i, 74.40.+k

In high  $T_c$  superconductors, thermal fluctuations are believed to melt the ground state vortex line lattice at temperatures well below the mean field  $H_{c2}$  line [1,2]. The resulting vortex line liquid has received intense theoretical and experimental study. In particular, recent "flux transformer" experiments [3,4] on YBCO show that superconducting coherence parallel to the applied magnetic field  $B$  exists over very long length scales well into the vortex liquid.

To investigate the fluctuating vortex line system, numerical simulations have been carried out. These have either involved a simplified model of vortex line interactions [5], or have used the approximation [6-8] that the bare magnetic penetration length  $\lambda \gg \xi$ , so that the magnetic field  $B$  inside the superconductor is uniform. Such  $\lambda \gg \xi$  simulations [8] show a sharp transition within the vortex line liquid, corresponding to the onset of coherence parallel to  $B$ . While this  $\lambda \gg \xi$  model is suggested by the large values of  $\lambda/\xi = \lambda_0$  in the high  $T_c$  materials, it may fail close to  $T_c$ , where the correlation length may exceed the finite bare  $\xi$ ; thus the finite model may display different critical behavior from the  $\lambda \gg \xi$  limit. To investigate this possibility, we present here new simulations of a system of fluctuating vortex lines, in which we include the effect of magnetic screening on the vortex interactions [9], due to a finite  $\lambda$ . We investigate the presence of superconducting coherence within the vortex line liquid, and discuss the length scale relevant for this effect.

Our model is a discretized lattice superconductor in the London limit [10]. For simplicity, we consider isotropic couplings. Following Cameiro et al. [7], a duality transformation maps this model onto one of interacting vortex lines, with Hamiltonian

$$H = 2^{-2} J_0^{-2} \sum_{i,j} n(r_i) n(r_j) G(r_i - r_j); \quad (1)$$

Here  $n(r_i)$  ( $i = x, y, z$ ) is the integer vorticity through plaquette at site  $r_i$  of a cubic mesh of points, and  $G(r)$  is the lattice London interaction, with Fourier transform

$$G_q = 1/(1 + Q^2); \quad Q^2 = \sum_{i=x,y,z} [2 - 2 \cos q_i]; \quad (2)$$

The coupling is  $J_0 = \frac{2}{\phi_0^2} = (16\pi^3)^{-2}$ , with  $\phi_0$  the flux quantum, and  $a_0$  the spacing of the discrete mesh, which we identify with the bare coherence length that determines the size of

a vortex core. Henceforth we measure lengths in units of  $\xi_0$ , and temperature in units of  $J_0$ . Periodic boundary conditions in all directions are taken.

To test for superconducting coherence, we consider the helicity modulus  $\chi(q)$  (where  $\chi = \epsilon$ ), defined as the linear response coefficient giving the supercurrent  $j$  induced by a transverse perturbation in the vector potential of the externally applied magnetic field,  $A^{\text{ext}}(q)^\wedge$ ,

$$j(q) = \chi(q) A^{\text{ext}}(q): \quad (3)$$

We have earlier derived [11] an expression for  $\chi(q)$  in a continuum London superconductor. The generalization to the lattice superconductor is

$$\chi(q) = \frac{[J_0^2] Q^2}{1 + Q^2} \left( 1 - \frac{4 J_0^2 \ln(q) n(q) i}{V T (1 + Q^2)} \right); \quad (4)$$

where  $x, y, z$  are a cyclic permutation of  $x, y, z$ , and  $Q^2 = 2 - 2 \cos q$  as  $q, q = 0$ .

In the absence of vortices,  $\chi(q) = [J_0^2] Q^2 = (1 + Q^2)$  describes the total screening of the Meissner state. With vortices, an expansion in powers of  $Q^2$ ,

$$\ln(q) n(q) i = n_0 + n_1 Q^2 + n_2 Q^4 + \dots; \quad (5)$$

leads to an expression for  $\chi(q)$  at small  $q$ , in terms of a renormalized coupling  $[J^2]_R$  and penetration length  $\xi_R$ ,

$$\chi(q) = \frac{[J^2]_R}{1 + \xi_R^2 Q^2} \quad (6)$$

with

$$\frac{[J^2]_R}{[J_0^2]} = 1 - \frac{4 J_0^2}{V T} n_0 \quad (7)$$

$$\frac{\xi_R^2}{\xi_0^2} = 1 + \frac{4 J_0^2}{V T} (n_1 - n_0^2): \quad (8)$$

To see the meaning of  $\chi$  and  $\xi_R$ , note that the current  $j(q)$  produced by  $A^{\text{ext}}(q)$ , induces a magnetic vector potential due to Ampere's Law, which in our units

is  $[J_0^{-2} Q^2 A^{\text{ind}}(q) = j(q)]$ . The change in the total magnetic field due to the external perturbation is therefore given by  $A^{\text{tot}}(q) = A^{\text{ind}}(q) + A^{\text{ext}}(q)$ , or

$$A^{\text{tot}}(q) = (1 - \frac{1}{Q^2 + \frac{2}{R}}) A^{\text{ext}}(q): \quad (9)$$

Thus a fraction  $1 - \frac{1}{Q^2 + \frac{2}{R}}$  of  $A^{\text{ext}}(q)$  penetrates into the material; the remaining fraction  $\frac{1}{Q^2 + \frac{2}{R}}$  is screened out, on the length scale  $\lambda_R$ . Equivalently,  $\lambda_R$  is the length on which fluctuations in magnetic field decay to equilibrium. For a perfect Meissner effect,  $\lambda_R = 1$ , and  $\lambda_R$  agrees with the usual definition of the London penetration length [12]. We therefore interpret  $1 - \frac{1}{Q^2 + \frac{2}{R}}$  as the density of superconducting electron pairs in direction  $\hat{q}$ , even in the more general case of a partial Meissner effect in the mixed state. Although  $A^{\text{tot}}(q)$  will have the same form Eq.(6) in both the superconducting and the normal metal state (with ordinary fluctuation diamagnetism), a transition will be signaled some singularity in  $\lambda_R$ . We focus now on  $\lambda_R$ .

Consider a uniform applied  $H = H \hat{z}$ .  $\chi_x(q_y)$  and  $\chi_y(q_z)$  then describe the response to external fields  $H_z(q_y)$  and  $H_x(q_z)$ , which represent compression and tilt perturbations of  $H$ , respectively. Correspondingly one finds [11]

$$\chi_x = dB_z/dH_z \quad \text{and} \quad \chi_y = dB_x/dH_x; \quad (10)$$

where these susceptibilities are evaluated at the applied field  $H$ . Since the high  $T_c$  materials display strong fluctuation diamagnetism even in the normal state, it is unclear whether or not  $\chi_{xy}$  will display a pronounced feature at the superconducting transition.

For behavior along  $\hat{z}$  however, parallel to  $H$ , the criteria for a superconducting transition is more clearly defined.  $\chi_z(q_x)$ , describes the response to an external field  $H_y(q_x)$ , representing a combined shear and tilt perturbation of the uniform applied  $H \hat{z}$ . In Ref. [11] we showed that for the vortex line lattice one has  $\chi_z = 1$  and a perfect Meissner screening. For a normal vortex line liquid however,  $\chi_z = 1 - dB_x/dH_x < 1$ . Thus the transition to the normal state is signaled by a discontinuous jump in  $\chi_z$  from unity. Expressed in terms of the expansion coefficients of Eq.(5), we have superconducting coherence along the field provided  $n_0 = 0$ ; for the normal state,  $n_0 > 0$ .

For our Monte Carlo simulation, we start with a fixed density  $f = B = 0$  of straight vortex lines parallel to  $\hat{z}$ , giving the ground state configuration for an internal field  $B\hat{z}$ . Following Carneiro et al. [7], we update the system, heating from the ground state, by adding elementary closed vortex rings (a square ring of unit area) with random orientation and position. These excitations are accepted or rejected according to the standard Metropolis algorithm. This provides a complete sampling of phase space for the vortex variables  $n(r_i)$ , subject to the constraints that vorticity is locally conserved, and the average internal field,  $B = (B_0 = V)^{-1} \sum_i n(r_i) = f_0 \hat{z}$ , is constant.

Our simulations are for the case  $f = 1/15$ , whose ground state on a cubic mesh is a close approximation to a perfect triangular lattice. We choose  $a_v = 5$ , comparable to the vortex line spacing,  $a_v = 1/\sqrt{f} = 3.87$ . We study system sizes  $L_x = 30$  in the  $xy$  plane, and  $L_z = 15$  and  $30$  parallel to  $H$ . Each data point is typically the result of 5,000 sweeps to equilibrate, followed by 8–16,000 sweeps to compute averages, where each sweep refers to  $L_x^2 L_z$  attempts to add an elementary vortex ring.

In Fig.1 we show a sample of our data, plotting  $\ln_y(q_k) \ln_y(-q_k) i$  vs.  $q_k$ , for various  $T$ , and  $L_z = 30$ . Fitting to Eq.(5) through  $O(Q^4)$  yields the solid curves, and determines the parameters  $n_0$  and  $n_1$ . Eq.(7) then gives the couplings  $\chi_{xy}$ , which we plot vs.  $T$  in Fig.2. We see that  $\chi_{xy}$  decrease towards zero at  $T_m \approx 1.2$ , while  $\chi_z$  decreases at  $T_c \approx 2.0$ . We also show our results for  $L_z = 15$ .

In Fig.3 we show intensity plots of vortex correlations within the same plane perpendicular to  $B$ ,

$$S(q_z) = \sum_{z, r_z} e^{iq_z \cdot r_z} \ln_z(r_z; z) \ln_z(0; z) i; \quad (11)$$

where  $q_z = (q_x, q_y)$ , for various  $T$ , and  $L_z = 30$ . Below  $T_m$  we see sharp Bragg peaks of a vortex line lattice. Above  $T_m$  we see behavior characteristic of a liquid.  $T_m$  is thus the melting transition. Since the discrete mesh of our simulation acts like a periodic pinning potential for vortices,  $T_m$  also coincides with a depinning of the vortex lines. We believe that the drop in  $\chi_{xy}$  at  $T_m$  is more a result of this depinning, rather than a direct result of

melting. We expect from Eq.(10) that  $\chi_{xy} = 1 - dB_x/dH_x$  is finite above  $T_m$ , but this value is too small for us to determine accurately.

With respect to coherence along  $H$ , we expect a discontinuous jump in  $\chi_z$  from unity to  $1 - dB_x/dH_x = 0$  at  $T_c$ . The finite width of the decrease observed in our data is a finite size effect; we see that the transition sharpens as  $L_z$  increases. We therefore estimate  $T_c \approx 2.0$ , well into the vortex line liquid. This is the main result of our simulations.

Recent flux transformer experiments on YBCO [3,4] show that there is a temperature  $T_{th}$  below which vortex line correlations parallel to  $H$  become comparable to the thickness of the sample.  $T_{th}$  is clearly above the  $T_{irr}$  where resistivity transverse to  $H$  vanishes. Resistivity parallel to  $H$  however appears [4] to vanish at  $T_{th}$ . A similar conclusion concerning vortex line correlations may be inferred from the measurements of Ref. [13], where the onset of pinning by twin grain boundaries is shown to occur distinctly above a sharp first order melting transition. If we identify  $T_{th}$  with our  $T_c$ , and  $T_{irr}$  with our  $T_m$ , our results are in complete accord with these experimental findings.

We have also tried to compute the lengths  $\xi_R^2$ , using Eq.(8) and our fitted  $n_0$  and  $n_1$ . However the factor  $(n_1 - n_0^2) = \frac{1}{2} \chi_{xy}$  that appears in Eq.(8) is, in the region of the transition, the quotient of two small numbers each with large relative error. We were therefore unable to obtain meaningful results for  $\xi_R$ .

Although we have simulated with  $L_z = 30$ , one can still question whether our results represent the true thermodynamic limit. In particular, in Refs. [3,4], it was found that  $T_{th}$  decreased towards  $T_{irr}$  as sample thickness  $L_z$  increased. This is also consistent with our results for  $\chi_z$  in Fig 2, where there is some suggestion that, in addition to a sharpening of the transition as  $L_z$  increases,  $T_c$  also decreases. It is therefore important to note that there is another length in the problem [2]

$$(T) \quad \xi_0^2 = (\xi(T) - \xi(T_0))^2 = (2 \xi(T_0) - T) : \quad (12)$$

For our simulation, we have  $30 = L_z \approx \xi(T_m) \approx 410$ .

It has been argued [14] that  $\xi_0$  determines the length on which phase correlations  $C(r)$

the  $\langle C(r) \rangle$  decay in the vortex line lattice; however these same calculations show that in the vortex liquid, the decay length of  $C(r)$  is comparable to the spacing between vortex lines  $a_v = L_z$ . Thus this analysis of  $C(r)$  does not indicate why  $\xi$  should be an important length above  $T_m$ , where we continue to see superconducting coherence.

Another possibility is suggested by Nelson's analogy [1] between vortex lines and the imaginary time world lines of 2D bosons. Nelson argued that there should be a Kosterlitz-Thouless (KT) superfluid transition of the analog bosons. For  $L_z$  sufficiently large, this KT transition would occur at a  $T_c < T_m$ , and so would be pre-empted by the formation of the vortex line lattice. But for  $L_z$  small enough,  $T_c > T_m$ , and one has a new state intermediate between the vortex line lattice and the normal vortex line liquid [15]. We now restate our earlier calculation [11] of this  $T_c$  in order to show that the length which distinguishes between these two possibilities is  $\xi(T_m)$ .

As shown by Pollock and Ceperley [16], the 2D boson superfluid density can be expressed in terms of the "winding number"  $W$  which is the net spatial distance traveled by the ensemble of bosons as they travel down the time axis of their world lines. One has  $\rho_s^{\text{boson}} = m T_{\text{boson}} \hbar W^2 / 2$ . According to the KT theory, the 2D superfluid transition occurs at a universal value of  $\rho_s^{\text{boson}}$ , which translates into the condition  $\hbar W_c^2 / 2 = 4\pi$ . In terms of vortex lines,  $W$  just measures the net vorticity transverse to  $H$  [11]. We thus have [17]

$$\hbar W_y^2 = \lim_{q \rightarrow 0} \frac{1}{L_z^2} \ln_y(q_x) \ln_y(-q_x) \quad (13)$$

This is precisely the same correlation as enters  $\chi_z$ , and comparing with Eq.(7) we can write  $\chi_z = 1 - (T/T_m) \hbar W_y^2$ . Thus  $\rho_s^{\text{boson}} / \hbar W_y^2 = 0$  implies  $\chi_z = 1$ ; the normal boson fluid corresponds to a vortex line liquid with coherence along  $H$ .  $\rho_s^{\text{boson}} > 0$  implies  $\chi_z < 1$ ; the boson superfluid corresponds to the normal vortex line liquid [18].

We have shown [11] that for a normal vortex line liquid,  $\ln_y(q_x) \ln_y(-q_x) = f^2 L_z^2 L_z T = c_{44}(q_x)$ , where  $c_{44}(0) = (B^2/4) dH_x/dB_x$  is the tilt modulus, and  $f = B/B_0$ . Thus we conclude that  $\hbar W_y^2 = \hbar W_x^2 + W_y^2 = 2\hbar W_y^2 = (8 L_z T = \frac{2}{0}) dB_x/dH_x$ . This yields

$$T_c = \frac{\frac{2}{0}}{2 L_z^2} \frac{dH_x}{dB_x}; \quad \text{or} \quad \frac{T_c}{T_m} = \frac{4}{L_z} \frac{(T_m)}{dB_x} \frac{dH_x}{dB_x} \quad (14)$$

For large  $B \ll H_{c1}$ ,  $dH_x = dB_x \ll 1$ . Thus for  $L_z < (4\pi) (T_m)$ , one has  $T_c > T_m$  and hence a vortex line liquid with superconducting coherence along  $H$ , intermediate between the vortex line lattice, and the normal vortex line liquid. Only for  $L_z > (4\pi) (T_m)$  will this intermediate state disappear [19]. For YBCO, with  $T_m \approx 90$  K, one has  $(T_m) \approx 1400$  m, much thicker than the samples ( $\approx 50$  m) in Refs. [3,4,13].

We note that for  $B \ll H_{c1}$ ,  $(T_m)$  is a factor  $B/H_{c1}$  larger than the "entanglement" length originally proposed by Nelson [1] as the criterion for the 2D boson superfluid transition. This is because the notion of superfluidity, as measured by  $W$ , does not precisely correspond to the geometric notion of line entanglement. If just as many lines wander to the right as wander to the left, one has  $W = 0$ , although the lines may still be quite twisted and geometrically entangled.

Finally, we note that for our model, Eqs.(12,14) would predict  $T_c = (8 J_0 / L_z) T_m \approx 25$ , much higher than the observed  $T_c \approx 20$ . We believe that this results from a breakdown of the boson analogy near our observed  $T_c$ , due to the proliferation of thermally excited closed vortex rings, and intersections between vortex lines, such as cause the transition in a  $B = 0$  model. This is clearly the case for the  $\phi = 1$  model [8], where  $\phi = 1$  at fixed  $J_0$ , also means  $\phi = 1$ . Eq.(14) would then imply  $T_c \approx 1$ . The finite  $T_c$  found in  $\phi = 1$  simulations [8] therefore indicates such a breakdown of the boson analogy. Our present results concerning vortex ring distributions and line intersections are similar to what was found for  $\phi = 1$  [8].

To conclude, we find from simulations with  $L_z \approx (T_m)$  (as is the case for recent experiments) that superconducting coherence parallel to  $H$  persists into the vortex line liquid state. We argue that this effect should vanish once  $(T_m) \approx L_z$ .

We would like to thank A.P. Young for very helpful discussions. This work has been supported by DOE grant DE-FG 02-89ER 14017.

## REFERENCES

- [1] D . R . Nelson, Phys. Rev. Lett. 60, 1973 (1988); J. Stat. Phys. 57, 511 (1989); D . R . Nelson and H . S . Seung, Phys. Rev. B 39, 9153 (1989).
- [2] D . S . Fisher, M . P . A . Fisher, and D . A . Huse, Phys. Rev. B 43, 130 (1991).
- [3] H . Safar, P . L . Gammel, D . A . Huse, S . N . Majumdar, L . F . Schneemeyer, D . J . Bishop, D . Lopez, G . N ieva, and F . de la Cruz, Phys. Rev. Lett. 72, 1272 (1994).
- [4] F . de la Cruz, D . Lopez, and G . N ieva, Phil. Mag. A., to be published.
- [5] S . Ryu, S . Doniach, G . Deutscher and A . Kapitulnik, Phys. Rev. Lett. 68, 710 (1992).
- [6] Y . H . Li and S . Teitel, Phys. Rev. Lett. 66, 3301 (1991); R . E . Hetzel, A . Sudb , and D . A . Huse, Phys. Rev. Lett. 69, 518 (1992).
- [7] R . Cavalcanti, G . Cameiro, and A . Gartner, Europhys. Lett. 17, 449 (1992); G . Cameiro, R . Cavalcanti, and A . Gartner, Phys. Rev. B 47, 5263 (1993).
- [8] Y . H . Li and S . Teitel, Phys. Rev. B 47, 359 (1993); *ibid.* 49, 4136 (1994).
- [9] A recent work that similarly studies vortex lines with nite , although with a different objective, is G . Cameiro, Phys. Rev. B 50, 6982 (1994).
- [10] C . Dasgupta and B . I . Halperin, Phys. Rev. Lett. 47, 1556 (1981).
- [11] T . Chen and S . Teitel, Phys. Rev. Lett. 72, 2085 (1994).
- [12] G . Baym , in Mathematical Methods in Solid State and Super uid Theory, eds. R . C . Clark and D . H . Derrick (O liver and Boyd, Edinburgh, 1969), p. 121.
- [13] W . K . Kwok, J . Fendrich, U . W elp, S . Fleshler, J . Downey, and G . W . Crabtree, Phys. Rev. Lett. 42, 1088 (1994).
- [14] M . A . Moore, Phys. Rev. B 45, 7336 (1992); R . Ikeda, T . Ohm i and T . Tsuneto, J. Phys. Soc. Jpn. 61, 254 (1992).

- [15] For free boundary conditions along  $\hat{z}$ , as opposed to the periodic boundary conditions of the analog 2D bosons, a sharp KT transition does not exist; nevertheless, a strong cross over should remain. See M. P. A. Fisher and D. H. Lee, Phys. Rev. B 39, 2756 (1989).
- [16] E. L. Pollock and D. M. Ceperley, Phys. Rev. B 36, 8343 (1987).
- [17] To compute  $W^2$  as a limit  $q \rightarrow 0$ , one should consider only one component, say  $W_y^2$ , and look at  $q$  in the xy plane transverse to this direction, i.e. take  $q_x = q_y = 0$  as  $q_x \rightarrow 0$ . This leads to a factor 2 correction to the KT transition temperature reported in Ref. [11]. We thank A. P. Young for clarification on this point.
- [18] M. V. Feigel'man, Physica A 168, 319 (1990); M. V. Feigel'man, V. B. Geshkenbein and V. M. Vinokur, JETP Lett. 52, 546 (1990); M. V. Feigel'man, V. B. Geshkenbein, L. B. Io e, and A. I. Larkin, Phys. Rev. B 48, 16641 (1993).
- [19] M. V. Feigel'man and L. B. Io e (unpublished) also suggest  $\xi$  as an important length in the vortex liquid. However their arguments seem unrelated to the KT transition discussed here, and they suggest that the intermediate superconducting line liquid persists even for  $L_z \rightarrow 1$ .

## FIGURES

FIG .1.  $\ln_x(q_y)n_x(q_y)$  vs.  $q_y = 2\pi m/L_y$ , ( $m$  integer) for various  $T$  and  $L_y = L_z = 30$ . Sample error bars are shown. Solid lines are a fit to Eq.(5).

FIG .2.  $\chi_{xy}$  vs.  $T$  for  $L_y = 30$  and  $L_z = 15; 30$ . Sample error bars are shown.  $\chi_{xy}$  decreases at  $T_m \approx 1.2$ ;  $\chi_z$  decreases at  $T_c \approx 2.0$ .

FIG .3. Intensity plot of  $S(q)$  for several  $T$  and  $L_y = L_z = 30$ . (a)  $T = 0.50 < T_m$  shows a lattice of Bragg peaks; (b)  $T = 1.25 \approx T_m$ ; (c)  $T_m < T = 1.60 < T_c$  in the vortex line liquid; (d)  $T = 2.0 > T_c$ .