Dislocations in uniaxial lamellar phases of liquid crystals, polymers and amphiphilic systems

by

Robert Hołyst¹ and Patrick Oswald²

¹Institute of Physical Chemistry of the Polish Academy of Sciences, Dept. III,

Kasprzaka 44/52, 01224 Warsaw, Poland

² Ecole Normale Superieure de Lyon, Laboratoire de Physique
46, Allée d'Italie-f-69364 Lyon Cedex 07, France

Abstract

Dislocations in soft condensed matter systems such as lamellar systems of polymers, liquid crystals and ternary mixtures of oil, water and surfactant (amphiphilic systems) are described in the framework of continuum elastic theory. These systems are the subject of studies of physics, chemistry and biology. They also find applications in the industry. Here we will discuss in detail the influence of dislocations on the bulk and surface properties of these lamellar phases. Especially the latter properties have only been recently studied in detail. We will present the experimental evidence of the existence of screw and edge dislocations in the systems and study their static properties such as: energy, line tension and core structure. Next we will show how does the surface influence the equilibrium position of dislocations in the system. We will give the theoretical predictions and present the experimental results on thin copolymer films, free standing films of liquid crystals and smectic droplets shapes. In semi-infinite lamellar systems characterized by small surface tension the

dislocation is stabilized at a finite distance, h_{eq} , from the surface, due to the surface bending elastic constant, K_s (for zero surface tension $h_{eq} \approx K_s/2K$, where K is the bulk bending elastic constant). For large surface tension the edge dislocations are strongly repelled by the surface and the equilibrium location for finite symmetric systems such as free standing liquid crystal films shifts towards the center of the system. The surface is deformed by dislocations. These deformations are known as edge profiles. They will be discussed for finite systems with small and large surface tension. Surface deformations induce elastic interactions between edge dislocations, which decay exponentially with distance with decay length proportional to \sqrt{D} , where D is the size of the system normal to lamellas. Two screw dislocations in finite system interact with the logarithmic potential, which is proportional to the surface tension and inversely proportional to D. The surface induced elastic interactions will be compared to, well known, bulk deformation induced interactions. A new phenomenon discussed in our paper is the fluctuations induced interactions between edge dislocations, which follows from the Helfrich mechanism for flexible objects. At suitable conditions edge dislocations can undergo an unbinding transition. Also a single dislocation loop can undergo an unbinding transition. We will calculate the properties of the loop inside finite system and discuss in particular the unbinding transition in freely suspended smectic films. We shall also compute the equilibrium size of the loop contained between two hard walls. Finally we will discuss the dynamical bulk properties of dislocations such as: mobility (climb and glide), permeation, and helical instability of screw dislocations. Lubrication theory will also be discussed.

PACS numbers: 61.30.Jf, 61.72.Lk, 61.41.+e, 61.30.Cz

I. Introduction

Before we enter the main subject of this review, which is the edge and screw dislocations in soft condensed matter systems such as smectic liquid crystals, lamellar phases of diblock copolymers and lamellar phases in ternary mixtures of oil, water and surfactants (amphiphilic system) we would like to put the subject of dislocations in a broader perspective. The phenomena of upheavals of the mountains, slipping of glaciers from the high mountains and easy deformations of metals are all controlled by the defects known as dislocations. In the defects free samples of solids the shear displacement requires (as theoretically calculated) shears 5 order of magnitude larger than is routinely applied in typical deformation processes (for an Introduction to dislocations in solids $see^{1,2}$). This fact aroused the curiosity of scientists and in 1936 G.I.Taylor, E.Orowan and M.Polanyi resolved the problem of deformations by postulating that deformations of solids are controlled by crystal imperfections (defects) called dislocations. It took almost 20 years before scientists observed dislocations in solid. One of the first observations were done in 1953 by Hedges and Mitchell and later in 1956 by Hirsch, Horne and Whelan and independently by Bollmann. The two techniques used in the experiments were: the decoration technique with optical observation and the transmission electron microscopy. In the decoration technique the guest atoms in a solid locate themselves along the dislocation line providing contrast for optical observations³. In the transmission electron microscopy (TEM) the diffraction and interference of electrons⁴ allows to see the dislocations. Strong scattering of electrons limits the application of TEM to rather thin samples.

Dislocations also appear in liquid partially ordered lamellar phases(Figs.1-3). The molecules in lamellar phases are arranged in liquid like layers parallel to each other. Although the symmetry of these phases is the same in amphiphilic systems⁵, diblock copolymers⁶ and liquid crystals⁷, their structure parameters can be very different. In liquid crystals the period of the lamellar structure, d, is set by the size of the molecule which is roughly 30Å; in amphiphilic system the amount of surfactant, water and/or oil allows to vary the lamellar size from ~20Å(for large concentration of surfactant) to ~1000Å(for very small concentration of surfactant)⁸. In block copolymers the period is determined by the size of the polymer molecule. In the strong segregation limit when the polymer molecules are strongly stretched in the lamellas the period is given by $M^{2/3}l$, where M is the number of statistical segments of a polymer and l is the length of a segment, thus the period can be as large as few hundred Å. Also the elastic constants characterizing the lamellar phases can be very different for these systems and as we will show the behavior of dislocations is sensitive to the value of elastic parameters characterizing a system. In the following we shall restrict our discussion to uniaxial lamellar phases, i.e. smectic A liquid crystals and L_{α} phases of lyotropics. Two types of dislocations, namely screw and edge dislocations, are shown schematically in Fig.4.

The bulk properties of dislocations have been very thoroughly studied⁹⁻¹¹ since 1972, when de Gennes presented the equation for elastic deformations induced by a single edge dislocation in the infinite lamellar system^{7,12}. The first observation of elementary edge dislocation has been done by Meyer et al in 1978¹³, although in earlier experiments the dislocations of large Burgers vector have already been seen¹⁴⁻¹⁸. The influence of surfaces on dislocations has been first studied by Pershan¹⁹. He found that dislocations are repelled from solid surfaces and attracted by a free surface as in solids. The latter conclusion is erroneous as shown by recent calculations²⁰ and experiments^{21,22}. Indeed, surface tension effects cannot be neglected at the air - smectic interface, contrary to Pershan's assumption. For instance, recent observations by TEM (transmission electron microscopy)²² and AFM (atomic force microscopy)^{21,22} of ultra-thin films of A-B diblock copolymers deposited on a solid substrate showed that elementary edge dislocations stabilize within the film and are repelled from the free surface. Moreover Pershan analysis failed to explain the shape of the surface deformations induced by dislocations. The repulsion of the dislocation from the surface is also observed in free standing films²³ and in the "gouttes à gradins" of Grandjean²⁴. The repulsion from the free surface of the giant dislocations separating two terraces of a "goutte à gradins" was first pointed out by C.Williams²⁵ in his thesis in 1976. Williams also emphasized that surface tension was responsible for this repulsion.

One of the aims of this review is thus the discussion of the recent progress in the dislocation theory for systems bounded by surfaces. The list of problems includes: surface deformations (edge profiles), equilibrium location of dislocations near surfaces and surface induced interactions between edge and screw dislocations. We shall also discuss some of their bulk, static properties such as the core structure and the formation of the giant dislocations (which do not exist in solids) and some consequences of their flexibility on their interactions. Finally we will analyse the dynamic properties of dislocations. These analysis will include the mobility, their instability under mechanical stress and their role in microplasticity and rheology.

The plan of the paper is as follows: In section II we present the experimental evidences for the existence of dislocations in lamellar phases. In section III we discuss the elastic theory for lamellar phases and in section IV we briefly recall the hydrodynamic equations governing their dynamical properties. In section V the distortions induced in the bulk by edge and screw dislocations are calculated. Here we also calculate the energy and line tension of dislocations. In section VI we find the equilibrium location of dislocation in finite system bounded by surfaces. Here we discuss both the theory and experiments. The edge profiles are calculated in section VII and elastic interactions are calculated in section VIII. Sections IX, X and XI are devoted to the flexibility of dislocation line and unbinding transition in the system of dislocations. Finally in sections XII, XIII and XIV the dynamical properties of dislocations are discussed. Conclusions are contained in section XV.

II. Experimental observations of dislocations

One of the main problem in optical detection of defects is the sufficient optical contrast against the lamellar background. In 1978 Meyer et al.¹³ observed an array of elementary edge dislocations in a wedge shaped sample of smectic liquid crystal, contained between two glass plates. In order to increase the optical contrast they used the phenomenon of phase transition between smectic-A, where molecules are roughly perpendicular to layers, and smectic-C, where liquid crystalline molecules are tilted with respect to layers. Tilting is accompanied by the decrease of the layer thickness and thus can relieve stress in a wedge shaped sample. Because of the wedged shape the thickness of the sample changes and the stress induces formation of dislocations in a sample as shown schematically in Fig.5. For temperatures close to the smectic-A smectic-C transition temperature the regions close to the dislocations are tilted. Thus under the polarizing microscope one can get dark regions separated by bright regions, depending on the tilt and the angle between the crossed polarizers. The distance between the dislocations in the array, l is given by $l = d/\alpha$, where α is a small angle between the glass plates. The accurate measurements of the angle were done by the Fabry-Perot interferometer. In this method one cannot tell wheather dislocations are located at the surface or in the bulk, but the fact that only dislocations satisfying the geometrical constraint given by l remain after annealing suggests that they are free to move and are not attached to the solid surface. This is confirmed by creep experiments discussed in section XIII.

Another optical method of observation based on fluorescence has been applied to phospholipid lamellar phase (example of self assembling amphiphilic system) with alternate layers of water and fluid-like bilayers of phospholipid²⁶. The system is placed in the same wedge shaped container and the phospholipid is doped with fluorescent, lipid analogue molecule. The sample is annealed for some time (several weeks) and next excited with a laser. The fluorescent intensity is monitored as a function of position as shown in Fig.6. The visible steps are clear signs of parallel, elementary edge dislocations. The long annealing time that is necessary to reach equilibrium in this system is related to permeation (flow of molecules across lamellas, Sections XII, XIII). Permeation is much more difficult in lyotropic systems like this one than in thermotropic systems studied by Meyer et al¹³, where the annealing times were much shorter.

The exact location of dislocation in a sample can be determined by TEM²². Here we briefly describe this experiment^{21,22} as shown schematically in Fig.7. The ultra-thin films (thickness $D \sim 1000$ Å) of lamellar phase of AB diblock copolymers (period $d \approx 315$ Å) are deposited on solid substrate. The films are first prepared in the disordered solid state and heated above their glass transition but below the order-disorder transition. The lamellar (smectic) ordering appears with layers parallel to the substrate. The free surface of the film is not flat since circular steps of micrometer size are formed, separated by equally large holes. The process of the formation of the holes and steps is associated with the nucleation of dislocations inside the film and is due to the incompatibility of the initial thickness of the disordered film, D, with the smectic period of the final lamellar phase i.e. Nd < D < (N + 1)d. Because N + 1 is the number of layers below the step and N is the number of layers below the hole the height of the step is equal to the lamellar period, d. Indeed applying TEM one can observe the dislocation itself, while by applying AFM one can measure the shape (size, height) of the step and the width of the profile at the edge of steps (edge profiles). The slices (cross section shown in Fig.7) of thickness of 500Å are prepared with layers parallel to the electron beam²². To have a contrast between the PS and PBMA domains PS are stained by treating it with RuO₄ vapor. The electrons are diffracted on the layers and the micrographs shows the positions of layers and in particular of defects. This is a direct way of seeing dislocations. The slices have to be thin, because of strong interactions between electrons and matter. The originally liquid samples are of course vitrified before observation. Since the polymers are very viscous fluids, the structure remains intact in the process of vitrification.

Edge dislocations are also visible in free standing films²³. They are usually obtained by smearing a smectic phase with a wiper across a fixed aperture made in a solid substrate. This technique used by most researchers and invented by Friedel 70 years ago²⁷ has been considerably improved by P.Pierański²³. He used a rectangular frame of **variable** area, allowing precise control (up to one layer) of the film thickness in the process of preparation. Fig.8a shows a schematic structure of the film near the edge of the aperture. As we see the dislocations are located in the middle of the smectic meniscus. Fig.8b shows a typical arch - texture obtained when the film is quickly stretched. Here the film is divided into areas of different thickness which are separated by lines of circular shape. In general the thickness variation between two adjacent regions is one layer. Some lines are linked by knots too. Pierański²³ showed that there exists some dust particles (not always visible under the microscope) at each junction (the knots) between the dislocations (Fig.8c).

Edge dislocations also play a crucial role in the problem of the equilibrium shape of a smectic A droplet deposited on a glass plate with strong homeotropic anchoring

(molecules arranged perpendicularly to the substrate) 28,29 . Droplets shapes can be measured very precisely $(\pm 50\text{\AA})$ by Michelson interferometry. This experiment was performed with materials that have either a nematic-smectic A phase transition (80CB, 40.8) or an isotropic-smectic A phase transition. It revealed that small droplets (usually less than 200 micrometers in diameter) have a single facet parallel to the substrate, while larger droplets are shaped like a spherical cap. Fig.9 shows typical profiles of a small 8OCB droplet, when the temperature is decreased below T_{NA} (nematic-smectic phase transition temperature). Because this transition is second order, the size of the facet vanishes at T_{NA} and increases like $(T_{NA} - T)^{0.45}$ when the temperature is decreased below T_{NA} . In 100CB where the first order smectic-A isotropic phase transition occurs, the facet has a finite size at the transition. If the radius of the droplet is larger than 200 micrometers, the top facet disappears and the droplet becomes spherical as in the previous case. It means that steps on the free surface associated with facets (Fig. 10a) are replaced by the dislocations distributed throughout the interior of the droplet (Fig.10b). This is possible since dislocations are repelled by both, the solid substrate and the free surface. In very large droplets, dislocations can group together and form giant dislocations separated by terraces parallel to the glass plate ("gouttes à gradins" Fig.11)

The shapes of the droplets has been explained by the theory, where interactions between the steps and between the dislocations, together with the surface and finite size effects have been properly taken into $\operatorname{account}^{30}$. These finite size effects are also important to explain the appearances in some materials (40.8) of a secondary facet around the primary one (Fig.12). This facet occurs at low temperatures and in large enough droplets (diameter more than 100 micrometers). This means that very special conditions must be fulfilled simultaneously in order to observe it. This unexpected facet (there is no terrace periodicity along the new facet direction) results from the elastic attraction between like steps, balanced by entropic repulsion. We shall see in section VIII that there can be an attraction between like dislocations (of the same sign) in films, similar to the attraction between steps as observed in this experiment.

The screw dislocations have been also observed in self assembled amphiphilic systems in $\text{TEM}^{16,31,32}$ experiments (Fig. 13). The density of screw dislocations can be as large as 10^8 per cm² in many lyotropic systems. High density suggests that their energy is rather small, a fact also established in the theory (Section V).

III. Elastic theory of lamellar phases

The lamellar phase consists of parallel, equidistant two dimensional liquid layers. The average distance between the layers is denoted d. For convenience we assume that unperturbed layers are perpendicular to the z-axis. The layers deform easily and their deformations are conveniently described by two unit vectors, one normal to the layer, $\hat{\mathbf{m}}(\mathbf{r})$ and one describing the average orientation of the molecules $\hat{\mathbf{n}}(\mathbf{r})$ (called in liquid crystals the director), and a scalar quantity, which measures the distance between the layers along the normal. We further assume that other quantities like the nematic order parameter and the density (for liquid crystals) or surfactant and water concentrations (for amphiphilic system) adjust to the layer deformations. In the first approximation, density changes do not generate new terms in the distortion energy, but only renormalize the lamellar elastic constants^{7,33}. Using the two aforementioned quantities we can write the distortion energy density in the simplest form invariant with respect to global rotations:

$$f_{b} = \frac{1}{2}B\left(\frac{d-d_{0}}{d_{0}}\right)^{2} + \frac{1}{2}K_{1}|\nabla\hat{\mathbf{n}}(\mathbf{r})|^{2} + \frac{1}{2}K_{2}|\hat{\mathbf{n}}(\mathbf{r}) \cdot \nabla \times \hat{\mathbf{n}}(\mathbf{r})|^{2} + \frac{1}{2}K_{3}|\hat{\mathbf{n}}(\mathbf{r}) \times (\nabla \times \hat{\mathbf{n}}(\mathbf{r}))|^{2} + \frac{1}{2}B_{1}(\hat{\mathbf{n}} - \hat{\mathbf{m}})^{2},$$
(3.1)

where d_0 is the unperturbed layer spacing, B is the Young modulus of the layers

associated with the variations of the thickness and $B_1 \sim B$ is the elastic modulus associated with the deviations of the average orientation of molecules from the normal to the layers³⁴. The divergence and the curl operators in Eq.(3.1) are taken with respect to variables in the distorted state and the point \mathbf{r} is uniquely related to some other point \mathbf{r}_0 on the unperturbed layer. We neglect the higher order terms in $d - d_0$ and in the derivatives of $\hat{\mathbf{n}}$. The last three terms in this distortion energy have their analogs in nematic liquid crystals. K_1 , K_2 and K_3 are the elastic constants for splay, twist and bend deformations of $\hat{\mathbf{n}}$, respectively. As one can see the splay of $\hat{\mathbf{n}}$ corresponds to the bend of the layers while the bend of $\hat{\mathbf{n}}$ corresponds to the splay of the layers. From now on we shall use the notion bend and splay in connection to layers. For the last term in Eq(3.1) one finds that $(\hat{\mathbf{n}} - \hat{\mathbf{m}})^2 \sim \lambda/R$ where $\lambda = \sqrt{K_1/B}$ is roughly proportional for most of the lamellar systems to d_0 and R is a typical radius of curvature for the director field. Consequently for $R \gg \lambda$ we can set $\hat{\mathbf{n}} = \hat{\mathbf{m}}$. We shall keep in mind however that this assumption is not valid close to the dislocation core. Nonetheless from now on we neglect the last term in Eq(3.1).

Since at this point we are interested in the local distortion energy density in the lamellar phase we can neglect dislocations, which means that the total number of layers crossed along any path going from some point A to another point B is constant i.e. for a closed path

$$\oint \frac{\hat{\mathbf{n}}}{d} d\mathbf{l} = 0, \tag{3.2}$$

This is equivalent to the condition 7 :

$$\nabla \times \frac{\hat{\mathbf{n}}}{d} = 0, \tag{3.3}$$

where d, in general, depends on the position **r**. Condition(3.3) eliminates the twist term from the distortion energy, but not the splay term (K_3) . Here we only note

that splay of layers does not affect the long wavelength properties of the system. Combining Eq(3.1) and Eq(3.3) we get

$$f_b = \frac{1}{2} \left(B \left(\frac{d - d_0}{d_0} \right)^2 + K_1 \left| \nabla \hat{\mathbf{n}}(\mathbf{r}) \right|^2 + K_3 \left(\left| \frac{1}{d} \nabla d \right|^2 - \left| \frac{\hat{\mathbf{n}}(\mathbf{r})}{d} \nabla d \right|^2 \right) \right)$$
(3.4)

It is important to notice that a dislocation should not affect the form of the distortion energy density, which is a local quantity, whereas dislocation is described by the global condition i.e. nonvanishing of (3.2). One can also verify this by direct calculations⁷. For the edge dislocation along y direction $\hat{\mathbf{n}}$ has only x, z components and does not depend on y and $\nabla \times \hat{\mathbf{n}}/d$ is along the y direction. Thus the twist term drops out in this case.

In lamellar phases, $\hat{\mathbf{n}}$ and d are not independent and can be expressed in terms of the vertical displacement field $u(\mathbf{r}_0)$. Although u is a multivalued function in the presence of dislocation, we can still use it away from the dislocation. The vector normal to the layer at point $\mathbf{r} = \mathbf{r}(\mathbf{r}_0)$ is simply given by:

$$\hat{\mathbf{n}} = \frac{\left(-\frac{\partial u}{\partial x_0}, -\frac{\partial u}{\partial y_0}, 1\right)}{\sqrt{1 + |\nabla_{\perp}^{(0)} u|^2}},\tag{3.5}$$

where $\mathbf{r}_0 = (x_0, y_0, z_0)$ is the coordination point in the unperturbed system. The distance between layers measured along $\hat{\mathbf{n}}$ is

$$d = d_z(\hat{\mathbf{n}}\hat{\mathbf{z}}),\tag{3.6}$$

where d_z is the distance between layers measured along the z-axis. We find, to the lowest order in the derivatives of u, that

$$d_z = d_0 \left(1 + \frac{\partial u}{\partial z_0} \right). \tag{3.7}$$

which together with Eqs(3.5-6) gives d in terms of u,

$$d = d_0 \frac{\left(1 + \frac{\partial u}{\partial z_0}\right)}{\sqrt{1 + |\nabla_{\perp}^{(0)} u|^2}}.$$
(3.8)

In order to represent the distortion energy given by Eq(3.4) in terms of u, we have to transform the point \mathbf{r} on a perturbed layer to the point \mathbf{r}_0 on the unperturbed layer and the corresponding nabla operator as follows:

$$x = x_0,$$

 $y = y_0,$
 $= z_0 + u(x_0, y_0, z_0),$

z

and

$$\frac{\partial}{\partial x} = \frac{\partial}{\partial x_0} - \frac{\frac{\partial u}{\partial x_0}}{\left(1 + \frac{\partial u}{\partial z_0}\right)} \frac{\partial}{\partial z_0},\tag{3.9}$$

$$\frac{\partial}{\partial y} = \frac{\partial}{\partial y_0} - \frac{\frac{\partial u}{\partial y_0}}{\left(1 + \frac{\partial u}{\partial z_0}\right)} \frac{\partial}{\partial z_0},\tag{3.10}$$

$$\frac{\partial}{\partial z} = \frac{1}{\left(1 + \frac{\partial u}{\partial z_0}\right)} \frac{\partial}{\partial z_0}.$$
(3.11)

Combining these equations we recover the condition given by Eq(3.3) for the constant number of layers. Finally we obtain the following expression for the distortion energy density³⁵:

$$f_{b} = \frac{1}{2} \left(B \left(\frac{d - d_{0}}{d_{0}} \right)^{2} + K_{1} \left| \nabla_{\perp}^{(0)} \hat{\mathbf{n}}_{\perp} \right|^{2} + K_{3} \left(\left| \frac{1}{d} \nabla_{\perp}^{(0)} d \right|^{2} - \left| \frac{\hat{\mathbf{n}}_{\perp}}{d} \nabla_{\perp}^{(0)} d \right|^{2} \right) \right),$$
(3.12)

where $\hat{\mathbf{n}}_{\perp} = -\nabla_{\perp}^{(0)} u / \sqrt{1 + |\nabla_{\perp}^{(0)} u|^2}}$ and $\nabla_{\perp}^{(0)} = (\partial / \partial x_0, \partial / \partial y_0)$ is the two dimensional nabla operator. As noted before, although the splay term associated with K_3 gives a coupling between compression and undulation of layers, it does not affect the long-wavelength properties of the system. Also it can be neglected in comparison to the compression term. Ignoring the splay term and anharmonic contribution to

the bend term, we find an approximate form of f_b :

$$f_b = \frac{1}{2} \left(B \left(\frac{1 + \frac{\partial u(\mathbf{r_0})}{\partial z_0}}{\sqrt{1 + |\nabla_{\perp}^{(0)} u(\mathbf{r_0})|^2}} - 1 \right)^2 + K_1 (\triangle_{\perp}^{(0)} u(\mathbf{r_0}))^2 \right).$$
(3.13)

Here $\triangle_{\perp}^{(0)}$ is the two-dimensional Laplacian with respect to x_0, y_0 . The distortion energy density given by Eq(3.13) is invariant with respect to rotations. For example, by rotating the system around y-axis by an angle θ , we find:

$$u = z_0 \left(\frac{1}{\cos\theta} - 1\right) - x_0 \tan\theta.$$
(3.14)

For such spurious deformation we find from Eq(3.13) that $f_b = 0$ as it should. Expanding Eq(3.13) in $|\nabla_{\perp}^{(0)}u|^2$ we recover the de Gennes distortion energy density^{7,36}

$$f_b = \frac{1}{2} \left(B \left(\frac{\partial u(\mathbf{r_0})}{\partial z_0} - \frac{1}{2} |\nabla_{\perp}^{(0)} u(\mathbf{r_0})|^2 \right)^2 + K_1 (\triangle_{\perp}^{(0)} u(\mathbf{r_0}))^2 \right),$$
(3.15)

in the lowest order of the expansion, losing however the rotational invariance of f_b . Alternatively, the distortion energy density can be expressed in terms of ∇u . We find

$$f_b = \frac{1}{2} \left(B \left(\frac{1}{\sqrt{1 - 2\left(\frac{\partial u}{\partial z} - |\nabla u(\mathbf{r})|^2/2\right)}} - 1 \right)^2 + K_1 |\nabla \hat{\mathbf{n}}(\mathbf{r})|^2 \right)$$
(3.16)

where

$$\hat{\mathbf{n}}(\mathbf{r}) = \frac{(-\partial u/\partial x, -\partial u/\partial y, 1 - \partial u/\partial z)}{\sqrt{1 - 2\left(\frac{\partial u}{\partial z} - |\nabla u(\mathbf{r})|^2/2\right)}}$$
(3.17)

and we have neglected the splay term. One easily checks that $f_b = 0$ when we rotate the system, i.e.

$$u = z(1 - \cos\theta) - x\sin\theta. \tag{3.18}$$

The transformation properties of u result from the fact that it is defined as the *vertical displacement* of the layer from its rest position. In the lowest order expansion

in $\partial u/\partial z - |\nabla u|^2/2$ we recover the Grinstein and Pelcovits expression³⁷:

$$f_b = \frac{1}{2} \left(B \left(\frac{\partial u(\mathbf{r})}{\partial z} - \frac{1}{2} |\nabla u(\mathbf{r})|^2 \right)^2 + K_1 (\Delta_\perp u(\mathbf{r}))^2 \right), \qquad (3.19)$$

If we neglect the anharmonic terms we find the harmonic approximation of the distortion energy:

$$f_b = \frac{1}{2} \left(B \left(\frac{\partial u(\mathbf{r})}{\partial z} \right)^2 + K(\Delta_{\perp} u(\mathbf{r}))^2 \right).$$
(3.20)

Here we define $K=K_1$. Once again we note that Eq(3.20) is valid far away from the dislocation core. This form of the bulk distortion energy will be used in our description of deformations induced by dislocations in a lamellar (smectic) system. At the harmonic level of approximation the form of the distortion energy is the same in coordinates of both, the deformed and undeformed state (Eq(3.15), Eq.(3.19)). The role of the anharmonic terms in lamellar phases for long wavelength distortions has been discussed in detail in Refs(7,37). In general its role for distortions induced by dislocations is not known.

IV. Hydrodynamics of smectics: elastic and viscous stress tensor

The motion of dislocations can be described in the framework of the hydrodynamical equations for the lamellar phases. Here we recall the basic ingredients of the theory^{7,33}. Let \mathbf{v} be the average velocity of the molecules. If the velocity of the dislocations is much smaller than the velocity of the first sound, then the medium can be regarded as incompressible i.e.

$$\nabla \mathbf{v} = 0 \tag{4.1}$$

The momentum conservation equation for the system is as follows.

$$\rho \frac{D\mathbf{v}}{Dt} = \nabla \sigma + \mathbf{F},\tag{4.2}$$

where ρ is the density, σ is the stress tensor and **F** the bulk forces (gravitation for example). The stress tensor can be decomposed into three terms:

$$\sigma = -P\mathbf{I} + \sigma^{\mathbf{E}} + \sigma^{\mathbf{V}}.$$
(4.3)

Here P is the hydrostatic pressure (given by condition (4.1)), $\sigma^{\mathbf{E}}$ is the elastic stress tensor and $\sigma^{\mathbf{V}}$ is the viscous stress tensor. The former is related to the layer displacement u and can be obtained from the following equation relating the change of the free energy f_b to the displacement:

$$df_b = \sigma_{zj}^E d\left(\frac{\partial u}{\partial r_j}\right),\tag{4.4}$$

Since u is the z-component of the displacement vector, the only nonvanishing component of this tensor have (z,j) indexes. Expanding (3.20) and equating the expansion to the right hand side of (4.4) we find

$$\sigma_{zj}^E = \frac{\partial f_b}{\partial u_{,j}} - \frac{\partial}{\partial r_i} \frac{\partial f_b}{\partial u_{,ij}}.$$
(4.5)

Here $u_{,j}$ and $u_{,ij}$ are the first and the second derivatives of u with respect to the components of **r**. More explicitly we find:

$$\sigma_{zz}^E = B \frac{\partial u}{\partial z},\tag{4.6}$$

$$\sigma_{zx}^{E} = -K \frac{\partial}{\partial x} \left(\triangle_{\perp} u \right), \qquad (4.7)$$

$$\sigma_{zy}^{E} = -K \frac{\partial}{\partial y} \left(\Delta_{\perp} u \right). \tag{4.8}$$

All other terms are zero. Note that elastic stress tensor is not symmetrical due to the curvature elasticity and the associated surface torque $C\hat{n}$. The nonvanishing components of the tensor C are

$$C_{xy} = \frac{\partial f_b}{\partial u_{,yy}},\tag{4.9}$$

and

$$C_{yx} = -\frac{\partial f_b}{\partial u_{,xx}}.$$
(4.10)

The elastic stress tensor satisfies the torque balance equation

$$C_{ij,j} - \epsilon_{ijk} \sigma_{jk}^E = 0 \tag{4.11}$$

automatically (we assume as stated in section III that $\hat{\mathbf{n}}$ is normal to layers).

In order to calculate the expression for the viscous stress tensor we have to find the thermodynamic fluxes and forces associated with the entropy production. One finds for the isothermal processes the following expression for the change of the entropy s in time:

$$T\frac{Ds}{Dt} = \left(\frac{Du}{Dt} - v_z\right)G + \sigma_{ij}^V A_{ij},\tag{4.12}$$

where

$$G = \sigma_{zj,j}^E \tag{4.13}$$

is the elastic force normal to layers and

$$A_{ij} = \frac{1}{2} \left(\frac{\partial v_i}{\partial r_j} + \frac{\partial v_j}{\partial r_i} \right).$$
(4.14)

Now from the Onsager relations between thermodynamic forces (G, σ_{ij}^V) and fluxes $(A_{ij}, (Du/Dt - v_z))$ we find

$$\sigma_{ij}^{V} = \mu_1 \delta_{ij} A_{kk} + \mu_2 \delta_{iz} \delta_{jz} A_{zz} + \mu_3 A_{ij} + \mu_4 \left(\delta_{iz} A_{zj} + \delta_{jz} A_{zi} \right) + \mu_5 \left(\delta_{iz} \delta_{jz} A_{kk} + \delta_{ij} A_{zz} \right)$$

$$(4.15)$$

and

$$\frac{Du}{Dt} - v_z = \lambda_p G. \tag{4.16}$$

Here μ_i $(i = 1 \cdots 5)$ are independent viscosities. In the following we shall take $\sigma_{ij}^V = \mu A_{ij}$ for simplicity. Eq.(4.16) is formally equivalent to the Darcy law in

porous medium. In our case the lamellar phase plays both the role of the fluid and of the porous medium. It can be shown that the permeation coefficient λ_p ,

$$\lambda_p \sim \frac{D_{\parallel} v_{\rm mol}}{k_B T} \tag{4.17}$$

where D_{\parallel} is the diffusion coefficient normal to the layers and $v_{\rm mol}$ is a molecular volume. The permeation coefficient is much smaller in lyotropic (e.g. amphiphilic systems) than in thermotropic smectic liquid crystals. This coefficient can be estimated from the measurements of the edge dislocation mobility as will be shown in Section XIII.

V. Static bulk properties of dislocations

Let us consider an elementary edge dislocation (of unit Burgers vector) located along the y-axis at x = l and z = h. The displacement u is a multivalued function in the z = h plane i.e.

$$u(x,z) = \begin{cases} 0, & \text{if } x \le l; \\ \text{sgn}(z-h)d/2, & \text{if } x > l. \end{cases}$$
(5.1)

This is equivalent to the condition

$$\oint \frac{\hat{\mathbf{n}}}{d} d\mathbf{l} = 1, \tag{5.2}$$

where the contour of integration is around the dislocation line. The distortions induced by a dislocation are described by the following equation⁷:

$$\frac{\partial^2 u}{\partial z^2} - \lambda^2 \triangle_{\perp}^2 u = 0 \tag{5.3}$$

obtained from the minimization of the total bulk distortion energy F_b ,

$$F_b = \int d\mathbf{r} f_b. \tag{5.4}$$

Here f_b is the energy density given by Eq.(3.20) and $\lambda = \sqrt{K/B}$. The equilibrium solution of Eq.(5.3) satisfying condition (5.1) is as follows⁷:

$$u_b(x,z) = \operatorname{sgn}(z-h) \left(\frac{d}{4\pi} \int dq \exp\left(-\lambda q^2 |z-h|\right) \frac{\exp\left(iq(x-l)\right)}{i(q-i0^+)} \right)$$

= $\frac{d}{4} \operatorname{sgn}(z-h) \left(1 + \operatorname{erf}\left(\frac{x-l}{2\sqrt{\lambda|z-h|}}\right) \right)$ (5.5)

where $\operatorname{erf}(t) = 2/\sqrt{\pi} \int_0^t \exp(-u^2) du$ is the error function. The solution is valid outside the dislocation core of size r_c . For dislocations of Burgers vector, **b**, of length nd, for which

$$\oint \frac{\hat{\mathbf{n}}}{d} d\mathbf{l} = \pm n, \tag{5.6}$$

the solution is simply given by $\pm nu_b$ (here *n* is a positive integer). Inserting the solution (5.5) into F_b (Eq.(5.4)) and introducing the cutoff r_c in (5.4) we find the energy of the edge dislocation line per unit length F_b/L_y :

$$E_0 = E_c + \frac{\sqrt{KB}(nd)^2}{2r_c},$$
 (5.7)

where E_c is the core energy. As expected this energy does not depend on h and lin the infinite systems, but as we shall see in the next section it does depend on the location of dislocation (l, h) in the finite system bounded by surfaces. The energy of dislocation per unit length is finite in lamellar phases whereas in solids it diverges logarithmically with the size of the system. Also stresses do not vary like 1/r as in solids. We find from section IV (Eq(4.6)) and Eq(5.5) that in lamellar phases

$$\sigma_{zz}^{E} = -\frac{(x-l)d}{8|z-h|\sqrt{\pi\lambda|z-h|}} \exp\left(-(x-l)^{2}/(4\lambda|z-h|)\right).$$
(5.8)

Thus σ_{zz}^E is large only for $4\lambda |z - h| \ge x^2$. Outside this region the stress vanishes very quickly because of the fluidity of layers. Let us now discuss the core structure of an edge dislocation. Let us assume that the core is nematic. We also assume that the core is anisotropic i.e. along the z direction it has the size $2r_c$ while along the x direction it has negligible size. Then

$$E_c = 2\gamma r_c \tag{5.9}$$

where γ is roughly proportional to the nematic-smectic surface tension. If we now minimize E_0 (Eq(5.7) with respect to r_c we find

$$E_0 = 2\sqrt{B\lambda\gamma}nd\tag{5.10}$$

and

$$r_c = \frac{nd}{2} \sqrt{\frac{B\lambda}{\gamma}}.$$
(5.11)

When γ is small the core size can be very large as shown in (Fig.4b). The total energy is now proportional to the length of the Burgers vector, nd, of an edge dislocation and this explains why dislocations may group together. When their Burgers vector is large (giant dislocations with $n \geq 10$), the core of dislocation can split^{17,11,7} into two $\pm 1/2$ disclinations a distance nd/2 apart (Fig.4c) The core energy is in this case,

$$E_c = \frac{\pi K}{2} \ln\left(\frac{nd}{2r_0}\right) + w_c, \qquad (5.12)$$

where w_c is the disclination core energy and r_0 is the disclination core size. Now the core energy is lowered by the gathering of elementary edge dislocations into dislocations of large n. The core structure of disclinations in smectics is not known, although recently the disclination core structure in nematic liquid crystals has been thoroughly studied in the Landau-de Gennes model³⁸ and in computer simulations for hard rod systems³⁹. The core structure of this defect depends on the length of molecules. For short molecules, the core is biaxial with molecules perpendicular to the disclination line, whereas for long molecules they are parallel to this line. The core size is proportional to molecular thickness, rather than molecular length. Let us now discuss the screw dislocation properties. In this case (Fig.4d) the Burgers vector is parallel to the dislocation line and perpendicular to layers. Recent discovery of the TGB (Twist Grain Boundary) phase consisting of lattice of screw dislocations^{40,41} (analogous to the type II superconductors) brought the renewal interests in these defects⁴². The static properties of screw dislocations have been intensively studied⁴²⁻⁴⁷ and here we shall briefly present the major results of this properties. The distortions induced by screw dislocation of strength *n* located along the *z* axis (perpendicular to smectic layers) are also described by Eq.(5.3) and the condition(5.6). For small distortions we have:

$$\oint \nabla_{\perp} u d\mathbf{l} = \pm n d, \tag{5.13}$$

Due to the symmetry u does not depend on z and the layer thickness d is equal to the undistorted value d_0 . We find in this case the equilibrium solution of the form⁴³:

$$u_b(x,y) = \pm \frac{nd\phi}{2\pi} = \pm \frac{nd}{2\pi} \left(\arctan\left(\frac{y}{x}\right) - \pi + (\pi/2)\mathrm{sgn}(y) \right).$$
(5.14)

where ϕ is the polar angle in cylindrical coordinates. The solution is only valid far away from the core, i.e. for $\rho \gg r_c$, where r_c is the core size and ρ is the distance, in polar coordinates, form the screw axis (given by z = 0). The total distortion energy is the core energy only, since the strain energy is zero. In solids the strain energy diverges logarithmically with the size of the system. If we include anharmonic terms in the distortion energy (section III, Eq(3.15)) and the splay term, which for distances not too far from the core can compete with the compressional term, we find the energy per unit length of the screw dislocation^{43,46} in the following form:

$$E_0 = E_c + \frac{(nd)^4 B}{128\pi^3 r_c^2} + \frac{(nd)^4 K_3}{64\pi^3 r_c^4}.$$
(5.15)

It should be noted that we have used the solution (Eq.(5.14)) which followed from the harmonic approximation (Eq.(5.3)). Since K_3 and Bd^2 are of the same order of magnitude, so both contribute significantly to the distortion energy. Note however that this elastic energy is three orders of magnitude smaller than the energy of the edge dislocation. The core energy (core size r_c) can be roughly estimated⁴⁴ as:

$$E_c = k_B (T_{NA} - T) \pi r_c^2 / v_{\rm mol}, \qquad (5.16)$$

where v_{mol} is the molar volume and T_{NA} is the transition temperature from the nematic liquid to the lamellar phase. The core energy vanishes at the transition which means that the formula (5.16) is valid only for the second order phase transition. In the case of the first order phase transition we find:

$$E_{c} = \pi r_{c}^{2} \frac{\Delta H(T_{NA} - T)}{T_{NA}} + 2r_{c}\gamma, \qquad (5.17)$$

where ΔH is the latent heat (per unit volume) of the transition and γ is the nematicsmectic surface tension. Here it has been assumed that the core is filled with undercooled nematic phase. Similarly as we did in the case of edge dislocations (Eqs(5.10-11)) we could minimize E_0 with respect to r_c . This calculation shows that the energy of the screw dislocation increases faster than the length of the Burgers vector nd so that elementary screw dislocations are favored. In fact the exact core structure of screw dislocation is not known in general, although some preliminary studies have been done for smectic liquid crystals^{42,46}. These studies indicate that the core is nematic (although there is a possibility for the completely isotropic core). Since layers are not well defined inside the core one has to use there the Landau-de Gennes description in terms of the order parameters⁷. The smectic order parameter ϵ , the nematic order parameter s and the local angle between the director field and the z axis, ϑ , are shown in Fig.14. The nematic order parameter does not change in comparison to its bulk value s_b . The smectic order parameter decreases to zero in the core as ρ^n , and approaches the bulk value ϵ_b as $-1/\rho^4$. Within the core the director **n** tends to lie along the screw axis and $\vartheta \sim \rho$ close to the center of the core. The director $\mathbf{n} = \mathbf{e}_{\rho} \cos \alpha_b \sin \vartheta + \mathbf{e}_{\phi} \sin \alpha_b \sin \vartheta + \mathbf{e}_z \cos \vartheta$ should be identified far from the core with the layer normal. Far from the core one finds $\alpha_b = \pi/2$ and $\vartheta = \arctan(nd/2\pi\rho)$. The size of the core increases with the strength of the screw dislocation n. Finally we note that the internal stress inside the core (giving rise to radial force) is balanced in the smectic by the non-uniform pressure $p = p_0 + (nd)^4 B/128\pi^4 \rho^4$, which can be as large as twice the athmospheric pressure, p_0 , of a defect free sample. The case of the isotropic screw core structure has also been studied^{42,46}. These cores are energetically unfavorable, although they may be stabilized close to the smectic liquid crystal – isotropic phase transition. The core structure for the polymers or amphiphilic systems certainly cannot be nematic since the nematic phase is not present in these systems. To our knowledge these cores have not been studied in detail (see however Refs.11,44).

Finally let us mention an important property of screw dislocations, namely the fact that although their energy per unit length is small their line tension is large⁴⁴. In order to calculate the line tension of the screw dislocations let us assume that the dislocation is tilted with respect to the layers, making an angle θ with the z axis Fig.15. For very small θ the displacement is given by:

$$u_b(x, y, z) = \frac{nd}{2\pi} \arctan \frac{y - \theta z}{x}$$
(5.18)

and the total energy is

$$E_0(\theta) = E_0(\theta = 0) + \frac{(nd)^2 B}{4\pi} \theta^2 \ln \frac{R}{r_c},$$
(5.19)

where R is the size of the system or the distance between the neighbouring screw dislocations of opposite signs. The line tension is defined as follows:

$$T_{\rm screw} = E_0(\theta = 0) + \frac{d^2 E_0(\theta)}{d\theta^2}\Big|_{\theta = 0}$$
 (5.20)

and it follows from (5.19) that $T_{\text{screw}} \gg E_0$ contrary to the case of edge dislocations for which $T_{\text{edge}} \sim E_0$. The main difference between the two types of dislocations is that edge dislocations located along the y axis do not change their character when tilted in the x-y plane with respect to the y-axis, while the screw dislocations along the z axis acquire the edge character when tilted with respect to the z axis. This result explains why screw dislocations prefer to be perpendicular to smectic layers and do not tilt easily (Fig.16). We shall also see that this property is crucial for understanding the helical instability under compression or dilation normal to layers.

VI. Equilibrium location of dislocations in finite systems

Experimental systems are always bounded by surfaces. In Meyer et al^{13} experiment two glass plates bound the lamellar phase (Fig.5). Thin freely suspended smectic liquid crystal films²³ (Fig.8) are attached to the aperture and bounded from above and below by a smectic free surface (smectic-air interface). Smectic droplets^{29,30} deposited on a solid substrate (Fig.10) are bounded by the solid surface and the free surface. The diblock copolymer lamellar film deposited on a solid substrate shown in Fig.7 is also bounded by a free surface. In the finite system dislocations are influenced by the bounding surfaces. The boundary effects can be incorporated in the form of the surface distortion energy. It should be noted that contrary to the solids, the surface energy of distortion in lamellar liquid phases is comparable to the bulk energy. In solids the energy scales for the surface and the bulk are well separated with surface energy being much smaller than the bulk energy.

The influence of surfaces on dislocations has been studied by Pershan¹⁹. However his analysis was not sufficient to explain interactions with a free surface²⁵. The problem has been first analyzed theoretically by Lejcek and Oswald²⁰ in the framework of the image dislocation approach. In the semi-infinite system bounded by the free surface at z = 0 the total energy contains the bulk part (5.4) and the surface part²⁰:

$$F_s = \frac{1}{2} \int d\mathbf{r}_\perp \gamma |\nabla u_s|^2, \tag{6.1}$$

where γ is the smectic-air surface tension and $u_s = u(\mathbf{r}_{\perp}, z = 0)$ is the surface displacement. Minimizing $F_b + F_s$ gives Eq.(5.3) and a boundary condition at the free surface:

$$B\frac{\partial u}{\partial z} = \gamma \triangle_{\perp} u_s. \tag{6.2}$$

Let us now consider a simple case of a dislocation of Burgers vector b = nd located at z = h. It can be shown that both equation (5.3) and (6.2) are satisfied by the solution (5.5) if we introduce a symmetric image dislocation (located at z = -h) of Burgers vector:

$$b_i = b \frac{\gamma - \sqrt{KB}}{\gamma + \sqrt{KB}}.$$
(6.3)

and take the linear combination of the bulk displacement field $(u_b \text{ Eq}(5.5))$ for both dislocations $u = nu_b(h) + n_i u_b(-h)$. Note that $b_i = n_i d$ does not have to be a multiple of d since it is a virtual dislocation and consequently n_i in general is not an integer. We shall see in section VIII that two dislocations repell each other when have the same sign and attract each other for opposite signs. Thus it follows that the surface attracts dislocation for $\gamma < \sqrt{KB}$ and repels it in the opposite case.

These calculations can be generalized to more complicated situations, when for example we have two surfaces^{20,30}, but in this case we have to introduce an infinite number of image dislocations, which is not very convenient. For this reason we shall adopt another approach to the problem based on de Gennes method of calculation⁷. We also note that the surface energy considered by Lejcek and Oswald is incomplete since it does not contain the surface curvature term which influences very strongly the equilibrium location of dislocations in the case of small surface tension^{48,49}. The surface distortion energy with the curvature term has the following form⁵⁰

$$F_s = \frac{1}{2} \int d\mathbf{r}_{\perp} \left(\gamma |\nabla u_s|^2 + K_s (\Delta_{\perp} u_s)^2 \right).$$
(6.4)

Here the new quantity is the surface elastic constant, K_s . It should be identified with the bending elastic constant of the last lamellar layer (at the surface). In general the properties of the surface layer are different from the bulk layers and the value of the surface constant can be different from the bulk value. In particular, if the surface layer is the same as the bulk one, they are related by the formula: $K_s = Kd$, where d is the layer spacing. The fact that the surface bending elastic constant must be included follows from the comparison of the distortion energy in the discrete⁵¹ and continuous^{50,52} representation. In the discrete representation the layers have indexes i = 0, 1, 2... and $u(x, z) = u_i(x)$. Then the last term in Eq(6.4) appears naturally with $K_s = Kd$. In the discrete representations we sum over iinstead of integrating over z and consequently each layer, including the surface one, has the bending elastic constant equal Kd.

Let us consider the experimental system shown in Fig.7 with the substrate located at z = D and an elementary edge dislocation (n = 1) located at z = h and x = l. The condition for the edge dislocation is given by Eq.(5.1). Now minimizing the total energy $F = F_b + F_s$ (Eq(5.4) and (6.4)) we find Eq.(5.3) plus the boundary condition at the free surface (z = 0):

$$-B\frac{\partial u}{\partial z} - \gamma \triangle_{\perp} u_s + K_s \triangle_{\perp}^2 u_s = 0$$
(6.5)

and the boundary condition at a solid substrate,

$$u(x, z = D) = 0. (6.6)$$

The equilibrium solution satisfying Eqs(5.1,5.3,6.5,6.6) is given by $u_{eq}(x, z)$,

$$u_{eq}(x,z) = u_b(x,z) + u_p(x,z)$$
(6.7)

where the singular bulk part of the solution, u_b , is given by Eq.(5.5) and the particular non-singular part of the solution, necessary to satisfy the boundary conditions (6.5-6), is ⁴⁸

$$u_p(x,z) = \frac{d}{4\pi} \int dq \frac{\exp(iq(x-l))}{iq} \left(\exp(-\lambda q^2 z) f_1(q) + \exp(\lambda q^2 z) f_2(q) \right).$$
(6.8)

Here

$$f_1(q) = -\frac{a_1(q)e^{-\lambda q^2 h} + a_1(q)e^{\lambda q^2(h-2D)}}{a_2(q) + a_1(q)e^{-2\lambda q^2 D}},$$
(6.9)

$$f_2(q) = \frac{a_1(q)e^{-\lambda q^2(h+2D)} - a_2(q)e^{\lambda q^2(h-2D)}}{a_2(q) + a_1(q)e^{-2\lambda q^2D}}$$
(6.10)

and

$$a_1(q) = 1 - \alpha_s - \lambda_s^2 q^2, \tag{6.11}$$

$$a_2(q) = 1 + \alpha_s + \lambda_s^2 q^2.$$
 (6.12)

Here $\alpha_s = \gamma/\sqrt{KB}$ is the dimensionless constant, whereas $\lambda = \sqrt{K/B}$ and $\lambda_s = \sqrt{K_s/\sqrt{KB}}$ are two microscopic lengths. The total distortion energy $F = F_b + F_s$ can be written in the following convenient form:

$$F(h) = E_0 + \frac{1}{2}B \int dx \frac{\partial u_p(x,z)}{\partial z} \left(u_b(x,z=h^-) - u_b(x,z=h^+) \right).$$
(6.13)

Inserting u_b and u_p into Eq(6.13) gives F(h) as a function of h in the following form:

$$F(h) = E_0 + \frac{\sqrt{KB}d^2}{8\pi} \int dq \frac{-a_1(q)e^{-2\lambda q^2 h} + a_2(q)e^{2\lambda q^2(h-D)} - 2a_1(q)e^{-2\lambda q^2 D}}{a_2(q) + a_1(q)e^{-2\lambda q^2 D}}.$$
(6.14)

As one notices the equilibrium location of the dislocation is still to be determined The equilibrium location of the dislocation, h_{eq} , corresponds to the minimum of F(h).

$$\frac{\partial F(h)}{\partial h} = 0. \tag{6.15}$$

First let us consider the case of the infinite thickness of the film $D = \infty$. The energy as a function of h is shown in Fig.17. For $\alpha_s = 0$ we find $h_{eq} = 1.08K_s/(2K)$ and for $\alpha_s \leq 0.2$ we get roughly $h_{eq} \geq (K_s/(2K))((1 + \alpha_s)/(1 - \alpha_s))$. For larger values of α_s , we find that the following inequality holds:

$$\frac{1+\alpha_s}{1-\alpha_s} > \frac{2h_{eq}K}{K_s} > \frac{1}{1-\alpha_s}.$$
(6.16)

For small surface tension the dislocation is stabilized at a finite distance due to the surface bending elastic constant K_s . Finally for $\alpha_s \to 1$ we have $h_{eq} \to \infty$, which means that the dislocation is no longer stabilized at a finite distance from the interface. This result is the same as obtained within the image dislocation approach of Lejcek and Oswald²⁰. For large surface tension $\alpha_s \gg 1$ and finite but large D the dislocation is stabilized roughly in the middle of the system at $h_{eq} \approx D/2^{19,20,22,48}$. For small surface tension and finite D the location of dislocation in a system depends strongly on D. (Fig.18) For small K_s the dislocation is close to the interface, while for larger K_s it moves towards the center of the system. For thin films there is a strong deviations from the linear dependence of h_{eq} on K_s . This is of course due to the strong repulsion of the dislocation from the solid substrate, which cannot be compensated by any finite value of K_s . Finally dislocations in free standing film shown in Fig.8a, are located exactly in the middle of the film, since $\gamma \gg \sqrt{KB}$ in this case⁵³ and the film is symmetric.

Usually the surface tension for the air-lamellar interface is about $\gamma = 30 \text{ dyn/cm}$ (this value characteristic for air-organic liquid interface (free surface)) and in general larger by an order of magnitude than \sqrt{KB} . However, there are also many systems characterized by a small value of the surface tension (smaller than \sqrt{KB}). They include nematic-smectic interface (for liquid crystals), microemulsion- lamellar interface in amphiphilic systems and AB diblock copolymer lamellar-A (or B) homopolymer melt interface. Our results can be used to describe dislocations in all these systems.

Here we may also ask the question concerning the average distance, l, between dislocations in a smectic meniscus (Fig.8a). Neglecting the elastic interactions we find

$$l = \frac{\gamma d \exp\left(x/\xi_0\right)}{\gamma_{AW} - \gamma_{LW} - F(h)/d},\tag{6.17}$$

for large film thickness and far from the aperture $(x \ge \xi_0)$. Here γ_{AW} is the airaperture surface energy (per unit area), γ_{LW} is the lamellar-aperture surface energy and F(h) is the energy of dislocation (per unit length) and $h = D_0/2$ is half of the thickness of the meniscus close to the aperture. $\xi_0 = \sqrt{\gamma/\rho g}$ is the capillary length, ρ is the density and g is the gravitational acceleration. This length can be very large (of the order of millimeters). Close to the aperture the dislocations are very close, interact strongly and the formula (6.17) may not be valid. That is why the smectic meniscus offers a very good opportunity to study the competition between gravitational forces and elastic interactions between dislocations. The system can also develop sharp step defects at the surface close to the aperture. These steps do not have to be related to dislocations inside the meniscus (see discussion on steps in Sec.II and droplets in Fig.10ab). The meniscus also plays an important role for explaining the tendency of the film to get thinner. Indeed, the pressure inside the film P is less than the athmospheric pressure, P_0 , because the meniscus is curved. The equilibrium condition at the surface gives $P - \sigma_{zz}^E = P_0$ and thus the layers are compressed. Consequently the film tends to get thinner. Let us assume that we have nucleated a dislocation loop, say by suddenly pulling a film. Then we find that the dislocation loop of size R and Burgers vector of length nd will spontaneously grow for $R > R_c = F(D/2)/((P_0 - P)nd)$. Here D is the thickness of the film.

Finally let us discuss the clustering of like dislocations (Fig.19ab) in a wedge shaped samples^{13,26,54,55}. Calculation of the energy in the case shown in (hatched region in Fig.19a) gives, for dislocations of Burgers vector nd:

$$E = 2E_0(n) + \frac{B(nd)^3}{12\alpha D},$$
(6.18)

where α is the wedge angle, and $E_0(n)$ is given by Eq(5.7) and D is the average thickness of the sample over a distance between the neighbouring dislocations. For the case shown in Fig.(19b) when dislocations are grouped in pairs of the doubled Burgers vector 2nd we find:

$$E = E_0(2n) + \frac{B(nd)^3}{3\alpha D},$$
(6.19)

where $E_0(2n)$ is given by (5.7). If $2E_0(n) > E(2n)$ then we find that dislocations form pairs for the angle, α , larger than the critical angle α_c ,

$$\alpha_c = \frac{B(nd)^3}{4D(2E_0(n) - E_0(2n)).}$$
(6.20)

Experimentally⁵⁴ one finds $\alpha_c \sim 10^{-3}$ when $D = 100\mu$ m and n = 1. Then from (6.20) we find $2E_0(n) - E_0(2n) \sim 10^{-3}K$, which means that $2E_0(n) \sim E_0(2n)$. Although they are not equal exactly as predicted by (5.10) they are very close, indeed. Certainly the small differences can come from the subtle changes in the core structure and/or anharmonic terms. Similar studies have been done for ferrosmectics⁵⁶.

VII. Edge profiles

Inserting h_{eq} into u_{eq} we get equilibrium distortions in the film; the edge profile at the interface is given by $u_{eq}(x, z = 0)$ (see Fig.7). The influence of the surface tension on the width of the profile is shown in Fig.20. Large surface tension broadens the edge profile^{22,48} and for a symmetric film of size D the width of the profile, Δx scales as ²² $\sqrt{\gamma D/B}$. Theoretical analysis^{22,48} explained qualitatively and quantitatively the results of $experiments^{21,22}$ performed on thin diblock copolymer films deposited on solid substrate. The comparison between the theory and experiment²³ is shown in Fig.21. The values of parameters obtained were as follows: $\gamma = 23.5 \text{ dyn/cm}^2$ (see also Ref.57), $\lambda = \sqrt{K/B} \approx d = 315\text{\AA}, \sqrt{KB} = 0.9$ dyn/cm, $\gamma/\sqrt{KB} \approx 26$. Also the scaling law for the width i.e. $\Delta x \sim \sqrt{D}$ has been verified experimentally. The same analysis has been also successfully applied to the analysis of the edge profiles in the smectic phase formed by main-side chain liquid crystal polymers deposited on a solid substrate 58,59 . In this experiment, the x-ray scattering has revealed the unsually large roughness at the surface⁵⁸. Then the scanning tunneling microscopy has shown the clear sign of steps at the free surface, an indication of dislocations inside the sample⁵⁹. The value of the parameters obtained in this experiments are as follows: $\gamma/\sqrt{KB} = 5$, $\lambda = \sqrt{K/B} = 101$ Å $\approx 5d$. The smectic length λ is much larger than the smectic period d, reflecting the fact that in the main-side chain liquid crystalline polymer we have two characteristic lengths. One is the size of the mesogenic unit related to d and one is the full length of the polymer chain related to λ . We also see that K increases with the length of the polymer.

So far we have assumed that steps at the free surface are due to dislocations inside the sample. However, it should be noted that steps at the surface do not have to be related to dislocations(Fig.22) and can have the same origin as steps in solids. Theoretically, the energy associated with a step⁶⁰ (Fig.14) is an order of magnitude larger than the one associated with the dislocation (Fig.7). The extra cost in the distortion energy per unit length shown in Fig.22. is $\Delta \gamma d/2$, where $\Delta \gamma$ is the surface tension difference for the PS and PBMA block of copolymer. It is roughly equal to 5ddyn/cm. At the same time the extra energy associated with dislocation is $\sqrt{KB}d/2$ which is equal to 0.5d dyn/cm. An order of magnitude difference clearly shows that the configuration with dislocations (Fig.7) is favored over the configuration with steps(Fig.22) in this particular system. Also TEM micrographs²² clearly show that under the step at the surface we have indeed edge dislocations. However as we have discussed in Section II in some cases the configuration with steps can have lower energy than the configuration with dislocations.

For small surface tension the edge profiles⁴⁹ strongly depends on K_s . Fig.23 shows the results for $\gamma = 0$. The most interesting feature of $u_{eq}(x, z = 0)$ is the nonmonotonic behavior of the profile as a function of x, observed for finite D. This is due to the finite size of the film and zero surface tension, since only in this case it is favorable to distort more the interface than the bulk. Large surface tension would make the profile perfectly monotonic. In very thin films we expect that the surface tension is important in determining the step structure when $\gamma \approx \sqrt{K_s B/D}$. In thick films the surface tension dominates when $\gamma \geq \sqrt{KB}$. We find that the width of the profile grows with increasing K_s .

VIII. Elastic interactions between dislocations

So far we have considered the properties of a single dislocation inside the system. Now let us consider two edge dislocations in the infinite system: one located at (x, z) = (0, 0) and one at (x, z) = (l, h). Since the equations for the displacement u are linear the total displacement, u_b due to dislocations 1 and 2 is the linear combination of individual displacements $u_b^{(1)}$ and $u_b^{(2)}$. The distortion energy can be conveniently written (using Eq.(5.3)) in the following form:

$$F_{b}(h,l) = E_{0}^{(1)} + E_{0}^{(2)} + \frac{1}{2}B \int dx \frac{\partial u_{b}^{(2)}(x,z)}{\partial z} \left(u_{b}^{(1)}(x,z=0^{-}) - u_{b}^{(1)}(x,z=0^{+}) \right) + \frac{1}{2}B \int dx \frac{\partial u_{b}^{(1)}(x,z)}{\partial z} \left(u_{b}^{(2)}(x,z=h^{-}) - u_{b}^{(2)}(x,z=h^{+}) \right)$$

$$(8.1)$$

Inserting the solutions obtained in section V we find^{10,19}

$$F_b(h,l) = E_0^{(1)} + E_0^{(2)} \pm \frac{\sqrt{KB}n^{(1)}n^{(2)}d^2}{4\pi} \int dq \exp\left(-\lambda q^2h\right)\cos\left(ql\right)$$
(8.2)

Here plus sign corresponds to like dislocations (same sign of the Burgers vector i.e. same sign in condition (5.6)) and minus sign to the unlike dislocations; $n^{(i)}$ i = 1, 2is the strength of the dislocations (see Eq(5.6)). The interaction energy is negligible for two edge dislocations located in the same plane (z = h = 0). Also for $l^2 \gg 4\lambda h$ the interactions are weak. Two like dislocations (same Burgers vector) always repel each other along the x direction ($\partial F_b/\partial l < 0$) and attract each other along the z direction only for $l^2 > 2\lambda h$ ($\partial F_b/\partial h > 0$). For $l^2 < 2\lambda h$ two like dislocations repel each other also along the z direction.

For two screw dislocations located at x = 0 and x = l one finds⁴³ that the interaction energy is zero in the harmonic approximation. If one includes anharmonic terms⁴⁶ in a simple perturbation scheme one finds that two screw dislocations interact with a logarithmic potential (per unit length of dislocation line):

$$F_b(l) = \pm 2 \left(B \frac{n^{(1)} n^{(2)} d^2}{4\pi^2} + K_3 \left(\frac{n^{(1)}}{n^{(2)}} + \frac{n^{(2)}}{n^{(1)}} \right) \right) \ln(l/r_0), \tag{8.3}$$

where r_0 is the larger core size of two screw dislocations. According to Eq(8.3) two screw dislocations of same sign (plus sign in Eq(8.3)) attract each other with the long range potential. Two screw dislocations of opposite sign (minus sign in Eq.(8.3)) repel each other preventing their annihilation. Although the procedure applied to this problem⁴⁶ casts some doubts on the full validity of this equation, nonetheless it shows that the complete role of the anharmonic terms in the theory of dislocations is not known.

So far we have considered the infinite system with no boundary effects. Here we go one step further and consider the finite symmetric system, bounded by two free surfaces (Fig.8a). The distortion energy is given by the bulk term (Eq.(5.4)) and two surface terms F_s (see Eq.(6.4)). Minimizing this energy we find Eq.(5.3) and two boundary conditions for each free surface (see Eq(6.5)). The solution is the sum of individual solutions (since the equations are linear). Because in our system $\gamma > \sqrt{KB}$ two edge dislocations are located in the same plane in the middle of the film and thus their bulk interactions are negligible. Now the only elastic interactions are surface induced. Inserting the equilibrium solution for two dislocations at a distance *l* apart we find the surface induced elastic interaction per unit length of dislocation:

$$F_s(l) = -\frac{\sqrt{KB}n^{(1)}n^{(2)}d^2}{(2\pi)^2} \int dq f(q)(1\pm e^{iql})$$
(8.4)

where the plus sign corresponds to like dislocations and minus to unlike dislocations.

$$f(q) = \frac{a_1(q)}{a_2(q) \exp(q^2 \lambda D) + a_1(q)}$$

and $a_1(q)$ and $a_2(q)$ are given by Eqs.(6.11-12). The total distortion energy for these dislocations is given by the sum of $F_s(l)$ and $F_b(h = 0, l)$ (Eq(8.4),Eq.(8.2)). For large α_s (how large α_s should be depends on the film thickness and the surface elastic constant, typically $\alpha_s > 2$ is sufficient) the interactions are repulsive for all distances for like dislocations and attractive for opposite dislocations. For $\alpha_s \gg 1$ we find from Eq.(8.4) the following form of the elastic interaction energy:

$$F_s(l) \approx \frac{\alpha_s \sqrt{KBn^{(1)}n^{(2)}d^2}}{16\pi\xi} (1 \pm \exp\left(-l/\xi\right)), \tag{8.5}$$

where $\xi = \sqrt{\alpha_s D\lambda/2} = \sqrt{\gamma D/2B}$ is proportional to the size of the edge profile as could be expected. We have neglected the bulk contribution to the interaction energy since at large l it decays as $\exp(-(l/d)^2)$. In the extreme limit of $\alpha_s \to \infty$ (which correspond to the system sandwiched between two walls) we find that this energy diverges for like dislocations. For large α_s we find for like dislocations:

$$F_s(l) = \frac{\alpha_s \sqrt{KB} n^{(1)} n^{(2)} d^2}{8\pi\xi} - B n^{(1)} n^{(2)} d^2 l / (8\pi D).$$
(8.6)

and for unlike ones:

$$F_s(l) = Bn^{(1)}n^{(2)}d^2l/(8\pi D).$$
(8.7)

As could be expected unlike dislocations attract each other while like dislocations repel each other in the system with large surface tension.

For small α_s , but still larger than 1, the behavior of $F_s(l)$ is more complex, than in the previous case. For like dislocations the potential is repulsive at shorter distances and attractive at larger distances, which results in the minimum of $F_s(l)$ roughly at $l \sim \sqrt{\lambda D} \approx d\sqrt{N}$ (D = Nd). For $\alpha_s = 1$ we find

$$F_s(l) \approx \frac{K_s n^{(1)} n^{(2)} d^2}{16 (\pi \lambda D)^{3/2}} \left(2 \pm \left(2 - \frac{l^2}{\lambda D} \right) \exp(-l^2/4\lambda D) \right)$$
(8.8)

This behavior of the interaction potential can be understood by comparing the edge profiles for large and small surface tension. In the former case the profile is a monotonic function of the distance (Fig.20) and like dislocations repel each other minimizing the free energy associated with the surface tension. In the case of small surface tension, surface energy associated with curvature dominates, the profiles become nonmonotonic functions (Fig.23) of the distance and like dislocations attract each other at large separations. For $\alpha_s \ll 1$ the attraction is even more pronounced.

Finally let us discuss the interactions between two screw dislocations in a finite system in a harmonic approximation. The solution given by Eq.(5.14) satisfies also the boundary condition (6.5) at the free surface. Thus we can use it for the calculation of the distortion energy in the system bounded by two free surfaces (Eq.(6.4)) The surface induced distortion energy per unit length is as follows:

$$F_{s}(l) = \gamma(n^{(1)})^{2} d^{2} / (\pi D) \ln (L_{\rho} / r_{c}^{(1)}) + \gamma(n^{(2)})^{2} d^{2} / (\pi D) \ln (L_{\rho} / r_{c}^{(2)}) \pm 2\gamma n^{(1)} n^{(2)} d^{2} / (\pi D) \ln (L_{\rho} / l)$$
(8.9)

Here L_{ρ} is the horizontal size of the system and D is the thickness of the film. Bulk terms (5.15),(5.16) and (8.3) are not included in Eq(8.9). The like screw dislocations repel each other and the unlike dislocations attract each other, contrary to the case of bulk induced interactions (8.3). In both cases the potential is long ranged and has the same logarithmic form. The bulk term (8.3) is much larger than the surface term even for very small $D \sim 10d$. However it should be noted that (8.3) has been obtained from the anharmonic terms. At the harmonic approximation the bulk interactions are zero and then (8.9) is the only contribution to the interaction potential.

IX. Fluctuations induced interactions between dislocations

Dislocations are low-dimensional manifolds just like strings⁶¹, membranes in solutions^{8,62}, steps at the solid-vacuum interfaces⁶³, polymers⁶⁴, interfaces⁶⁵ and domain walls in monolayers⁶⁶. This fact has not been fully recognized so far(see however^{7,67,68}). Here we would like to explore the consequences of the flexibility of dislocations on their behavior in finite lamellar films. Such studies are important for understanding the behavior of walls formed by dislocations in liquid crystals, diblock copolymers or lamellar phases of microemulsions, formation of meniscus in lamellar phases, interactions and mobility in systems of dislocations.

From the seminal work of Helfrich⁶² it follows that flexible strongly fluctuating objects such as membranes experience long range repulsive forces when brought together⁸. They are called undulation forces and arise from strong fluctuations and short range repulsion between the objects. In the case of membranes in aqueous solution this short range repulsion is due to the hydration forces⁶⁹. Here we shall provide the same analysis and discuss these forces for edge dislocations.

The single edge dislocation of length L_y located along the y axis and fluctuating in the x - y plane (Fig.24) in the bulk lamellar system can be described by the following elastic energy:

$$H_0 = \frac{1}{2} \int dy E_0 \left(\frac{\partial u_x}{\partial y}\right)^2,\tag{9.1}$$

where u_x is the displacement along the x direction (Fig.24), and E_0 is the line tension given by Eq(5.7). Due to strong fluctuations $\langle u_x^2 \rangle$ grows as the length of the dislocation L_y . However these fluctuations are damped in the presence of other dislocations. In a system of parallel dislocations located in the x - y plane and separated from one another by a distance l, the full elastic energy:

$$H = \frac{1}{2} \int dx dy \left(\frac{E_0}{l} \left(\frac{\partial u_x}{\partial y} \right)^2 + B_0 \left(\frac{\partial u_x}{\partial x} \right)^2 \right), \tag{9.2}$$

where the dislocation compressional modulus $B_0 = (3\pi k_B T)^2/(16E_0 l^3)$ arises self consistently from the fluctuation free energy, in the same way as in a stack of membranes⁶². Here *l* is the average separation of edge dislocations. Following Helfrich⁶² we find, using Eq(9.2), the undulation interactions per unit length, between the dislocations:

$$F_H(l) = \frac{3\pi^2 (k_B T)^2}{32E_0 l^2} \tag{9.3}$$

Eq(9.3) differs from Helfrich result only by a numerical factor. As we discussed above, short range repulsion must be present in the system in order for the Helfrich mechanism to hold. In general the source of the short range repulsion can come from the core structure. The edge dislocation with the core splitted into two disclinations (Fig.4c) is indeed characterized by large core energy and complex core structure and consequently two such dislocations of opposite or same Burgers vectors might repel each other at short distances.

The fluctuations of the screw dislocations are more subtle than those of edge dislocations. In particular the line tension is not equal to the energy of a straight screw dislocation per unit length (compare Eq(5.19-20)), but is much larger⁴⁴. The crucial point here is that in the process of deformation the screw dislocation aquires an edge character. This is the main source of the large configurational tension given by Eq(5.20).

X. Unbinding transition for edge dislocations

Our strongly fluctuating objects can also attract each other (e.g. membranes interact via the van der Waals potential) and at large distances this interaction may compete with undulation forces. At sufficiently low temperatures or sufficiently strong attraction the fluctuating objects stay close minimizing their energy. When the temperature is raised or attraction weakened they separate, maximizing their entropy. The transition from the bound to the free state is called the unbinding transition⁷⁰. As follows, there are three elements necessary to induce unbinding transition: strong fluctuations of objects, short range repulsive forces and sufficiently strong attraction between the objects at large distances. We have already discussed them in the previous sections. Here we will show that edge dislocations can undergo the unbinding transition at suitable conditions⁷¹.

Since for opposite dislocations the elastic interaction (Eq(8.7)) is attractive, this competes with the Helfrich repulsion given by Eq(9.3). In the extreme limit of $\alpha_s \to \infty$ (which correspond to the system sandwiched between two walls) we find that, as a result of this competition, the opposite dislocations are stabilized at the distance, $l_{eq} = \pi((3(k_BT)^2D)/(2d^2BE_0))^{1/3}$. This distance corresponds to the minimum of the sum of undulation and elastic interactions $F_H(l) + F_s(l)$ (here for simplicity we assumed $n^{(1)} = n^{(2)} = 1$). One finds for the typical values of the smectic parameters and $D = 100\mu$ m that this distance is very small, i.e. $l_{eq} = 100$ Å. It is understandable that we cannot expect an unbinding transition in this case, since in the limit of hard walls the elastic interactions grow linearly as a function of l. For finite α_s , although in principle the unbinding transition would be possible in thin films, we find for typical smectic liquid crystal parameters ($\gamma = 30$ dyn/cm, $\sqrt{KB} = 6$ dyn/cm, $k_BT = 4 \cdot 10^{-14}$ erg (room temperature), $\lambda = d =$ 30Å) that it does not occur. For all film thicknesses the opposite dislocations are stabilized at finite separations, providing that the Helfrich mechanism holds in their case. In general these results tell us that in the case of large surface tension elastic interactions are much stronger than the Helfrich repulsion.

For small surface tension (comparable to \sqrt{KB}) the undulation interactions (Eq.(9.3)) compete with the attractive potential for like dislocations (Eq(8.8)) in thick films (large D). As the thickness of the film is increased the undulation interactions win and the unbinding transition occurs.

In our calculations we have used the same parameters as above, assuming $\alpha_s \approx 1, 2 > K_s/(Kd) > 1$ and $n^{(1)} = n^{(2)} = 1$. We have also assumed $r_c = d$ and $E_c = \sqrt{KB}d^2/(2r_c)$.

We have noted that practically for $\alpha_s > \alpha_s^* = 1.5$ no bound states for dislocations exist for any film thicknesses (for $K_s/K = 1$). This critical value of α_s^* depends on the surface bending elastic constant e.g. for $K_s/Kd = 10$ we find $\alpha_s^* = 4$.

In Fig.25 the plot of $F(l) = F_s(l) + F_H(l)$ versus l is shown for three film thicknesses (N = 30,40 and 54) (D = Nd). As the thickness of the film is increased the value of the energy at the minimum at $l_0 \approx 3d\sqrt{N}$ approaches zero. The unbinding transition for $K_s/Kd = 1$ and $\alpha_s = 1$ takes place at N = 54, when $F(l_0) = F(\infty)$. For thicker films (N > 54) the dislocations are free. For thinner films (N < 54) they are bound.

In Fig.26 we show the diagram of K_s/Kd versus N. The dotted line separates the regions where the unbound state is expected from the one where the dislocations are bound. For large surface bending elastic constant we find the unbinding transitions at larger thicknesses of the film. On the contrary for larger surface tensions we find the unbinding transition takes place for thinner films (Fig.27).

One notes that the transition is extremely sensitive to the value of the surface tension for $\gamma \approx \sqrt{KB}$. Changing it by 1% we get the decrease of N by a factor of 2. We can check that at the room temperature changing the temperature by one degree upwards decreases the thickness at which the unbinding transition takes place (for $\alpha_s = 1, K_s/Kd = 1$) from N = 54 to N = 52. Therefore there are four parameters which affect the unbinding transition: surface tension, surface bending elastic constant, film thickness and temperature. All of them can be controlled, and so our results can be tested experimentally, especially that the number of soft condensed matter systems characterized by small surface tension is quite large.

XI. Unbinding transition for dislocation loops

Dislocation loops in bulk smectic systems have been first studied by Kléman⁷². Later Helfrich⁶⁷ argued that the nematic-smectic (NA) phase transition in liquid crystals could be initiated by the unbinding of dislocation loops. The mechanism would be similar to the one proposed by Kosterlitz and Thouless (KT) for the phase transitions in two dimensions⁷³. As shown by Nelson and Toner⁶⁸ the smectic with unbound loops behaves like a nematic. The estimate of the transition temperature in the loop mechanism is simple and similar to the KT estimate. The free energy of the loop in the bulk has the following form:

$$F_{loop} = F_c L - k_B T \frac{L}{d} \ln p, \qquad (11.1)$$

where L is the total length of the loop, F_c is the self energy of the loop per unit length and p is the number larger than one (for the problem considered on the lattice this number would be close to the coordination number of the lattice). Here $k_B(\ln p)/d$ is the entropy of the loop per unit length; we count the number of loop configurations and neglect the entropy of placing and closing the loop. The latter is proportional to the log of the size of the loop and in general controls only the density of loops but does not influence the transition temperature,

$$T_{NA} = F_c d/(k_B \ln p).$$
 (11.2)

At this temperature F_{loop} changes sign and the spontaneous growth of loops occurs. Then, according to Nelson and Toner, the layered smectic structure is destroyed. A very instructive approach to this problem can be found in Ref.7. Here we shall estimate the influence of the boundaries on the loops, their growth and size.

Let us consider a smectic liquid crystal film of thickness D, bounded by two surfaces located at $z = \pm D/2$, with a single circular dislocation loop of radius Rlocated in the middle of the film at z = 0. The loop is described by the following condition for the vertical displacement, $u(\mathbf{r}_{\perp}, z)$, of smectic layers:

$$u(\mathbf{r}_{\perp}, z = 0) = \begin{cases} 0, & \text{if } |\mathbf{r}_{\perp}| \ge R;\\ \operatorname{sgn}(z)d/2, & \text{if } |\mathbf{r}_{\perp}| < R. \end{cases}$$
(11.3)

Since in the smectic liquid crystal the surface tension is larger than \sqrt{KB} ($\alpha_s > 1$) the dislocation loop is stabilized in the middle of the film. The solution of Eq(5.3) consistent with the condition (11.3) and satisfying the boundary condition (6.5) (and similar condition for the second surface obtained from (6.5) by changing the sign of z). is given by $u_{eq}(\mathbf{r}_{\perp}, z)$,

$$u_{eq}(\mathbf{r}_{\perp}, z) = u_b(\mathbf{r}_{\perp}, z) + u_p(\mathbf{r}_{\perp}, z)$$
(11.4)

where 72

$$u_b(\mathbf{r}_{\perp}, z) = \operatorname{sgn}(z) \frac{dR}{4\pi} \int d\mathbf{q}_{\perp} \exp\left(-\lambda q^2 |z|\right) \frac{\exp\left(i\mathbf{q}_{\perp}\mathbf{r}_{\perp}\right)}{q} J_1(qR)$$
(11.5)

 and^{74}

$$u_p(\mathbf{r}_{\perp}, z) = \frac{dR}{4\pi} \int d\mathbf{q}_{\perp} \frac{\exp\left(i\mathbf{q}_{\perp}\mathbf{r}_{\perp}\right)}{q} J_1(qR) \left(\exp\left(\lambda q^2 z\right) - \exp\left(-\lambda q^2 z\right)\right) f(q).$$
(11.6)

Here $q = |\mathbf{q}_{\perp}|$ and f(q) is defined after Eq(8.4). Inserting our solution into the distortion energy $F_b + F_s$ (Eq(5.4,6.4)) we find the distortion energy of the smectic film of thickness D with the circular dislocation loop of radius R in the middle of the film:

$$F(D,R) = 2\pi R E_c + \sqrt{KB} d^2 \frac{\pi}{2} R^2 \int_0^{2\pi/r_c} dq q J_1^2(qR) -2\sqrt{KB} \pi d^2 R^2 \int_0^{\infty} dq q J_1^2(qR) f(q)$$
(11.7)

In the limit of $R \gg d$ we find the following form of the distortion energy $F_c(D)$ per unit length as a function of the film thickness, D:

$$F_c(D) = \lim_{R \to \infty} \frac{F(D, R)}{2\pi R} = E_c + \frac{\sqrt{KB}d^2}{2r_c} - \sqrt{KB}d^2 \int_0^\infty dq f(q).$$
(11.8)

The first two terms of the energy are associated with the bulk distortions (Eq(5.7)) and do not depend on the surface tension or the film thickness. In fact they are the same as for the edge dislocation. Thus the local distortions induced by a large dislocation loop are the same as the ones induced by an edge dislocation. The sum of E_c and $\sqrt{KB}d^2/2r_c$ is equal to F_c (Eqs(11.1,2)). The last term in Eq(11.8) is associated with the finite size of the system and the surface tension. In the limit of $D \to \infty$ it vanishes and consequently $F_c(D)$ approaches F_c as it should. In order to estimate the NA transition temperature as a function of the film thickness we use $F_c(D)$ in Eqs(11.1,2). In general, p should also change with D. For thin films this number should be close to 4 (coordination number for the two dimensional square lattice) while for thick ones it will be close to 6. Here we neglect this contribution to Eq(11.1). From Eqs(11.1,11.8) we find that 48,74 :

$$\frac{T_{NA}(D) - T_{NA}(\infty)}{T_{NA}(\infty)} = \frac{\sqrt{KB}d^2}{\sqrt{\lambda D}F_c}C(\alpha_s, K_s/(KD)).$$
(11.9)

where

$$C(\alpha_s, \eta) = -\int_0^\infty dq \frac{(1 - \alpha_s - \eta q^2)}{(1 + \alpha_s + \eta q^2)e^{q^2} + (1 - \alpha_s - \eta q^2)}$$
(11.10)

and $T_{NA}(\infty)$ is given by Eq(11.2). The function $C(\alpha_s, K_s/KD)$, depends on $K_s/(KD)$ very weakly, thus the dominant dependence of $T_{NA}(D)$ on D is $1/\sqrt{D}$. For $\alpha_s = 5$ (typical for smectic liquid crystal⁵¹) we find C=1.25. For the purpose of rough estimate we neglect the core energy E_c and set C = 1 in Eq(11.9), finding:

$$\frac{T_{NA}(D) - T_{NA}(\infty)}{T_{NA}(\infty)} = \frac{2r_c}{\sqrt{\lambda D}}.$$
(11.11)

The transition temperature is larger in thin films than in the bulk, thus the smectic phase is stabilized in films and near free surfaces. The large surface tension and finite size effects are responsible for this behavior. For three layer film, D = 3d, $\lambda \approx d =$ 30\AA , and the core radius r_c equal to the width of the molecule, $r_c \approx 3\text{\AA}$ (chosing the smallest length scale in the problem is consistent with $E_c = 0$; usually it is assumed that $r_c \approx d$; however we may encounter situations when the size of the core can be smaller³⁹ or larger (see Fig.4b)), the transition temperature can be shifted by tens of degrees upwards in comparison to the bulk. It means that it should be relatively easy to overheat a smectic film. It must be realized however, that for large temperature shifts it is not justified to neglect the temperature dependence of the smectic elastic constants.

Growth of the dislocation loops is only one particular mechanism of the nematic smectic phase transition. However it can be preempted by some other mechanisms⁷. In thin films different mechanisms can be characterized by different temperature dependence on D. For the loop unbinding mechanism we have already obtained $\delta T_{NA} = (T_{NA}(D) - T_{NA}(\infty))/T_{NA}(\infty) \sim 1/\sqrt{D}$. For the 3D XY universality class⁷⁵ $\delta T_{NA} \sim D^{-1/\nu}$ with⁷⁶ $\nu \sim 0.7$, by comparing the correlation length to the thickness of the film. Finally for the first order phase transition we find⁷⁷ $\delta T_{NA} \sim 1/D$. Since for each model of NA transition we find different behavior of $T_{NA}(D)$, this temperature can serve as yet another test for the order and mechanism of NA transition.

So far we have tacitly assumed that γ is finite. If we set $\gamma \to \infty$, the surfaces become rigid and we obtain the film sandwiched between solid boundaries. The distortion energy of the loop located between solid boundaries is proportional to the area of the loop, contrary to the previous case of the freely suspended film when the loop distortion energy has been proportional to the length of the loop. Since F(D, R) grows now as R^2 while the entropy still as R, we conclude (see Eq(11.1)) that the loop mechanism is supressed in this case for any finite D. Now let us estimate the size of the loop in the film contained between solid boundaries. At $T > T_{NA}(\infty)$ the loop can grow up to the point when F_{loop} changes sign from negative to positive. This happens for the finite radius of the loop, R_{eq} . For $D, R \gg d$ and $\gamma \to \infty$ we can make the following approximations:

$$-\int_0^\infty dq q \mathcal{J}_1^2(qR) f(q) \approx \frac{A}{\lambda D},\tag{11.12}$$

and

$$\int_{0}^{2\pi/r_{c}} dq q \mathcal{J}_{1}^{2}(qR) \approx \frac{2}{Rr_{c}}.$$
(11.13)

Here $A \approx 0.5$ is a constant. Now using Eq(11.1) and Eqs(11.7,8) we find that $F_{loop} = 0$ at R = 0 and at

$$R_{eq} = \frac{\lambda DF_c}{A\sqrt{KB}d^2} \frac{T - T_{NA}(\infty)}{T_{NA}(\infty)}$$
(11.14)

As we see for $D \to \infty$ we get $R_{eq} \to \infty$. Certainly before R_{eq} could grow to infinity the smectic phase would undergo a transition to the nematic phase. The mechanism of this phase transition would be different from the loop unbinding mechanism. However in the overheated smectic between solid boundaries one should observe the loops of size given by Eq(11.14).

Our approach to the loop deformations neglected completely the fact that the loop can have an edge as well as screw parts. Certainly for large thicknesses of the film the screw character of the loops should be visible⁷⁸. In the experiments conducted on lamellar phases of non-ionic surfactants the density of loops increased at the approach to the isotropic-lamellar phase transition⁷⁸. In fact large number of dislocation loops and their interactions might modify the transition temperature. This is not taken into account in our approach.

XII. Dynamical properties of dislocations: mobility

Dislocations can move inside a sample under the action of an external stress or stress created by **another** dislocation. Let σ^E be this stress (excluding the stress created by the dislocation itself). The force \mathbf{F}^E acting on the dislocation (per unit length) can be calculated similarly as in solids from the Peach Koehler formula³³:

$$\mathbf{F}_{i}^{E} = \epsilon_{ikl} \sigma_{lm}^{E} b_{m} t_{k} \tag{12.1}$$

where **b** is the Burgers vector of the dislocation (of length $|\mathbf{b}| = nd$) and **t** is the unit vector along the dislocation line. The stress tensor is given by Eqs.(4.6-8) (see also Ref[43]). This force sets the dislocation in motion. If the dislocation moves slowly with respect to the sound velocity the effective inertial forces can be neglected, since the effective mass is very small in this case (typically a row of molecules). Thus the equation of motion can be simplified to the following form:

$$\mathbf{F}^E + \mathbf{F}^V = 0, \tag{12.2}$$

where \mathbf{F}^{V} is the viscous force (section IV). Now based on Eq(12.2) we can discuss the motion of screw and edge dislocations. Since the distiction between these two types of dislocations are more pronouced in smectics than in solids we shall consider their mobility separately. Let us first consider the edge dislocations. There are two basic kinds of motion: the glide and climb. The former is perpendicular, while the latter is parallel to the layers. These two kinds of motion are different: glide is conservative, while climb requires transport of matter by diffusion (permeation). In solids glide is favored and in fact is responsible for plastic deformations at low temperatures ($T < T_m/2$; T_m is the melting temperature). By contrast climb seems to be favored in smectics (at least in thermotropic smectics) and can be induced by the compression or dilation of layers while glide requires bending of the layers. Let us first consider the climb motion of an edge dislocation in a smectic system submitted to the normal stress $\sigma_{zz}^E = \sigma$ (Fig.28). The force acting on the dislocation of Burgers vector length $|\mathbf{b}| = nd$ is (Eq(12.1)):

$$F^E = -\sigma nd, \tag{12.3}$$

while the friction force is

$$F^V = -\frac{ndv}{m}.\tag{12.4}$$

From Eq(12.2) we find the velocity:

$$v = -m\sigma, \tag{12.5}$$

where m is the mobility of the dislocation, a priori being a function of the velocity, the length of the Burgers vector, nd, and the material constants. The mobility of an elementary dislocation⁷⁹ is related to the self diffusion coefficient, D_{\parallel} , for thermotropic smectics assuming that the mean distance between jogs, l, along the line is comparable to the molecular size. This assumption is reasonable in thermotropic smectics and gives with analogy to solids (metallurgical model):

$$m \approx \frac{D_{\parallel} v_{\rm mol}}{k_B T l}.$$
(12.6)

Here $v_{\rm mol}$ is the molecular volume and $l \sim d$. This model is not correct for giant dislocations, especially those with core splitted into two $\pm 1/2$ disclinations. In this case it is better to assume that the dislocation acts as an obstacle of width *nd* perpendicular to layers (Fig.29). The flow of a smectic around such a ribbon leads to four permeation boundary layers in which dissipation occurs due to permeation^{80,81}. A calculation of dissipation gives the force of friction acting on the ribbon and the following expression for the mobility of the dislocation:

$$m = \sqrt{\frac{\lambda_p}{\mu}},\tag{12.7}$$

where λ_p is the permeation coefficient and μ is the shear viscosity (see section IV). A more sophisticated calculation⁸² taking into account deformations of the layers and assuming strong permeation $(l_p = \sqrt{\lambda_p \mu} > \lambda = \sqrt{K/B})$ gives the following formula:

$$m = A \frac{\lambda}{d} \sqrt{\frac{\lambda_p}{\mu}},\tag{12.8}$$

where A is a numeric factor of the order of one. The mobility does not depend on the Burgers vector nor on the velocity, due to the fluidity of the layers. The two formulas (12.6) and (12.8) are compatible since $\lambda_p \sim D_{\parallel} v_{\rm mol} / k_B T$ (section IV) and $\mu \sim k_B T / l D_{\parallel}$.

Let us now describe the glide motion of an edge dislocation. In this motion, the dislocation moves perpendicularly to the layers (Fig.30). Two cases must be considered. Below the Peierls-Nabarro stress the dislocations remain pinned in its Peierls valley (at zero temperature). For smectics this stress has been calculated by Lejcek ⁸³:

$$\sigma_{PN} = \frac{3}{4} B \sqrt{\frac{2\pi\lambda}{r_c}} \exp\left(-\pi r_c/nd\right).$$
(12.9)

The process of glide must be thermally activated for $\sigma_{zz}^E < \sigma_{PN}$. It requires the formation of small bulges (Fig.31) which can afterwards spread sideways. For stresses larger than σ_{PN} dislocations can glide easily and the mobility is⁸⁴

$$m = \frac{16r_c \sqrt{\pi \lambda r_c}}{\mu n d(1 + 3\lambda/(2r_c))}.$$
 (12.10)

The glide mobility is of the same order of magnitude as the climb mobility Eq.(12.8). The more dissociated the core is (r_c large, Fig.4b) the easier glide proceeds (large mobility). However for the giant dislocations with core splitted into $\pm 1/2$ disclinations the glide is much more difficult than climb, since the core is extended along the x direction.

To finish this section let us give the mobility of screw dislocations. These defects can easily glide without the layer resistance. The mobility is given by the following formula:

$$m = \frac{8\pi^2 r_c^2}{\mu n d}.$$
 (12.11)

The motion of the screw dislocation is conservative and thus permeation is negligible. The friction force is due to the viscosity of the medium μ .

XIII. Microplasticity and helical instability of screw dislocations

Experimentally we can reveal the dynamical properties of dislocations by compressing a homeotropic wedge sample (see section II) and recording its viscoelastic response. More precisely one can impose a step like variation or a sinusoidal variation of the thickness with piezoelectric ceramics and measure the normal stress as a function of time. The first experiment of this type was performed by Bartolino and Durand⁸⁵ in smectic-A liquid crystal. By applying very small thickness variation (a few Å or less) they showed for the first time the elastic behavior of smectics in compression normal to layers and its plastic relaxation in time. Ribotta also studied with this system the undulation instabilities of layers in dilation and their subsequent instabilities leading to focal parabolas^{34,86}. In order to study dislocationsand plasticity a new cell with stackings of piezoelectric ceramics, allowing for much larger deformations, was used⁸⁷. The step like thickness variations (ranging from d to 10d typically) and the normal stress as a function of time are shown schematically in Fig.32ab. The stress first jumps abruptly to $\sigma_0 \approx B\delta_0/d$ (elastic regime) and then relaxes exponentially to zero with the characteristic time τ . This time depends on the initial stress⁸⁸ (Fig.32c) and decreases by successive jumps with the increase of σ_0 . Each jump is associated with the change of the thickness by $N_p = pN_1$ layers (p is the index of the jump) and by the relaxation time τ_p defined by:

$$\frac{1}{\tau} = \frac{1}{\tau_g} + \frac{1}{\tau_p}.\tag{13.1}$$

The time τ_g is the relaxation time at small deformations. The experiment shows that $N_1 \sim 3$ independent of the thickness of the sample D and the angle α between the plates. One finds from the experimental results that $\tau_g \sim D/\alpha$ and $\tau_p \sim D/p$, where p is the index of the jump (Fig.32c). Also τ_p is independent of α . Two relaxation mechanisms are involved in the observed phenomena. The first one is the motion of edge dislocations which are present in the sample because of the wedge geometry. The relaxation time for this motion is

$$\tau_g = \frac{D}{mB\alpha} \tag{13.2}$$

proportional to D/α in agreement with experiment. From (13.2) we can extract the mobility. For 8CB at room temperature one finds $m \sim 5 \cdot 10^{-7} \text{cm}^2 \text{s/g}$ and from Eq.(12.7) we calculate $\lambda_p \approx 5 \cdot 10^{-13} \text{ cm}^2/\text{poise}$ ($\mu \approx 2\text{poise}$). This gives $l_p = \sqrt{\mu \lambda_p} \approx 10$ Å. This length is of the order of molecular size as expected from Eq.(12.6) and Einstein relation for viscosity.

The second mechanism which explains the jumps of the relaxation time is the sudden instability of screw dislocations under the applied deformation⁴⁴. If

$$\sigma_0 > p \frac{2\pi T_{\text{screw}}}{D} \tag{13.3}$$

then, each elementary screw dislocation (n = 1) joining two plates (and anchored to them) is unstable with respect to the formation of a helix of pitch D/p. This helical shape is equivalent to the removal (under compression) of p layers inside the cylinder in which the screw dislocation is located. (Fig.33). That is why the relaxation time is inversely proportional to the jump order p. Finally we can use the formula for N_1 :

$$N_1 = 2\pi \frac{T_{\text{screw}}}{Bd^2} \tag{13.4}$$

to estimate E_c using the theoretical value of T_{screw} (5.19-20). One finds $E_c \simeq 0.1Bd^2$. This value of the core energy is compatible with the one obtained for the core filled with nematic. The relaxation time associated to jump p can also be calculated:

$$\tau_p \simeq \frac{d^2 D}{2\pi^2 m T_{\text{screw}} p} \tag{13.5}$$

where m is the screw dislocation mobility given by Eq.(12.11). From Eq(13.5) and τ_p measurements we find $m \sim 10^{-6} \text{cm}^2 \text{s/g}$ in agreement with Eq(12.11).

So far we have assumed that both relaxation processes are independent, but we know that edge dislocation must cross the screw dislocation in the process. This crossing leads to the formation of the jogs on the edge dislocation (Fig.34). The jog has the screw character so its energy (Eq(5.15)) is

$$E_{\rm jog} \sim \frac{Bd^3}{64\pi^3} \tag{13.6}$$

assuming n = 1 for both dislocations and $r_c = \lambda = d$. Experimentally $B \sim 5 \cdot 10^7 \text{dyn/cm}^2$ and $d \sim 30 \text{Å}$, thus $E_{\text{jog}} \sim 10^{-2} k_B T$. This jog can be very easily thermally activated thus elementary dislocations can very easily cross. Also two edge dislocations interact only when they are in the same slip plane which is rarely the case, consequently each dislocation moves independently from the other dislocations, contrary to the case of dislocations in solids. Of course once again fluidity of the layers is responsible for this behavior of dislocations. Finally, one may ask why helical instability of screw dislocation is more favorable than the nucleation ex-nihilo of dislocation when it aquires a helical shape of radius R is $2\pi R \times \pi R/D$, whereas the nucleation of the dislocation loop of equivalent radius requires to make a length $2\pi R$ of edge dislocation. The helical instability is thus much more favorable energetically than the nucleation ex-nihilo of dislocation ex-nihilo of dislocation.

Dislocations may also play an important role in the process of growth. This has been observed at the smectic A-smectic B interface. When the smectic B grows from the undercooled smectic A, it generates stresses that are mainly relaxed by the motion of dislocations in the smectic A phase. This phenomenon is detectable owing to the entrapment of dust particles which are dragged away when they climb parallel to the layers. If the growth rate is too large, then dislocations may no longer relax the stresses efficiently and then smectic A breaks with the formation of many focal conic domains⁸⁴.

So far we have considered measurements performed on smectic liquid crystals. Similar measurements have been done for self assembling amphiphilic systems of $C_{12}E_5$ (pentaethylene glycoldodecyl ether) and water. Surprisingly this lamellar system orients very easily and spontaneously in homeotropic anchoring. For example few minutes are enough to obtain a good homeotropic sample without visible defects, whereas several weeks of annealing are necessary to obtain similar results with phospholipid lamellar phase²⁶. This simple observation shows that permeation is much faster in $C_{12}E_5$ than in usual lyotropic systems, the fact also confirmed by the direct measurements of the edge dislocation mobility⁸⁹. The mobility has been found of the same order of magnitude as in thermotropic liquid crystals considered previously in this section. The screw dislocations are very numerous in this lyotropic system⁹⁰ and presumably they favor permeation. In fact it was shown that these defects act as vortices when a pressure gradient is imposed perpendicularly to the layers. This mechanism leads to the effective permeation coefficient⁹¹

$$\lambda_p = \frac{A(nd)^4}{\mu L^2} \tag{13.7}$$

where L is the mean distance between dislocations and

$$A = 0.07 + 0.009 \ln L/r_c. \tag{13.8}$$

Finally we note that dislocations strongly affect flows as will be shown in the next section.

XIV. Lubrication⁹²

It is well known that lamellar phases are very good lubricants. As an example one can cite soaps, graphite, and also lamination oils, which under high pressure and temperature acquire a lamellar structure. In the classical theory, lubrication occurs when a fluid is sheared between two planar surfaces making a small angle α . The lubrication force is due to the increase of pressure in the locally compressed fluid. By replacing the isotropic fluid with smectic A one expects similar, but more spectacular effects, since apart from the easy flow of the layers past each other, there is a genuine solid like strength perpendicular to layers. Fig.35 shows the lubrication geometry. The sample is sandwiched between two plates with homeotropic anchoring at an angle α . In this sample as we know there is an array of dislocations at a mean distance d/α . At time t = 0 the upper slide starts to move with the horizontal velocity v. At time t the thickness of the sample has varied perpendicularly to a fixed position by an amount $\Delta D = -vt\alpha$, which is positive (dilation) when v < 0and negative (compression) when v > 0. This thickness variation creates a normal stress σ_{zz}^E which makes the edge dislocations to climb together in a direction which favors the relaxation of the imposed deformation. The dislocations are dragged by the flow with velocity v/2 at time t = 0 and then progressively slow down until they stop in the stationary regime $(t \to \infty)$. A direct calculation of the normal stress gives:

$$\sigma_{zz}^{E} = -\frac{v}{2m} \left(1 - \exp\left(-t/\tau_{g}\right) \right), \tag{14.1}$$

with τ_g given by (13.2). The stress exerts a normal force on the slides, which adds to the one exerted by the hydrostatic pressure. Both terms can be calculated in the limit of a very small angle α . In the limit $t \gg \tau_g$ one finds⁹² the force per unit length

$$F_n = F_{\text{hydrostatic}} + F_{\text{smectic}} = \frac{1}{2}\mu \left(\frac{L}{D}\right)^3 v\alpha + \frac{Lv}{2m}.$$
 (14.2)

Here L is the horizontal size of the sample. The first term is related to the hydrostatic pressure and is always present, even for isotropic lubricants, whereas the second one is specific for layered structures. In fact the second term can be much larger than the first one. We estimate $F_{\text{hydrostatic}} = 10^3 v [\text{dyn s/cm}^2]$ and $F_{\text{smectic}} = 10^6 v [\text{dyn s/cm}^2]$, assuming L = 2 cm, $D = 200 \mu \text{m}$, $\mu = 1 \text{poise}$, $\alpha = 2 \cdot 10^{-4}$ and $m = 10^{-6} \text{cm}^2 \text{ s/g}$. Since the normal force is three orders of magnitude larger in the case of smectics it means that smectics better keep the two moving surfaces apart and consequently are better lubricants than an ordinary fluid of the same viscosity. Of course the full comparison of the lubrication properties involves the calculation of the force of friction. Assuming simple flow pattern $v_x = vz/D$ we

find the force of friction (per unit length)

$$F_{\rm friction} = -\mu \frac{vL}{D} - \frac{\alpha L v}{4m}, \qquad (14.3)$$

and therefore the smectic behaves as a fluid with apparent viscosity

$$\mu_{\rm app} = \mu + \frac{\alpha D}{4m} \simeq \mu + \frac{\alpha D\mu}{4l_p}.$$
(14.4)

Thus the corrections to viscosity μ can be very significant even for very small angles $\alpha,$ because D is much larger than the permeation length $l_p \sim d$ (see section XII before Eq.(12.8)). For instance $\mu_{app} = 5\mu$, when $\alpha = 2 \cdot 10^{-4}$ rad, $D = 200\mu$ m and $l_p = 25$ Å. This larger viscosity is of course not favorable for lubrication. Another consequence of this calculation is that lubrication effects must be taken into account when one measures the shear viscosity with rheometer. Nevertheless, it is possible, at certain conditions, to completely eliminate the lubrication effects and to measure the intrinsic shear viscosity of the sample. Even in this limit, the viscosity appears to be strongly dependent on the shear rate S = v/D; large at small S, μ_{app} approaches μ at large S (Fig.36). Careful observations of the motion of dust particles in the samples show that the viscosity increase at smaller shear rates is related to strong departure from the linear velocity profile (Fig.37). In order to explain the rigidification of the velocity profile in the middle of the sample a mechanism of strong interaction between screw dislocation and the flow has been proposed⁹³. Their stationary shape can be obtained by comparing the viscous torque that the flow exerts on the line with the elastic torque due to the line tension. The dislocations bend while acquiring a mixed character and tend to occupy a finite fraction of the whole thickness of the sample, when the shear rate becomes larger than the critical shear

$$S_c = \frac{16Bd^2}{\mu D^2} \approx \frac{16K}{\mu D^2}.$$
 (14.5)

The larger the shear rate the thinner is the zone where the flow is rigidified (small velocity) (Fig.37). At very large S a dislocation is completely stretched and do not longer contribute to the total dissipation. In this limit the apparent viscosity μ_{app} is equal to the intrinsic viscosity μ . This model allowed us to explain most of the experimental results and to estimate the density of screw dislocations (10^6cm^{-2}) in usual sample of thermotropic smectic liquid crystals⁹⁴.

Summary

In this review paper we have tried to summarize the progress in the theory of dislocations which took place in the recent decade. Both equilibrium and nonequilibrium, bulk and surface properties have been discussed. It has been shown that theoretical and experimental studies are very closely related in this field and that many interesting aspects of the behavior of dislocations can be studied experimentally. Many properties of dislocations in smectics are very much different from those of solids. We have tried to emphasize all the differences. In general we can say that smectics have certain solid like and liquid like properties combined in the very unsual way and in this review we have shown how the solid-like and liquid-like behavior of smectics influences dislocations.

Acknowledgements

We are grateful to CNRS for making our collaboration possible. This work has been also partially supported by KBN under grants 2 P 30219004 and 2 P30302007. RH. acknowledges the hospitality of Ecole Normale Superieure.

References

- J.Weertman and J.R.Weertman, *Elementary Dislocation Theory*, (Oxford University Press, New York, Oxford, 1992).
- 2. D.Hull, Introduction to Dislocations, (Pergamon Press second ed. 1975).
- 3. see e.g. S.Amelinckx, Acta Metall 6, 34 (1958).

- 4. see e.g. S.Amelinckx and W.Dekeyser, Solid State Physics 8, 327 (1959).
- G.Gompper and M.Schick, Self-Assembling Amphiphilic Systems in Phase Transitions and Critical Phenomena eds. C.Domb and J.L. Lebowitz vol. 16 (Academic Press, 1994).
- 6. F.S.Bates and G.H.Fredrickson, Annu.Rev.Phys.Chem. 41, 525 (1990).
- P.G. de Gennes and J.Prost, *Physics of Liquid Crystals*, (Clarendon Press, Oxford 1993).
- 8. D.Roux and C.R.Safinya, J.Phys. (France), 49, 307 (1988).
- Y.Bouligand, in *Physics of Defects*, Les Houches, ed. Balian et al. (North Holland Publishing, 1981).
- 10. S.Chandrasekhar and G.S.Ranganath, Adv.Phys. **35**, 507 (1986).
- 11. M. Kléman, Rep.Prog.Phys., **52**, 555 (1989).
- 12. P.G. de Gennes, C.R. Acad.Sci. Paris 275B, 939 (1972).
- 13. R.B.Meyer, B.Stebler and S.T.Lagerwall, Phys.Rev.Lett. 41, 1393 (1978).
- M. Kléman, C.Colliex and M.Veyssie in *Lyotropic Liquid Crystals*, ed S.Freiberg p. 71 (1976).
- 15. S.A. Asher and P.S.Pershan, Biophys. J. 27, 393 (1979).
- M.Kléman, C.E.Williams, M.J. Costello and T. Gulik Krzywicki, Philos. Mag. 35, 33 (1977).
- 17. C.E. Williams and M.Kléman, J.Phys.Lett. (France) 35, L33 (1974).
- 18. R.Ribotta, J.Phys. Coll. (France) 37, C3 149 (1976).
- 19. P.S.Pershan, J.Appl.Phys. 45, 1590, (1974).
- 20. L.Lejcek and P.Oswald, J.Phys.II 1, 931 (1991).
- M.Maaloum, D.Ausserre, D.Chateney, G.Coulon and Y. Gallot, Phys.Rev.Lett 68, 1575 (1992).

- M.S.Turner, M.Maaloum, D.Ausserré, J-F. Joanny and M. Kunz, J.Phys. II (France), 689 (1994).
- 23. P.Pierański et al. Physica A **194**, 364 (1993).
- F. Grandjean, Bull.Soc.Franç.Minér **39**, 164 (1916); C.R.Acad.Sci.Paris **166**, 165 (1918).
- 25. C.Williams, Thèse d'Etat, Université d'Orsay n. A012720 (1976).
- 26. W.K.Chan and W.W.Webb, J.Phys. (France), 42, 1007 (1981).
- 27. G.Friedel, Annales de Physique 18, 273 (1922).
- 28. J. Bechhoefer and P. Oswald Europhys.Lett. 15, 521 (1991).
- 29. J. Bechhoefer, L.Lejcek and P.Oswald, J.Phys. II (France) 2, 27 (1992).
- 30. L.Lejcek, J.Bechhoefer, P.Oswald, J.Phys. II (France) 2, 1511 (1992).
- 31. M. Allain, J.Phys. (France) 48, 225 (1985).
- 32. J.A.N. Zasadzinsky, Biophys.J. 49, 1119 (1986).
- L. D. Landau and E. M. Lifshitz, "Theory of Elasticity" (Pergamon Press, Third edition, 1986), p. 172-177.
- 34. R.Ribotta, G.Durand, J.Phys. (Paris) **38**, 179 (1977).
- 35. R.Hołyst and A.Poniewierski, J.Phys. (France) II, 3, 177 (1993).
- 36. P.G. de Gennes, J.Phys(Paris) Colloq.30,C4 65 (1969).
- 37. G. Grinstein and R.A. Pelcovits Phys.RevA, 26, 915 (1982).
- 38. N.Schopohl and T.J.Sluckin, Phys.Rev.Lett.59, 2582 (1987).
- 39. S.D.Hudson and R.G.Larson, Phys.Rev.Lett. 70, 2916 (1993).
- 40. S.R.Renn and T.C.Lubensky, Phys.Rev.A 38, 2132 (1988);
 S.R.Renn, Phys.Rev. A 45, 953 (1992).
- 41. J.W. Goodby, M.A. Waugh, S.M. Stein, E.Chin, R.Pindak and J.S. Patel, Nature 337, 449 (1989).
- 42. S.Kralj and T.J. Sluckin, Phys Rev E 48, 3244 (1993).

- 43. M.Kléman Point, Lines and Walls, (Wiley 1983).
- 44. L.Bourdon, M.Kléman, L.Lejcek and D.Taupin, J.Phys. (Paris) 42, 261 (1981).
- 45. M.Kléman and L.Lejcek, Phil.Mag. A 42, 671 (1980).
- 46. H. Pleiner, Liq.Cryst. 1, 197 (1986); Phil.Mag. A54, 421 (1986); Liq.Cryst. 3, 249 (1988).
- 47. L.Lejcek, Liq.Cryst. 1, 473 (1986).
- 48. R.Hołyst, Phys.Rev.Lett. **72**, 4097 (1994).
- 49. R.Hołyst, Macromol. Theory Simul. **3**, 817 (1994).
- 50. A.Poniewierski and R.Hołyst, Phys.Rev. B 47, 9840 (1993).
- R.Hołyst, D.J.Tweet and L.Sorensen, Phys.Rev.Lett. 65, 2153 (1990);
 R.Hołyst, Phys.Rev A 44, 3692 (1991).
- 52. A.N.Shalaginov and V.P.Romanov, Phys.Rev E 48, 1073 (1993) actually in this reference the authors miss the surface curvature term.
- D.J.Tweet, R.Hołyst, B.D. Swanson, H.Stragier and L.B.Sorensen, Phys.Rev.Lett. 65, 2157 (1990).
- 54. R.Bartolino and G.Durand, Mol.Cryst.Liq.Cryst. 40, 117 (1977).
- 55. F.Nallet and J.Prost, Europhys.Lett. 4, 307 (1987).
- 56. C.Guilliet, P.Fabre and M.Veyssié, J.Physique II 3, 1371 (1993).
- 57. S.Wu, J.Phys.Chem. **74**, 632 (1970).
- G.Henn, H.Poths and M.Stamm, Polymers for Advanced Technology, 5, 582 (1994).
- 59. G.Henn, M.Rücker, J.P. Rabe and M.Stamm (in press, 1995).
- Z.Cai, K.Huang, P.A.Montano, T.P.Russell, J.M.Bai and G.W.Zajac, J.Chem.Phys. 98, 2376 (1993).
- N.G. van Kampen, Stochastic Processes in Physics and Chemistry, (North Holland Publishing Company, 1981) p. 67; R.R.Netz and R.Lipowsky, J.Phys I 4,

47 (1994).

- W.Helfrich Z.Naturforsch. 33a, 305 (1978); also in *Liquids at interfaces*, eds J.Charvolin, J.F.Joanny and J.Zinn-Justin (Elsvier Science Publisher 1990), p.212.
- P.Nozières in Solids far from Equilibrium, ed C.Godrèche, (Cambridge University Press, 1992, p.1.
- P.G.de Gennes Scaling concept in polymer physics (Cornell University Press, 1979).
- G.Forgacs, R.Lipowsky and Th.M.Nieuwenhuizen in *Phase transitions and Critical Phenomena*, eds. C.Domb and J.L.Lebowitz vol 14 (Academic Press, 1991) p.136.
- X.Qiu, J.Ruiz-Garcia, K.J.Stine, C.M.Knobler and J.V.Selinger, Phys.Rev.Lett
 67, 703 (1991); S.Rivière, S. Hènon and J.Meunier, Phys.Rev. E 49, 1375 (1994).
- 67. W.Helfrich, J.Phys. (Paris) **39**, 1199 (1978).
- D.Nelson and J.Toner, Phys.Rev. B 24, 363 (1981); J.Toner, Phys.Rev. B 26, 462 (1982).
- 69. R.P.Rand, Ann.Rev.Biophys.Bioeng. 10, 277 (1981).
- R.Lipowsky and S.Leibler, Phys.Rev.Lett. 56, 2541 (1986); R.Lipowsky, Europhys.Lett 7, 255 (1988).
- 71. R.Hołyst and T.A.Vilgis, Europhys. Lett. 28, 647 (1994).
- 72. M.Kléman, J.Phys. (Paris) **35**, 595 (1974).
- 73. J.M.Kosterlitz and D.J.Thouless, J.Phys.C 6, 1181 (1973); J.M. Kosterlitz *ibid*,
 7, 1046 (1974).
- 74. R.Hołyst, Phys.Rev. B 50, 12398 (1994).
- 75. P.G.de Gennes, Mol.Cryst.Liq.Cryst. **21**, 49 (1973).

- 76. J.D.Litster et al, J.Phys Colloq. (Paris) 40, C3-339 (1979); C.C.Huang,
 R.S.Pindak and J.T.Ho, Solid State Comm. 25, 1015 (1978).
- 77. see e.g. A.Poniewierski and T.J. Sluckin, Liq.Cryst. 2, 281 (1987).
- 78. A.Allain and M.Kléman, J.Phys. (France), 48, 1799 (1987).
- 79. M.Kléman and C.E. Williams, J.Phys.Lett. (Paris) 35, L-49 (1974).
- 80. P.G. de Gennes, Physics of Fluids 17, 1645 (1974).
- 81. N.A.Clark, Phys.Rev.Lett. 40, 1663 (1978).
- 82. E.Dubois Violette, E Guazzelli and J.Prost, Phil.Mag. 48, 727 (1983).
- 83. L.Lejcek, Czech.J.Phys. B**32**, 767 (1982).
- 84. P.Oswald and L.Lejcek, J.Physique II 1, 1067 (1991).
- R.Bartolino and G.Durand, Phys.Rev.Lett. **39**, 1346 (1977); J.Phys.Lett. (Paris) **44**, L79 (1983).
- 86. R.Ribotta, Thése d'Etat, Orsay (1975).
- 87. P.Oswald and D le Fur, C.R.Acad.Sci. Paris 297, Série II, 699 (1983).
- 88. P.Oswald and M.Kléman, J.Phys.Lett (France) 45, L319 (1984).
- 89. P.Oswald and M.Allain, J.Physique 46, 831 (1985).
- 90. M. Allain, Europhys.Lett **2**, 597 (1986).
- 91. P.Oswald, C.R.Acad.Sci, **304**, 1043 (1987).
- 92. P.Oswald and M.Kléman, J.Physique Lett. 43,L411 (1982).
- 93. P.Oswald, J.Physique Lett. 44, L303 (1983).
- 94. P.Oswald, J.Physique 47, 1091 (1986).

Figure captions

- Fig.1 Schematic picture of smectic (lamellar) liquid crystal obtained in computer simulation of a hard rod system by D.Frenkel.
- Fig.2 Lamellar phase in binary mixture of water and surfactant. The surfactant molecuels form bilayers. From F.B. Rosevear J.Soc.Cosmetic Chemist 19, 581

(1968).

- Fig.3 Schematic picture of lamellar phase in diblock copolymer system. The linear copolymer consists of two homopolymers A (solid line) and B (dashed line) joined by chemical bond (dot). Alternating A rich and B rich domains are shown. After Ref.6.
- Fig.4 (a) The edge dislocation with small core, (b) The edge dislocation with extended core (c) The edge dislocation with core splitted into two disclinations(d) The screw dislocation, after Ref.16
- Fig.5 (a) Schematic cross section of a sample containing a dislocation array. (b) strain versus position (c) accompanying variations of tilt angle versus position (d) Lagerwall subgrain boundary at the smectic A smectic C phase transition. after Ref.13.
- Fig.6 Scan of the well annealed sample in the lamellar phase showing regular steps due to the edge dislocations. Each step corresponds to the termination of the single bilayer. The shot noise level is approximately 10% of the step size. after Ref.26.
- Fig.7 (a) AFM image of the holes and islands at the free surface of AB diblock copolymer (here PS/PBMA diblock copolymer). The height of the circular elevation is 310 Å. (b) Cross section of the island. (c) The schematic representation of the structure with the dislocation. Since the islands are circular here we have dislocation loops. Locally the distortions induced by large edge dislocation loop are the same as those induced by linear edge dislocation(Fig.4a). The dark and white regions corresponds (see also Fig.3) to PS and PBMA domains. The dark lines represent PS/PBMA interfaces, while dotted lines are fictive PS-PS or PBMA-PBMA separations. (d) TEM picture showing the edge dislocation. after Ref.21.

- Fig.8(a) The idealized smectic meniscus of the freely suspended smectic liquid crystal film, after Ref.23.
- Fig.8(b) The arch-texture, after Ref.23.
- Fig.8(c) Knots after Ref.23.
 - Fig.9 Profiles of 8OCB droplets obtained by Michelson interferometry at different temperatures. The indicated temperatures are the numbers in of °C below T_{NA} . The apparent droplet diameter is $177 \pm 5\mu$ m. The matching of the facet with the curved part of the droplet is tangential.
 - Fig.10 Possible droplet configurations. In (a) the layers are parallel to the substrate.The top surface shows a single facet parallel to the substrate and steps. In(b) the top layer is curved to follow the free surface and dislocation loops run through the bulk of the smectic liquid crystal.
 - Fig.11 (a) Part of the "goutte à gradins" seen through themicroscope in reflection with natural light. (b) Schematic view of a "goutte à gradin" (c) Probable structure of a "gradin".
 - Fig.12 Droplet profiles of 4O.8 for different temperatures below T_{NA} (droplet diameter 145 μ m). When the temperature decreases the droplet shows a clear tendency to develop a discontinuity in slope at the facet edge. A secondary facet is well visible on the profile at $T_{NA} T = 9.8^{\circ}$ C.
 - Fig.13 TEM picture of screw dislocations in lecithin (courtesy of M.Allain). Arrows show the emergence points of screw dislocations. Sample has been frozen and then fractured under vacuum. A replica of its surface is observed by TEM.
 - Fig.14 The smectic order parameter ϵ , nematic order parameter s and the local angle ϑ , normalized by their bulk values, as a function of the distance from the center of the screw dislocation core. The distance is measured in the units of the correlation length for smectic ξ_{\perp} . This length is of the size of a molecule for

small temperatures but diverges at the approach to the smectic-nematic phase transition temperature (in the case of continuous transition in liquid crystals⁷). After Ref.42.

- Fig.15 The screw dislocation tilted with respect to the layers.
- Fig.16 Two configurations of a dislocation pinned at the solid substrate (a) unfavorable(b) favorable.
- Fig.17 The energy of a single edge dislocation $F^* = (F(h) E_0) 8\pi \lambda_s / (\sqrt{KB}d^2) \ (\lambda_s = \sqrt{K_s / \sqrt{KB}})$ versus the distance from the surface $h^* = 2hK/K_s$ for $\gamma / \sqrt{KB} = 0$ (dashed line) and $\gamma / \sqrt{KB} = 0.5$ (solid line). In the latter case the shallow minimum (not visible on the scale of the Figure) is located at $h^* = 2.55$.
- Fig.18 The equilibrium location of the dislocation inside the film $h_{eq}^* = h_{eq}/d$ versus the surface bending elastic constant $K_s^* = K_s/Kd$ for D/d = 3 – long dashed line; D/d = 10 – short dashed line; and $D/d = \infty$ – solid line. $\alpha_s = 0$.
- Fig.19. Clustering of dislocations in a wedge shaped sample (Nallet and $Prost^{55}$).
- Fig.20 The edge profile $u^* = -u_{eq}(x, z = 0)/d$, versus $x^* = (x l)/\sqrt{\lambda h}$ at the free surface of thin lamellar film deposited on solid substrate (dashed line). Here $K_s = Kd, \gamma/\sqrt{KB} = 5, D = 3d, h = d/2$. For comparison (solid line) we show the profile, obtained in the previous approach¹⁹ with finite size and surface effects neglected $(D \to \infty, \gamma = 0, K_s = 0)$.
- Fig.21 A plot of the local film thickness against position measured along an axis parallel to the substrate and normal to the domain edge (see Fig.5) (a) the average film thickness, D is d < D < 2d; (b) 2d < D < 3d; (c) 3d < D < 4d; (d) 5d < D < 6d. Dots display experimental results and the solid line was obtained from the theory (however here $K_s = 0$). After Ref.22.
- Fig.22 The same schematic picture as shown in Fig.7 with steps at the free surface, without dislocations in the bulk. (this configuration is in fact unfavorable

in comparison to film structure with steps induced by dislocations Fig.5 see Section VI). After Ref.60.

- Fig.23 The edge profile $u^* = -u(x, z = 0)/d$ versus $x^* = (x l)/\sqrt{\lambda d}$ for the film on a solid substrate bounded by the interface with the surface tension $\gamma = 0$ for three thicknesses of the lamellar film: D/d = 3 – long dashed line; D/d = 10 – short dashed line; and $D/d = \infty$ – solid line. (a) $K_s = Kd$ (b) $K_s/Kd = 10$.
- Fig.24 The top view of the z = 0 surface containing the edge dislocation. The dashed line represents the unperturbed position of the dislocation and $u_x(y)$ is the amplitude of thermal distortions of the dislocation in the x-y plane (see also Eq(9.1)).

Fig.25 The dimensionless interaction energy per unit length $V(x) = 2\pi^2 \sqrt{N}/(\sqrt{KBd})$ $(F_s(x) + F_H(x) - F_s(0))$ versus the separation $x = l/\sqrt{\lambda dN}$ for N = 30, N = 40and N = 54. Here N is the number of lamellar layers. As N increases the minimum of V(x) (at $x_0 \approx 3$) moves upward. At N = 54 $V(x_0) = V(x = \infty) = 0$ and the unbinding transition occurs $(K_s/Kd = 1, \alpha_s = 1)$.

- Fig.26 The surface bending elastic constant $K_s^* = K_s/Kd$ ($\alpha_s = 1$) versus the number of lamellar layers, N, at the unbinding transition. The dotted line divides the diagram into two regions. Above the line the dislocations are free and below they are bound.
- Fig.27 The surface tension $\alpha_s = \gamma/\sqrt{KB} (K_s/Kd = 1)$ versus the number of lamellar layers, N at the unbinding transition. The dotted line divides the diagram into two regions. Above the line the dislocations are free, below they are bound. At the line the unbinding transition occurs.
- Fig.28 The climb motion of an edge dislocation submitted to a normal stress σ_{zz}^{E} . v is the velocity, **b** is the Burgers vector and **t** is the unit vector along the dislocation.

- Fig.29 (a) (b) climb of the giant dislocation and equivalent rheological model.
- Fig.30 The glide motion of a dislocation submitted to shear (see Fig.29).
- Fig.31 Thermally activated bulge.
- Fig.32 The schematic view of the dynamical measurements. (a) step like deformations. Initial thickness variation is δ_0 . (b) Normal stress measured experimentally. The characteristic relaxation time is τ . (c) Time τ versus σ_0 in a 400 μ m thick sample of 8CB at room temperature.
- Fig.33 Helical instability of screw dislocation.
- Fig.34 Crossing of an edge and a screw dislocation with the formation of the jog.
- Fig.35 Lubrication geometry.
- Fig.36 The apparent (effective) viscosity versus the shear rate (8CB, $D = 100 \mu m$, 22°C from Ref.91).
- Fig.37 Velocity profile in the sample and a dislocation distorted by the flow.