

$$+ \frac{[\text{curl} \mathbf{A}(\mathbf{r})]^2}{8} g + \sum_i [B(\mathbf{r}_i) g_{n_i} I_i + \hat{H}_a(I_i)] + \hat{H}_{\text{imp}}: \quad (1)$$

Here, $\langle \rho \rangle$, $\langle \mathbf{r} \rangle$, \mathbf{A} ; $J_{\text{en}}(\mathbf{r})$ and V are the quasiparticle energy, the superconducting order parameter, the vector potential, the hyperfine contact coupling between electronic spins (Pauli matrices) and localized nuclear moments (LM's) I_i and the electron-phonon coupling constant respectively. The first three terms in Eq. (1) describe the superconducting mean-field Hamiltonian in the magnetic field $B(\mathbf{r}) = \text{curl} \mathbf{A}(\mathbf{r})$ due to LM's and screening current, while the term \hat{H}_{imp} describes the electron scattering (including also the spin-orbit one) on nonmagnetic impurities. The term $B(\mathbf{r}_i) g_{n_i} I_i$ describes the dipole-dipole interaction of LM's, as well as their interaction with the magnetic field due to screening superconducting current (see more below). $\hat{H}_a(I_i)$ is (together with the dipole-dipole interaction) responsible for magnetic anisotropy of LM's. In the case of AuIn_2 , which is simple cubic crystal, its form is unknown (see discussion below). Later we show that under experimental conditions reported in Refs. 1,10,11 the ferromagnetic structure, which would be in absence of S order, is transformed in the presence of superconductivity into spiral (or domain-like) one (depending on magnetic anisotropy).

A. The characteristic parameters of AuIn_2

The magnetic critical temperature $T_M = 35$ K is very small compared to $T_S = 0.2$ K, and it is much larger than the characteristic dipole-dipole temperature $T_{\text{em}} (1$ K), see below. This fact allows us to estimate the hyperfine contact interaction between electrons and LM's, which is characterized by the parameter $h_{\text{ex}} = J_{\text{en}}(0) n_m \langle \mathbf{h}_i \rangle$ where n_m is the concentration of LM's. The indirect exchange energy (via conduction electrons) between the LM's of nuclei is characterized by the RKKY temperature $T_{\text{ex}} = N(0) h_{\text{ex}}^2 / n_m$, where $N(0)$ is the electronic density of states at the Fermi level. The crystallographic structure gives $n_m = 3 \cdot 10^{22} \text{ cm}^{-3}$. $N(0)$ is obtained by knowing $H_{c0}(\Gamma = 0) = 14.5$ G, see Refs. 1,10, which gives $N(0) = 0.64 \cdot 10^4 \text{ erg}^{-1} \text{ cm}^{-3}$. Since $T_M (= 35$ K) is predominantly due to the indirect exchange interaction between In nuclei moments one has $T_M \approx T_{\text{ex}}$, which gives $h_{\text{ex}} \approx 1$ K. Note that one has $h_{\text{ex}} > 0$ (0.36 K), which gives rise to a gapless quasiparticle spectrum in S state below T_M in clean samples ($l > l_0$) of AuIn_2 , see below.

The electromagnetic (EM) dipole-dipole interaction between LM's is characterized by $T_{\text{em}} = 2 n_m^{-2}$, where $n_m = g_{n_i} I_i$: In case of the In nuclei in the AuIn_2 cubic crystal one has $n_m = 5.5 \cdot 10^{22} \text{ cm}^{-3}$, i.e. $T_{\text{em}} = 1.2$ K (T_M), which means that the dipole-dipole interaction does not contribute to T_M in AuIn_2 . However, it makes the magnetic structure transverse in S state, see below.

From $l_0 (= 1.76 T_S)$ and $v_F = 1.68 \cdot 10^8 \text{ cm/s}^{10,11}$ one gets $l_0 = 10^5$ A, while from the resistivity measurements^{1,11}, where $R_{RR} = 500$, one obtains $l = 3.6 \cdot 10^4$ A. Accordingly, the spin-orbit scattering mean-free path is very large, i.e. $l_{\text{so}} > 3.6 \cdot 10^4$ A, because

one always has $l_{\text{so}} > l$. Note that $l < l_0$ and the system is in the dirty (but not very dirty) limit. The London penetration depth $\lambda_L = 200$ A is estimated from H_{c0} and by knowing l_0 and l , which means that AuIn_2 is the type I superconductor at temperatures where S and M orderings coexist. From the above analysis we estimate the parameter $(h_{\text{ex}} = h^2) = 0.1$. It is small and dirty limit may be used to treat effect of exchange field on superconductivity. This simplifies the theoretical analysis given below. Here $l = l_{\text{sc}}$ is the electron scattering time.

B. Theoretical analysis of AuIn_2

It was shown in Refs. 3,6,17 that when the electron spin-orbit interaction is weak, i.e. when $l_{\text{so}} = 1$ ($k_F^{-1} l_0 = l^2$)²⁼³, there is a peak in the spin susceptibility in the superconducting state at nonzero wave vector Q . This means that in the superconducting state an oscillatory magnetic order is more favorable than the Fermi one. In AuIn_2 one has $k_F = 1.45 \text{ \AA}^{-1}$ and thus the condition for an oscillatory magnetic order is $l_{\text{so}} = 10^2$ l. Since by definition $l_{\text{so}} > l$ we see that the spin-orbit interaction does not play any role in the formation of the magnetic structure in the coexistence phase of AuIn_2 . The magnetic order can be a spiral or domain-like one, depending on the magnetic anisotropy, see below. The problem is now reduced to the study of electrons moving in an oscillatory (with the wave vector Q) exchange and magnetic field $h_{\text{ex}}(\mathbf{R}) = h_{\text{ex}} S(\mathbf{R})$, $B(\mathbf{R}) = \text{curl} \mathbf{A}(\mathbf{R})$ respectively. By using the Eilenberger equations for the normal $f_0(\mathbf{v}; \mathbf{R})$ and anomalous $f_1(\mathbf{v}; \mathbf{R})$ electronic Green's function, where the superconducting order parameter $\Delta(\mathbf{R})$ is a solution of the self-consistency equation $\Delta(\mathbf{R}) = 2 g \int d\mathbf{n} f_1(\mathbf{R}; \mathbf{n})$ ($g = N(0)V$ is the electron-phonon coupling constant) one obtains the free-energy functional of the system $F_{\text{SM}} = F_S + F_M + F_{\text{int}}$. It may be presented as a sum of magnetic (F_M), superconducting (F_S) and interacting (F_{int}) parts, i.e. $F_{\text{SM}} = F_S + F_M + F_{\text{int}}$.

By assuming that: a) $E_S = F_{\text{int}} > 1$, $E_S = N(0) \Delta^2 = 2 n_m$ (this is indeed fulfilled in AuIn_2 , where $E_S = F_{\text{int}} = 100$, and b) the Fermi surface is isotropic (it is also fulfilled in AuIn_2 , one gets the free-energy F_{SM}

$$F_S = - \frac{1}{2} N(0) \Delta^2 \ln \frac{e^{\frac{\Delta}{2}}}{2}; \quad (2)$$

$$F_{\text{int}} = F_{\text{int}}^{\text{ex}} + F_{\text{int}}^{\text{em}} = F_{\text{int}}^{\text{ex}} + \frac{3}{2} \frac{n_m \langle \mathbf{h}_i \rangle^2 \int d\mathbf{Q}}{v_F Q (\lambda_L Q)^2};$$

Here the terms $F_{\text{int}}^{\text{ex}}$ and $F_{\text{int}}^{\text{em}}$ in Eq. (2) describe the exchange EX and EM interaction of superconducting electrons with LM's respectively. $F_{\text{int}}^{\text{ex}}$, and F_M depend on h_{ex} , S_Q , l , l_0 etc. We consider only those cases which might be important for the physics of AuIn_2 .

1. Dirty case ($l < l_0$). This case is realized in AuIn_2 as reported in Refs. 1,10, where $l = 3.6 \cdot 10^4$ A and $l_0 = 10^5$ A. Immediately below the magnetic critical temperature

$T_M = 35$ K the magnetization is small and F_M has the form

$$F_M = \sum_Q \left[\frac{1}{2} \chi_{ex}^{-1}(Q) \left(\sum_j j_{S_Q;j} + \sum_k j_{S_Q;k} \right) \right]^2 + \frac{1}{2} \chi_{em} j_{S_Q;k}^2 + F_0 + F_a \quad (3)$$

where $Q = Q_{S_Q;k}$ and $\chi_{ex}^{-1}(T;Q) = (\chi_{ex}^{-1})_{ex} + Q^2 = 12k_F^2$. Here, $k_F = 1.45 \text{ \AA}^{-1}$ is the Fermi wave vector. The isotropic term F_0 (per LM) describes higher order terms in S_Q^2 , while F_a (per LM) describes magnetic anisotropy of the system, see discussion below.

Since the sample of AuIn_2 is in dirty limit¹ (it holds also $Ql \ll 1$, see below, $(h_{ex} = h^2) \ll 1$, the mean-free path drops out from the term F_{int}^{ex} in Eq. (2)). Since we consider the spiral (helical) structure with the amplitude S_Q , which contains only one harmonic Q . Then the sum over Q in Eqs. (2),(3) drops out and one obtains $F_{int}^{ex} = \frac{1}{2} \chi_{ex}^{-1} S_Q^2 = 2v_F Q$. By minimizing $F_{SM} = \frac{1}{2} \chi_{ex}^{-1} S_Q^2 + \frac{1}{2} \chi_{em} j_{S_Q;k}^2$ with respect to j_{S_Q} and Q one gets the spiral magnetic structure at T very near T_M with the wave vector $Q_S = (3k_F^2 = 0)^{1/3} = 5 \cdot 10^2 \text{ \AA}^{-1}$ and the period is $L_S = 2\pi/Q_S = 120 \text{ \AA}$ - see Fig.1a. Note, one has $Q_S l \ll 10^3$, i.e. the required theoretical condition $Ql \ll 1$ is fulfilled in AuIn_2 . In this case the EM interaction in Eq. (2) is negligible, i.e. $F_{int}^{em} = F_{int}^{ex}$ ($\chi_{em} = \chi_{ex} \frac{2}{L} Q^2$) $< 10^{-2}$ and the spiral magnetic structure is due to the effective EX interaction between electrons and LM's (of In nuclei) mainly. However, the magnetic dipole-dipole interaction between In nuclei, although small ($\chi_{em} = \chi_{ex}$), makes the structure transverse ($Q = Q_S = 0$) due to the term $\chi_{em} j_{S_Q;k}^2$ in Eq. (3).

On cooling, S_Q^2 grows and higher order terms of S_Q^2 must be included in F_M as well as magnetic anisotropy F_a . However, in AuIn_2 , which is simple cubic structure, only higher order terms contribute to F_a (per LM), i.e. $F_a = D(S_x^4 + S_y^4 + S_z^4)$. One expects that $D < \chi_{em}$ (or more realistic $D = \chi_{em}$, see below). However, if D fulfills the condition $(D = \chi_{ex})^{3/4} > 0.25(k_F a_0)^{1/2}$ (one should have $D = \chi_{ex} > 10^3$ in the case of AuIn_2) the spiral structure is transformed into a striped one-dimensional transverse domain structure^{3;6} - see Fig.1b. The condition on D means that the domain-wall thickness should be much smaller than the period of the domain structure. The magnetic energy (per LM's) in the case of the domain magnetic structure is given by $F_M = F_0(S_Q^2) + \chi_{ex} S_Q^2 + (S_Q^2; T)Q = \dots$, where $F_0(S_Q^2)$ contains terms of higher order in S_Q^2 . Here $\chi_{ex} = k_F^{-1} \omega S_Q^2$ is the surface energy of the domain wall, and $\omega = 0.58(\chi_{ex} D)^{1/2}$ in the case of rotating Bloch wall (where $D = \chi_{ex}$). The wave vector of the domain structure Q_D , obtained by minimizing F_{SM} , at $T = T_M$ is given by $Q_D = 2(\chi_{ex} = \omega k_F a_0)^{1/2}$. Note, the wave vector of the domain structure Q_D is smaller than Q_S for the spiral. Because of the simple cubic structure of AuIn_2 it is more probable that $D = \chi_{ex} < 10^3$ than opposite,

which means that AuIn_2 is the strong candidate to be the first system where superconductivity coexists with spiral magnetic order down to $T = 0$, see below. Namely, it turns out that at $T = 0$ the magnetic energy per LM is $F_M = \chi_{ex} = 35$ K, while the superconducting energy per LM is $F_S = 4$ K. However, the interaction energy (per LM) is very small, $F_{int} = 10^{-2}$ K. This result means that even at $T = 0$ the loss of energy due to the interaction, F_{int} , is much smaller than the gain due to the condensation energy F_S , i.e. $F_S + F_{int} - F_S < 0$, and the oscillatory magnetic structure and S order coexist in AuIn_2 down to $T = 0$.




FIG. 1. (a) The spiral magnetic structure $S(x)$, with the period L_S in the superconducting phase for small anisotropy $D = \chi_{ex} < 10^3$. (b) The domain-like magnetic structure $S(x)$, with the period L_D in the superconducting phase for appreciable anisotropy $D = \chi_{ex} > 10^3$.

2. Clean limit ($l > a_0$). The present experiments were performed on dirty (but not very dirty) AuIn_2 samples, where $l < a_0$. In that case the motion of Cooper pairs in the coexistence phase is diffusive and there is an isotropization of the quasiparticle spectrum. This means that the oscillatory magnetic structure acts like magnetic impurities (for similarity and differences of effects of magnetic impurities and the oscillatory magnetic structure see Ref. 3). However, it would be interesting to perform experiments on clean AuIn_2 samples with $l > a_0$ (for instance on samples with a residual resistivity ratio $RRR > 1500$). Namely, it was shown in Refs. 3,7 that the oscillatory magnetic order in clean superconductors can give rise to the gapless quasiparticle spectrum with nodes on a line at the Fermi surface if $h_{ex} > 0$. This is just the case in AuIn_2 , where $h_{ex} = 1$ K and $a_0 = 0.36$ K. In the clean limit the quasiparticle motion is anisotropic in the presence of an oscillatory magnetic structure with the wave vector Q , and the

quasiparticle energy vanishes on lines at the Fermi surface given by $v_F Q = 0$ if $h(T) = \frac{h}{2\pi} S_Q(T) > 0$, see Ref. 3. In this case the density of states for $E < 0$ is $N_s(E) = N(0) (E h = 0 v_F Q_d) \ln(4 \mu_0 E)$ for the domain structure and $N_s(E) = N(0) (E h = 0 v_F Q_d)$ for the spiral one. $N_s(E)$ can be experimentally obtained by measuring voltage dependence of the tunneling conductivity in the S(N junction with AuIn₂ being in the coexistence phase.

C. Effect of magnetic field

Because of very small interaction energy one expects that the critical field $H_c(T)$ does not vanish down to $T = 0$. Indeed, equating Gibbs energy for superconducting state and that of normal ferromagnetic state one gets

$$F_S + F_M + F_{int} = F_M^0 - \frac{H_c^2}{8} M^2 \quad (4)$$

and if one defines $H_{SM} = \beta (F_M^0 - F_M - F_S - F_{int})^{1/2}$

$$H_c = \frac{q}{H_{SM}^2 + (4 M_0)^2} 4 M_0 \quad (5)$$

At $T = T_M$ the magnetization M is saturated, i.e. $M = M_0 = 5.5 n_m \mu_B$. Because $F_{int} = F_S; F_M$ one has small difference in magnetic energy of oscillatory state, F_M and that of ferromagnetic state, F_M^0 . As result, $H_{SM} = H_{c0}(0) = \beta (F_S^0)^{1/2}$. The experimental values¹ are $H_{c0}(0) = 14.5$ G and $4 M_0 = 11$ G which gives $H_c(0) = 7$ G. It was found experimentally¹ that $H_c = 8.7$ G at $T = 25$ K, and thus our estimate is reasonable. Nonzero value of $H_c(0)$ in AuIn₂ is in a contrast to the case of magnetic type II superconductors ErRh_4B_4 and HoMoO_6S_8 , where $H_c(T)$ tends to zero [as well as $H_c(T)]$ at $T = T_M$, because in these compounds one has $F_{int} = F_N = F_S$ near some temperature $T_{S2} < T_M$. At $T > T_M$ one obtains $H_c = H_c^0 = (1 + 4 M_0)$ in absence of demagnetization effects, where $M(T) = m = (T - T_{ex})$ and $m = m = 6$: The change of the slope of $H_c(T)$ takes place at T very near T_M . The experimental broadening of the transition in the magnetic field can be due to the polycrystallinity of the sample, where even small magnetic anisotropy of the crystallites can produce percolation-like broadened resistive transition in magnetic field^{18;19}.

In conclusion, we found, that superconductivity coexists with a domain-like magnetic structure if the anisotropy parameter D is not too small, i.e. $D = \mu_{ex} > 10^{-3}$. We estimate the period $L_D = 300$ Å for $D = 1$ K. In the opposite case, $D = \mu_{ex} < 10^{-3}$, the magnetic structure is spiral with the period $L_S = 120$ Å. The realization of the spiral structure in AuIn₂ is more probable due to the simple cubic structure of this compound and accordingly due to small magnetic anisotropy.

It is also proposed that in the case of very clean AuIn₂ samples with $RRR > 1500$ there is a line, given by $v_F Q = 0$, at the Fermi surface with nodes in the quasiparticle spectrum in the coexistence phase. It would

be interesting to study this regime experimentally, because in that case thermodynamic and transport properties show power law behavior.

We would like to devote this paper to the pioneer in the field of magnetic superconductors Vitalii Lazarevich Ginzburg on the occasion of his 80-th anniversary. M. L. K. acknowledges Université de Bordeaux for kind hospitality and O. Andersen, L. Hedin, H.-U. Habermann, C. Irslinger, Y. Leroyer, M. Mehring, K.-D. Schotte and V. S. Odovenko for support.

-
- ¹ S. Rehmann, T. Hermansdorfer and F. Pobel, Phys. Rev. Lett. 78, 1122 (1997).
 - ² V. L. Ginzburg, Zh. Eksp. Teor. Fiz. 31, 202 (1956).
 - ³ L. N. Bulaevskii, A. I. Buzdin, M. L. Kubic and S. V. Panyukov, Adv. Phys., 34, 175 (1985); Sov. Phys. Uspekhi 27, 927 (1984).
 - ⁴ M. B. Maple, H. C. Hamaker and L. D. Wolf, in Superconductivity in Ternary Compounds II, Topics in Current Physics, ed. M. B. Maple and F. Fischer, Springer Verlag, v. 34, (1982).
 - ⁵ A. I. Buzdin, L. N. Bulaevskii, Sov. Phys. Uspekhi 29, 412, (1986).
 - ⁶ L. N. Bulaevskii, A. I. Buzdin, M. L. Kubic and S. V. Panyukov, Phys. Rev. B 28, 1370 (1983).
 - ⁷ L. N. Bulaevskii, M. L. Kubic and A. I. Rusinov, Solid State Comm., 30, 59 (1979); J. Low Temp. Phys., 39, 256 (1980).
 - ⁸ E. I. Bunt and C. M. Varma, Phys. Rev. Lett. 42, 1079 (1979).
 - ⁹ L. J. Chang, C. V. Tom, D. M. Paul and C. Ritter, Phys. Rev. B 54, 9031 (1996).
 - ¹⁰ T. Hermansdorfer and F. Pobel, J. Low Temp. Phys., 100, 253 (1995).
 - ¹¹ T. Hermansdorfer, P. Smid, B. Schroder-Smid and F. Pobel, Phys. Rev. Lett. 74, 1665 (1995).
 - ¹² F. Pobel, Physics Today, January 1993; Physikalische Blätter, 50, 853 (1994); Physica B 197, 115 (1994).
 - ¹³ O. V. Lounasmaa, Physics Today, October 1989; P. Hakonen and O. V. Lounasmaa, Science 265, September 1994; P. Hakonen, O. V. Lounasmaa and A. Oja, J. Magn. and Magn. Mat. 100, 394 (1991).
 - ¹⁴ A. S. Oja and O. V. Lounasmaa, Rev. Mod. Phys., 69, 1 (1997).
 - ¹⁵ Ch. Buchal, F. Pobel, R. M. Mueller, M. Kubota and J. R. Owers-Bradley, Phys. Rev. Lett. 50, 64 (1983).
 - ¹⁶ P. J. Hakonen, R. T. Vuorinen, and J. E. M. Artikainen, Phys. Rev. Lett. 70, 2818 (1993).
 - ¹⁷ M. Kaufman and O. Entin-Wohlman, Physica, B 69, 77 (1976).
 - ¹⁸ L. N. Bulaevskii, A. I. Buzdin, M. L. Kubic, Solid State Comm., 41, 309 (1981); Phys. Lett. A 85, 169 (1981).
 - ¹⁹ A. I. Buzdin and L. N. Bulaevskii, Fiz. Nizkih, Temp. 6, 1528 (1980).