

Staggered pairing phenomenology for UPd_2Al_3 and UNi_2Al_3

V. M. Artisovits

Department of Physics, Ohio State University, Columbus, Ohio 43210

D. L. Cox

Department of Physics, Ohio State University, Columbus, Ohio 43210

and Department of Physics, University of California, Davis, California 95616

We apply the staggered-pairing Ginzburg-Landau phenomenology to describe superconductivity in UPd_2Al_3 and UNi_2Al_3 . The phenomenology was applied successfully to UPt_3 so it explains why these materials have qualitatively different superconducting phase diagrams although they have the same point-group symmetry. UPd_2Al_3 and UNi_2Al_3 have a two-component superconducting order parameter transforming as an H-point irreducible representation of the space group. Staggered superconductivity can induce charge-density waves characterized by new Bragg peaks suggesting experimental tests of the phenomenology.

Heavy-fermion superconductors^{1,2} exhibit many signs of unconventional superconductivity thus playing an important role in advancing our knowledge of this important subject. One of the clearest signs of this unconventional pairing is a complex phase diagram with multiple superconducting phases. This is clearly the case for UPt_3 which has three distinct superconducting phases.^{3,5} On the other hand, UPd_2Al_3 and UNi_2Al_3 have simple phase diagrams with only one superconducting phase.⁶ The crystal structures of UPt_3 , UPd_2Al_3 , and UNi_2Al_3 are characterized by the same point group (D_{6h}) and the same Bravais lattice (simple hexagonal) with different numbers of uranium atoms in the basis (two for UPt_3 , one for UPd_2Al_3 and UNi_2Al_3).

So far no comprehensive microscopic theory exists for these materials. Many phenomenological approaches^{7,10} have tried to explain exotic superconductivity in UPt_3 . Most of them use a multidimensional superconducting order parameter transforming as a representation of the point group D_{6h} and a Ginzburg-Landau free energy invariant under this group. If one tries to apply this approach to describe superconductivity in UPd_2Al_3 and UNi_2Al_3 , it is necessary to choose an order parameter transforming as a different representation of the group D_{6h} . No single phenomenology is able to predict satisfactorily the relevant representation for each material.

In this paper, we apply the staggered-superconductivity Ginzburg-Landau theory^{11,12} to describe superconductivity in UPd_2Al_3 and UNi_2Al_3 . This theory has been successful in explaining the H-P-T superconducting phase diagram of UPt_3 ^{3,5} including the tetracritical point for all directions of the magnetic field. The distinctive feature of this theory is a superconducting order parameter transforming as an irreducible representation of the space group characterizing the crystal structure which resides away from the center of the Brillouin zone. Namely, we have finite center-of-mass or staggered pairing. For UPd_2Al_3 and UNi_2Al_3 , the star in the reciprocal space carrying the representation is determined by the negative pair hopping model.

We introduce a two-component H-point superconducting order parameter and write a free energy including gradient terms and coupling to a symmetry-breaking strain. Minimizing the free energy in the absence of the magnetic field, we find stability domains in the parameter space, and identify sequences of possible phases for each domain. Application of an external or spontaneous symmetry-breaking strain does not split the superconducting transition. The calculated upper critical field as a function of the temperature shows no kink. We introduce charge-density-wave and magnetic order parameters and investigate their possible coupling to the superconducting order parameter. Charge-density-wave order can be induced by staggered superconductivity suggesting a possible experimental test of the phenomenology. On the other hand, magnetic order cannot be induced.

The motivation for the staggered-superconductivity theory is based upon the theory of odd-in-frequency pairing characterized by a gap function which is an odd function of the frequency.^{13,14} This motivation is two-fold: (i) there are strong reasons to believe that an odd-in-frequency superconducting state cannot be stable for pairs with zero center-of-mass momentum,^{15,16} and (ii) the two-channel Kondo lattice, which is one candidate theory for heavy fermion compounds, has recently been shown to produce odd-frequency superconductivity in infinite spatial dimensions¹⁷ which is likely to be staggered for finite dimensionality. (For a recent review of two-channel Kondo lattice models and related physics, see¹⁸.)

In consequence, we develop a phenomenology for a non-uniform superconducting state described by a staggered superconducting order parameter and a negative pair hopping energy between uranium sites.¹⁵ We then write a hopping model for Cooper pairs assuming in-plane and out-of-plane nearest neighbors. The energy band for this model has a two-fold degenerate minimum for the crystal momenta located at the opposite corners $H_1; H_2$ of the Brillouin zone shown in Fig. 1. (For UPt_3 , the different number of uranium atoms in the basis moves the minimum to the M points.¹¹) Cooper pairs will con-

dense in states with these momenta so in this picture there are pairs with finite center-of-mass momenta. The Bloch functions $\psi_1(\mathbf{r}); \psi_2(\mathbf{r})$ of these states are uniquely determined by specifying the Wannier function. We assume that it transforms as a real one-dimensional representation of the uranium-site point group D_{6h} . For example, it will transform as A_2 if we use a two-channel quadrupolar Kondo model to describe UPd_2Al_3 .¹⁸ However, all the following results do not depend on this specific choice.

We introduce a two-component superconducting order parameter $\psi_1; \psi_2$ using the gap function $\Delta(\mathbf{r})$ ¹⁹ where \mathbf{r} is the pair center-of-mass coordinate:

$$\Delta(\mathbf{r}) = (\psi_1 - i\psi_2)\psi_1(\mathbf{r}) + (\psi_1 + i\psi_2)\psi_2(\mathbf{r}); \quad (1)$$

The choice of the coefficients in front of the Bloch functions gives the usual transformation properties under the time reversal transformation $\psi_1 \rightarrow \psi_1, \psi_2 \rightarrow \psi_2$. With respect to the space group D_{6h}^1 , the order parameter transforms as a two-dimensional H -point irreducible representation.

The free-energy density F is required to be invariant under the elements of the space group D_{6h}^1 , the $U(1)$ gauge transformations, and time reversal. We include coupling to the hexagonal-symmetry-breaking strains $\epsilon_1 = x^2 - y^2, \epsilon_2 = 2xy$ which transform as the center-of-Brilouin-zone representation E_{2g} . The bulk part F_0 and the gradient part F_g are given by

$$F = F_0 + F_g; \quad (2a)$$

$$F_0 = \frac{1}{2}(\mathbf{T}) \left[j_1^2 + j_2^2 + \epsilon_1 j_1^2 + j_2^2 + \epsilon_2 j_1^4 + j_2^4 + \frac{1}{2}\epsilon_1^2 + \frac{1}{2}\epsilon_2^2 \right]; \quad (2b)$$

$$F_g = \sum_n \left[\frac{1}{2} \dot{\mathbf{p}}_{x,n}^2 + \frac{1}{2} \dot{\mathbf{p}}_{y,n}^2 + \frac{1}{2} \dot{\mathbf{p}}_{x,n}^2 + \frac{1}{2} \dot{\mathbf{p}}_{y,n}^2 + \frac{1}{2} \dot{\mathbf{p}}_{x,n}^2 + \frac{1}{2} \dot{\mathbf{p}}_{y,n}^2 + \frac{1}{2} \dot{\mathbf{p}}_{x,n}^2 + \frac{1}{2} \dot{\mathbf{p}}_{y,n}^2 \right] + \sum_n \left[\frac{1}{2} \dot{\mathbf{p}}_{x,n}^2 + \frac{1}{2} \dot{\mathbf{p}}_{y,n}^2 + \frac{1}{2} \dot{\mathbf{p}}_{x,n}^2 + \frac{1}{2} \dot{\mathbf{p}}_{y,n}^2 + \frac{1}{2} \dot{\mathbf{p}}_{x,n}^2 + \frac{1}{2} \dot{\mathbf{p}}_{y,n}^2 + \frac{1}{2} \dot{\mathbf{p}}_{x,n}^2 + \frac{1}{2} \dot{\mathbf{p}}_{y,n}^2 \right] + \sum_n \left[\frac{1}{2} \dot{\mathbf{p}}_{x,n}^2 + \frac{1}{2} \dot{\mathbf{p}}_{y,n}^2 + \frac{1}{2} \dot{\mathbf{p}}_{x,n}^2 + \frac{1}{2} \dot{\mathbf{p}}_{y,n}^2 + \frac{1}{2} \dot{\mathbf{p}}_{x,n}^2 + \frac{1}{2} \dot{\mathbf{p}}_{y,n}^2 + \frac{1}{2} \dot{\mathbf{p}}_{x,n}^2 + \frac{1}{2} \dot{\mathbf{p}}_{y,n}^2 \right] + \sum_n \left[\frac{1}{2} \dot{\mathbf{p}}_{x,n}^2 + \frac{1}{2} \dot{\mathbf{p}}_{y,n}^2 + \frac{1}{2} \dot{\mathbf{p}}_{x,n}^2 + \frac{1}{2} \dot{\mathbf{p}}_{y,n}^2 + \frac{1}{2} \dot{\mathbf{p}}_{x,n}^2 + \frac{1}{2} \dot{\mathbf{p}}_{y,n}^2 + \frac{1}{2} \dot{\mathbf{p}}_{x,n}^2 + \frac{1}{2} \dot{\mathbf{p}}_{y,n}^2 \right]; \quad (2c)$$

Here $\mathbf{T} = a_0(\mathbf{T} - T_c)$ with $T_c = T_{c0} \left(\frac{1}{2} + \frac{1}{2} \right) = a_0$; $\epsilon_1, \epsilon_2, \epsilon_3$, and ϵ_4 are phenomenological Ginzburg-Landau parameters; $p = i\hbar \nabla - 2eA = \hbar c (e < 0)$. j_1^2 and j_2^2 enter the quadratic term in the bulk part F_0 with the same coefficient \mathbf{T} which is valid up to any order in the strains $\epsilon_1; \epsilon_2$ (the above expression demonstrating this explicitly up to the second order). This implies that the presence of any finite symmetry-breaking strains do not split the superconducting transition which is in agreement with experiment in that only one superconducting transition is found (despite the presence of

magnetic order at elevated temperatures which, at least for UPd_2Al_3 is not of the same moment variety found in UPt_3).⁶

Minimizing the free energy, we can investigate possible superconducting phases for $T < T_c$ in the absence of the magnetic field. There are two regions of stability in the parameter space $\psi_1; \psi_2$ in which the free energy has a stable lower bound. For the region I defined as $\psi_1 > 0, \psi_2 > 0$ there is only one phase $(\psi_1; \psi_2) = (i; 1)$ breaking the symmetry under the time reversal (as favored by the last term in the bulk part F_0). The region II defined as $\psi_1 + \psi_2 > 0, \psi_2 < 0$ is characterized by the phase $(\psi_1; \psi_2) = (0; 1)$ having only one component of the order parameter condensed.²⁰

Let us now discuss the upper critical field H_{c2} . Minimizing the free-energy functional with respect to the components of the superconducting order parameter and keeping only terms linear in them, we get two identical decoupled linearized Ginzburg-Landau equations. This means that the field H_{c2} does not have any kink as a function of the temperature T as observed experimentally (for UPt_3 there are three different decoupled equations, and the field H_{c2} is given by the largest of the three values generated by each equation so we get a kink corresponding to the tetracritical point¹¹). The dependence of H_{c2} on the direction of the magnetic field has the same form as the result for a conventional free energy with effective-mass anisotropy:

$$H_{c2}(T) = \frac{\hbar c}{2\pi j} \frac{\mathbf{T}}{R}; \quad (3a)$$

$$R = \frac{1}{2} \left[j_1^2 \cos^2 + j_2^2 \sin^2 \right]; \quad (3b)$$

with $\mathbf{T} = \psi_1 - i\psi_2$.

Finally, let us investigate the possibility of charge-density waves and magnetic order induced by staggered superconductivity. Starting from the staggered gap function (1), we can introduce order parameters for them in a very general way.²¹ The gap function $\Delta(\mathbf{r})$ does not have the periodicity of the original simple hexagonal Bravais lattice; it has the periodicity of a new larger simple hexagonal Bravais lattice of Fig. 2 with $a^0 = \sqrt{3}a, c^0 = 2c$. Thus the most general charge and magnetic structures are described by this new lattice and a basis consisting of six uranium atoms. Assigning different charges and magnetic moments for each element of the basis, we define six-component order parameters. The six components can be replaced by three interplanar-bonding combinations and three interplanar-antibonding ones. To simplify the following discussion, we can ignore the bonding combinations because they do not couple to the superconducting order parameter. Then the basis atoms in a plane and the basis atoms in a neighboring plane have the same charges $\psi_1; \psi_2; \psi_3$ and the same magnetic moments $\psi_1; \psi_2; \psi_3$.

The components $\mathbf{r}_1; \mathbf{r}_2; \mathbf{r}_3$ of the charge order parameter transform under the space group D_{6h}^1 as a three-dimensional reducible representation composed of the totally symmetric irreducible representation and a two-dimensional K -point irreducible representation (Fig. 1). The totally symmetric combination $\mathbf{r}_1 + \mathbf{r}_2 + \mathbf{r}_3$ represents the total charge in the large primitive cell which can be put equal to zero in the context of charge-density waves. Then the relevant part of the free-energy density is

$$F_{cdw} = \frac{1}{2} \mathbf{r}_1^2 + \frac{1}{2} \mathbf{r}_2^2 + \frac{1}{2} \mathbf{r}_3^2 + g_1 \mathbf{r}_1 \mathbf{r}_2 + g_2 \mathbf{r}_1 \mathbf{r}_3 + g_3 \mathbf{r}_2 \mathbf{r}_3 + \frac{1}{3} g_4 (\mathbf{r}_1 \mathbf{r}_2 + \mathbf{r}_1 \mathbf{r}_3 + \mathbf{r}_2 \mathbf{r}_3) \quad (4)$$

where \mathbf{r}_i and g_i are phenomenological Ginzburg-Landau parameters. Minimizing this free energy, we find possible charge-density-wave structures for all the superconducting phases identified above. There is no induced charge-density wave for the phase $(\mathbf{r}_1; \mathbf{r}_2) = (i; 1)$ at the region I. For the phase $(\mathbf{r}_1; \mathbf{r}_2) = (0; 1)$ at the region II, staggered superconductivity induces a charge-density wave described by the order parameter $(\mathbf{r}_1; \mathbf{r}_2; \mathbf{r}_3) = (2; 1; 1)$. The structure is characterized by new Bragg peaks $\frac{1}{3}n_1; \frac{1}{3}n_1 + n_2; n_3$ where n_1, n_2 , and n_3 are any integers. This important experimental prediction can be verified using neutron or x-ray scattering.

The components $\mathbf{r}_1; \mathbf{r}_2; \mathbf{r}_3$ of the magnetic order parameter transform under the space group as the product of the axial-vector representation and the representation for the charge order parameter discussed above. The product is a nine-dimensional reducible representation composed of two center-of-B Brillouin-zone irreducible representations and two K -point irreducible representations. In the free energy there are no invariants coupling the magnetic order parameter linearly to the square of the superconducting order parameter. Staggered superconductivity does not induce magnetic order (either in-plane or perpendicular-to-plane).

In summary, the Ginzburg-Landau theory of staggered superconductivity was applied to UPd_2Al_3 and UNd_2Al_3 . Motivated by odd-in-frequency pairing, we found the minimum of the negative hopping model for Cooper pairs at the corners $H_1; H_2$ of the Brillouin zone. We introduced a two-component superconducting order parameter $\mathbf{r}_1; \mathbf{r}_2$ transforming as an H -point irreducible representation of the space group. We constructed the free energy including gradient terms and coupling to symmetry-breaking strains. The superconducting transition is not split by any finite value of the strains. In the parameter space there are two zero-magnetic-field regions of stability characterized by the superconducting phases $(\mathbf{r}_1; \mathbf{r}_2) = (i; 1)$ and $(0; 1)$, respectively. The upper critical field as a function of the temperature has no kink. We defined charge and magnetic order parameters and investigated whether the superconducting order parameter can induce them. For the phase $(\mathbf{r}_1; \mathbf{r}_2) = (0; 1)$ there is an induced

charge-density wave characterized by new Bragg peaks $\frac{1}{3}n_1; \frac{1}{3}n_1 + n_2; n_3$ which could be seen by neutron or x-ray scattering.

We acknowledge useful discussions with F. B. Anders, R. Heid, T.-L. Ho, and H. R. Krishnamurthy. This research was supported by the National Science Foundation under Grant No. DMR-9420920. The part of this research done at the Institute for Theoretical Physics, University of California, Santa Barbara, California was supported by the National Science Foundation under Grant No. PHY-9407194.

Permanent address.

- ¹ N. G. Grewe and F. Steglich, in *Handbook on the Physics and Chemistry of Rare Earths*, edited by K. A. G. Schneider, Jr. and L. Eyring (Elsevier, Amsterdam, 1991), Vol. 14, p. 343.
- ² D. W. Hess, P. S. Riseborough, and J. L. Smith, in *Encyclopedia of Applied Physics*, edited by G. L. Trigg (VCH Publishers, New York, 1993), Vol. 7, p. 435.
- ³ G. B. Nuls, D. W. Eber, B. Wolf, P. Thalmeier, B. Luthi, A. de Visser, and A. M. Enosky, *Phys. Rev. Lett.* **65**, 2294 (1990).
- ⁴ S. Adenwalla, S. W. Lin, Q. Z. Ran, Z. Zhao, J. B. Ketterson, J. A. Sauls, L. Taillefer, D. G. Hinks, M. Levy, and B. K. Samal, *Phys. Rev. Lett.* **65**, 2298 (1990).
- ⁵ M. Boukhny, G. L. Bullock, B. S. Shivaram, and D. G. Hinks, *Phys. Rev. Lett.* **73**, 1707 (1994).
- ⁶ C. Geibel, A. Bohm, R. Caspar, K. G. Loos, A. G. Raul, P. Hellmann, R. Modler, C. Schank, G. Weber, and F. Steglich, *Physica B* **186**(188, 188 (1993).
- ⁷ D. W. Hess, T. A. Tokuyasu, and J. A. Sauls, *J. Phys. Condens. Matter* **1**, 8135 (1989).
- ⁸ T. Ohmichi and K. Machida, *Phys. Rev. Lett.* **71**, 625 (1993).
- ⁹ D.-C. Chen and A. Garg, *Phys. Rev. Lett.* **70**, 1689 (1993).
- ¹⁰ J. A. Sauls, *Adv. Phys.* **43**, 113 (1994).
- ¹¹ R. Heid, Ya. B. Bazaliy, V. M. Artisovits, and D. L. Cox, *Phys. Rev. Lett.* **74**, 2571 (1995).
- ¹² R. Heid, Ya. B. Bazaliy, V. M. Artisovits, and D. L. Cox, *Physica B* **223& 224**, 33 (1996).
- ¹³ A. V. Balatsky and E. Abrahams, *Phys. Rev. B* **45**, 13125 (1992).
- ¹⁴ A. V. Balatsky, E. Abrahams, D. J. Scalapino, and J. R. Schrieffer, *Physica B* **199& 200**, 363 (1994).
- ¹⁵ P. Coleman, E. Miranda, and A. Tsvetlik, *Phys. Rev. B* **49**, 8955 (1994).
- ¹⁶ R. Heid, *Z. Phys. B* **99**, 15 (1995).
- ¹⁷ M. Jarrell, H.-B. Pang, and D. L. Cox, *Phys. Rev. Lett.* **78**, 1996 (1997).
- ¹⁸ D. L. Cox and A. Zawadowski, preprint (to be published); Report No. cond-mat/9704103.
- ¹⁹ If our staggered order parameter arises from odd-frequency pairs, it must be understood to correspond to the expectation value of the first derivative of the equal time pair amplitude.
- ²⁰ In the region II, it is necessary to consider sixth-order

terms in the bulk free energy in order to lift the degeneracy present up to the fourth order.

- ²¹ J.-C. Toledano and P. Toledano, *The Landau Theory of Phase Transitions* (World Scientific, Singapore, 1987), Chap. VI.

FIG. 1. Brillouin zone for the simple hexagonal Bravais lattice and elements of stars for representations characterizing different order parameters. The stars $\Gamma_1; M_2; M_3g$ and $\Gamma_1; H_2g$ correspond to the superconducting order parameters for UPt_3 and UPd_2Al_3 , respectively. The stars Γ_g and $\Gamma K_1; K_2g$ describe the charge and the magnetic order parameters for UPd_2Al_3 .

FIG. 2. Original and cell-tripled hexagonal Bravais lattices (with only one plane shown) used to define the charge and the magnetic order parameters. The original lattice consists of all the points drawn. The new lattice consists of the points on the dotted lines and describes the most general charge and magnetic structures. Points characterized by different symbols represent uranium atoms with different charges and magnetic moments.





