arXiv:cond-mat/9712128v2 [cond-mat.supr-con] 21 May 1998

Enhanced Electron-Phonon Coupling and its Irrelevance to High T_c Superconductivity

[1]T. P. Devereaux, [2]A. Virosztek, [2]A. Zawadowski, [3]M. Opel, [3]P. F. Müller, [3]C. Hoffmann, [3]R. Philipp, [3]R. Nemetschek, [3]R. Hackl, [4]A. Erb, [4]E. Walker, [5]H. Berger and [5]L. Forró

[1]*Department of Physics, George Washington University, Washington, DC 20052*

[2]*Institute of Physics and Research Group of the Hungarian Academy of Sciences, Technical University of Budapest, H-1521 Budapest, Hungary and Research Institute for Solid State Physics, P.O.Box 49, H-1525 Budapest, Hungary*

[3]*Walther Meissner Institut, Bayerische Akademie der Wissenschaften, Garching, D-85748, Germany*

[4]*DPMC, Université de Genève, CH-1211 Genève, Switzerland*

[5]*EPFL, Ecublens, CH-1015 Lausanne, Switzerland*

It is argued that the origin of the buckling of the CuO_2 planes in certain cuprates as well as the strong electron-phonon coupling of the B_{1g} phonon is due to the electric field across the planes induced by atoms with different valence above and below. The magnitude of the electric field is deduced from new Raman results on $YBa_2Cu_3O_{6+x}$ and $Bi_2Sr_2(Ca_{1-x}Y_x)Cu_2O_8$ with different O and Y doping, respectively. In the latter case it is shown that the symmetry breaking by replacing Ca partially by Y enhances the coupling by an order of magnitude, while the superconducting T_c drops to about two third of its original value.

PACS numbers: 74.72.-h, 63.20.Kr, 78.30.-j, 71.10.-w

Recently there have been several suggestions [1] that out of plane oxygen vibrations of the CuO_2 plane may play an important role in mediating superconducting pairing in certain high temperature superconductors. It is also known that the presence of buckling (when the oxygen atoms are placed outside of the plane of the copper atoms) correlates with a strong interaction of a particular out-of-phase c-axis vibration (the so-called B_{1g} phonon) with planar quasiparticles [2]. As such, considerable attention has been focused on the strong interaction of electrons with this particular phonon and its connection to phonon-mediated $d_{x^2-y^2}$ superconductivity [3,4].

The present paper provides the first direct experimental evidence to support that the buckling and consequent large value of the electron- phonon interaction are indeed correlated as a result of a local crystal electric field surrounding the vibrating atoms. Using the above ideas in conjunction with a three band model for the electron system, the strength of the electron phonon coupling and consequently the value of the electric field perpendicular to the plane can be determined by fitting the Fano interference in the B_{1g} Raman spectra. We find that even though the electron-phonon coupling can be engineered in different materials to increase by an order of magnitude, the effect has essentially no correlation with T_c of the material. Therefore we argue that the B_{1g} phonon is irrelevant to superconductivity in the cuprates.

Raman scattering data are presented in the normal state for different doping levels of $YBa_2Cu_3O_{6+x}$ (Y-123) and $Bi_2Sr_2CaCu_2O_8$ (Bi-2212). Experimentally the electron-phonon coupling can be determined from the line shape of the B_{1g} Raman phonon for both Y-123 where the surroundings of the CuO_2 plane is highly asymmetric and Bi-2212 where the plane is placed in a more symmetrical environment with respect to the charges of the nearby atoms.

The resulting electron-phonon coupling is then used to interpret the Fano interference in the Raman spectra of Y-123, where the light is scattered by both the B_{1g} phonon and the electronic charge fluctuation in the plane described above.

However, for Bi-2212 the B_{1g} phonon has an almost Lorentzian line shape indicating the lack of any substantial coupling between that phonon and the charge transfer between the two oxygens in accordance with the absence of a significant electric field. This striking difference in the data taken on these two groups of materials can be considered as strong evidence in favor of the linear (involving one phonon) electron-phonon coupling due to the electric field. In order to complete this argument, the data for a Bi-2212 sample with the calcium partially (38%) substituted by yttrium are presented, where the doping most likely breaks locally the reflection symmetry through the CuO_2 plane, thereby making this material similar to the asymmetrical ones.

Finally, the value obtained for the electron-phonon coupling is in excellent agreement with the value calculated using the electric field value determined by the experimentally observed buckling [5,6] and the restoring force calculated from the frequency of the A_{1g} phonon. The change in the doping is essential in light of the closeness of the Fermi level to a van Hove singularity in the density of states.

Much of the development of the crystal field model was given in Ref. [7]. However, the electronic dispersion is now calculated for a three band model including direct $O-O$ hopping t' as well as $Cu-O$ hopping t [6]. As




FIG. 1. The unit cell of the CuO_2 plane shown with the atomic displacements corresponding to the B_{1g} (a) and A_{1g} (b) phonons. The electric field E perpendicular to the planes is due to the asymmetric environment (Ba^{2+} above, Y^{3+} below), and causes a static deformation of the A_{1g} type, usually referred to as buckling. $\delta\rho$ and the double arrows denote the charge transfer which accompanies the lattice vibration.

in Ref. [7] we consider only a reduced one band model appropriate for near half filling and take only the upper band into account. The electron - phonon reduced Hamiltonian for the B_{1g} $\mathbf{q} = 0$ phonon was given as

$$H_{el-ph} = \frac{1}{\sqrt{N}} \sum_{\mathbf{k},\sigma} g(\mathbf{k}) d^{\dagger}_{\mathbf{k},\sigma} d_{\mathbf{k},\sigma} [c + c^{\dagger}], \qquad (1)$$

where $d_{\mathbf{k},\sigma}$ annihilates an electron of spin σ and momentum $\mathbf{k}$, and $c^{\dagger}$ creates a B_{1g} phonon mode of wavevector $\mathbf{q} = 0$. The coupling constant $g(\mathbf{k})$ of the B_{1g} mode to an electron with momentum $\mathbf{k}$ was evaluated in Ref. [7] and is given by

$$g(\mathbf{k}) = eE \sqrt{\frac{\hbar}{2M\omega_{B_{1g}}}} \frac{1}{\sqrt{2}} [\mid \phi_x(\mathbf{k}) \mid^2 - \mid \phi_y(\mathbf{k}) \mid^2], \qquad (2)$$

where M is the oxygen mass, $\omega_{B_{1g}}$ is the phonon frequency, and E is the $\hat{\mathbf{z}}$- component of the electric crystal field at both the $O(2)$ and $O(3)$ sites. The functions $\phi_{x,y}$ are the amplitudes of the $O-$orbitals in the wave functions from the three band model [6].

In Ref. [7] a generalized form of the Breit-Wigner or Fano lineshape describing the interaction of a discrete excitation (phonon) with an electronic continuum was given in terms of the channel dependent electronic susceptibility χ_λ [8], the electron-phonon coupling constant, the effective photon-phonon coupling constant g_{p-p}, and the intrinsic damping Γ^i_λ of the phonon lineshape due to e.g. an anharmonic lattice potential. The expression for the full Raman response measured in channel λ was given as

$$\chi''_{\lambda,full}(\omega) = \frac{(\omega + \omega_a)^2}{(\omega^2 - \hat{\omega}^2_\lambda)^2 + [2\omega_\lambda \Gamma_\lambda(\omega)]^2}$$
$$\times \left\{ \gamma^2_\lambda \chi''_\lambda(\omega) \left[(\omega - \omega_a)^2 + 4\Gamma^i_\lambda \Gamma_\lambda(\omega) \left(\frac{\omega_\lambda}{\omega + \omega_a} \right)^2 \right] \right.$$
$$\left. + 4 g^2_{p-p} \Gamma^i_\lambda \left(\frac{\omega_\lambda}{\omega + \omega_a} \right)^2 [1 + \lambda(\omega)/\beta]^2 \right\}. \qquad (3)$$

The parameters are chosen to model the background spectrum seen of the normal state measured via Raman scattering. Then the remaining parameters are chosen to fit the Fano profile. Specifically, the effect of the parameters is as follows: the photon-phonon coupling constant g_{p-p} determines the position of the antiresonance ω_a of the Fano profile, the electron-phonon coupling constant g determines the asymmetry of the lineshape around the phonon position $\hat{\omega}$, which differs from its position ω in the absence of electron-phonon coupling, and the photon-electron coupling constant γ determines the overall strength of the background continuum under the phonon measured via Raman scattering [9]. Here $\gamma_{B_{1g}}$ is the projected part of the electron-photon vertex $\gamma(\mathbf{k})$ which possesses B_{1g} symmetry. $g^2_{B_{1g}}$ is the average of the coupling $\mid g(\mathbf{k}) \mid^2$ over the Fermi surface including the electron density for the two spins at a temperature T. We can now evaluate the Fano lineshape as a function of doping.

Before a comparison of the theoretical predictions with the data is made a few experimental details are given and the results are summarized. The Raman experiments were performed in back-scattering geometry, with the resolution set at 8 cm^{-1} being completely sufficient for the observation of the changes. The coordinate system is locked to the $Cu - O$ bonds with x = [100], x' = [110], etc. All symmetries refer to a tetragonal point group. The B_{1g} phonon and continuum are projected out with $x'y'$ polarization. The samples we used were of superior quality which manifests itself in a small transition width to the superconducting state and a large intensity ratio I_{phonon} to $I_{continuum}$. Y-123 in particular was prepared in $BaZrO_3$ resulting in an unprecedented purity of 99.995% [10]. More details of the samples will be described in another publication.

Results obtained at B_{1g} symmetry for Y-123 are plotted in Fig. 2 (a)-(c). All spectra are divided by the Bose-Einstein thermal function in order to get the response $\chi''_{\lambda,full}$ as described in Eq. (3). As a result of doping the shape of the B_{1g} phonon at approximately 330 cm^{-1} changes considerably. At low doping it is narrow and close to a Lorentzian. When carriers are added the line broadens and becomes more asymmetric exhibiting a Fano-type dependence on frequency. $I_{phonon}/I_{continuum}$ decreases since the B_{1g} continuum gains intensity [11]. Excellent fits to the data on optimally-doped Y-123 in both the superconducting and normal states were given in [7], which, when interpreted, supported evidence for $d_{x^2-y^2}$-pairing in this material. We now extend these results by examining fits to the normal state data of different samples and dopings. We find that once again excellent fits to the data can be obtained (Fig. 2). The respective fitting parameters for χ_λ (see [8]) are given in Table I.

We now can make a comparison to the crystal field model predictions for the electron-phonon coupling constant. We see from the fits that for Y-123 the coupling




FIG. 2. Comparison of the theory from the crystal field model to the B_{1g} Raman results on (from left to right) under-doped, optimally-doped, over-doped $YBa_2Cu_3O_{6+x}$, respectively, and optimally-doped (second panel from right) and $Y-$doped $Bi_2Sr_2(Ca_{1-x}Y_x)Cu_2O_{8+\delta}$ (right panel), respectively, and the scales for each are arbitrary. The parameters used are listed in Table I.

increases up to a factor of two with increasing doping. This can be understood in part by an increase in the density of states at the Fermi level with an increase in oxygen doping as the van Hove singularity moves closer to the Fermi level. Our calculations yield the following values for λ as a function of filling factor $< n >$: for $< n >= 0.875, \lambda = 0.0321$, for $< n >= 0.85, \lambda = 0.0382$, and for $< n >= 0.8, \lambda = 0.0482$ [6]. Here we have taken $T = 100K, t = 1.6eV, t'/t = 0.35$, the difference of Cu and O site energies $\varepsilon = 1eV, \omega_{B_{1g}} = 348\text{cm}^{-1}$, $M = 16m_P$, where m_P is the proton mass, and used a value of the electric field which is 1.3V/Å [7,6]. We observe that these values of λ are quite close to the values used to obtain the fits in Fig. 2. Given the assumption that the hopping and site energy parameters [7] are independent of doping, the agreement is quite good. The agreement could be refined once parameter choices for various levels of doping are determined via, e.g., fitting to experimentally observed Fermi surfaces.

In Bi-2212 (Fig. 2 (d)) the B_{1g} phonon line is much weaker while the continuum has roughly the same cross section as comparable Y-123 (Fig. 2 (b)). The bigger line width comes at least in part from inhomogeneous broadening as Bi-2212 single crystals cannot be synthesized stoichiometrically in equilibrium [12]. The electron-phonon coupling for Bi-2212 obtained from the fit is more than one order of magnitude smaller than for any of the Y-123 compounds and as a result the weight of the phonon is also reduced by at least the same amount. Indeed, in our model we would expect that the electron-phonon coupling is significantly smaller since the crystal electric field must be much weaker (the charges above and below the planes are not so drastically different as in Y-123) in this compound. We attribute then the small electron-phonon coupling to a much smaller local asymmetry and also to local inhomogeneities which manifest themselves in the larger linewidth of the phonon. A weaker spontaneous symmetry breaking is also possible.

Inhomogeneities can be introduced in a controlled way by replacing the Ca with $(Ca_{0.62}Y_{0.38})$ in Bi-2212. It is expected that significant parts of the CuO_2 planes experience a stronger local field loosing the reflection symmetry through that plane. Most likely, the Y replaces big regions of the Ca planes, just like in Y-123 where upon oxygen doping of the chains some of the chains are more doped than the others [13].

To test this idea we look at the measurements of Bi-2212 which has been doped with Y in place of Ca. When Y is doped in for Ca the line gains intensity and shifts by 15-20 cm^{-1} (Fig. 2 (e)). A reminder of the line found in Y-free crystals is still seen as a shoulder on the left-hand side of the new line. Since here the valence of the Y (+3) is different from that of Ca (+2), once again the mirror plane symmetry is broken and we would expect a much larger electron-phonon coupling than in the undoped compound. The fit to the B_{1g} data using Eq. (3) is given in Fig. (2e). The coupling constant (see Table I.) is indeed increased over that of the undoped compound when Y is introduced, and in accordance the intensity of the phonon line is also essentially enhanced. The fact that the Fano effect increases gives strong support for the crystal field coupling model as the driving source of electron-phonon coupling.

The electric field E perpendicular to the CuO_2 plane results in an A_{1g}-type static distortion of the plane since the charges of oxygen and copper are different. For an estimation of the buckling [5], a simplified model is sufficient [6] where Cu is pinned rigidly to the elementary cell, and the oxygen moves in a harmonic potential being characterized by the frequency of the A_{1g} phonon at $\omega_{A_{1g}} = 435$ cm^{-1} [14]. The restoring force at the buckling amplitude Δz must balance the electric force acting on the oxygen with charge $q = -1.75e$. Thus, $qE = M\omega_{A_{1g}}^2 \Delta z$ must hold. With the experimental value $\Delta z = 0.24\mathring{A}$ [5], $E = 1.53V/\mathring{A}$ is obtained which is close both to the $1.3V/\mathring{A}$ used for estimating the electron-phonon coupling strength and to the theoretically calculated number [15]. On the other hand, in the case

Fig.	α	$\hat{\omega}$	ω	τ^{*-1}	ω_a	Γ_i	λ	scale
(2a)	0.55	343	347.5	3000	352.5	4	0.0257	22
(2b)	0.95	340.5	348	1200	349.3	6.5	0.0426	20
(2c)	0.75	342	352	900	352.5	6	0.056	30
(2d)	0.1	305	305.2	1600	306.5	28	0.00131	20
(2e)	0.2	320	322	1200	326	20	0.0124	10

TABLE I. Summary of fitting parameters used in Fig. (2). All quantities except α, λ, and the scale factor (dimensionless) are given in units of cm^{-1}. Also $\omega_c = 12,000\ \mathrm{cm}^{-1}$ and $\beta' = 3.3$ have been used. A scale factor was multiplied to Eq. (3) to account for the overall magnitude of the cross section. Since the experimentally determined response is in arbitrary units, this has no affect on the conclusions.

of CuO_2 planes in a more symmetrical environment as in Bi-2212 and the infinite-layer compound $CaCuO_2$ the buckling, if it exists at all, is at least an order of magnitude smaller as found in structural studies [16].

In summary, studying Y-123 with different doping levels we have shown that the electric field across the CuO_2 planes is sufficiently strong to produce both the observed buckling and the strong electron-phonon coupling for the Fano line shape. In order to check this idea experiments were performed on Bi-2212 with and without Y doping. While the sample without Y shows very weak electron-phonon coupling, the interaction is enhanced by an order of magnitude and becomes comparable to the one in Y-123 if the local reflection symmetry is broken more substantially by replacing part of the Ca by Y. As doping Bi-2212 with Y results in a change of T_c from $T_c = 91.5K$ to $T_c = 57K$ along with a large increase of the coupling λ, the B_{1g} phonon can not play an important role for the superconductivity, in agreement with the conclusion of Savrasov and Andersen [3].

This work was supported by the Hungarian National Research Fund under Grant Nos. OTKA T020030, T016740, T02228/1996, T024005/1997. Acknowledgment (T.P.D.) is made to the Donors of The Petroleum Research Fund, administered by the American Chemical Society, for partial support of this research. A. Z. is grateful for enlightening discussions with O. K. Andersen and W. Pickett and for the support by the Humboldt Foundation. The experimental work was supported by the Bayerische Forschungstiftung via the consortium FORSUPRA. We are grateful to the BMBF for financial support via the program "Bilaterale wissenschaftlich-technische Zusammenarbeit" under grant no. WTZ-UNG-052-96. One of us (T.P.D.) was partially supported by the American Hungarian Joint Fund No. 587.

[1] A. Nazarenko and E. Dagotto, Phys. Rev. B **53**, R2987 (1996); T. Dahm *et.al.*, Phys Rev. B **54**, 12006 (1996); O. Jepsen *et.al.*, cond-mat/9710266 (to be published in J. Phys. Chem. Sol.).

[2] E. Altendorf *et al.*, Phys. Rev. B **47**, 8140 (1993), and references therein.

[3] S. Y. Savrasov and O. K. Andersen, Phys. Rev. Lett. **77**, 4430 (1996).

[4] N. Bulut and D. J. Scalapino, Phys. Rev. B **54**, 14971 (1996).

[5] J. D. Jorgensen *et.al.*, Phys. Rev. B **36**, 3608 (1987).

[6] Further details will appear in a forthcoming publication.

[7] T. P. Devereaux, A. Virosztek and A. Zawadowski, Phys. Rev. B **51**, 505 (1995).

[8] In [7] the form for χ used was that derived by one of us when electron dynamics is considered in materials which possess nesting properties along the Fermi surface [A. Virosztek and J. Ruvalds, Phys. Rev. B **45**, 347 (1992)]:

$$\chi''_\lambda(\omega) = N_F \omega \bar{\tau}_\lambda^{-1} / [\bar{\omega}^2 + \bar{\tau}_\lambda^{-2}], \text{ where}$$

$$\bar{\tau}_\lambda^{-1} = \tau_\lambda^{*-1} + \alpha\sqrt{(\beta' T)^2 + \omega^2}, \text{ and}$$

$$\bar{\omega} = \omega m^*(\omega)/m,$$

$$\text{with } m^*(\omega)/m = 1 + \frac{2\alpha}{\pi}\ln[\omega_c/\sqrt{(\beta' T)^2 + \omega^2}].$$

Here $1/\tau_\lambda^* = 1/\tau_{m=0} - 1/\tau_\lambda$ is the channel-dependent impurity scattering rate reduced by vertex corrections [A. Zawadowski and M. Cardona, Phys. Rev. B **42**, 10732 (1990)], and α, β' and ω_c are constants determined by a fit to the electronic continuum in the normal state. This form for the Raman susceptibility provides an adequate description to the continuum in the normal state of both Y-123 and Bi-2212.

[9] These parameters are related as in [7]

$$\beta = 2 g_{p-p} g_{B_{1g}} [\gamma_{B_{1g}} \omega_{B_{1g}}]^{-1}, \qquad \omega_a^2 = \omega_{B_{1g}}^2 [1 + \beta],$$

$$\lambda(\omega_{B_{1g}}) = g_{B_{1g}}^2 / \omega_{B_{1g}},$$

$$\Gamma_{B_{1g}}(\omega_{B_{1g}}) = \Gamma_{B_{1g}}^i + g_{B_{1g}}^2 \chi''(\omega_{B_{1g}})/N_F,$$

with N_F the density of states per spin at the Fermi level.

[10] A. Erb, E. Walker, J.-Y. Genoud and R. Flükiger, Physica C **282-287**, 89 (1997).

[11] T. Katsufuji *et al.*, Phys. Rev. B **48**, 16131 (1993); X.K. Chen *et al.*, Phys. Rev. B **56**, R513 (1997); R. Nemetschek *et al.*, Phys. Rev. Lett. **78**, 4837 (1997).

[12] B. Revaz, private communication.

[13] S. Pekker *et.al.*, Physica C **181**, 11 (1991).

[14] This assumption is a reasonable approximation for results obtained by ab-initio frozen-phonon calculations [C.O. Rodriguez et al. Phys. Rev. B **42**, 2692 (1990)].

[15] J. Li and J. Ladik, Sol. State Commun. **95**, 35 (1995).

[16] J. Karpinski *et.al.*, Physica C **234**, 10 (1994). It remains to study why the electronic energy calculations provide a spontaneous symmetry breaking for $CaCuO_2$.