

# Role of Conduction Electrons in the ortho-KC<sub>60</sub> Polymer

T. Ogitsu, K. Kusakabe, S. Tsuneyuki and Y. Tateyama

Institute for Solid State Physics, University of Tokyo, Roppongi, Minato-ku, Tokyo 106, Japan  
(April 15, 2024)

We present first-principles band calculations as well as structural optimization of the orthorhombic KC<sub>60</sub> polymerized phase. We found three-dimensional inter-fullerene bonding/anti-bonding characters consisting of t<sub>1u</sub> molecular orbitals with p-like symmetry in the conduction bands. The formation of the four-membered ring connecting the fullerenes lifts the p<sub>x</sub> band from the continuous p<sub>y</sub>-p<sub>z</sub> band, where the z-axis is parallel to the chain. The asymmetry between p<sub>x</sub> and p<sub>y</sub> may play an important role in binding the chains with the proposed rotational conformation [1].

31.15 Ar, 61.46+ w, 61.48+ c, 61.50-f, 71.20-b

The recent discoveries of new alkali-doped fullerene polymers [1] [2] [3] [4] [5] show diversity in the geometries of the interconnections of fullerenes. An impressive property of this polymer family is that the charge state of the fullerene seems to govern the polymer geometry. The A<sub>1</sub>C<sub>60</sub> (A = K, Rb) [1] [2] and the Na<sub>2</sub>RbC<sub>60</sub> polymers [3] [4] have one-dimensional interconnections, while the Na<sub>4</sub>C<sub>60</sub> polymer has two-dimensional interconnections. Even in the case of the one-dimensional polymers, we can find a remarkable difference between the A<sub>1</sub>C<sub>60</sub> (A = K, Rb) and the Na<sub>2</sub>RbC<sub>60</sub> polymers; the former is known to have two covalent bonds between the fullerenes [1], while the latter is deduced from its larger inter-molecular separation [3] [4] to have one covalent bond. These dramatic differences in bonding which are controlled by the charge states give rise to the question as how the excess electrons on the fullerenes affect the polymer geometry.

In this paper, we present a first-principles electronic structure study of the ortho-KC<sub>60</sub> polymer to elucidate how the electronic states of the conduction bands are related to its one-dimensional polymer geometry. Although electronic band structure calculations of A<sub>1</sub>C<sub>60</sub> have been reported by two other groups [7] [8], to our knowledge, this is the first quantitatively reliable calculation on the system with a realistic atomic conformation. The calculation method is based on the density functional theory within the local density approximation (DFT-LDA) [6]. A plane-wave basis expansion and optimized pseudopotentials in separable form were adopted in this simulation.

Structural optimization is performed on the KC<sub>60</sub> polymer, which has an orthorhombic unit cell containing two C<sub>60</sub> molecules and two K atoms. The cell parameters are fixed at the experimental values [1]. Initially, the C<sub>60</sub> molecules are placed at the body-centered positions, in which the atomic conformation of an isolated I<sub>h</sub>C<sub>60</sub> molecule is used. We choose the initial orientational conformation of the fullerenes as the one proposed by Stephens et al. [1], i.e., the unit cell is taken to be simple orthorhombic. The structural optimization is then performed without any symmetry constraint. To obtain as precise a geometry as possible, we have checked the convergence of the geometry as a function of the cut-

o energy for plane waves ranging from 30Ry to 80Ry with uniform sampling of either one ( ) or four k-points. The geometry is relaxed until all the forces acting on the atoms become less than  $5 \times 10^{-4}$  [Hartree/au]. Covalent bonds spontaneously appeared between the  $C_{60}$  molecules during the optimization process, resulting in a one-dimensional chain structure.

The calculated bond lengths are displayed in TABLE 1 along with the experimental values. The calculated values are consistent with the experimental values within the limit of error, with the largest discrepancy occurring in the C1-C1 intra-fullerene distance. Refinement of the experimental value (1.74Å) is desired, since it seems quite large compared with the typical C-C bond lengths known thus far.

Let us discuss the geometrical character of the KC<sub>60</sub> polymer from the viewpoint of the coupling between the conduction electrons and the deformation of the  $C_{60}$  molecule. It would be natural to speculate that the character of the LUMO state of isolated  $C_{60}$  would be reflected in the conduction band. Therefore, we shall note the symmetry of the LUMO state of isolated  $I_h C_{60}$  before explaining the resultant structure.

The LUMO of the  $I_h C_{60}$  molecule are threefold-degenerate  $t_{1u}$  states with p-like symmetry. The coordinate axes for these p-like ( $t_{1u}$ ) states can be mapped on the three orthogonal  $C_2$  rotational pivots on the  $I_h C_{60}$  molecule.

If we now go back to the calculated polymer structure, we note that the chain direction is parallel to one of the  $C_2$  rotational pivots. Therefore, if we take the chain direction as the z-axis of the  $t_{1u}$  states, the other two coordinate axes are automatically determined: one (x-axis) is on the plane which includes the four-membered ring of the inter-molecular connection and the other (y-axis) is normal to the above two. We then measure the diameters of the polymerized fullerene along these coordinate axes. Interestingly, even the two diameters normal to the chain are significantly different from each other: they are 6.98Å and 6.83Å along the x- and y-axes, respectively. As is expected, the diameter along the z-axis is elongated to 7.48Å.

We emphasize here that this ellipsoidal distortion may be plausibly associated with the Jahn-Teller effect; however, as will be clarified later in this paper, the relative positions of the  $t_{1u}$  levels in the polymer are instead determined by the crucial change in the local electronic states around the four-membered ring connecting the fullerenes as well as the strength of the inter-molecular interaction.

The electronic states of this orthorhombic polymer crystal have been investigated using the first-principles band calculation method. The householder diagonalization method with a plane-wave expansion is used to maintain the symmetry of the eigenstates as precisely as possible. The cutoff energy for the plane waves is reduced to 25Ry to save on the computational cost. The number of basis functions is then reduced to 25000. We note

here that the convergence of the band structure has been confirmed for both diamond and potassium crystals with this cutoff energy, though it is inadequate for the structural optimization. Because the diagonalization of a matrix with a dimension of 25000 requires a huge amount of CPU time even for the newer parallel supercomputers, we did not perform fully a self-consistent diagonalization calculation but instead obtained the eigenvalues and the eigenstates through the following two steps. First, the effective potential for the Kohn-Sham equation was calculated self-consistently by means of conjugate gradient minimization of the total energy, in which 75 uniform  $k$ -points in the first Brillouin zone were sampled. We then diagonalized the matrix calculated from the given effective potential.

The calculated band structure is shown in FIG. 2. Although the band dispersion along the  $\Gamma$ -H line (parallel to the chain) is slightly larger than that along the  $\Gamma$ -M line (normal to the chain), the band structure indicates essentially three-dimensional character. This is qualitatively consistent with previous calculations [7] [8], although the band profile is considerably different. Empirical tight-binding calculations by Tanaka et al. [7] gave a similar band structure along the  $\Gamma$ -M line, while the  $\Gamma$ -H dispersion was not fully represented by the simplified model Hamiltonian. In a different paper, Tanaka et al. also pointed out that the dispersion of the conduction band is very sensitive to the orientational configuration of the chains [9]. This is probably why the discrepancy with the DFT-LDA calculation for  $\text{RbC}_{60}$  by Erwin et al. [8] is much worse: they used a model structure in which all the chains have the same orientation so that the unit cell includes only one  $\text{A}_1\text{C}_{60}$  unit, while in the Reithveld model [1] and therefore in the resultant structure of the present calculation, the adjacent chains are rotated by  $90^\circ$  from each other.

Next, we would argue the character of the conduction band. The lower six conduction bands seem to be categorized from their profiles along  $\Gamma$ -M line as three sets of two pairs as follows (FIG. 1.): looking at the energy levels at the  $\Gamma$ -point, the lowest and the third lowest, the second and the fourth lowest, the fifth and the sixth lowest, can be recognized as pairs.

Direct inspection of these wavefunction ensures the above categorization. We have examined the iso-surfaces of these six wavefunctions at the  $\Gamma$ -point. Those belonging to the lowest and the third lowest are displayed in FIG. 2 (a) and (b), respectively.

We can clearly see the bonding and the anti-bonding characters of the wavefunctions between the polymer chains in FIG. 2. (a) and (b), respectively. Furthermore, we can see the  $t_{1u}$  character surviving in these states, i.e. the character of the  $\text{C}=\text{C}$  double bonds and the nodal plane which includes the four-membered ring connecting the fullerenes. There is almost no evidence of hybridization with the other states. The  $t_{1u}$  symmetry and the bonding/anti-bonding characters as described above are also seen in the other four eigenstates, though the  $t_{1u}$

mark in the sixth eigenstate is weakened; the second (see FIG. 3.) and the fourth lowest eigenstates at the  $\Gamma$ -point have a nodal plane normal to the chain, while the fifth (see FIG. 4.) and the sixth lowest eigenstates have a nodal plane normal to the above two nodal planes.

We can now understand that the wavefunctions of the conduction bands of the ortho-KC<sub>60</sub> polymer are, at least at the  $\Gamma$ -point, linear combinations of the  $t_{1u}$  molecular orbitals (MOs) as follows,

$$p_i = \frac{1}{\sqrt{2}} (p_i^0 + p_i^1); \quad i = x, y, z; \quad (0.1)$$

Here,  $p_i$  and  $p_i^0$  denote the MOs belonging to the first and the second fullerenes in the unit cell, respectively. Note that the x-axis for the first fullerene is taken to be parallel to the y-axis for the second fullerene, since the coordinate axes of these p-like states for each fullerene have been taken independently so that the x-axis includes the four-membered ring connecting the fullerenes.

Due to the polymerization, the threefold degenerate  $t_{1u}$  states split into three different levels,  $E_{p_x}$ ,  $E_{p_y}$ , and  $E_{p_z}$ . These levels then constitute the inter-chain bonding/anti-bonding states, and the lowest state which has the inter-chain bonding character will be occupied. Clear inter-chain bonding character can be seen in FIG. 2. (a), where the inter-chain interaction is large enough to form a conduction band with three-dimensional dispersion.

We note here that the occupied levels associated with the four-membered ring connecting the fullerenes sink below the energy gap and so have not appeared in the above discussions. This may be confounding because alkali doping is known to be crucial to the synthesis of the ortho-KC<sub>60</sub>. Below, we argue as to how the formation of the covalent connections couples with the profile of the conduction band.

We now focus on the change in the local electronic states around the carbon atoms forming the four-membered ring. Due to the polymerization, the local electronic states are converted from  $sp^2$  to  $sp^3$ . This means that the  $p_x$  and  $p_y$  states of the  $sp^2$  re-hybridize into the  $sp^3$  states of the  $sp^3$ . We emphasize here that  $p_x$  has an amplitude around the ring (see FIG. 4), while  $p_y$  and  $p_z$  do not. This means that only the levels which are functions of  $p_x$  will be affected by the re-hybridization. As can be seen from FIG. 1., the  $p_x$  band is lifted about 0.7 eV from the  $p_y$ / $p_z$  band, and forms a continuous band with the higher energy states.

To confirm above the scenario in which the re-hybridization lifts only the  $E_{p_x}$  level, we have performed first-principles MO calculations on two different C<sub>60</sub> molecules having geometry equivalent to the polymer using Gaussian 94 [10]. One is the bare C<sub>60</sub> molecule and the other is the C<sub>60</sub> molecule with the two carbon atoms which belong to the four-membered ring terminated with hydrogen bonds. In these calculations, Becke's 3 parameter hybrid method [11] with Perdew's gradient-corrected

correlation functional [12] (B3P86) and a 6-31G basis set were used. The bare deformed fullerene shows a too-low  $E_{p_x}$  level, with  $E_{p_x} = 4.6\text{eV} < E_{p_z} = 4.2\text{eV} < E_{p_y} = 4.1\text{eV}$ , while hydrogen termination serves to lift the  $E_{p_x}$  level, giving levels comparable to the band calculation, with  $E_{p_z} = 4.0\text{eV} < E_{p_y} = 3.9\text{eV} < E_{p_x} = 2.9\text{eV}$ . Thus, we conclude that the formation of the four-membered ring connecting the fullerenes raises the  $p_x$  band from the continuous  $p_y\{p_z$  band. In the latter MO calculation, the sequence,  $E_{p_z} < E_{p_y}$ , is opposite from the  $\Gamma$ -point levels of our band calculation, but the difference is small in both cases. This is due to the crystal field effect, which is observed as the difference in the strength of the inter-fullerene interaction; in  $p_y$ , intra-chain as well as inter-chain bonding character can be seen between the fullerenes, while the no intra-chain bonding character can be seen in  $p_z$ ; (see FIG. 3).

Finally, we argue as to how the orientational conformation of the chains could be restricted as was reported experimentally [1]. There may be two key factors, one of which is the symmetry of the  $t_{1u}$  molecular orbitals, the other being the rise of the  $E_{p_x}$  level above  $E_{p_y}$  and  $E_{p_z}$  as seen in our results.

Nikolaev et al. calculated the  $t_{1u}$  level splitting in the FCC  $A_1C_{60}$  crystal [14] as the function of the orientational conformation of the fullerenes by model calculations in which the symmetry of the  $t_{1u}$  state as well as the charge state of the fullerene are taken into account. They found that the two conformations which correspond to the local maxima in the energy splittings can be extended to represent the ortho- $A_1C_{60}$  ( $A = K, Rb$ ) and monoclinic  $A_2A^0C_{60}$  ( $A = Na, A^0 = K, Rb$ ) polymers. Tanaka et al., using the empirical tight binding method [9], found that even in the orthorhombic  $A_1C_{60}$  polymer, two orientational conformations of the chains give local maxima in the band width.

Although the threefold degenerate  $t_{1u}$  eigenfunctions have p-like symmetries, they cannot be represented by spherical harmonics with  $l = 1$ . Owing to the icosahedral symmetry of the fullerene, they must be represented as the linear combinations of  $Y_m$  with  $l = 5$  [14]. The above studies suggest that the symmetry of the  $t_{1u}$  state is the major factor in determining the geometry of the ortho- $A_1C_{60}$  polymer. We then have to question as to why, if the model calculations show comparable energies for both local minima,  $A_1C_{60}$  chooses an angle of 45 degrees.

We can speculate that the asymmetry between the x-direction and the y-direction around the chain causes the energy difference between the orientational conformations. The considerable rise of the  $p_x$  band from the continuous  $p_y\{p_z$  band, or the difference in the diameters along the x-axis and along the y-axis may be the reason for the preference of the observed orientational conformation [1].

Further first-principles calculations of other orientational conformations, or of polymers with different charge states, are required to clarify the role of the conduction electrons in determining the polymer geometry.

In conclusion, we have performed semi-SCF DFT-LDA band calculations as well as first-principles geometry optimization of the ortho-KC<sub>60</sub> polymer. The simulations were performed using cell dimensions equivalent with experiment. The resulting band has a three-dimensional dispersion which has a considerably different profile from those previously calculated [7] [8]. We found that the lower six conduction eigenstates at the  $\Gamma$ -point are represented as the linear combination of the  $t_{1u}$  MOs. The rise of the  $p_x$  band is found to be due to the local conversion of the electronic state, from  $sp^2$  to  $sp^3$ , by the formation of the four-membered ring connecting the fullerenes. The conduction electrons will assist to form the one-dimensional chain as well as to bind the chains in the orthorhombic cell with this peculiar orientational conformation.

The authors thank Professor Iwasa for stimulating discussions. T.O. thanks Dr. Suzuki for helpful suggestions. T.O. also thanks Dr. T.M. Briere for critical readings of this manuscript. This work was performed on Fujitsu VPP500 supercomputers at the super computer center, Institute for Solid State Physics, Univ. of Tokyo and at the computer center, Nagoya University, the VPP700 at RIKEN and at the computer center, Kyushu University, and on the Hitach SR2201 at the computer centre, University of Tokyo. This work was conducted as part of the JSPS Research for the Future Program in the Area of Atomic-Scale Surface and Interface Dynamics.

- 
- [1] P. W. Stephens, G. Bortel, G. Faigel, M. Tegze, A. Janossy, S. Pekker, G. Oszlanyi and L. Forro, *Nature* 370, 636 (1994).
  - [2] O. Chauvet, G. Oszlanyi, L. Forro, P. W. Stephens, M. Tegze, G. Faigel, and A. Janossy, *Phys. Rev. Lett.* 72, 2721 (1994).
  - [3] K. Prassides, K. Vavakis, K. Kordatos, K. Tanigaki, G. M. Bendele, and P. W. Stephens, *J. Am. Chem. Soc.* 119, 834 (1997).
  - [4] G. M. Bendele, P. W. Stephens, K. Prassides, K. Vavakis, K. Kordatos, and K. Tanigaki, submitted to PRL.
  - [5] G. Oszlanyi, G. Baumgartner, G. Faigel, and L. Forro, *Phys. Rev. Lett.* 78, 4438 (1997).
  - [6] M. C. Payne, M. P. Teter, D. C. Allen, T. A. Arias, and J. D. Joannopoulos, *Rev. Mod. Phys.* 64, 1045 (1992), and references therein.
  - [7] K. Tanaka, Y. Matsuura, Y. Oshima, T. Yamabe, H. Kobayashi, and Y. Asai, *Chem. Phys. Lett.* 241, 149 (1995).
  - [8] S. C. Erwin, G. V. Krishna, and E. J. Mele, *Phys. Rev. B*, 51, 7345 (1995).
  - [9] K. Tanaka, T. Saito, Y. Oshima, T. Yamabe, and H. Kobayashi, *Chem. Phys. Lett.* 272, 189 (1997).
  - [10] M. J. Frisch, G. W. Trucks, H. B. Schlegel, P. M. W. Gill, B. G. Johnson, M. A. Robb, J. R. Cheeseman, T. Keith,

G .A .Petersson, J.A .M ontgom ery, K .R aghavachari, M .  
A .A Haham , V .G .Zakrzew ski, J.V .O rtiz, J.B .Fores-  
m an, J.C ioslow ski, B .B .Stefanov, A .N anayakkara, M .  
C hallacom be, C .Y .Peng, P .Y .A yala, W .Chen, M .W .  
W ong, J.L .Andres, E .S .R eplogle, R .G om perts, R .L .  
M artin, D .J.Fox, J.S.B inkley, D .J.D efrees, J.Baker,  
J.P .Stewart, M .H ead-G ordon, C .G onzalez, and J.A .  
Pople, Gaussian, Inc., Pittsburgh PA , 1995.

- [1] A .D .Becke, J.Chem .Phys. 98, 5648 (1993).  
[2] J.P.Perdew and Y.W ang, Phys.Rev.B 33, 8800 (1986).  
[3] Based on the M O calculations, we have further discussed  
why the  $t_{1u}$  character can survive in the polym er phase.  
See, T.O gitsu, K.Kusakabe, T.M .B riere, Y.Tateyam a,  
and S.T suneyuki, subm itted to the proceedings of M a-  
terial Research Society, fall 97 m eeting.  
[4] A .V .N ikolaev, K .P rassides, and K .M ichel, subm itted  
to J.Chem .Phys.

	Experm ent	T his work	
Lattice param eter [Å]	9.109(5)		-
	9.953(5)		-
	14.321(5)		-
C1-C1 inter-fullerene	1.65 0.20	1.62	
C1-C1 intra-fullerene	1.74 0.20	1.59	
C1-C2, C1-C3	1.50 0.20	1.51	

TABLE I. The calculated structural param eters and the  
experim ental values. The notation is the sam e as Stephens et  
al. [1]

FIG. 1. Band structure of the ortho-KC<sub>60</sub> polymer. The  $\Gamma$ -H direction is parallel to the chain and the  $\Gamma$ -M direction is normal to the chain. The vertical axis denotes the energy in eV. The origin placed at the Fermi level. Note: the Fermi level is not determined self-consistently; it is evaluated as the energy where the filling becomes half of the full occupation number during preparation of the effective potential by the CG method.

FIG. 2. The iso-surfaces of the lowest, (a), and the third lowest, (b), eigenstate wavefunctions at the  $\Gamma$ -point are drawn with the atoms represented by a ball and stick model in the orthorhombic unit cell. The yellow balls denote the carbon atoms, and the white balls denote the potassium atoms. The viewpoint is parallel to the chain direction. The iso-level is set to 1/5 of the maximum absolute amplitude. The yellow and the blue curved surfaces denote the iso-surfaces of the positive and negative values of the wavefunction, respectively.

FIG. 3. The iso-surfaces of the second lowest eigenstate wavefunction at the  $\Gamma$ -point is drawn with the atoms represented by a ball and stick model in the orthorhombic unit cell. The viewpoint is normal to the chain direction.

FIG. 4. The contour plot of the fifth lowest eigenstate wavefunction at the  $\Gamma$ -point is drawn with the atoms represented by a ball and stick model in the orthorhombic unit cell. The blue and red areas correspond to the negative and positive values of the wavefunction, respectively. The viewpoint is normal to the chain direction. The contour plane includes the four-membered ring connecting the fullerenes.

This figure "Fig1.jpg" is available in "jpg" format from:

<http://arxiv.org/ps/cond-mat/9712285v1>

This figure "Fig2a.jpg" is available in "jpg" format from:

<http://arxiv.org/ps/cond-mat/9712285v1>

This figure "Fig2b.jpg" is available in "jpg" format from:

<http://arxiv.org/ps/cond-mat/9712285v1>

This figure "Fig3.jpg" is available in "jpg" format from:

<http://arxiv.org/ps/cond-mat/9712285v1>

This figure "Fig4.jpg" is available in "jpg" format from:

<http://arxiv.org/ps/cond-mat/9712285v1>