Fingering Instability of D islocations and R elated Line D efects

Ming Li^y, Brian B. Smith, and Robin L.B. Selinger

Physics Department, Catholic University of America, Washington, DC 20064

^y Center for Nonlinear Science, Los A lam os National Laboratory, Los A lam os, New Mexico 87545

(M arch 23, 2024)

W e identify a fundam entalm orphological instability of mobile dislocations in crystals and related line defects. A positive gradient in the local driving force along the direction of defect motion destabilizes long-wavelength vibrational modes, producing a $\$ ngering" pattern. The minimum unstable wavelength scales as the inverse square root of the force gradient. We demonstrate the instability's onset in simulations of a screw dislocation in Al (via molecular dynamics) and of a vortex in a 3-d XY $\$

PACS numbers: 61.72 Lk, 62.20 Fe, 75.10 Hk, 47.32 Cc

M odeling the motion of dislocations in crystals is mathematically challenging due to their long-range interaction through the elastic strain eld¹, and computational approaches include atom istic molecular dynamics^{2;3} and mesoscale models^{4;5}. In some contexts the complexity of the problem can be reduced by approximating the motion of an individual dislocation as that of a damped elastic string⁶, and such models can be used to describe the motion of other types of line defects as well, e.g. magnetic ux lines in type-II superconductors. Recent research using this approach has focused on locked vs. running behavior⁷ of a line defect in a periodic potential due to the underlying crystal lattice. A morphological instability associated with a periodic driving force at a frequency resonant with the periodic potential has also been studied⁸.

In the present Letter we identify a ngering instability in the glide of a mobile line defect under a spatially varying driving force that increases along the direction of motion. This work was motivated by unpublished molecular dynam ics studies of screw dislocation pair annihilation in pure Cu performed by Swam inarayan and LeSar⁹. The simulations appeared to show that initially straight parallel screw dislocations of opposite Burgers vector spontaneously developed a wavy pro leprior to pair annihilation, something like the wellknown C row instability of parallel vortices in

uid dynam ics¹⁰. We were motivated by this result to consider whether the instability is driven by the attractive force gradient between the dislocations, and indeed whether a single dislocation could be unstable under a positive gradient in the driving stress. Since such stress gradients arise from common sources(e.g. external loading or dislocation interactions with a free surface or other microstructural features(such an instability might be active during metal deformation.

Consider the stability of an initially straight dislocation under an attractive force gradient, approximating its response as that of a damped elastic string. (The approximation is useful only to model the onset of any instability, because once the defect line deviates strongly from its initial state then nonlocal interactions can no longer be neglected.) The string's displacement obeys the familiar wave equation with linear damping and a spatially varying driving force:

$$\frac{\theta^2}{\theta t^2} = c^2 \frac{\theta^2}{\theta z^2} - \frac{\theta}{m} \frac{\theta}{\theta t} + \frac{F(z;t)}{m}; \qquad (1)$$

Here (z;t) is the displacement of the string in the x direction, c is the wave speed of an oscillation on the string, is a linear damping coe cient, m is the mass per unit length, and F (z;t) is the driving force per unit length along the string. We take periodic boundary conditions with z in the interval (0;L). For our present purposes we do not include an underlying periodic potential; this is appropriate for modeling dislocation motion in FCC metals where the Peierls stress is small and unpinned dislocations are mobile even at low temperature.

We consider a driving force with a value that increases linearly in the direction the string is moving, as if the string were moving down a hill that gets continuously steeper. The force on the string at any point along its length may then be written:

$$F(z;t) = F_0 + F_1(z;t):$$
(2)

Any portion of the string that gets slightly ahead of the rest feels a stronger driving force. More generally Eqn. (2) represents the state two terms in an expansion, so that F_1 is defined as the local gradient of a spatially dependent driving force. If $F_1 > 0$ the force gradient is destabilizing and will cause a sinusoidal perturbation of su ciently long wavelength to grow rather than die away, while small wavelength perturbations are suppressed by line tension, as shown below.

To linearize the equation we switch to a (non-inertial) moving reference fram e. Consider perturbations \sim (z;t) from a stable uniform running solution $_0$ (t),

$$(z;t) = _{0}(t) + ^{\sim}(z;t)$$
 (3)

where

$$\frac{\theta^2}{\theta t^2} = \frac{\theta}{m} \frac{\theta}{\theta t} + \frac{F_0}{m} + \frac{F_1}{m} _0:$$
(4)

This procedure gives rise to the linearized equation of motion for the perturbation:

$$\frac{\theta^2}{\theta t^2} = c^2 \frac{\theta^2}{\theta z^2} - \frac{\theta}{m} \frac{\theta}{\theta t} + \frac{F_1}{m} \sim :$$
(5)

Taking a solution of the form $\sim = A e^{i(kz \ ! t)}$; we not the dispersion relation

$$! (k) = \frac{i}{2m} - \frac{1}{2} - \frac{i}{m^2} - 4 - \frac{F_1}{m} - c^2 k^2 :$$
 (6)

W e identify three regions of k.

(1) Underdam ped region: short wavelength ($k > k_d$, or < d) perturbations are underdam ped, with

$$k_{\rm d} = \frac{r}{\frac{2}{4c^2m^2} + \frac{F_1}{mc^2}};$$
(7)

We identify a characteristic length $_{d} = 2 = k_{d}$ as the wavelength associated with critical dam ping; modes with smaller wavelength are underdam ped.

(2) O verdam ped region: for interm ediate wavelength (k < k < k_d, or $_d$ < ~) perturbations are overdam ped. The cut-o ~ value k is

$$k = \frac{r}{\frac{F_1}{m c^2}}$$
(8)

W e identify the characteristic length

$$= \frac{2}{k} = 2 \qquad \frac{m c^2}{F_1}:$$
(9)

Note that decreases as the stress gradient F_1 increases, and that it is independent of the damping constant \cdot .

(3) Unstable region: long wavelength modes (k < k, or >) are unstable, and will grow, leading to the form ation of a \ ngering" pattern. The fastest growing mode (which has largest positive Im !) is always that with the largest unstable wavelength.

To evaluate these characteristic lengths for a real m aterial, we consider the case of a m obile screw dislocation in pure A L. The damping coe cient has been estimated at about 10⁴ Pa-sec¹¹, but in m olecular dynamics simulation at temperatures close to zero we have found it to be about an order of magnitude smaller¹². The wave speed is c = 29 A/psec and the electrive mass depends logarithm ically on system size but is in the range of 5 amu/A for a system of about 300 300 A^2 in cross section, again as found in a molecular dynamics simulation¹². In the absence of a stress gradient, the wavelength associated with critical damping at low temperature is $_d = 0.2 \text{ to } 0.3 \text{ m}$; at higher temperatures where the damping is stronger, $_d$ may be as small as a few hundred A. The minimum unstable wavelength depends on the local force gradient. For alum in um we estimate the energy/length of a screw dislocation as roughly 1 eV/A, and the driving force is b, where is the driving stress and b is the Burgers vector= 2.86A. Then the characteristic unstable wavelength can be estimated roughly as $= 5 \times 10^4 \text{ m}$ (=1)¹⁼² where the stress gradient =1 is in units of GPa/m. Thus for a screw dislocation in A l, we estimate that a stress gradient of 1 GPa/cm gives a minimum unstable wavelength of order = 50 m, and a stress gradient of 100 GPa/cm gives = 5 m.

If < L, where L is the length of the defect line, then all vibrational modes with wavelength > will be unstable. While the lowest unstable mode grows the fastest, in the early stages of growth all unstable modes are visible and give rise to a disordered ngering structure. If we follow the evolution of the linearized equation of motion in Eqn. (5) beyond the early stages of growth, we observe a coarsening process in which neighboring peaks in the structure m erge until only a single sinusoid pro le rem ains. In Fig.1 we show the results of a num erical integration of Eqn. (5), show ing the type of patterns that arise, where the initial condition was a straight line with a sm allam plitude random perturbation.

For dislocations in m etals, the linearized equation is only valid to describe the very earliest stage of m otion, so we would not necessarily expect to see — ngering behavior like that shown in Fig. 1. However the initial growth of the instability should be described by the analysis above. To test this hypothesis, we perform ed a molecular dynam ics simulation of the motion of a screw dislocation in a single crystal of alum inum using an Embedded Atom M ethod potential provided by D iana Farkas et al^{13} . To see the instability in an atom ic scale simulation is not an easy task, because to get a minimum unstable wavelength as small as 500 A in a bulk solid, we would need an enorm ous stress gradient in the range of 10^8 G Pa/m. Luckily, there is a much easier way: we make use of the force gradient produced by the attraction between a dislocation line and a nearby free surface.

The force/length on a screw dislocation at a distance R from a parallel free surface scales as 1=R, so the gradient in the driving force diverges as $1=R^2$. When the dislocation is far enough from the surface, the local force gradient is small, the minimum unstable wavelength is longer than the dislocation line, and the dislocation is stable. At a critical distance from the wall R (which depends on dislocation length L) the dislocation's rst vibrationalm ode becomes unstable and ngers toward the free surface. As the dislocation continues to move toward the free surface, the force gradient gets stronger and higher order vibrationalm odes go unstable one by one in a cascade of instabilities.

O ur simulated system has periodic boundary conditions only along the z-axis and thus has four free surfaces; the dislocation is initially parallel to the z-axis which lies in the [110] direction. The system size is 45 45 183 = 370;575 atom s, or 111 105 524 A³, and the tem perature is close to 0° K. The dislocation is placed a distance of 26.5 A from one free surface and is given a very slight sinusoidal perturbation with wavelength = $L = 524A \cdot W = estim$ ate the minimum unstable wavelength as:

$$= 2 \frac{4}{\frac{\log(\frac{2R}{a_{\circ}}) + \log(\frac{2D-2R}{a_{\circ}}) - \log(\frac{2D}{a_{\circ}})}{R^{2} + (D-R)^{2}} \frac{3}{5}$$
(10)

where the numerator is the energy/length of the dislocation (m c^2) and the denominator is the gradient of the driving force/length¹, using in age terms from free surfaces ahead and behind, and canceling the energy prefactor. Here D = 111A is the length of the crystal in the direction of dislocation motion, and $a_o = b$ is the dislocation core size. For a dislocation at position R = 26.5A; Eqn. (10) predicts = 258 A. Since is about half the size of the defect length L = 524 A, we expect both the rst and second vibrationalm odes to be unstable and grow.

The dislocation is shown in Fig.2, where we display only atom s whose local potential energy di ers from that of the bulk. The initial state is shown in gray, the later state in black. The dislocation splits into two partial dislocations separated by a ribbon of stacking fault. In each of the partials, the initial sinusoidal perturbation grows along with the second vibrational mode, and each of the partials ngers toward the wall. The apparent minimum unstable wavelength is roughly = 250 A, in agreement with our prediction. We have also run a simulation of the same set-up performed in a crystal of height 150 A; in this case the initial perturbation does not grow, as its wavelength = L <, and the instability is suppressed by nite size.

O ur sin ulation of a dislocation moving toward a free surface is closely related to Swam inarayan's⁹ study of dislocation pair annihilation. In our case, the dislocation is attracted to an \im age" dislocation¹ of opposite sign located in a sym metric position across the free surface. In order to see the longer time evolution of the instability, we need a larger system, so we have perform ed simulations of vortex motion in a three-dimensional XY \rotator" model of a simple m agnet¹⁴. This system is very e cient computationally, and we have run simulations of up to 4 10^6 spins on a DEC A lpha workstation. In this model, each spin on a cubic lattice has a moment of inertia I = 1 and one rotational degree of freedom with angular position $_i$ and angular velocity $!_i$. The spins have nearest-neighbor interactions with an XY H am iltonian, an applied magnetic eld B, plus a rotational kinetic energy term :

$$H = \sum_{\substack{\langle i_{j}j \rangle \\ \langle i_{j}j \rangle \\ i}}^{X} B \cos(i_{j}) + \frac{1}{2} I!_{i}^{2}:$$
(11)

W e derive equations of motion from Eqn. (11) under constant energy. A straight vortex line has properties analogous to those of a screw dislocation in a crystal, particularly the e ective mass/length, mobility behavior, Peierls barrier, and vortex-vortex interactions¹².

We use periodic boundary conditions along the z direction only with four free surfaces, and size 100 100 400 spins. In the initial state a vortex line lies parallel to the z axis at an initial tem perature $k_B T = 0.25$, in the ordered phase. Since the simulation is run at constant energy, $k_B T$ uctuates. We apply a smallexteral eld B = -0.003 which drives the vortex in the + x direction.

In Fig. 3 we show the time evolution of the vortex, starting at x = 40 and moving toward the free surface at x = 100. U sing Eqn.(10) with $a_0 = 1$ and D = 100, we predict that the rst vibrationalmode should become unstable when the vortex reaches a distance R = 38 lattice sites from the free surface. Since this system is at nite temperature, the vortex line roughens initially due to thermal uctuations (like those studied by Charan and Daw¹⁵ in dislocations.) The rst vibrationalmode starts to grow at about the predicted location, around x = 60 (R = 40 units from the surface.) A round x = 65; the second mode become es prominent (with two \peaks" visible) and grows until the vortex annihilates at the free surface. The second mode appears earlier than predicted by Eqn. (10); perhaps nonlinear e ects play an important role. In future work we plan to simulate a larger system in which more steps in the cascade of instabilities may be seen.

The physical signing ance of this instability is an open question. Most important, we have learned how nite size elects play a major role in simulations of line defects in general; and that the largest characteristic length is dened by the smallest force gradient present. Beyond that we speculate that the characteristic length scale might play a role in the form ation of dislocation patterns during work hardening. The instability could also control pair annihilation of threading dislocations in thin lms, dening an elective \kill radius" that depends on lm thickness. C on ming any of these mechanisms via experiment may be dicult. The motion of an individual dislocation in a thin metal sample can be observed via TEM, but it is not clear whether the necessary time resolution and length scales are technically feasible. It would be easier to observe the motion of a defect line in a liquid crystal driven by a gradient in an applied eld, since defect motion can be viewed with an optical microscope and polarizers.

A closely related instability has previously been identi ed by Z.Sud¹⁶ who noted that a dislocation moving via climb can be unstable in the presence of a gradient in the density of vacancies. However since climb is a di usive process, the dynam ics of that instability mechanism occur on a far slower time scale where inertial e ects are not important. How ever both mechanisms should play an important role in dislocation pattern form ation in metals.

W e thank Lyle Levine, Robb Thompson, and Shujia Zhou for helpful discussions. This work was supported by NSF G rant No. DM R-59702234.

- ³ V.Bulatov, F.Abraham, L.Kubin, B.Devincre, S.Yip, Nature 391, 669 (1998).
- ⁴ L.P.Kubin et al, Solid State Phenom . 23, 455 (1992).
- ⁵ K.W. Schwarz, Phys. Rev. Lett. 78, 4785 (1997); K.W. Schwarz and F.K. LeG oues, Phys. Rev. Lett. 79, 1877 (1997).
- ⁶ A.Granato and K.Lucke, J.Appl. Phys. 27, 583 (1956); J.Appl. Phys. 27, 789 (1956).
- ⁷ C.Cattuto and F.Marchesoni, Phys. Rev. Lett. 79, 5070 (1997).
- ⁸ E.B.Kolomeisky, T.Curcic, and J.P.Straley, Phys. Rev. Lett. 75, 1775 (1995).
- ⁹ S.Swam inarayan and R.LeSar, presented at the Combined W orkshops on Fracture, Friction, and D eform ation, held at the Center for N onlinear Studies, Los A lam os N ational Laboratory, Los A lam os, N ew M exico, A pril 19-24, 1996.
- 10 S.C.Crow, AIAA 8, 2172 (1970).
- ¹¹ L.Kubin, private com munication.
- ¹² M. Li, Jianling Xu, Brian Sm ith, and R. L. B. Selinger, in preparation.
- ¹³ Y.M ishin, M.Mehl, D.Farkas and D.Papaconstantopoulos, to appear, Phys Rev.B.
- ¹⁴ For a study of a related two-dim ensional system, see S.Rom ano, Phys.Rev.B 42, 8647 (1990).
- ¹⁵ D.C.Chrzan and M.S.Daw, Phys.Rev.B 55, 798 (1997).

¹⁶ Z.Suo, A cta M et. 42, 3581 (1994).

¹ For a general introduction to dislocations and their interactions, see J.P.H irth and J.Lothe, Theory of D islocations (K rieger Publishing, F lorida, 1992).

² S.J. Zhou, D.M. Beazley, P.S. Lom dahl, and B.L.Holian, Phys. Rev. Lett. 78, 479 (1997); S.J. Zhou, * D.L. Preston, P. S. Lom dahl, D.M. Beazley, Science 279, 1525 (1998).



FIG.1. Evolution of a line defect from numerical integration of Eqn. (10), = 0.1; c = 1; m = 1, and L = 1000: (a) W ith a weak force gradient $F_1 = 0.01$, = 63: (b) W ith stronger force gradient $F_1 = 0.1$, = 20. The pattern coarsens via tip combination.



FIG.2. M olecular dynam ics simulation of screw dislocation motion in Al. (a) Initial con guration. (b) Later con guration; dislocation has split into partials which $\$ nger" toward the free surface. Curves are drawn to guide the eye.



FIG.3. Time evolution of vortex motion in a 3-d XY \rotator model simulation. As the vortex line approaches the free surface the rst and then second vibrationalm odes become unstable.