Low tem perature structuralm odel of hcp solid C 70

G.Ghosh, V.S. Sastry and T.S. Radhakrishnan

M aterials Science D ivision, Indira G andhi Centre for A tom ic Research, K alpakkam 603 102, India.

We report interm olecular potential energy calculation for solid C₇₀ and determ ine the optimum static orientations of molecules at low temperature which are consistent with the monoclinic structural model proposed by us in an earlier report [Solid State Commun., 105, 247 (1997)]. This model indicates that the C₅-axis of the molecule is tilted by an angle 18° from the monoclinic b-axis in contrast with the molecular orientation proposed by Verheijen et al.[J. Chem. Phys., 166, 287 (1992)] where the C₅-axis is parallel to the monoclinic b-axis. In this calculation we have incorporated the elective bond charge C culom b potential together with the Lennard-Jones potential between the molecule at the origin of the monoclinic unit cell and its six nearest neighbours, three above and three below. The minimum energy con guration for the molecular orientations.

PACS nos.: 61.48.+ c, 61.50 A h, 61.50 Lt

The orientational ordering transform ation in solid C₆₀ is well understood¹. Potential energy calculations using only the Lennard-Jonespotential derive the low tem perature structure of solid C $_{60}$ to be orthorhom bic², in sharp contradiction with the experimentally observed simple cubic structure. Lu et al.³ could successfully derive the simple cubic structure for the low temperature phase of solid C₆₀ by adding a Coulomb potential term to the Lennard-Jones potential. This Coulomb interaction between neighbouring molecules arises from the e ective charges at the single bonds and the double bonds of the molecules in the ordered phase at low temperature. In the case of solid C_{70} , the elongated m olecular shape causes much greater diversity in the structural phase transformation sequence as well as in the orientational ordering of m olecules. One of the rst experim ental studies of structural phase transform ation, on cooling, in solid C_{70} is by Verheiten et al.⁴ and they reported the following sequence of phase transform ations

fcc \dagger rh hcp-1 (c/a 1.63) \dagger hcp-2 (c/a 1.82) \dagger monoclinic

where the fcc is the high temperature phase and the m onoclinic is the low tem perature phase. The lattice param eters reported for the monoclinic unit cell are, a = c = 19.96 A , b = 18.51 A and 120° with space group $P112_1/m$. They proposed a structural model for this monoclinic structure in which the orientation of the long axis (C_5) of the static molecules is parallel to the monoclinic b-axis (i.e., the original hop c-axis). Subsequently, they have also carried out the potential energy calculation using the atom -atom Lennard-Jones potential and the corresponding result was in agreem ent with their model. Later, Que et al⁵ pointed out that the unique angle for a monoclinic structure with space group $P112_1/m$ cannot be 120° , but should be less than 120° which is not consistent with the molecular orientations proposed by Verheijen et al. They have carried out a detailed group theoretical analysis of librations in solid C₇₀ and proposed an orthorhom bic structure for

which the two space groups P bnm or P nm a have the sam e Ram an modes. Nelissen et al.⁶ have carried out a harmonic lattice dynamical calculation using the Lennard-Jones potential which proposed that the structure of solid C₇₀ should be monoclinic at low temperature with space group $P2_1/m$. This structure requires two independent angles which they de ned as 1 and 2 and pointed out that for their structure 1 + 2 should be 36° . Later, A gterberg et al.⁷ have pointed out that the calculation of Nelissen et al. can also adm it of an orthorhom bic structure with space group Pbnm . In another detailed study using the anisotropic interaction potential between two C₇₀ m olecules in term s of C ayley-K lein param eters, they have con med that the structure could be orthorhom bic with space group Pbcm or Pbnm⁸. The experimental results of van Smaalen et al.⁹ also conclude in favour of an orthorhom bic structure with space group P bnm of the solid C_{70} at low temperature. It is to be noted that this structure has resulted by a two step transform ation from the ideal h.c.p. phase at high tem perature. Oh et al.¹⁰ have reported detailed potential energy calculations using Girifalco-Lennard-Jonespotential for di erent molecular orientations depicting various possible structures of the solid and the corresponding lattice param eters. They have com pared their results with experim ental reports by others¹⁰. They reported two possible transform ation sequences on cooling, viz.,

fcc * ortho (I,II) * rh h cp I * m ono

or, fcc hcp II hcp (III, IV) mono

where the fcc is the high temperature phase and the monoclinic is the low temperature phase. Here hcp I – IV correspond to the c/a ratios of the unit cells which are 1.84, 1.61, 1.50 and 1.53 respectively. The ortho I and II correspond to the lattice parameters, a = 16.2A, b = c = 14.0A and a = 16.0A, b = 14.4A, c = 14.8A respectively. The monoclinic structures in both cases are the same and correspond to the C₅-axis of orientation being parallel to the b-axis of the unit cell. This

is sim ilar to the molecular orientation in the monoclinic structure predicted by Verheijen et al.⁴, but the lattice param eters in the two reports are signi cantly di erent. Pickholz et al.¹¹, while using atom -atom Lennard-Jones interaction in their calculation, obtain the low temperature structure to be hop with c/a 1.77, instead of a monoclinic structure. The molecular orientations in their model are, how ever, parallel to the unit cell c-axis. Sprik et al.¹² have carried out constant pressure molecular dynam ics calculations incorporating Lennard-Jones potential together with the bond charge Coulomb potential in a phase transform ation study of fcc solid C_{70} . Their result indicates a two step transform ation, viz., foc f rh f m on oclinic which is in excellent agreement with the experim ental results reported by Christides et al.¹³. In the low temperature monoclinic phase predicted by these authors, the molecules in alternate layers of the structure are oriented parallel to the (111) direction and to the (110) direction respectively. We have reported in our earlier paper¹⁴ that the ideal hop (c/a = 1.63) solid C₇₀ undergoes a single step transform ation, on cooling, to a monoclinic phase which is in contrast with the two step transform ation reported by Verheigen et al.⁴. We conjectured that the single step transform ation im plies simultaneous freezing of the molecular rotations around their long axes (C_5 -axes) and the short axes (C_2 -axes), as compared to sequential freezing, which results in a two step transform ation. The form er is likely to lead to a different m onoclinic structure as com pared to the latter^{4;5}. W e had proposed a structuralm odel, consistent with the lattice param eters for the m onoclinic structure m easured from our x-ray di ractogram (XRD) at 100 K, wherein the molecular C_5 -axis has a tilt of about 18° from the m onoclinic b_m -axis. O ur recent experim ental studies on the kinetics of phase transform ation in hep solid C_{70}^{15} show that, except for very slow cooling rates, a two step transform ation invariably results. Such a two-step transform ation may be similar to that reported by Verheiren et al.⁴ and Christides et al.¹³. The low tem perature m onoclinic structures and the C 70 m olecular orientations reported by these authors must, therefore, correspond to som e localpotential energy m in im a of the system raised above the globalm in im um by m isorientation stresses.

In this paper, we report the results of the potential energy calculation pertaining to the monoclinic structure obtained by us from our 100 K XRD. Since the cooling rate was very slow (typically, 0.0033 K /m in.) the monoclinic structure determined from our experiment is expected to be close to the equilibrium structure at low temperature. In this calculation, we have considered the interactions between the seven molecules, one at the origin (0,0,0) of the monoclinic unit cell and the remaining six at the six nearest neighbour positions, three above and three below the basal plane. The orientation of the molecules has been de ned using the angles, , and , as explained later. The nalorientation of the molecules, as obtained by locating the minimum of the potential energy has = 18° , = 8° and = 5° .

The structure of our C₇₀ sample at room temperature is ideal hqp¹⁶ and the XRD pattern of this structure has been analysed in detail in an earlier work¹⁷. The hop lattice constants are, a_h = b_h = 10.53A , c_h = 17.26A and $h = 120^{\circ}$. The 100 K pattern ts well to a monoclinic structure with lattice parameters, $a_m = 10.99A$, b_m = 16.16A , c_m = 9.85A and $_m$ = 107.75° and space group $P2_1 / m^{14}$. It is clear that the following correspondence of lattice parameters is appropriate in going from the hop to the monoclinic: c_h shrinks and form $s b_m$, b_h increases and form $s a_m$, and a_h shrinks to form c_m . This correspondence is shown in Fig.1. The hexagonal angle h can be seen to reduce to the monoclinic unique angle m by a shear along the direction show n by the arrow s in Fig.1 (b). It can be seen that the above correspondence indicates a tilt of the C₅-axis of C₇₀ m olecules by an angle of approximately 18° from the b_m -axis of the monoclinic unit cell (see Fig. 1(b)).

In this calculation we have used the Lennard-Jones potential together with the bond charge C oulom b potential. Following Lu et al.³ in the ordered state of the solid there is less charge density distribution around the C-C single bonds (long bonds) compared to that around the C-Cdouble bonds (short bonds). Such a charge density difference on the surface of the molecule leads to short range intermolecular Coulomb interaction which decays as 1/ R^5 at long distances in the case of C_{70} . In this calculation we have used the same notation for the interaction sites as was done by Sprik et al.¹² in their calculation for the fcc solid C 70. The Lennard-Jones centres are taken to be the carbon atom s sites (C sites: $_{\rm C\,C}$ = 3.4A) as well as the mid-points of the electron-rich C-C double bonds (D sites: $_{DD}$ = 3.6A , whereas $_{CD}$ = 3.5A) and the magnitude of the interaction has been taken as, = 2.964 m eV^{18;19}.

The e ective charge around the single bonds are assum ed to be localised around the C sites¹². Though in C₇₀ m olecules, there are ve types of C sites, for the sake of sim plicity all C sites can be treated to be of the sam e type as in the case of C₆₀. If a C site carries an e ective charge q_C , the corresponding value at the D sites will be $q_D = -2q_C$. The values of these e ective charges are fractions of the electronic charge, e.g., $q_c = 0.175e$ and $q_D = -0.35e^{12}$. The bonds around the equatorial region of the molecule have a length intermediate between the length of a single bond and a double bond and, therefore, are term ed as interm ediate bonds (or, Ibonds). For these bonds, I = 3.5A and $q_I = 0.5q_D$. Since the polar cap of them olecule consists of both long bonds and short bonds, the Coulomb interaction is stronger at the two opposite poles of a molecule in the ordered phase. Therefore the bond charge interaction between two molecules in adjacent planes is dom inated by the polar caps and can be term ed "polar cap" interaction. The coordinates of the 70 carbon atoms in the molecule were generated from data available in published literature²⁰. The total interaction potential between any two C_{70}^{3} m olecules is given by

$$V_{12} = \begin{array}{c} P \\ i; j \\ P \\ m; m \end{array} \begin{pmatrix} xx \\ jr_{1i} \\ r_{2j}j \\ r_{1i} \\ r_{2j}j \\ r_{2j} \\ r_{2j$$

where the subscript x indicates interaction sites, e.g., C, D, or, I, and $r_{1\,i;2\,j}$ are the coordinates of the atom s, b_{1m} ;_{2n} coordinates of bond centres and q_m ;_n are e ective bond charges (e.g., q_c , q_b and q_I).

U sing the above interaction potentials between the seven nearest neighbourm olecules for the lattice param – eters measured from our 100 K x-ray di ractogram, we optim ise the molecular orientations with respect to the unit cellparam eters by minim ising the total energy. The molecular orientations are de ned using the polar coordinates and , where is the polar angle, i.e., the angle between the b_m -axis and the molecular long axis and is the azim uthal angle. Furtherm inim isation of the potential energy has been performed by varying the angle () which de nes the body rotation (spin) of the molecules around their C₅-axes of the six molecules above and below the basal plane relative to the molecule at the origin of the monoclinic unit cell.

W e calculate the potential energy per cluster for each con guration of the seven molecules de ned by the values of between 0° and 90° , between 0° and 180° , between 0° and 72° . In Fig.2, we show the variand ation of potential energy with respect to , and C learly, for $= 8^{\circ}$ and $= 5^{\circ}$ the potential energy is m in imum at $= 18^{\circ}$. This result is consistent with the model we proposed for the molecular orientation in the monoclinic unit cell experimentally measured by us^{14} . The minimum potential energy per cluster obtained for ourmodel is -3.923 eV which is signi cantly lower than other calculations reported in literature^{4;10}. It is to be mentioned here that there are two other minima with respect to at 54° and 88° (not shown in the qure). Though these three m in in a have energy values com parable to each other, the energy barriers between them are nearly 0.04 eV which is too large to spontaneously ip the molecule from one minimum to the other at low tem peratures (100 K). These multiple m in im a indicate that the system may have degenerate states with respect to , or, that they m ay even correspond to di erent structures which can be obtained by applying some external driving force, e.g., pressure etc. The degeneracy may arise as a consequence of the repulsive interactions between the C-C bonds as indicated by Sprik et al^{21} . in their extended model. Since the present calculation is based on the static orientations of m olecules (m olecular static calculation) the study of the structural transform ation or the change of m olecular orientations with temperature cannot be carried out by this method. A detailed molecular dynamics calculation is needed for this purpose which is in progress. Nevertheless, we argue that the equilibrium low temperature structure will be consistent with the molecular C5-axis tilted away from the

unit cell long axis, because of the polar cap interaction, as proposed in the present model and supported by the potential energy calculation, rather than being oriented parallel to $it^{4,5}$. We recall from the introductory section that the molecular dynam ics calculation of Sprik et al.¹² leads to two competing orientations for the molecules. A pictorial view of the optim ised static orientation of the seven molecules for our monoclinic lattice parameters is shown in Fig.3. This picture is generated using a public dom ain software MOLDRAW .

In conclusion, our results of potential energy calculation using the Lennard - Jones potential together with the bond charge Coulom b potential support the structural model proposed by us in our earlier paper¹⁴. The calculation shows that the minimum potential energy state appears with a tilt of the C₅-axis of the molecule with respect to the monoclinic long axis (b_m -axis) by an angle of 18°. Furtherm in im isation of the interaction energy between the neighbouring molecules has been carried out using an angle which de nes the rotational con quration of the molecule around its own C_5 -axis. The molecular orientations obtained from our calculation have an implication of signi cant polar cap interaction between the nearest neighbourm olecules in adjacent planes. The bond charge interaction is thus seen to play a key role in determ ining the equilibrium low temperature structure of solid C_{70} . Our calculations show also that the structuralm odel proposed by us corresponds to the most stable low temperature structure of solid C $_{70}$ reported so far.

ACKNOW LEDGM ENTS

W e gratefully acknow ledge M.C.Valsakum ar and C.S. Sundar for valuable discussions. G.G hosh is thankful to the D irector, Indira G andhiC entre for A tom ic R essarch, for the visiting scientist position enabling this work to be carried out.

- ¹ P.A.Heiney, J.Phys.Chem.Solids 53, 1333 (1992).
- ² Y. Guo, N. Karasawa, and W. A. Goddard III, Nature (London) 351,464 (1991).
- ³ J.P.Lu, X.-P.Liand R.M.Martin, Phys.Rev.Lett.68, 1551 (1992).
- ⁴ M.A.Verheijen, H.M. eekes, G.M. eijer, P.Bennema, J.L. de Boer, S.van Smaalen, G.van Tendeloo, S.Am.elinckx, S.M. uto and J.van Landuyt, Chem. Phys. 166, 287 (1992).
- ⁵ W . Que, D. F. Agterberg and M. B. W alker, Phys. Rev. B 47, 13074 (1993).
- ⁶ B.J.Nelissen, P.H.M. van Loosdrecht, M.A.Verheijen, A.van der Avoird and G.Meijer, Chem.Phys.Lett.207, 343 (1993).

- ⁷ D.F.Agterberg, W.Que and M.B.Walker, Chem.Phys. Lett. 213, 208 (1993).
- ⁸ D.F.Agterberg and M.B.W alker, Phys.Rev.B 48, 5630 (1993).
- ⁹ S. van Sm aalen, V. Petricek, J. L. de Boer, M. Dusek, M. A. Verheigen and G. Meiger, Chem. Phys. Lett. 223 323 (1994).
- ¹⁰ D. H. Oh and Young Hee Lee, Phys. Rev. Lett. 75, 4230 (1995), and references therein.
- $^{11}\,\text{M}$.Pickholz and Z.G a_m ba, Phys.Rev.B 53, 2159 (1996).
- ¹² M.Sprik, A.Cheng and M.L.Klein, Phys. Rev. Lett., 69, 1660 (1992).
- ¹³ C.Christides, I.M. Thom as, T.J.S.D ennis and K.Prassides, Europhys.Lett.22, 611 (1993).
- ¹⁴ G.Ghosh, V.S. Sastry, C.S. Sundar and T.S.Radhakrishnan, Solid State Commun., 105, 247 (1997).
- ¹⁵ G.Ghosh, V.S.Sastry, C.S.Sundar and T.S.Radhakrishnan (To be published).
- ¹⁶ G.V.N.Rao, V.S.Sastry, M.Premila, A.Bharathi, C. S.Sundar, Y.Hariharan, V.Seshagiri and T.S.Radhakrishnan, Powder Dir., 11, 5 (1996).
- ¹⁷ M. C. Valsakum ar, N. Subram anian, M. Yousuf, P. Ch. Sahu, Y. Hariharan, A. Bharathi, V. S. Sastry, G. V. N. Rao, T. S. Radhakrishnan and C. S. Sundar, Phys. Rev. B 48, 9080 (1993).
- ¹⁸ W .G auster and I.Fritz, J.Appl.Phys. 45, 3309 (1991).
- ¹⁹ Encyclopedia of X-Rays and Gamma Rays, edited by G. Clark (Reinhold, New York, 1963).
- ²⁰ W . Andreoni, F. Gygi, and M. Parrinello, Chem. Phys. Lett., 189, 241 (1992).
- ²¹ M. Sprik, A. Cheng, and M. L. Klein, J. Phys. Chem., 96, 2027 (1992).

FIG.1. (a) High temperature hcp structural model; C_{70} m olecules are freely rotating m in icking spheres, (b) M onoclinic unit cell model proposed for the lattice parameters obtained from XRD pattern at 100 K (Ref. 10).

FIG .2. Variation of the potential energy in eV / cluster (a) with , (b) with , and (c) with

FIG. 3. Final orientational con gurations of the 7 m olecules of the unit cellarising from the potential energy calculation; a_m , b_m , and c_m represent the monoclinic cellparam eters.





 $b_{m \mid}$



b unique Monoclinic

