Electronic structure of spinel-type LiV_2O_4

J. Matsuno, A. Fujimori and L. F. Mattheiss

Department of Physics, University of Tokyo, Bunkyo-ku, Tokyo 113-0033, Japan

(February 12, 2022)

The band structure of the cubic spinel compound LiV_2O_4 , which has been reported recently to show heavy Fermion behavior, has been calculated within the local-density approximation using a full-potential version of the linear augmented-plane-wave method. The results show that partiallyfilled V 3d bands are located about 1.9 eV above the O 2p bands and the V 3d bands are split into a lower partially-filled t_{2g} complex and an upper unoccupied e_g manifold. The fact that the conduction electrons originate solely from the t_{2g} bands suggests that the mechanism for the mass enhancement in this system is different from that in the 4f heavy Fermion systems, where these effects are attributed to the hybridization between the localized 4f levels and itinerant spd bands.

PACS numbers: 71.27.+a, 71.20.-b, 71.15.Mb

The recent discovery of heavy Fermion (HF) behavior in LiV_2O_4 by Kondo *et al.*¹ has significant importance because this is the first *d*-electron system that shows HF characteristics, a phenomenon that has previously been observed only in f-electron systems. Kondo *et al.* have reported a large electronic heat coefficient of $\gamma \approx 0.42$ $J/mol K^2$ and a crossover with decreasing temperature T from local moment to renormalized Fermi-liquid behavior.² Recently Takagi et al. have reported that the electrical resistivity ρ of single crystals exhibits a T^2 temperature dependence $\rho = \rho_0 + AT^2$ (Ref. 3) with an enormous A, which is another HF characteristic. The Curie-Weiss law at high temperatures implies that each V ion has a local moment and their coupling is antiferromagnetic⁴ although no magnetic ordering is observed down to $0.02~\mathrm{K}.^1$

The purpose of the present study is to determine from first principles the electronic band properties of LiV₂O₄, with particular emphasis on features near the Fermi level E_F . This provides a reference framework for evaluating the magnitude of the heavy Fermion mass-enhancement effects in this material. In addition, a simple tightbinding model⁵ which captures the essential features of the LiV_2O_4 electronic structure is presented. In heavy Fermion systems, the enhanced electron mass manifests itself in terms of an exceptionally large value of the density of quasi-particles at E_F . Experimentally, this high density is reflected in the large specific-heat γ and the large spin susceptibility χ^{spin} which is nearly Tindependent. The calculated band DOS at $E_F D(E_F)$ can be compared directly with the experimental results, and the ratio of the experimental and calculated band $D(E_F)$ values then provides a direct measure of the enhancement factors.

LiV₂O₄ forms with the well known cubic spinel structure in which the Li ions are tetrahedrally coordinated by oxygens while the V sites are surrounded by a slightlydistorted octahedral array of oxygens. The spinel structure features a face-centered-cubic Bravais lattice and a nonsymmorphic space group (Fd3m) which is identical with that of the diamond structure. The primitive unit



FIG. 1. A portion of the unit cell for the spinel-type LiV_2O_4 , where *a* is the lattice parameter for the face-centered-cubic Bravais lattice. (See text)

cell contains two LiV₂O₄ formula units (14 atoms). One can construct the spinel structure by an alternate stacking along [100]-type directions of the two different kinds of cubes shown in Fig. 1. The LiV₂ substructure is the same as the C15 structure AB_2 , where the local moments at the B sites are highly frustrated.² The observed lattice constant of the LiV₂O₄ is 8.22672 Å at 4 K.⁶ The eight oxygen atoms in the primitive cell are situated at the 32*e*-type sites, at positions which are determined by the internal-position parameter x = 0.2611. The VO₆ octahedra are trigonally distorted in the spinel structure unless the parameter x is equal to the "ideal" value 0.25.

The present band-structure calculations for LiV_2O_4 have been carried out in the local-density approximation (LDA) using a full-potential, scalar-relativistic implementation⁷ of the linear augmented-plane-wave (LAPW) method.⁸ The LAPW basis has included plane waves with a 14-Ry cutoff (~60 LAPW's/atom) and sphericalharmonic terms up to l = 6 inside the muffin tins. The



FIG. 2. Comparison of the LAPW (a) and tight-binding (b) energy-band results for LiV_2O_4 .

crystalline charge density and potential have been expanded using ~7300 plane waves (60 Ry cutoff) in the interstitial region and lattice harmonics with $l_{\rm max} = 6$ inside the muffin-tin spheres ($R_{\rm Li} \approx 1.98$ a.u., $R_{\rm V} \approx 2.16$ a.u., $R_{\rm O} \approx 1.54$ a.u.). Brillouin-zone (BZ) integrations have utilized a ten-point **k** sample in the 1/48 irreducible wedge. Exchange and correlation effects have been treated via the Wigner interpolation formula.⁹ The atomic Li(2s¹), V(3d⁴4s¹) and O(2s²2p⁴) states were treated as valence electrons in this study whereas the more tightly bound levels were included via a frozen-core approximation.

The results of the present LAPW calculations for LiV_2O_4 are plotted along selected BZ symmetry lines in Fig. 2(a). The O 2s states, which are not shown, form narrow (~1 eV) bands and are situated about 19 eV below the Fermi level E_F . The lowest band complex shown in this figure evolves from the O 2p states: it contains 24 bands, and has an overall width of ~4.8 eV. The 20 V 3d bands lie above the O 2p bands, separated by a 1.9-eV gap. A broad plane-wave conduction band evolves from the Γ point above 4.4 eV. These general features are quite similar to those exhibited by previous results for the closely related isostructural compound LiTi_2O_4 .^{11,12}

The octahedral crystal field at the V sites in the spinel structure splits the 20 V 3*d* bands into twelve partially-filled t_{2g} bands and eight e_g states. The Fermi level lies within the t_{2g} complex, and thus the transport properties of LiV₂O₄ are solely associated with t_{2g} bands. The formal valence of vanadium is 3.5+, yielding exactly six valence electrons per cell in a perfectly stoichiometric ma-

terial. The point symmetry at the V sites is D_{3d} . In the fully localized limit, this allows the cubic t_{2g} crystal-field-type states to be split into a_{1g} and e_g levels. As discussed below, tight-binding estimates of this splitting show that it is quite small (~0.14 eV) in LiV₂O₄, about 6 % of the octahedral e_g - t_{2g} splitting (~2.5 eV). The 0.14-eV difference between the a_{1g} and e_g orbital energies is small compared to the overall t_{2g} bandwidth (~2.2 eV). As a result, this splitting of the a_{1g} and e_g orbital energies does not produce effects which are readily discernible in the band-dispersion curves for LiV₂O₄.

In order to provide a convenient starting point for future investigations of electron-correlation effects in the present LiV₂O₄ system, we have applied a simple tightbinding (TB) model⁵ to fit the present LAPW results at six symmetry points in the BZ. This TB model has included the V 3*d* as well as the O 2*s* and 2*p* orbitals. Using 12 independent TB parameters, a moderately accurate (rms error = 0.17 eV) fit has been obtained to the 52 LiV₂O₄ valence and conduction bands. The fitting has involved two-center energy as well as overlap parameters. The TB parameters are listed in Table I. The TB representation of the LiV₂O₄ bands is shown in Fig. 2(b). It is clear that, although the agreement is not perfect, the TB model captures the essential features of the LAPW results.

A different TB model excluding the oxygen orbitals has been applied to the LAPW V 3d band results in order to obtain estimates of the orbital energies for the individual a_{1q} and e_q subbands in this system. (Note that the TB parameters in Table I include only a single V 3d orbital energy E_d). These TB orbital energies represent the mean band energy for each subband. They are in fact the crystal-field levels that come into play in the limit where the V 3d electrons are localized by electron-correlation effects. According to the present analysis, the mean band energy for the upper e_q complex is 2.82 eV while those for the t_{2g} -derived a_{1g} and e_g manifold are 0.43 and 0.29 eV, respectively. Thus, crystal-field splitting that arises from the octahedral coordination of oxygens (2.48 eV) is more than an order-of-magnitude larger than that originating from the trigonal distortion ($\sim 0.14 \text{ eV}$). This TB model, which also involved a total of 12 parameters, yielded a moderate fit (rms error = 0.15 eV) to the V 3*d*-band states. The effective d-d hopping integrals $[(dd\sigma), (dd\pi),$ $(dd\delta)$] over three shells of V-V neighbors $[d_1 = 2.91 \text{ Å}, d_2]$ = 5.04 Å, $d_3 = 5.82$ Å] that have been included in this fit have values (in eV) [-0.425, 0.008, 0.152], [-0.034, 0.026]-0.021], and [-0.060, 0.064, -0.026], respectively. These parameters may provide a useful starting point for future studies of electron-electron correlation effects in this system.

A more detailed view of the t_{2g} portion of the LAPW V 3*d* energy-band results for LiV₂O₄ is shown in Fig. 3. The six LiV₂O₄ valence electrons per cell are sufficient to fill, on average, three of the 12 t_{2g} conduction bands. In fact, the calculated LAPW band dispersion produces several partially-filled bands, leading to a rather compli-



FIG. 3. Expanded plot of the LAPW t_{2g} bands for LiV₂O₄.

cated Fermi-surface topology in this system. While two bands are completely filled, the third conduction band contains holes near the X and L symmetry points (h_3) and electron pockets at Γ (e_4 and e_5) and W (e_4). Since the unit cell contains an even number of electrons, compensation requires that there exist equal numbers (i.e. BZ volumes) of electrons and holes. The existence of Fermi-surface sheets with both electron and hole character in LiV₂O₄ provides a ready explanation for the experimental observation that the Hall coefficient changes sign with temperature³ in accordance with a two-carrier model.

The total DOS and the projected contributions to the DOS from various muffin-tins are shown in Fig. 4. The dominant contribution to the DOS over this energy range originates from the O 2p and V 3d states. The O 2p bands are filled by electrons transferred from the Li 2s and V 3dorbitals so the system can be described by the ionic configuration $Li^+(V^{3.5+})_2(O^{2-})_4$. Previous photoemissionspectra data are in general agreement with these results.¹⁰ However, the calculated band DOS and the photoemission spectra do not agree with each other in the V 3d band region near E_F . In particular, the photoemission intensity at E_F is an order of magnitude lower than the calculated DOS. On the other hand, the density of quasiparticles at E_F derived from the specific heat is much higher than the calculated $D(E_F)$. According to our results, the calculated $D(E_F) = 7.1$ states/(eV·formulaunit) corresponds to $\gamma_{\rm cal} = 17 \text{ mJ/mol K}^2$; this is ~25 times smaller than the experimental value of $\gamma \approx 0.42$



FIG. 4. Total and muffin-tin projected DOS results for LiV_2O_4 . The inset shows an enlarged view of the total DOS near E_F .

J/mol K². It is well-known that electron-phonon interactions enhance the electronic specific heat as in the closelyrelated spinel compound LiTi₂O₄, where band calculations indicated strong electron-phonon-coupling effects, yielding a coupling parameter $\lambda = 1.8$ and hence a mass enhancement factor of $1 + \lambda = 2.8$.¹² In the present case, however, the deduced enhancement factor of ~25 suggests that a different mechanism such as electroncorrelation effects would be responsible for the observed HF behavior in LiV₂O₄.

In comparison with the band structures of typical 4felectron HF systems, our result show similar behavior in that the calculated density of states at E_F is much smaller than those obtained from the analysis of experimental specific-heat data. For example, the ratio $\gamma_{\exp}/\gamma_{cal}$ is ~100 for CeCu₂Si₂ and ~70 for CeAl₃.¹³ Also, the band structures of the *f*-electron HF and LiV₂O₄ systems are similar in that there is a sharp DOS peak just above E_F (~0.3 eV for CeCu₂Si₂ and ~0.1 eV for LiV₂O₄, see inset of Fig. 4). In order to explain the high density of quasi-particles deduced from the electronic specific heats, a renormalized band picture was proposed, in which a strong renormalization of the f band due to the strong correlation at the 4f site was taken into account.¹⁴ In the renormalized band picture, it is considered that electrons with two different degrees of wave function localization, namely, the itinerant sdconduction electrons and the well localized f electrons hybridize with each other. In the case of LiV_2O_4 , however, all the conduction bands crossing E_F consist of V $t_{2a}(3d)$ orbitals, i.e., electrons with the same degrees of localization, and therefore the mechanism of the mass enhancement may be totally different from the f-electron systems. The narrowing of the energy bands due to electron correlation within the t_{2g} bands is likely. Given a high-temperature local moment behavior in a metallic system, a prerequisite for a HF behavior is that the local moments do not show long-range order at low temperatures. In the 4f-electron HF systems, long-range order is prohibited by weakness of the coupling between the 4flocal moments.¹⁵ In the case of LiV_2O_4 , the long-range order is disfavored by the magnetic frustrations originating from the spinel structure. This phenomenological consideration remains to be justified by microscopic theories.

In conclusion, the results of LAPW band calculations for the spinel-type compound LiV_2O_4 show that the O 2p, V $3d(t_{2q})$ and V $3d(e_q)$ bands as well as the higherlying sp conduction band are well separated from each other and that the Fermi level lies within the t_{2q} bands. The electronic structure of LiV_2O_4 can be well described by electrons in the triply-degenerate t_{2q} bands, thereby indicating that the mechanism of the mass enhancement in this compound should be different from that in the *f*-electron heavy Fermion systems. Further experimental studies on various physical properties at low and high temperatures are necessary to characterize the nature of the heavy Fermion behavior in LiV_2O_4 . High-resolution photoemission studies would be especially useful for clarifying the renormalization of quasi-particles in this system.

The authors would like to thank Prof. Y. Ueda for valuable discussions. This work was supported by a Special Coordination Fund for Promoting Science and Technology from the Science and Technology Agency of Japan. L. F. M. is grateful to Yamada Science Foundation for supporting his visit to the University of Tokyo. J. M. acknowledges support from the Japan Society for the Promotion of Science for Young Scientists.

¹ S. Kondo *et al.*, Phys. Rev. Lett. **78**, 3729 (1997).

- ³ H. Takagi, C. Urano, S. Kondo, and Y. Ueda, *Proceedings* of the NEC Symposium on Phase Control in Spin-Charge-Orbital Coupled Complex Systems, to be published.
- ⁴ H. Kessler and M. J. Sienko, J. Chem. Phys. 55, 5414 (1971).
- ⁵ L. F. Mattheiss and W. Weber, Phys. Rev. **B** 25, 2248 (1982).
- ⁶ O. Chemaissem, J. D. Jorgensen, S. Kondo, and D. C. Johnston, Phys. Rev. Lett. **79**, 4866 (1997).
- ⁷ L. F. Mattheiss and D. R. Hamann, Phys. Rev. B **33**, 823 (1986).
- ⁸ O. K. Andersen, Phys. Rev. B **12**, 3060 (1975).
- ⁹ E. Wigner, Phys. Rev. 46, 1002 (1934).
- ¹⁰ A. Fujimori, K. Kawakami, and N. Tsuda, Phys. Rev. B 38, 7889 (1988).
- ¹¹ S. Massidda, J. J. Yu, and A. J. Freeman, Phys. Rev. B 38 11352 (1988).
- ¹² S. Satpathy and R. M. Martin, Phys. Rev. B 36, 7269 (1987).
- ¹³ J. Sticht, N. d'Ambrumenil, and J. Kübler, Z. Phys. B 65, 149 (1986); A. Yanase, J. Magn. Magn. Mat. 52, 403 (1985); T. Jarlborg, H. F. Braun, and M. Peter, Z. Phys. B 52, 295 (1983).
- ¹⁴ G. Zwicknagl, Advances in Physics **41**, 203 (1992).
- ¹⁵ K. Yamada, K. Yosida, and K. Hanzawa, Prog. Theor. Phys. **71**, 450 (1984).

² Until the discovery of the heavy Fermion behavior in LiV_2O_4 , the largest electronic specific heat in *d*-electron systems had been $\gamma = 0.150 \text{ J/mol K}^2$ for $Y_{1-x}\text{Sc}_x\text{Mn}_2$ with x = 0.03 [H. Wada, M. Shiga, and Y. Nakamura, Physica B **161**, 197 (1989).]

TABLE I. Tight-binding parameters for LiV₂O₄ (rms error = 0.17 eV). Parameters in braces $\{...\}$ have been approximated using simplifying relations (i.e., $(dd\pi) = 0.5|(dd\sigma)|$, etc.), leaving 12 independent parameters.

Site/interaction	Distance (Å)	Parameters	Value (eV)
		Energy	
V		E_d	-0.569
О		E_s, E_p	-18.715, -4.390
V-V	2.91	$(dd\sigma), (dd\pi), (dd\delta)$	$-0.524, \{0.262\}, \{-0.052\}$
V-O	1.97	$(sd\sigma), (pd\sigma), (pd\pi)$	$-2.278, -2.190, \{1.095\}$
O-O	2.65	$(ss\sigma), (sp\sigma), (pp\sigma), (pp\pi)$	$-0.239, \{0.413\}, 0.711, \{-0.284\}$
O-O	2.91	$(ss\sigma), (sp\sigma), (pp\sigma), (pp\pi)$	$-0.110, \{0.229\}, 0.479, \{-0.192\}$
		Overlap	
V-O	1.97	$[sd\sigma], [pd\sigma], [pd\pi]$	$0.046, 0.051, \{-0.026\}$