

Onset of pattern formation in thin ferromagnetic films with perpendicular anisotropy

Birger Brietzke¹ and Hans Knüpfers²

¹ Institute of Applied Mathematics, Heidelberg University, Im Neuenheimer Feld 205, 69120 Heidelberg, Germany, birger.brietzke@alumni.uni-heidelberg.de

² Institute of Applied Mathematics, Heidelberg University, Im Neuenheimer Feld 205, 69120 Heidelberg, Germany, knuepfer@uni-heidelberg.de, (corresponding author)

May 23, 2022

Abstract

We consider the onset of pattern formation in an ultrathin ferromagnetic film of the form $\tilde{\Omega}_t := \tilde{\Omega} \times [0, t]$ for $\tilde{\Omega} \in \mathbb{R}^2$ with preferred perpendicular magnetization direction. The relative micromagnetic energy is given by

$$\mathcal{E}[M] = \int_{\tilde{\Omega}_t} d^2 |\nabla M|^2 + Q \int_{\tilde{\Omega}_t} (M_1^2 + M_2^2) + \int_{\mathbb{R}^3} |\mathcal{H}(M)|^2 - \int_{\mathbb{R}^3} |\mathcal{H}(e_3 \chi_{\tilde{\Omega}})|^2,$$

describing the energy difference for a given magnetization $M : \mathbb{R}^3 \rightarrow \mathbb{R}^3$ with $|M| = \chi_{\tilde{\Omega}_t}$ and the uniform magnetization $e_3 \chi_{\tilde{\Omega}_t}$. For $t \ll d$, we establish the scaling of the energy and a BV-bound in the critical regime where the base area of the film is of order $|\tilde{\Omega}| \sim (Q - 1)^{1/2} d e^{\frac{2\pi d}{t} \sqrt{Q-1}}$. We furthermore investigate the onset of non-trivial pattern formation in the critical regime depending on the size of the rescaled film.

Keywords: 78A30, 49S05, 78A99, 49K20

Contents

1 Introduction and statement of main result

2

2	Dimensional reduction	9
3	Lower bound and compactness	15
4	Proof of upper bound	20

1 Introduction and statement of main result

Ferromagnetic materials are a complex class of solids which are capable of forming a wide range of spatially ordered magnetization patterns. These patterns can be tuned by e.g. changing the crystalline structure of materials or applying external fields which has lead to a variety of applications, e.g. in data storage (see e.g. [33]). From a mathematical point of view these patterns can be understood as ground states of the underlying energy functional [5, 17, 21]. From the perspective of the variational principle, the formation of magnetic domains — large regions with uniform magnetization — has been studied in the physical literature [30, 24, 38], see also [21] for an overview as well as the mathematical literature (e.g. [8, 9, 14, 25, 36, 19, 6, 16, 28]). In the last years there has been increased interest in the study of extremely thin ferromagnetic films with thickness of only a few atomic layers. In such films due to surface effects magnetization in perpendicular direction to the film plane is energetically preferred [37, 29]. One feature of these films is that they exhibit the formation of so called *bubble* or *stripe domain* patterns and that the domain size grows exponentially in terms of the inverse of the film thickness (cf. (3)) as experimental and numerical observations suggest [23, 13]. In [27], these findings have been rigorously confirmed in a periodic setting by minimization of energy. In this work, we consider a domain of critical size, associated with the onset of pattern formation. In this paper, we confirm the above scaling laws for the case of a finite film and furthermore derive conditions for the presence and absence of non-trivial patterns, depending on the film size. Mathematically, we have to deal with an energy functional where local terms of diffuse perimeter type compete with the impact of the nonlocal magnetostatic energy. In the critical regime, these two parts of the energy have the same magnitude which makes the analysis interesting.

Let $\tilde{\Omega}_t = \tilde{\Omega} \times [0, t]$ for a bounded domain $\tilde{\Omega} \subset \mathbb{R}^2$. In a partially non-dimensionalized form the (relative) energy associated with the magnetization $M : \mathbb{R}^3 \rightarrow \mathbb{R}^3$ with $|M| = 1$ in Ω and $M = 0$ else, is

$$\mathcal{E}[M] = \int_{\tilde{\Omega}_t} d^2 |\nabla M|^2 + Q \int_{\tilde{\Omega}_t} (M_1^2 + M_2^2) + \int_{\mathbb{R}^3} |\mathcal{H}(M)|^2 - \int_{\mathbb{R}^3} |\mathcal{H}(e_3 \chi_\Omega)|^2. \quad (1)$$

The first three integrals above are the Landau-Lifshitz energy associated with the magnetization [30]. In particular, the first integral is called the *exchange energy* and reflects the preference of neighboring spins to be aligned. The second integral describes the fact that the considered material energetically prefers a direction of the magnetization normal to the film plane and is called *anisotropy energy*. The third integral is the *magnetostatic* (or stray field) energy where the stray field operator is the projection on rotation free vector fields, i.e.

$$\mathcal{H}(M) = -\nabla\Phi, \quad \text{where } \Phi \in H^1(\mathbb{R}^3) \text{ solves } \Delta\Phi = \operatorname{div} M. \quad (2)$$

With the last integral we have subtracted the energy of the uniform magnetization $e_3\chi_{\tilde{\Omega}_t}$; this term does not depend on the specific magnetization. Hence, \mathcal{E} is the relative energy of the magnetization M with respect to the energy of the uniform magnetization. Finally, the parameter d is called exchange length and the dimensionless parameter $Q > 0$ is called quality factor. We consider thin films where the thickness is much smaller than the exchange length, i.e. $t \ll d$. The quality factor is fixed throughout this work and we assume $Q > 1$ which corresponds to a so called hard material.

A good way to understand the magnetostatic energy is from the perspective of electrostatics: In fact, in view of (2), the magnetostatic field is created by the distributional divergence $\operatorname{div} M$ in the same way as the electrostatic field is created by charge density in electrostatics. With this analogy in mind, $\operatorname{div} M$ is hence denoted as *magnetic charge* (density). In turn $\operatorname{div} M$ consists of two parts: The absolutely continuous part $(\operatorname{div} M)_{ac}$ are the so called *volume charges*; any non-zero normal component $(\operatorname{div} M)_s = M \cdot n \mathcal{H}_{|\partial\tilde{\Omega}_t}^2$ at the boundary $\partial\tilde{\Omega}_t$ with outer normal n are the so called *surface charges*.

The analysis of this functional is non-trivial as it amounts to a nonconvex and non-local variational problem. The local parts of the energy in (1), i.e. the exchange energy and anisotropy energy, favor a uniform magnetization, at the same time a uniform magnetization leads to a high magnetostatic energy. The competition of the local and nonlocal (magnetostatic) part of the energy hence leads to the formation of magnetostatic domains, i.e. extended regions of uniform magnetization which are separated by thin transition layers where the magnetization rotates rapidly (see Fig. 1). Experimental and numerical findings [23, 13] indicate the following scaling laws




Figure 1: Sketch of a stripe domain pattern structure in a thin ferromagnetic film.

for the typical domain width and the ground state energy:

$$s := d \frac{e^{\frac{2\pi d}{t}\sqrt{Q-1}}}{\sqrt{Q-1}} \quad \text{scaling of typical domain width,} \quad (3)$$

$$\inf_M \mathcal{E}[M] \sim dt^2 \frac{e^{\frac{2\pi d}{t}\sqrt{Q-1}}}{\sqrt{Q-1}} \quad \text{scaling of ground state energy.} \quad (4)$$

These scaling laws have been investigated in [27] in a periodic setting. In this paper, the authors correspondingly identified a subcritical and a supercritical regime. In particular, they showed that the above scaling laws holds in the supercritical regime. In this work we investigate the critical regime for a finite magnetic sample associated with the onset of formation of magnetic domains and the corresponding ground state energy. We confirm these scaling laws in the critical regime in the case of a finite sample. Due to the nonlocal character of the energy, this requires some adaption of the methods used in [27]. While the analysis in [27] is mainly concerned with the situation of the subcritical and supercritical regime, in this paper we precisely consider the critical regime at the onset of pattern formation and we use a rescaling of the model which is suited to the critical regime. We then show that the onset of non-trivial pattern formation occurs in the critical regime and give some conditions for the presence and absence of non-trivial pattern formation. We note that, in general, the parameters in (1) also dependent on the temperature which hence also impacts the domain structure [18]. Other effects such as the Dzyaloshinskii-Moriya interaction are also relevant in some parameter regimes and have been considered in the literature as well (see e.g. [32, 31]).

In view of the above considerations we rescale the energy according to the scaling of the ground state energy and the minimum of the length scale according to the

typical width s of the magnetic domains or the sample, i.e.

$$E_\epsilon[M] := \frac{\pi}{st^2} \mathcal{E}[\tilde{M}] \quad \text{where } M(x, x_3) := \tilde{M}(sx, tx_3) \quad (5)$$

for $(x, x_3) \in \mathbb{R}^2 \times \mathbb{R}$ and where we introduce the non-dimensional parameter

$$\epsilon := e^{-\frac{2\pi d}{t}\sqrt{Q-1}}, \quad (6)$$

which represents the ratio between the typical width of transition layers versus the typical domain width. Our problem can hence be characterized by the two dimensionless parameters Q and ϵ . The thin film regime $t \ll d$ corresponds to the regime $\epsilon \ll 1$. We will assume $Q > 1$ throughout the paper. With the notation $\Omega_1 := \Omega \times [0, 1] \subset \mathbb{R}^3$, we correspondingly investigate the energy E_ϵ on the class of magnetizations

$$\mathcal{A} = \left\{ M \in L^2(\mathbb{R}^3; \mathbb{R}^3) : M \in H^1(\Omega_1), |M| = 1 \text{ in } \Omega_1 \text{ and } M = 0 \text{ else} \right\}.$$

Variation of the magnetization in thickness direction is energetically unfavorable for thin films and penalized in terms of the exchange part of the energy. We hence reduce this problem in Section 2 to a two-dimensional model, formulated in terms of the average magnetization over the film height, given by

$$\overline{M}(x) := \left(\int_0^t M(sx, x_3) dz \right) \chi_{[0,t]}(x_3). \quad (7)$$

We first give a criterion on the onset of pattern formation in terms of the size of the underlying domain Ω :

Theorem 1.1 (Onset of domain formation). *Let $\Omega \Subset \mathbb{R}^2$ be convex and bounded. Then there is a universal constant $\epsilon_0 > 0$ such that for $\epsilon \in (0, \epsilon_0)$ we have*

(i) (Domains with small diameter) *If $\text{diam } \Omega < \frac{\pi}{2\epsilon} \left(1 - \frac{2}{|\ln \epsilon|}\right)$, then*

$$\inf_{M \in \mathcal{A}, M = \overline{M}} E_\epsilon[M] = 0. \quad (8)$$

Furthermore, the only two minimizers in (8) are given by $M = \pm e_3 \chi_{\Omega_1}$.

(ii) (Minimal energy for large domains) *There are universal constants $0 < c, R < \infty$ such that for $\Omega^{(R)} := \{x \in \Omega : \text{dist}(x, \Omega^c) \geq R\} \subset \Omega$ we have*

$$-\frac{\pi^2 e}{4} |\Omega| \leq \inf_{M \in \mathcal{A}} E_\epsilon[M] \leq -c |\Omega^{(R)}|.$$

Theorem 1.1 characterizes the onset of magnetic domains. In particular, statement (i) shows that for samples with small diameter and for magnetizations with $M = \overline{M}$, the energy is minimized by $m = \pm e_3 \chi_{\Omega_1}$. For general magnetizations a related estimate holds true up to a small error as stated in Lemma 3.2. For larger films, statement (ii) shows that the uniform magnetization is not optimal anymore. Furthermore, this statement confirms the scaling law (4) for the ground state energy, formulated in the rescaled variables.

The theorem is concerned with the scaling law (3) for the average size of the domain. These statements are formulated in terms of the total interfacial length which can be seen as a measure for the typical width of the domains (since Ω has area of order one). In turn, this (scalingwise) implies that the average width of the magnetic domains is of order one. We have the following rigorous justification for these observations:

Theorem 1.2 (BV bounds and compactness). *With the assumptions of Theorem 1.1 and with \overline{M} defined in (7) we have*

(i) (BV estimate) *For the average magnetization (7) we have*

$$\left| \ln \left(\frac{\|\nabla \overline{M}_3\|_{\Omega_1}}{\pi^2 e^2 |\Omega|} \right) \right| \|\nabla \overline{M}_3\|_{\Omega_1} \leq E_\epsilon[\overline{M}] + \frac{\pi^2 e}{4} |\Omega| \quad \forall M \in \mathcal{A}.$$

(ii) (BV estimate for low energy configurations) *For any $\alpha > 0$ there are constants $c_\alpha, C_\alpha > 0$ such that for any $M \in \mathcal{A}$ with $E_\epsilon[M] < -\alpha |\Omega|$ we have*

$$c_\alpha |\Omega| \leq \|\nabla \overline{M}_3\|_{\Omega_1} \leq C_\alpha |\Omega|.$$

(iii) (Compactness) *For any family $M_\epsilon \in \mathcal{A}$ with*

$$\limsup_{\epsilon \rightarrow 0} E_\epsilon[M_\epsilon] < \infty$$

there is $m \in BV(\mathbb{R}^2, \pm e_1)$ with $|M| = 1$ in Ω and $M = 0$ else such that for a subsequence $\epsilon \rightarrow 0$ and with $(m \otimes \chi_{[0,1]})(x, x_3) := m(x) \chi_{[0,1]}(x_3)$ we have

$$M_\epsilon \rightarrow m \otimes \chi_{[0,1]} \quad \text{in } L^1(\Omega_1).$$

The above theorem gives a rigorous justification for the conjecture on the scaling law (3) for the typical domain size. Statement (i) shows that a sharp bound for the BV norm in terms of the nonlocal energy. In particular, for configurations with small relative energy (ii) shows that the total length of the interfaces is of order 1. Finally,

(iii) gives a corresponding compactness result which is a direct consequence of these bounds on the BV norm.

In the course of the proof, we first show that the energy (5) can be approximated in our regime by another two-dimensional energy, given by

$$F_\epsilon[m] = |\ln \epsilon| \int_{\Omega} \left(\frac{\epsilon}{2} |\nabla m|^2 + \frac{1}{2\epsilon} (1 - m_3^2) \right) dx - \frac{1}{8} \iint_{\mathbb{R}^4} \frac{|m_3(x) - m_3(x')|^2}{|x - x'|^3} dx dx'. \quad (9)$$

In fact, the corresponding results to Theorems 1.1 and 1.2 also hold for the energy F_ϵ . The natural domain for the energy F_ϵ is the class of magnetizations

$$\bar{\mathcal{A}} := \{m \in L^2(\mathbb{R}^2; \mathbb{R}^2) : m \in H^1(\Omega), |m| = 1 \text{ in } \Omega \text{ and } m = 0 \text{ else}\}.$$

Without the nonlocal term, by standard Modica–Mortola theory the first two terms on the right hand side of (9) would Γ -converge to the BV norm of m_3 . The second term is nonlocal and is the homogeneous $H^{\frac{1}{2}}$ -norm of m_3 . Note that the BV-norm has the same scaling as the $H^{\frac{1}{2}}$ -norm which is a major difficulty in the proof of the results and which explains the appearance of logarithms in the statement of Theorem 1.2. In the proof we will show that the leading order contributions of these two terms cancel in the limit $\epsilon \rightarrow 0$ and the bound on the ground state energy is derived from the remaining term.

We note that the corresponding model in a periodic setting has been investigated in [27] by Muratov, Nolte and the second author. The authors identified a subcritical and a supercritical regime. In the subcritical regime, they then show a Γ -limit result where the energy converges to a local limit energy. In the supercritical case, energy bounds are derived which confirm the scaling laws (3)–(4). In this work we consider the critical regime in the geometry of a finite sample where additional surface charges may occur at the lateral boundary of the magnetic film. In this setting, we show that the same scaling laws still hold. Furthermore, we derive new conditions on the onset of pattern formation within the critical regime.

We also note that a corresponding sharp interface versions of the energy (1) has been considered by different authors. In these models, compared to the energy (9), the local part of the energy is replaced by the perimeter term. At the same time, the $H^{\frac{1}{2}}$ -norm is replaced by a regularized version of this norm with an ϵ -dependent high frequency cut-off. This is reminiscent of the results of Bourgain, Brezis, Mironescu [4] and Dávila [15] which show the convergence of a class of nonlocal perimeter functionals towards the BV-norm. A related two-dimensional model energy has been studied by Muratov and Simon in [35], where the authors show among other

results a Γ -convergence result. For a different approximation of the nonlocal term, a corresponding Γ -convergence result has been given by Cesaroni and Novaga [7]. A corresponding Γ -convergence result in arbitrary dimensions and for a more general class of approximations of the nonlocal energy has been shown in [26] by Shi together with the second author. These results can be seen as second order extensions of the result in [15].

More generally, pattern formation has also been investigated in related models which include a competition between a local isoperimetric term and an opposing nonlocal term such as e.g. the Ohta-Kawasaki energy [1, 2, 10, 11, 20], liquid drop models [12, 22, 34] or elastic materials (these references are certainly not complete). The methods used are typically specific for the model at hand. In particular, in the above models the nonlocal term does not have the same scaling as the perimeter contrary to the problem considered here.

Structure of paper: In Section 2 we derive estimates on the stray field which show that the energy (5) can be approximated by the two-dimensional energy (9). The proofs of Theorem 1.1 and Theorem 1.2 are then given in Sections 3 and 4. In particular, the theorems are a consequence of Lemma 3.2 and Propositions 3.3, 3.4 and 4.3.

Notation: We write $A \lesssim B$ if $A \leq CB$ for some universal constant $C < \infty$. The notations \gtrsim and \sim are defined analogously.

For two sets $E, F \subset \mathbb{R}^n$ we write $E \Subset F$ if the set E is compactly embedded in the set F . By $B_\delta(E) := \{x \in \mathbb{R}^n : \text{dist}(x, E) < \delta\}$ we denote the δ -neighborhood of the set E . For a set $\Omega \subset \mathbb{R}^n$ with non-zero interior we write $|\Omega| := \mathcal{L}^n(\Omega)$ and $|\partial\Omega| := \mathcal{L}^{n-1}(\partial\Omega)$. By χ_Ω we denote the characteristic function of the set Ω . The total variation of a function on the set Ω is written as $\|\nabla f\|_\Omega := \int_\Omega |\nabla f|$.

We denote points in \mathbb{R}^3 usually by $\bar{x} = (x, x_3) \in \mathbb{R}^3$. On the other hand, the magnetization vector field $M : \mathbb{R}^3 \rightarrow \mathbb{R}^3$ is written in the form $M = (M', M_3)$. We use the notation $M := m \otimes \chi_{[0,t]}$ for the function $M(x, x_3) = m(x)\chi_{[0,t]}(x_3)$. For the two-dimensional Fourier transform we use the convention

$$\widehat{f}(\xi) = \frac{1}{2\pi} \int_{\mathbb{R}^2} f(x) e^{-i\xi \cdot x} dx,$$

so that in particular Plancherel's identity holds with prefactor 1.

2 Dimensional reduction

In this section, we show that the two-dimensional energy (9) is a good approximation for the initial energy in the considered regime of thin-films. Due to the specific geometry of our sample, it is useful to differentiate between directions within the film plane and normal directions. We hence consistently write $(x, x_3) \in \mathbb{R}^2 \times \mathbb{R}$ for points in \mathbb{R}^3 . We first recall that the stray field operator (2) is the orthogonal projection onto gradient fields:

Lemma 2.1 (Stray field). *For any $M \in H^1(\mathbb{R}^3; \mathbb{R}^3)$ we have*

$$\mathcal{H}(M)(x, x_3) = \nabla \int_{\mathbb{R}^3} K(x - x', x_3 - x'_3) \operatorname{div} M(x', x'_3) dx' dx'_3, \quad (10)$$

where the kernel $K : \mathbb{R}^2 \times \mathbb{R} \rightarrow \mathbb{R}$ and its Fourier transform (in terms of x) are

$$K(x, x_3) := \frac{1}{4\pi\sqrt{|x|^2 + x_3^2}}, \quad \widehat{K}(\xi, x_3) = \frac{1}{4\pi|\xi|} e^{-|x_3||\xi|}.$$

Furthermore, $\mathcal{H} : L^2(\mathbb{R}^3; \mathbb{R}^3) \rightarrow L^2(\mathbb{R}^3; \mathbb{R}^3)$ is linear, $\mathcal{H}^2(M) = \mathcal{H}(M)$ and

$$(i) \int_{\mathbb{R}^3} \mathcal{H}[M] \cdot (\mathcal{H}[\tilde{M}] - \tilde{M}) = 0 \quad \forall \tilde{M} \in H^1(\mathbb{R}^3; \mathbb{R}^3).$$

$$(ii) \int_{\mathbb{R}^3} |\mathcal{H}[M]|^2 \leq \int_{\mathbb{R}^3} |M|^2.$$

Proof. The kernel K is just the Newton kernel in \mathbb{R}^3 which justifies (10). A standard integral formula [39, eq 6.554.1] then yields

$$\widehat{K}(\xi) = \frac{1}{2\pi} \int_{\mathbb{R}^2} \frac{e^{-i\xi \cdot x}}{4\pi\sqrt{|x|^2 + x_3^2}} dx = \int_0^\infty \frac{J_0(|\xi|r)}{4\pi\sqrt{r^2 + x_3^2}} r dr = \frac{1}{4\pi|\xi|} e^{-|x_3||\xi|},$$

where J_0 is the Bessel function of first kind. We next give the proof for (i)–(ii): Multiple integration by parts yields

$$\int_{\mathbb{R}^3} \mathcal{H}(M) \cdot \mathcal{H}(\tilde{M}) = - \int_{\mathbb{R}^3} \varphi \cdot \Delta \tilde{\varphi} = \int_{\mathbb{R}^3} \varphi \cdot \operatorname{div} \tilde{M} = \int_{\mathbb{R}^3} \mathcal{H}(M) \cdot \tilde{M}.$$

Estimate (ii) follows from (i) and an application of Cauchy-Schwarz. \square

Variation of the magnetization in thickness direction is energetically unfavorable for thin films and penalized in terms of the exchange part of the energy. For $M \in H^1(\Omega_t; \mathbb{R}^3)$ we hence consider the corresponding magnetization (7) which is averaged in the thickness direction.

The following result is a version of [27, Theorem 5.2] for finite domains. The different geometry requires some adaptations to the proof since the magnetization might be discontinuous at the lateral boundary. This is reflected on the right hand side of (11) which incorporates the lateral sample boundary $\partial\Omega \times [0, t]$:

Theorem 2.2 (Reduction of stray field). *Let $\tilde{\Omega} \Subset \mathbb{R}^2$ and let $\tilde{\Omega}_t := \tilde{\Omega} \times [0, t]$. Let $M = (M', M_3) \in \mathcal{A}$ and let \bar{M} be given by (7). Then*

$$\int_{\mathbb{R}^3} |\mathcal{H}[M]|^2 = \int_{\mathbb{R}^3} |\mathcal{H}[\bar{M}]|^2 + \mathcal{O}\left(t|B_t(\partial\tilde{\Omega}) \cap \tilde{\Omega}| + t^2 \int_{\tilde{\Omega}_t} |\nabla M|^2\right). \quad (11)$$

Proof. We define $U := M - \bar{M}$. Since $\bar{U} = 0$ by Lemma 2.1 and Poincaré's inequality we have

$$\int_{\mathbb{R}^3} |\mathcal{H}(U)|^2 \leq \int_{\tilde{\Omega}_t} |U|^2 \leq t^2 \int_{\tilde{\Omega}_t} |\partial_3 M|^2 = \mathcal{O}\left(t^2 \int_{\tilde{\Omega}_t} |\nabla M|^2\right). \quad (12)$$

We write $M = \bar{M} + U$ and expand the expression on the left hand side of (11) using the fact that \mathcal{H} is a linear operator. By (12) it is then enough to show that

$$\left| \int_{\tilde{\Omega}_t} \mathcal{H}(\bar{M}) \cdot U \right| = \mathcal{O}\left(t|B_t(\partial\tilde{\Omega}) \cap \tilde{\Omega}| + t^2 \int_{\tilde{\Omega}_t} |\nabla M|^2\right). \quad (13)$$

For $\delta > 0$, we choose a cut-off function $\zeta_\delta \in H^1(\mathbb{R}^2)$ by $\zeta_\delta(x) := \min\{1, \frac{1}{\delta} \text{dist}(x, \partial\tilde{\Omega})\}$ for $x \in \tilde{\Omega}$ and $\zeta_\delta = 0$ else. Then we have $0 \leq \zeta_\delta \leq 1$ and $\zeta_\delta = 0$ in $\tilde{\Omega}^c$ and $\zeta = 1$ in $\tilde{\Omega} \setminus \tilde{B}$ where $\tilde{B} := B_\delta(\partial\tilde{\Omega}) \cap \tilde{\Omega}$. We now define $M_\delta(x, x_3) := \zeta_\delta(x) \bar{M}(x, x_3)$. By Lemma 2.1, by Jensen's inequality and with the choice $\delta := t$ we then have

$$\begin{aligned} \int_{\tilde{\Omega}_t} |\mathcal{H}(M_\delta) - \mathcal{H}(\bar{M})|^2 &\leq \int_{\tilde{\Omega}_t} |M_\delta - \bar{M}|^2 \leq \delta |\tilde{B}| = t |\tilde{B}|, \\ t^2 \int_{\tilde{\Omega}_t} |\nabla M_\delta|^2 &\leq t^2 \left(\frac{t |\tilde{B}|}{\delta^2} + \int_{\tilde{\Omega}_t} |\nabla \bar{M}|^2 \right) = \mathcal{O}\left(t |\tilde{B}| + t^2 \int_{\tilde{\Omega}_t} |\nabla M|^2\right). \end{aligned}$$

By an application of Cauchy–Schwarz and in view of (12), we then also have

$$\left| \int_{\tilde{\Omega}_t} \mathcal{H}(M_\delta - \bar{M}) \cdot U \right| = \mathcal{O}\left(t |\tilde{B}| + t^2 \int_{\tilde{\Omega}_t} |\nabla M|^2\right).$$

In view of these calculations, (13) then follows if we can show that

$$X := \left| \int_{\widehat{\Omega}_t} \mathcal{H}(\overline{M}_\delta) \cdot U \right| = \mathcal{O}\left(t^2 \int_{\widehat{\Omega}_t} |\nabla M|^2\right).$$

The advantage of the new function M_δ is that $M_\delta = 0$ on $\partial\widehat{\Omega} \times [0, t]$ which implies

$$\int_{\widehat{\Omega}_t} |\nabla' \overline{M}|^2 dx dx_3 = \int_{\mathbb{R}^3} |\nabla' \overline{M}|^2 dx dx_3 = \int_{\mathbb{R}^3} |\xi|^2 |\widehat{\overline{M}}|^2 d\xi dx_3. \quad (14)$$

We use the stray field formula from Lemma 2.1 and apply the Fourier transform in x . Integrating by parts and since $\overline{M}(x, x_3) = \overline{M}(x) \chi_{[0, t]}(x_3)$ with $P := \widehat{\overline{M}_\delta}(\xi)$ we get

$$\begin{aligned} \widehat{\mathcal{H}}'(\overline{M})(\xi, x_3) &= 4\pi \left(\int_0^t |\xi|^2 \widehat{K}(\xi, x_3 - x'_3) dx'_3 P' - \int_0^t i\xi \partial_3 \widehat{K}(\xi, x_3 - x'_3) dx'_3 P_3 \right) \\ \widehat{\mathcal{H}}_3(\overline{M})(\xi, x_3) &= 4\pi \left(\int_0^t \partial_3^2 \widehat{K}(\xi, x_3 - x'_3) dx'_3 P_3 - \int_0^t i\xi \partial_3 \widehat{K}(\xi, x_3 - x'_3) dx'_3 P' \right). \end{aligned} \quad (15)$$

We note that the antiderivative and derivative of $K = \frac{1}{4\pi|\xi|} e^{-|\xi||x_3|}$ in x_3 are given by $\int K = \frac{\text{sign } x_3}{4\pi|\xi|^2} (1 - e^{-|\xi||x_3|}) + c$ and $\partial_3 K = \frac{\text{sign } x_3}{4\pi} e^{-|\xi||x_3|}$. With these identities we compute the Fourier multipliers in (15) for $x_3 \in (0, t)$. We get

$$\begin{aligned} \mu_1(\xi, x_3) &:= 4\pi |\xi|^2 \int_0^t \widehat{K}(\xi, x_3 - x'_3) dx'_3 = \frac{1}{2} (e^{-|\xi||x_3-t|} + e^{-|\xi||x_3|} - 2), \\ \mu_2(\xi, x_3) &:= 4\pi |\xi| \int_0^t \partial_3 \widehat{K}(\xi, x_3 - x'_3) dx'_3 = \frac{1}{2} (e^{-|\xi|(t-x_3)} - e^{-|\xi|x_3}), \\ \mu_3(\xi, x_3) &:= 4\pi \int_0^t \partial_3^2 \widehat{K}(\xi, x_3 - x'_3) dx'_3 = \frac{1}{2} (e^{-|\xi|(t-x_3)} + e^{-|\xi|x_3}). \end{aligned}$$

We now use the fact that U has a vanishing average, i.e. $\overline{U} = 0$, to conclude that

$$X = \left| \int_{\mathbb{R}^3} \mathcal{H}(M_\delta) \cdot U dx \right| = \left| \int_{\mathbb{R}^3} (\mathcal{H}(M_\delta) - M_{\delta,3} e_3) \cdot U dx \right|.$$

Hence, by Plancherel's identity we can estimate X in the form

$$\begin{aligned} X &= \left| \int_{\mathbb{R}^3} (\mathcal{H}(M_\delta) - M_{\delta,3} e_3) \cdot U dx \right| \\ &\stackrel{(15)}{\leq} \sum_{i=1}^3 \int_{\mathbb{R}^3} |\mu_i - \delta_{i3}| |\widehat{M}_\delta(\xi)| |\widehat{U}(\xi, x_3)| d\xi dx_3. \end{aligned} \quad (16)$$

By Taylor expansion we have $|\mu_i(\xi, x_3) - \delta_{i3}| \leq |\xi|t$ for $i = 1, 2, 3$ and $|x_3| \leq t$. Also using Cauchy–Schwarz and (12) and in view of (14) the proof is concluded by

$$\begin{aligned} X &\stackrel{(16)}{\leq} t \int_0^t \int_{\mathbb{R}^2} |\xi| |\widehat{M}_\delta(\xi)| |\widehat{U}(\xi, x_3)| \, d\xi dx_3 \\ &\leq t \left(\int_{\tilde{\Omega}} |\nabla' M_\delta|^2 \, dx dx_3 \right)^{\frac{1}{2}} \left(\int_{\mathbb{R}^3} |U|^2 \, dx dx_3 \right)^{\frac{1}{2}} \lesssim t^2 \int_{\tilde{\Omega}} |\nabla M_\delta|^2 \, dx. \end{aligned}$$

□

We next derive the kernels for the main contribution of the stray field in thin–films.

Theorem 2.3 (Representation of stray field). *Let $M = (M', M_3) \in H^1(\mathbb{R}^3; \mathbb{R}^3)$ with $\text{spt } M \subset \mathbb{R}^2 \times [0, t]$ and let \overline{M} be given by (7). Then*

$$\int_{\mathbb{R}^3} |\mathcal{H}[\overline{M}]|^2 \, dx = \int_{\mathbb{R}^3} |\mathcal{H}[\overline{M}_3 e_3]|^2 \, dx + \int_{\mathbb{R}^3} |\mathcal{H}[\overline{M}']|^2 \, dx. \quad (17)$$

Furthermore, we have the representations:

$$\begin{aligned} \int_{\mathbb{R}^3} |\mathcal{H}[\overline{M}_3 e_3]|^2 \, dx &= t \int_{\mathbb{R}^2} \overline{M}_3^2 \, dx - \frac{t^2}{8\pi} \iint_{\mathbb{R}^4} \Gamma\left(\frac{1}{t}|x - x'|\right) \frac{|\overline{M}_3(x) - \overline{M}_3(x')|^2}{|x - x'|^3} \, dx dx' \\ \int_{\mathbb{R}^3} |\mathcal{H}[\overline{M}']|^2 \, dx &= \frac{t^2}{4\pi} \iint_{\mathbb{R}^4} \Theta\left(\frac{1}{t}|x - x'|\right) \frac{\text{div } \overline{M}'(x) \text{div } \overline{M}'(x')}{|x - x'|} \, dx dx' \end{aligned}$$

where the monotonically increasing functions $\Gamma, \Theta : [0, \infty) \rightarrow \mathbb{R}$ are given by

$$\Gamma(\alpha) := 2\alpha^2 \left(1 - \frac{\alpha}{\sqrt{1 + \alpha^2}} \right), \quad \Theta(\alpha) := 2 \left(\alpha \operatorname{arsinh}\left(\frac{1}{\alpha}\right) + \alpha^2 - \sqrt{1 + \alpha^2} \right). \quad (18)$$

In particular, $\Gamma(0) = \Theta(0) = 0$ and $\Gamma(\alpha), \Theta(\alpha) \rightarrow 1$ for $\alpha \rightarrow \infty$.

Proof. To prove the assertion (17) we write $\overline{M} = \overline{M}_3 e_3 + \overline{M}'$ and expand the expression $\mathcal{H}(\overline{M}_3 e_3 + \overline{M}')$. The assertion then follows from

$$\int_{\mathbb{R}^3} \mathcal{H}(\overline{M}_3 e_3) \cdot \mathcal{H}(\overline{M}') \, dx = 0. \quad (19)$$

The identity (19) holds in view of the following symmetries: The (surface) charge density $\partial_3 \overline{M}_3$ is antisymmetric w.r.t. the plane $\{x_3 = \frac{1}{2}\}$, while the charge density $\nabla' M'$ is symmetric w.r.t. the same plane. These symmetry properties carry over to the created stray fields.

The proof of the representation formulas is based on the real space representation (20) of the stray field energy in Lemma 2.1. In particular, we have

$$\int_{\mathbb{R}^3} |\mathcal{H}[\overline{M}]|^2 dx = \iint_{\mathbb{R}^6} K(x - x', x_3 - x'_3) \operatorname{div} \overline{M}(x) \operatorname{div} \overline{M}(x') dx_3 dx'_3 dx dx'. \quad (20)$$

We apply this formula for $M_3 e_3$ as well as for M' . Integrating by parts two times in x_3 in the formula (20) yields

$$\begin{aligned} \int_{\mathbb{R}^3} |\mathcal{H}[\overline{M}_3 e_3]|^2 dx &= \iint_{\mathbb{R}^4} \left(\iint_{[0,t]^2} \partial_3^2 K(x - x', x_3 - x'_3) dx_3 dx'_3 \right) \overline{M}_3(x) \overline{M}_3(x') dx dx' \\ &=: \iint_{\mathbb{R}^4} G_t(x - x') \overline{M}_3(x) \overline{M}_3(x') dx dx', \end{aligned} \quad (21)$$

where

$$\begin{aligned} G_t(x) &= \int_0^t \left[\partial_3 K(x, x_3 - x'_3) \right]_{x_3=0}^{x_3=t} dx'_3 = 2(K(x, 0) - K(x, t)) \\ &= \frac{1}{2\pi|x|} \left(1 - \frac{1}{\sqrt{1 + (\frac{t}{|x|})^2}} \right) \stackrel{(18)}{=} \frac{t^2}{4\pi|x|^3} \Gamma\left(\frac{|x|}{t}\right). \end{aligned}$$

We write the right hand side of (21) as a difference operator, i.e.

$$\int_{\mathbb{R}^3} |\mathcal{H}[\overline{M}_3 e_3]|^2 dx = \iint_{\mathbb{R}^4} \left(G_t(x - x') |\overline{M}_3(x)|^2 - \frac{1}{2} G_t(x - x') |\overline{M}_3(x) - \overline{M}_3(x')|^2 \right).$$

The proof of the first assertion is concluded by an application of Fubini together with

$$\int_{\mathbb{R}^2} G_t(x_3) dx_3 = \int_0^\infty 1 - \frac{\rho}{\sqrt{t^2 + \rho^2}} d\rho = \left[\rho - \sqrt{t^2 + \rho^2} \right]_0^\infty = t.$$

For the proof of the second assertion we note that for $\Psi(x, x_3) := \frac{|x|}{4\pi} \left[\left(1 + \frac{x_3^2}{|x|^2} \right)^{1/2} - \frac{x_3}{|x|} \operatorname{arsinh}\left(\frac{x_3}{|x|}\right) \right]$, we have $\partial_3 \Psi(x, x_3) = -\frac{1}{4\pi} \operatorname{arsinh}\left(\frac{x_3}{|x|}\right)$ and $\partial_3^2 \Psi(x, x_3) = K(x, x_3)$. Hence, as before we calculate

$$\begin{aligned} \iint_{[0,t]^2} K(x, x_3 - x'_3) dx_3 dx'_3 &= 2 \left[\Psi(x, 0) - \Psi(x, t) \right] \\ &= \frac{|x|}{2\pi} \left[\frac{t}{|x|} \operatorname{arsinh}\left(\frac{t}{|x|}\right) + 1 - \sqrt{1 + \frac{t^2}{|x|^2}} \right] = \frac{t^2}{4\pi|x|} \Theta\left(\frac{|x|}{t}\right). \end{aligned}$$

A straightforward calculation shows that both Γ and Θ are monotonically increasing with $\Gamma(0) = \Theta(0) = 0$ and $\Gamma(s), \Theta(s) \rightarrow 1$ for $s \rightarrow \infty$. \square

It is useful to keep the following relations between our parameters in mind:

Remark 2.4 (Parameter relations). *We collect the relations of the three dimensional parameters d , t and s in terms of the dimensionless parameters $\epsilon = \frac{d}{s\sqrt{Q-1}}$ and Q where we consider the regime $\epsilon \ll 1$ with fixed $Q > 1$. By (6) we have $|\ln \epsilon| = \frac{2\pi d}{t}\sqrt{Q-1}$. By (3)–(6) we get $\frac{d}{s} = \epsilon\sqrt{Q-1}$. Hence,*

$$\frac{d}{s} = \epsilon\sqrt{Q-1}, \quad \frac{s}{t} = \frac{|\ln \epsilon|}{2\pi(Q-1)\epsilon}, \quad \frac{d}{t} = \frac{|\ln \epsilon|}{2\pi\sqrt{Q-1}}.$$

It is convenient to introduce the notation

$$\omega := \frac{t}{s} = 2\pi(Q-1)\frac{\epsilon}{|\ln \epsilon|} \quad (22)$$

for the aspect ratio of the film. Combining the previous formulas for the stray field we obtain an asymptotic representation of the energy:

Lemma 2.5 (Representation for E_ϵ). *Let $\Omega \Subset \mathbb{R}^2$ be a set of finite perimeter. Let $M = (M', M_3) \in \mathcal{A}$ and let $\bar{M} = m \otimes \chi_{[0,1]}$ be given by (7). Then*

$$\begin{aligned} E_\epsilon[M] &= F_\epsilon[m] + G_\epsilon[M] \\ &+ \mathcal{O}\left(\frac{\epsilon}{|\ln \epsilon|} \int_{\Omega_1} |\nabla' M|^2 + \frac{|\ln \epsilon|}{\epsilon} \int_{\Omega_1} |\partial_3 M|^2 + \frac{\alpha_0 |\ln \epsilon|}{\epsilon} |B_\omega(\partial\Omega) \cap \Omega|\right). \end{aligned}$$

where $\alpha_0 = 1$ if $M \neq \bar{M}$ and $\alpha_0 = 0$ else and where (with notations (6), (22))

$$\begin{aligned} G_\epsilon[M] &= \epsilon |\ln \epsilon| \int_{\Omega_1} \left(|\nabla' M|^2 - |\nabla' \bar{M}|^2 \right) + \frac{|\ln \epsilon|^3}{\epsilon(Q-1)^2(2\pi)^2} \int_{\Omega_1} |\partial_3 M|^2 \\ &+ \frac{1}{8} \iint_{\Omega \times \Omega} \left(1 - \Gamma\left(\frac{1}{\omega}|x-x'\right) \right) \frac{|m_3(x) - m_3(x')|^2}{|x-x'|^3} dx dx' \\ &+ \frac{1}{4} \iint_{\Omega^c \times \Omega} \Gamma\left(\frac{1}{\omega}|x-x'\right) \frac{1 - m_3(x')^2}{|x-x'|^3} dx dx' \\ &+ \frac{1}{4} \iint_{\Omega \times \Omega} \Theta\left(\frac{1}{\omega}|x-x'\right) \operatorname{div} m'(x) \operatorname{div} m'(x') dx dx' \\ &\geq 0. \end{aligned}$$

Proof. Let $\tilde{\Omega} = s\Omega$, $\tilde{\Omega}_t := \tilde{\Omega} \times [0, t]$ and $\tilde{M}(sx, tx_3) := M(x, t)$. By Theorem 2.2 and Theorem 2.3 we have

$$\int_{\mathbb{R}^3} |\mathcal{H}[\tilde{M}]|^2 = \int_{\mathbb{R}^3} |\mathcal{H}[\bar{M}_3 e_3]|^2 + \int_{\mathbb{R}^3} |\mathcal{H}[\bar{M}']|^2 + \alpha_0 \mathcal{O}\left(t |B_t(\partial\tilde{\Omega}) \cap \Omega| + t^2 \int_{\tilde{\Omega}_t} |\nabla \tilde{M}|^2\right).$$

We rewrite the expression on the right hand side using Theorem 2.3. We also rescale length and use the notations from the statement of the lemma. We also use the fact that $|m| = \chi_\Omega$. With $\Omega_1 := \Omega \times [0, 1]$ we then obtain

$$\mathcal{E}[\tilde{M}] = \mathcal{F}[m] + \mathcal{G}[M] + \mathcal{O}\left(ts^2|B_\omega(\partial\Omega) \cap \Omega| + t^3 \int_{\Omega_1} |\nabla' M|^2 + ts^2 \int_{\Omega_1} |\partial_3 M|^2\right).$$

where with $(\cdot) := (\frac{s}{t}|x - x'|)$ we have

$$\begin{aligned} \mathcal{F}[m] &= \int_{\Omega} td^2|\nabla m|^2 + s^2t(Q-1)(1-m_3^2) dx - \frac{st^2}{8\pi} \iint_{\Omega \times \Omega} \Gamma(\cdot) \frac{|m_3(x) - m_3(x')|^2}{|x - x'|^3} \\ \mathcal{G}[M] &= td^2 \left(\int_{\Omega_1} |\nabla' M|^2 - |\nabla \bar{M}|^2 \right) + \frac{s^2d^2}{t} \int_{\Omega_1} |\partial_3 M|^2 \\ &\quad + \frac{st^2}{4\pi} \left(\iint_{\Omega^c \times \Omega} \Gamma(\cdot) \frac{1 - m_3(x')^2}{|x - x'|^3} + \iint_{\Omega \times \Omega} \Theta(\cdot) \frac{\operatorname{div} m'(x) \operatorname{div} m'(x')}{|x - x'|} \right). \end{aligned}$$

We recall that $E_\epsilon = \frac{\pi}{st^2} \mathcal{E}$ so that every prefactor needs to be multiplied with $\frac{\pi}{st^2}$. Using the identities from Remark 2.4 we compute, $\frac{\pi d^2}{st} = \frac{1}{2}\epsilon |\ln \epsilon|$, $\frac{\pi(Q-1)s}{t} = \frac{|\ln \epsilon|}{2\epsilon}$ and $\frac{sd^2}{t^3} = \frac{|\ln \epsilon|^3}{\epsilon(2\pi)^3}$. This yields the representation formula. We finally note that $G_\epsilon \geq 0$ follows from $0 \leq \Gamma \leq 1$ and $0 \leq \Theta \leq 1$. \square

3 Lower bound and compactness

In this section, we give a lower bound for the energy for both energies F_ϵ and E_ϵ . Throughout the section, we use the notation $F_\epsilon[m] = L_\epsilon[m] - N[m]$ where

$$\begin{aligned} L_\epsilon[m] &:= |\ln \epsilon| \int_{\Omega} \frac{\epsilon}{2} |\nabla m|^2 + \frac{1}{2\epsilon} (1 - m_3^2)^2 dx, \\ N[m] &:= \frac{1}{8} \int_{\Omega} \int_{\Omega} \frac{1}{|x - y|^3} |m_3(x) - m_3(y)|^2 dx dy. \end{aligned} \tag{23}$$

One important ingredient for the proof of the lower bound is the following interpolation inequality which estimates the $H^{1/2}$ -finite difference norm in terms of BV and L^∞ -norm with a small term of higher order. We note that the leading order constant 8 in (24) below is sharp. The analogous inequality in the case of the torus has been shown in [27]. We state the lemma in a slightly different form, adapted to the case of finite domains. For the convenience of the reader we sketch the proof and refer to [27] for details.

Lemma 3.1 (Interpolation inequality). *Let Ω be convex with $\delta := |\text{diam } \Omega|$. Let $f \in C^\infty(\overline{\Omega})$. Then for any $0 < r \leq R$ we have*

$$\begin{aligned} \int_{\Omega} \int_{\Omega} \frac{1}{|x-y|^3} |f(x) - f(y)|^2 dx dy &\leq \pi r \int_{\Omega} |\nabla f|^2 dx \\ &+ 8 \ln \frac{R}{r} \|f\|_{L^\infty} \int_{\Omega} |\nabla f| dx + \frac{4\pi\alpha_0}{R} \|f\|_{L^\infty} \min \left\{ \delta \int_{\mathbb{R}^2} |\nabla f| dx, 2|\Omega| \|f\|_{L^\infty} \right\}, \end{aligned} \quad (24)$$

where $\alpha_0 = 1$ if $R < \delta$ and $\alpha_0 = 0$ else.

Proof. Let X be the left hand side of (24). Without loss of generality, we may assume that f is not constant. We show that for $0 < r \leq R$ and $\Omega_z := \Omega - z$ we have

$$\int_{B_r} \int_{\Omega \cap \Omega_z} \frac{|f(x+z) - f(x)|^2}{|z|^3} dx dz \leq \pi r \int_{\Omega} |\nabla f|^2 dx, \quad (25)$$

$$\int_{B_R \setminus B_r} \int_{\Omega \cap \Omega_z} \frac{|f(x+z) - f(x)|^2}{|z|^3} dx dz \leq 8 \ln \left(\frac{R}{r} \right) \|f\|_{L^\infty} \int_{\Omega} |\nabla f| dx, \quad (26)$$

$$\int_{B_R^c} \int_{\Omega \cap \Omega_z} \frac{|f(x+z) - f(x)|^2}{|z|^3} dx dz \leq \frac{4\pi}{R} \|f\|_{L^\infty} \min \left\{ \delta \int_{\mathbb{R}^2} |\nabla f|, 2|\Omega| \|f\|_{L^\infty} \right\}. \quad (27)$$

The assertion of the lemma then follows by adding (25) – (27). The proof of these estimates follows similarly as in [27]. For the convenience of the reader we sketch the details: We note that for convex sets Ω and for $p \geq 1$ we have

$$\int_{\Omega \cap \Omega_z} |f(x+z) - f(x)|^p dx \leq \int_{\Omega} |\nabla f(x) \cdot z|^p dx \quad \forall z \in \mathbb{R}^2. \quad (28)$$

Indeed, by the Fundamental Theorem of Calculus and Jensen's inequality,

$$\begin{aligned} \int_{\Omega \cap \Omega_z} |f(x+z) - f(x)|^p dx &= \int_{\Omega \cap \Omega_z} \int_0^1 \left| \nabla f(x+tz) \cdot z \right|^p dt dx \\ &= \int_0^1 \int_{\Omega \cap \Omega_z} |\nabla f(x+tz) \cdot z|^p dx dt \leq \int_{\Omega} |\nabla f(x) \cdot z|^p dx \quad \forall z \in \mathbb{R}^2, \end{aligned}$$

noting that $x + [0, 1]z \in \Omega$ for $x \in \Omega \cap \Omega_z$ since Ω is convex. The estimates (25) and (26) then follow analogously as in [27]. For the proof of (27) we estimate

$$\int_{B_R^c} \int_{\Omega \cap \Omega_z} \frac{|f(x+z) - f(x)|^2}{|z|^3} dx dz \leq 2 \|f\|_{L^\infty} \int_{B_R^c} \frac{1}{|z|^3} \int_{\Omega \cap \Omega_z} |f(x+z) - f(x)| dx dz.$$

The estimate then follows by noting that (28) with $p = 1$ entails

$$\int_{\Omega \cap \Omega_z} |f(x+z) - f(x)| dx \leq \min \left\{ \delta \int_{\mathbb{R}^2} |\nabla f \cdot z| dx, 2|\Omega| \|f\|_{L^\infty} \right\}$$

and integrating in z . □

We turn to the proof of Theorem 1.1 and Theorem 1.2. We first consider the case of a domain with small diameter:

Lemma 3.2 (Small diameter). *Let $\Omega \Subset \mathbb{R}^2$ be convex. Then there is $\epsilon_0 > 0$ such that for $\epsilon \in (0, \epsilon_0)$ the following holds: If the diameter of the set Ω is bounded by*

$$\text{diam } \Omega < \frac{\pi}{2e} \left(1 - \frac{2}{|\ln \epsilon|} \right)$$

then the following holds

$$(i) \quad \inf_{M \in \mathcal{A}, M = \bar{M}} E_\epsilon[M] = \inf_{m \in \bar{\mathcal{A}}} F_\epsilon[m] = 0.$$

$$(ii) \quad -c|\partial\Omega| \leq \inf_{M \in \mathcal{A}} E_\epsilon[M] \leq 0.$$

Furthermore, the infimum in (i) is only achieved by either one of the configurations $\pm e_3 \chi_\Omega \in \bar{\mathcal{A}}$ for F_ϵ and $(\pm e_3 \chi_\Omega) \otimes \chi_{[0,t]}$ for E_ϵ .

Proof. The upper bound for the ground state energy in (i) is given by either one of the two configurations $\pm e_3 \chi_\Omega$ for the energy F_ϵ or $\pm e_3 \chi_{\Omega_1}$ for the energy E_ϵ . It hence remains to give a proof for the lower bounds. We write $m(x) := \bar{M}(x, \frac{1}{2})$.

We first note that by convexity of the set Ω we have

$$\frac{|\ln \epsilon|}{\epsilon} |B_\omega(\partial\Omega) \cap \Omega| \leq \frac{|\ln \epsilon| \omega}{\epsilon} |\partial\Omega| \stackrel{(22)}{\leq} 2\pi(Q-1) |\partial\Omega| = c |\partial\Omega|.$$

With the estimate $\frac{\epsilon}{2} |\nabla m|^2 + \frac{1}{2\epsilon} (1 - m_3^2) \geq |\nabla m_3|$ we get

$$\begin{aligned} L_\epsilon[m] &= |\ln \epsilon| \left(\frac{\epsilon}{2} \|\nabla m_3\|_{L^2(\Omega)}^2 + \frac{1}{2\epsilon} \|1 - m_3^2\|_{L^1(\Omega)} \right) \\ &\geq \frac{\epsilon}{2} \|\nabla m_3\|_{L^2(\Omega)}^2 + (|\ln \epsilon| - 1) \|\nabla m_3\|_\Omega. \end{aligned} \tag{29}$$

By an application of Lemma 2.5 and for $\epsilon < \epsilon_0$ sufficiently small we hence get

$$\begin{aligned} E_\epsilon[M] + c\gamma_0|\partial\Omega| &\geq F_\epsilon[m] - \frac{\epsilon}{|\ln \epsilon|} \|\nabla m\|_{L^2(\Omega)}^2 \\ &\stackrel{(29)}{\geq} \left(\frac{\epsilon}{2} - \frac{\epsilon}{|\ln \epsilon|}\right) \|\nabla m_3\|_{L^2(\Omega)}^2 + (|\ln \epsilon| - 1) \|\nabla m_3\|_\Omega - N[m] \end{aligned} \quad (30)$$

with $\gamma_0 = 1$ if $M \neq \bar{M}$ and $\gamma_0 = 0$ else. We then apply Lemma 3.1 with

$$r := \frac{1}{\pi} \left(\frac{\epsilon}{2} - \frac{\epsilon}{|\ln \epsilon|} \right), \quad R := \max \{r, \delta\}.$$

which yields

$$N[m] \leq \left(\frac{\epsilon}{2} - \frac{\epsilon}{|\ln \epsilon|}\right) \|\nabla m_3\|_{L^2(\Omega)}^2 + \left(|\ln \epsilon| - \ln \left(\frac{\pi}{2\delta} \left(1 - \frac{2}{|\ln \epsilon|}\right)\right)\right) \|\nabla m_3\|_\Omega. \quad (31)$$

By inserting (31) into (30) we obtain the estimate

$$\min \left\{ E_\epsilon[M] + \gamma_0 c |\partial\Omega|, F_\epsilon[m] \right\} = \ln \left(\frac{\pi}{2\delta e} \left(1 - \frac{2}{|\ln \epsilon|}\right) \right) \|\nabla m_3\|_\Omega > 0.$$

which yields both assertions (i) and (ii). \square

We next give the proof for a general lower bound for the energy which is relevant for larger sets and some corresponding estimates for low energy states:

Proposition 3.3 (Lower bound). *Let $\Omega \Subset \mathbb{R}^2$ be convex and let $\epsilon \in (0, \frac{1}{4})$. Then*

$$\min \left\{ \inf_{M \in \mathcal{A}} E_\epsilon[M] + c|\partial\Omega|, \inf_{m \in \bar{\mathcal{A}}} F_\epsilon[m] \right\} \geq -\frac{\pi^2 e}{4} |\Omega|. \quad (32)$$

Furthermore, there is $C > 0$ such that

$$\begin{aligned} \left| \ln \left(\frac{4 \|\nabla \bar{M}_3\|_{\Omega_1}}{\pi^2 e^2 |\Omega|} \right) \right| \|\nabla \bar{M}_3\|_{\Omega_1} &\leq E_\epsilon[M] + \frac{\pi^2 e}{4} |\Omega| + c|\partial\Omega|, \\ \left| \ln \left(\frac{4 \|\nabla m_3\|_{\Omega_1}}{\pi^2 e^2 |\Omega|} \right) \right| \|\nabla m_3\|_{\Omega_1} &\leq F_\epsilon[m] + \frac{\pi^2 e}{4} |\Omega|. \end{aligned} \quad (33)$$

If the configuration $M \in \mathcal{A}$ satisfies for some $\alpha > 0$

$$E_\epsilon[M] \leq -\alpha |\Omega|,$$

then for constants C_α, c_α depending on α (with Notation (23)) we have

$$(i) \quad c_\alpha |\Omega| \leq \|\nabla \bar{M}\|_{\Omega_1} \leq C_\alpha |\Omega|,$$

$$(ii) \quad 0 \leq \left(\frac{\epsilon}{2} \|\nabla \bar{M}\|_{L^2(\Omega_1)}^2 + \frac{1}{2\epsilon} \|1 - \bar{M}_3\|_{L^1(\Omega_1)}^2 \right) - \|\nabla \bar{M}\|_{\Omega_1} \leq \frac{C_\alpha}{|\ln \epsilon|} |\Omega|,$$

$$(iii) \quad c_\alpha |\Omega| |\ln \epsilon| \leq L_\epsilon[\bar{M}], N[\bar{M}] \leq C_\alpha |\Omega| |\ln \epsilon|.$$

$$(iv) \quad \|\partial_3 M_3\|_{L^2(\Omega_1)}^2 \leq \frac{\epsilon}{|\ln \epsilon|^3} (E_\epsilon[\bar{M}] + C).$$

If $m \in \bar{\mathcal{A}}$ satisfies $F_\epsilon[m] \leq -\alpha|\Omega|$, then (i)–(iii) hold with \bar{M} replaced by m .

Proof. We write $m = \bar{M}(x, \frac{1}{2})$.

Proof of (32) and (33): As in the proof of Lemma 3.2 for $\epsilon < \epsilon_0$ sufficiently small and in view of $F_\epsilon = L_\epsilon - N$ we have (30)–(29), i.e.

$$\begin{aligned} E_\epsilon[M] + c|\partial\Omega| &\geq F_\epsilon[m] - \frac{\epsilon}{|\ln \epsilon|} \|\nabla m\|_{L^2(\Omega)}^2 \\ &\stackrel{(29)}{\geq} \left(1 - \frac{2}{|\ln \epsilon|}\right) \frac{\epsilon}{2} \|\nabla m\|_{L^2(\Omega)}^2 + (|\ln \epsilon| - 1) \|\nabla m\|_\Omega - N[m]. \end{aligned} \quad (34)$$

Applying Lemma 3.1 with $f = m_3$ and with the choice

$$r := \frac{\epsilon}{2\pi} \left(1 - \frac{2}{|\ln \epsilon|}\right), \quad R := \frac{\pi|\Omega|}{\|\nabla m\|_\Omega}$$

we get (also using that $\ln y + 1 = \ln(ey)$)

$$\begin{aligned} N[m] &\leq \left(1 - \frac{2}{|\ln \epsilon|}\right) \frac{\epsilon}{2} \|\nabla m\|_{L^2(\Omega)}^2 + \left(\ln \frac{2\pi R}{\epsilon(1 - \frac{2\epsilon}{|\ln \epsilon|})}\right) \|\nabla m\|_\Omega + \frac{\pi|\Omega|}{R} \\ &= \left(1 - \frac{2}{|\ln \epsilon|}\right) \frac{\epsilon}{2} \|\nabla m\|_{L^2(\Omega)}^2 + \left(|\ln \epsilon| + \ln \frac{2e\pi^2|\Omega|}{1 - \frac{2\epsilon}{|\ln \epsilon|}}\right) \|\nabla m\|_\Omega. \end{aligned} \quad (35)$$

Inserting (35) into (34) (again using that $\ln y + 1 = \ln(ey)$) we arrive at

$$\min \{E_\epsilon[M] + c|\partial\Omega|, F_\epsilon[m]\} \geq -\ln \left(\frac{\pi^2 e^2 |\Omega|}{4 \|\nabla m\|_\Omega} \right) \|\nabla m\|_\Omega. \quad (36)$$

As we do not know the value of $\|\nabla m\|_\Omega$, we minimize the right hand side of (36) over all values $X := \|\nabla m\|_\Omega \geq 0$: This yields the lower bound $-\frac{\pi^2 e}{4} |\Omega|$ and hence (32). Estimate (33) then follows from (36) as well.

Proof of (i)–(iv): Estimate (i) follows from (33). In the estimate (34) we have neglected the nonnegative term

$$(|\ln \epsilon| - 1) \left(\int_{\Omega} \frac{\epsilon}{2} |\nabla m_3|^2 + \frac{1}{2\epsilon} (1 - m_3^2) dx - \int_{\Omega} |\nabla m_3| dx \right).$$

Keeping this term yields additionally the estimate (ii). Estimate (iii) follows from (i) and (ii) and the definition (23) \square

The proof of the compactness statement in Theorem 1.2(iii) is a straightforward consequence of the BV–bound of Lemma 3.3:

Proposition 3.4 (Compactness). *Let $\Omega \subset \mathbb{R}^2$ be convex.*

(i) *For any sequence $m_\epsilon \in \overline{\mathcal{A}}$ with $\limsup_{\epsilon \rightarrow 0} F_\epsilon[m_\epsilon] < \infty$ there is $m \in BV(\Omega, \pm e_1)$ with $|m| = \chi_\Omega$ and a subsequence with $m_\epsilon \rightarrow m$ in $L^1(\Omega)$ for $\epsilon \rightarrow 0$.*

(ii) *The assertion of Theorem 1.2(iii) holds.*

Proof. By Lemma 3.3(i) we have $\|\nabla m_{3,\epsilon}\|_{\Omega} \leq C$. This shows that $m_{3,\epsilon} \rightarrow m_3$ in $L^1(\mathbb{R}^2)$ for some $m_{3,\epsilon} \in L^1(\mathbb{R}^2)$ and for a subsequence by the compact embedding of $BV(\Omega)$ into $L^1(\Omega)$. From Proposition 3.3(iii) we also get

$$\int_{\Omega} m_{1,\epsilon}^2 + m_{2,\epsilon}^2 dx = \int_{\Omega} (1 - m_{3,\epsilon}^2) dx \leq \epsilon L_\epsilon[m_\epsilon] \leq C\epsilon |\ln \epsilon| \rightarrow 0.$$

Altogether this implies the assertion (i). Similarly, the corresponding compactness holds for \overline{M} which again follows from Proposition 3.3. This shows (ii). \square

4 Proof of upper bound

We recall the family of asymptotically one–dimensional profiles from [27]:

Lemma 4.1 ([27, Lem. 4.2]). *For $0 < \epsilon < 1$, let $\xi_\epsilon \in C^1(\mathbb{R})$ be given by*

$$\xi_\epsilon(\rho) := \sin \left(\frac{\pi \arcsin(\tanh(\rho/\epsilon))}{2 \arcsin(\tanh(\epsilon^{-1/2}))} \right) \quad |\rho| < \epsilon^{1/2}$$

and $\xi_\epsilon(\rho) = \text{sign}(\rho)$ for $|\rho| \geq \epsilon^{1/2}$. Then for universal $C, c_1, a > 0$, we have

$$(i) \quad \frac{1}{2} \int_{\mathbb{R}} \left(\frac{\epsilon |\xi'_\epsilon|^2}{1 - \xi_\epsilon^2} + \frac{1 - \xi_\epsilon^2}{\epsilon} \right) d\rho \leq 2 + C e^{-a\epsilon^{-1/2}},$$

$$\begin{aligned}
(ii) \quad & \frac{1}{4} \int_{-H}^H \int_{-H}^H \frac{|\xi_\epsilon(\rho) - \xi_\epsilon(\rho')|^2}{|\rho - \rho'|^2} d\rho d\rho' \geq 2 \ln \left(\frac{c_1 H}{\epsilon} \right) \quad \text{for } H \geq 2\epsilon, \\
(iii) \quad & \frac{1}{4} \int_{-H}^H \int_{-H}^H \frac{|\xi_\epsilon(\rho) - \xi_\epsilon(\rho')|^2}{|\rho - \rho'|} d\rho d\rho' \leq CH, \\
(iv) \quad & \frac{1}{4} \int_{-H}^H \int_{-H}^H |\xi_\epsilon(\rho) - \xi_\epsilon(\rho')|^2 d\rho d\rho' \leq CH^2.
\end{aligned}$$

Proof. (i) and (ii) follow from [27, Lem. 4.2] with the special choice of a transition layer with support of size $2\epsilon^{\frac{1}{2}}$. (iii) and (iv) are straightforward estimates. \square

For the special case $\lambda = 0$, the Γ -convergence and in particular the construction of a recovery sequence is a classical result, relying on the optimal one-dimensional transition profiles to smooth out the jump discontinuity in the limit configuration [3]. As it turns out, this construction also works for $\lambda > 0$, where $F_{\epsilon, \lambda}$ is nonlocal. We will use a similar construction based on the nearly optimal profile ξ_ϵ from Lemma 4.1. As the calculations for the local part of the energy are well-known, our focus is on the contribution of the homogeneous $H^{1/2}$ -norm. We define the finite range version of the energy F_ϵ by

$$F_{\epsilon, R}[m] = |\ln \epsilon| \int_{\Omega} \frac{\epsilon}{2} |\nabla m|^2 + \frac{1}{2\epsilon} (1 - m_3^2) dx - \frac{1}{8} \iint_{\mathbb{R}^2, |x-y| \leq R} \frac{|m_3(x) - m_3(x')|^2}{|x - x'|^3} dx dx' \quad (37)$$

noting that for all $m \in \overline{\mathcal{A}}$ we have

$$F_\epsilon[m] \leq F_{\epsilon, R}[m].$$

We next give an upper bound construction related to circular domains:

Lemma 4.2 (Upper bound construction for disk). *Suppose that $B_{2R} \subset \Omega \subset \mathbb{R}^2$ for some $R > 0$. There is a universal constant $R_0 > 0$ such that if $R > R_0$ then there are sequences $m_\epsilon \in \overline{\mathcal{A}}$ such that*

$$m_\epsilon = -e_3 \quad \text{in } B_{R-\epsilon^{1/2}} \quad \text{and} \quad m_\epsilon = -e_3 \quad \text{in } \Omega \setminus B_{R+\epsilon^{1/2}} \quad (38)$$

and for $\epsilon > 0$ sufficiently small we have

$$F_{\epsilon, R}[m_\epsilon] \leq -C. \quad (39)$$

Proof. We proceed similarly as in the construction of [27, Lem. 4.3], however with a slightly more careful estimate since we need to capture the sign of the leading order term of the energy. We write $d(x) := R - |x|$ for the signed distance function for ∂B_R . For $x \in \mathcal{S}_\epsilon := B_{R+\epsilon^{1/2}} \setminus B_{R-\epsilon^{1/2}}$ we set

$$m_\epsilon(x) := \xi_\epsilon(d(x))e_3 + \sqrt{1 - \xi_\epsilon^2(d(x))} \frac{x^\perp}{|x|},$$

where ξ_ϵ is given in Lemma 4.1. We also set $m_\epsilon = e_3$ in $B_{R-\epsilon^{1/2}}$ and $m_\epsilon = -e_3$ in $\Omega \setminus B_{R+\epsilon^{1/2}}$. Then $m_\epsilon \in \overline{\mathcal{A}}$ and satisfies (38).

It remains to show (39): We use the coarea formula to integrate on the level sets of d . By Lemma 4.1 we then get

$$\begin{aligned} L_\epsilon[m_\epsilon] &:= |\ln \epsilon| \int_\Omega \left(\frac{\epsilon}{2} |\nabla m_\epsilon|^2 + \frac{1}{2\epsilon} (1 - m_{\epsilon,3}^2) \right) dx \\ &= |\ln \epsilon| \int_{-\epsilon^{1/2}}^{\epsilon^{1/2}} \left(\frac{\epsilon |\xi'_\epsilon(\rho)|^2}{2(1 - \xi_\epsilon^2(\rho))} + \frac{1}{2\epsilon} (1 - \xi_\epsilon^2(\rho)) \right) 2\pi(R + \rho) d\rho \\ &\stackrel{(i)}{=} 2|\partial B_R| |\ln \epsilon| + \mathcal{O}(\epsilon^{1/2}). \end{aligned} \quad (40)$$

For $\ell < \pi R$ and $H < R$ to be chosen later, let $Q := (-\ell, \ell) \times (-H, H)$. We define the diffeomorphism $\Phi : Q \rightarrow \Phi(Q)$ by $\Phi(s, \rho) = (R + \rho)\nu(s)$ with $\nu(s) := (\cos \frac{s}{2\pi R}, \sin \frac{s}{2\pi R})$, i.e. s is the geodesic distance on ∂U from e_1 and ρ is the distance to ∂U . By rotational symmetry

$$\begin{aligned} N[m] &:= \frac{1}{4} \int_{\mathbb{R}^2} \int_{\mathbb{R}^2} \frac{|m_{\epsilon,3}(x) - m_{\epsilon,3}(y)|^2}{|x - y|^3} dx dy \\ &\geq \frac{|\partial U|}{4} \iint_{(-H, H)^2} \left(\int_{-\ell}^{\ell} \frac{1}{|\Phi(\rho, 0) - \Phi(\rho', s)|^3} ds \right) |\xi_\epsilon(\rho') - \xi_\epsilon(\rho)|^2 \left(1 + \frac{\rho'}{R}\right) d\rho d\rho'. \end{aligned} \quad (41)$$

We consider $X := |(\sigma, \rho - \rho')|$ and $Y := |\Phi(0, \rho) - \Phi(\sigma, \rho')|$. We have $\partial_s \Phi(s, \rho) = (1 + \frac{\rho}{R})\tau(s)$ and $\partial_\rho \Phi(s, \rho) = \nu(s)$. Since $D\Phi(0, 0) = \text{Id}$ and $\|D^2\Phi\|_{L^\infty(Q)} \leq \frac{2}{R}$ for $|\rho| < R$, by Taylor expansion we have $|X - Y| \leq \frac{X^2}{R}$. We also have $|X - Y| \leq \frac{1}{2}X$ and hence $Y \sim X$ for $X \leq \frac{R}{2}$. Therefore, for $X \in Q$ we have

$$\int_{-\ell}^{\ell} \left| \frac{1}{X^3} - \frac{1}{Y^3} \right| d\sigma = \int_{-\ell}^{\ell} \left| \frac{(X - Y)(X^2 + Y^2)}{X^3 Y^3} \right| d\sigma \leq \int_{-\ell}^{\ell} \frac{C}{R X^2} d\sigma \leq \frac{C}{R|\rho - \rho'|}$$

where we have used the integral identity

$$\int_{-\ell}^{\ell} \frac{1}{s^2 + (\rho - \rho')^2} ds = \frac{2}{\rho - \rho'} \arctan \left(\frac{\ell}{\rho - \rho'} \right) \leq \frac{\pi}{|\rho - \rho'|}.$$

The second estimate follows since $\|\arctan\|_{L^\infty} \leq \frac{\pi}{2}$. By standard integration and using Taylor's formula we also have

$$\int_{-\ell}^{\ell} \frac{1}{(s^2 + (\rho - \rho')^2)^{3/2}} ds = \frac{2}{(\rho - \rho')^2} \left(1 + \frac{(\rho - \rho')^2}{\ell^2}\right)^{-\frac{1}{2}} \geq \frac{2}{(\rho - \rho')^2} - \frac{1}{\ell^2},$$

We use the above calculations to estimate the inner integral in (41), noting that the integrand is pointwise nonnegative everywhere. We arrive at

$$\begin{aligned} N[m_\epsilon] &\geq \frac{|\partial U|}{4} \iint_{(-H,H)^2} \left(\frac{2}{|\rho - \rho'|^2} - \frac{C}{R|\rho - \rho'|} - \frac{1}{\ell^2} \right) |\xi_\epsilon(\rho') - \xi_\epsilon(\rho)|^2 \left(1 + \frac{\rho'}{R}\right) d\rho d\rho' \\ &= \frac{|\partial U|}{4} \iint_{(-H,H)^2} \left(\frac{2}{|\rho - \rho'|^2} - \frac{C}{R|\rho - \rho'|} - \frac{1}{\ell^2} \right) |\xi_\epsilon(\rho') - \xi_\epsilon(\rho)|^2 d\rho d\rho', \end{aligned}$$

where the identity in the second line above follows from symmetry. An application of the last three estimates in Lemma 4.1 then yields

$$N[m_\epsilon] \geq 2|\partial U| |\ln \epsilon| + 2|\partial U| \left(\ln \frac{c_1 H}{2} - \frac{CH}{R} - \frac{CH^2}{\ell^2} \right) =: 2|\partial U| |\ln \epsilon| + C_1. \quad (42)$$

For R sufficiently large we can hence find H and ℓ with $1 \ll H \ll \ell \ll R$ such that C_1 is positive. Adding equations (40) and (42) yields the asserted inequality. In particular, since $H \leq R$ the bound holds for the finite range energy $F_{\epsilon,R}$. \square

Proposition 4.3 (Upper bound). *Let $\Omega \Subset \mathbb{R}^2$ and let $\Omega_R := \{x \in \Omega : \text{dist}(\tilde{\Omega}, \Omega^c) \geq R\}$ for $R > 0$. Then there is $R > 0$ such that the following holds. There are sequences $m_\epsilon \in \overline{\mathcal{A}}$ and $M_\epsilon(x) := m_\epsilon \otimes \chi_{[0,t]} \in \mathcal{A}$ such that*

$$\max \left\{ \limsup_{\epsilon \rightarrow 0} E_\epsilon[M_\epsilon], \limsup_{\epsilon \rightarrow 0} F_\epsilon[m_\epsilon] \right\} \leq -C|\Omega_R|.$$

Proof. Step 1: In this step we give the proof for the energy F_ϵ . Let R_0 be the constant from Lemma 4.2 and let $R := 10R_0$. Then the family of balls $\mathcal{U} = \{B_R(x) : x \in \Omega\}$ is an open covering of $\Omega^{(R)}$. Since Ω is compact and by Vitali's covering theorem there is a finite subcovering $\{B_i(x_i) : i = 1, \dots, N\}$ such that the balls $\tilde{B}_i := B_i(\frac{x_i}{5})$ are pairwise disjoint. Let $\widehat{B}_i := B_i(\frac{x_i}{10})$. By construction we have $\sum_{i=1}^N |\tilde{B}_i| \sim |\Omega^{(R)}|$. For $x \in \widehat{B}_i$ we define $m_\epsilon := m_\epsilon^{(i)} : B_i \rightarrow \mathbb{S}^1$ as in Lemma 4.2. For $x \notin \bigcup_i \widehat{B}_i$ we define $m_\epsilon := e_3$.

We next apply Lemma 4.2. Since, the domain constructions on the single balls have distance $\geq 2R$ we do not need to take the interaction energy between the balls for

the finite range energy $F_{\epsilon,R}$ into account, cf. (37). We hence get

$$F_{\epsilon}[m_{\epsilon}] \leq \sum_{i=1}^N F_{\epsilon}[m_{\epsilon}^{(i)}] \leq - \sum_{i=1}^N C|\tilde{B}_i| \leq -C|\Omega^{(R)}|$$

which is (i). In order to show (ii) we apply Theorem 2.2 and Theorem 2.3. For this we note that the error term in Theorem 2.2 vanishes since $M_{\epsilon} = \overline{M_{\epsilon}}$. We also note that by construction we have $\operatorname{div}' M'_{\epsilon} = 0$. With analogous calculations as in the proof of Proposition 3.3 we hence get

$$\begin{aligned} E_{\epsilon}[M_{\epsilon}] &= F_{\epsilon}[m_{\epsilon}] + \frac{1}{2} \iint_{\Omega \times \Omega} \frac{1 - \Gamma(\frac{1}{\omega}|x - x'|)}{|x - x'|^3} |m_3(x) - m_3(x')|^2 dx dx' \\ &\quad + \iint_{\Omega^c \times \Omega} \frac{\Gamma(\frac{1}{\omega}|x - x'|)}{|x - x'|^3} (1 - m_3(x)^2) dx dx' \\ &=: F_{\epsilon}[m_{\epsilon}] + I_{\epsilon} + J_{\epsilon}. \end{aligned}$$

Since $\omega \rightarrow 0$ as $\epsilon \rightarrow 0$ we have $1 - \Gamma(\frac{1}{\omega}|x - x'|) \rightarrow 0$ in $\Omega \times \Omega$ pointwise. Since $\|1 - \Gamma\|_{L^{\infty}} \leq 1$ by dominated convergence we have $I_{\epsilon} \rightarrow 0$ as $\epsilon \rightarrow 0$. Finally, in our construction we have $m_{3,\epsilon} = 1$ in $\Omega \setminus \Omega^{(R)}$. Since $\|\Gamma\|_{L^{\infty}} \leq 1$ and $\|m_3\|_{L^{\infty}} \leq 1$ we get

$$\begin{aligned} J_{\epsilon} &\leq C_R \int_{\Omega^{(R)}} |1 - m_3(x)^2| dx \leq C_R |\Omega|^{\frac{1}{2}} \left(\int_{\Omega^{(R)}} |1 - m_3|^2 dx \right)^{\frac{1}{2}} \\ &\leq \epsilon C_R |\Omega|^{\frac{1}{2}} \left(\int_{\Omega^{(R)}} |1 - m_3|^2 dx \right)^{\frac{1}{2}}. \end{aligned}$$

□

Acknowledgements. The authors gratefully acknowledge support from the DFG under Grant No. #392124319 and under Germany's Excellence Strategy EXC-2181/1 – 390900948.

Data availability statement All data generated or analysed during this study are included in the main article file

References

- [1] E. Acerbi, N. Fusco, and M. Morini. Minimality via second variation for a nonlocal isoperimetric problem. *Comm. Math. Phys.*, 322(2):515–557, 2013.

- [2] G. Alberti, R. Choksi, and F. Otto. Uniform energy distribution for an isoperimetric problem with long-range interactions. *J. Amer. Math. Soc.*, 22(2):569–605, 2009.
- [3] G. Anzellotti, S. Baldo, and A. Visintin. Asymptotic behavior of the Landau-Lifshitz model of ferromagnetism. *Appl. Math. Optim.*, 23:171–192, 1991.
- [4] J. Bourgain, H. Brezis, and P. Mironescu. Another look at Sobolev spaces. In *Optimal control and part. diff. eq.*, pages 439–455. IOS, Amsterdam, 2001.
- [5] W. Brown. *Interscience Tracts of Physics and Astronomy*, volume 18. Interscience Publishers, 1963.
- [6] G. Carbou. Thin layers in micromagnetism. *Math. Models Methods Appl. Sci.*, 11:1529–1546, 2001.
- [7] A. Cesaroni and M. Novaga. Second-order asymptotics of the fractional perimeter as $s \rightarrow 1$. *Math. Eng.*, 2(3):512–526, 2020.
- [8] R. Choksi and R. Kohn. Bounds on the micromagnetic energy of a uniaxial ferromagnet. *Commun. Pure Appl. Math.*, 51:259–289, 1998.
- [9] R. Choksi, R. Kohn, and F. Otto. Domain branching in uniaxial ferromagnets: A scaling law for the minimum energy. *Commun. Math. Phys.*, 201:61–79, 1999.
- [10] R. Choksi and M. Peletier. Small volume fraction limit of the diblock copolymer problem: I. Sharp-interface functional. *SIAM J. Math. Anal.*, 42(3):1334–1370, 2010.
- [11] R. Choksi and M. Peletier. Small volume-fraction limit of the diblock copolymer problem: II. Diffuse-interface functional. *SIAM J. Math. Anal.*, 43(2):739–763, 2011.
- [12] M. Cicalese and E. Spadaro. Droplet minimizers of an isoperimetric problem with long-range interactions. *Comm. Pure Appl. Math.*, 66(8):1298–1333, 2013.
- [13] N. Condatte. *Pattern formation in magnetic thin films : analysis and numerics*. PhD thesis, Humboldt-Universität Berlin, 2010.
- [14] S. Conti. Branched microstructures: scaling and asymptotic self-similarity. *Commun. Pure Appl. Math.*, 53:1448–1474, 2000.
- [15] J. Dávila. On an open question about functions of bounded variation. *Calc. Var. Partial Differential Equations*, 15(4):519–527, 2002.
- [16] A. DeSimone, R. Kohn, S. Müller, and F. Otto. A reduced theory for thin-film micromagnetics. *Commun. Pure Appl. Math.*, 55:1408–1460, 2002.
- [17] A. DeSimone, R. Kohn, S. Müller, and F. Otto. *The Science of Hysteresis, Recent analytical developments in micromagnetics*. Academic Press, Oxford, 2006.

- [18] M. Yamanouchi et al. Domain structure in CoFeB thin films with perpendicular magnetic anisotropy. *IEEE Magn. Lett.*, 2:3000304, 2011.
- [19] C. Garcia-Cervera. *Magnetic domains and magnetic domain walls*. PhD thesis, New York University, 1999.
- [20] D. Goldman, C. Muratov, and S. Serfaty. The Γ -limit of the two-dimensional Ohta-Kawasaki energy. I. Droplet density. *Arch. Ration. Mech. Anal.*, 210(2):581–613, 2013.
- [21] A. Hubert and R. Schäfer. *Magnetic domains: the analysis of magnetic microstructures*. Springer Science & Business Media, 2008.
- [22] Vesa Julin and Giovanni Pisante. Minimality via second variation for microphase separation of diblock copolymer melts. *J. Reine Angew. Math.*, 729:81–117, 2017.
- [23] B. Kaplan and G.A. Gehring. The domain structure in ultrathin magnetic films. *J. Magn. Magn. Mater.*, 128:111–116, 1993.
- [24] C. Kittel. Theory of the structure of ferromagnetic domains in films and small particles. *Phys. Rev.*, 70:965–971, 1946.
- [25] H. Knüpfer and C. B. Muratov. Domain structure of bulk ferromagnetic crystals in applied fields near saturation. *J. Nonlinear Sci.*, 21:921–962, 2011.
- [26] H. Knüpfer and W. Shi. A second order expansion for the nonlocal perimeter functional. *submitted*, 2022.
- [27] H. Knüpfer, C. Muratov, and F. Nolte. Magnetic domains in thin ferromagnetic films with strong perpendicular anisotropy. *Arch. Rational Mech. Anal.*, 2018.
- [28] R. Kohn and V. Slastikov. Another thin-film limit of Micromagnetics. *Arch. Ration. Mech. Anal.*, 178:227–245, 2005.
- [29] M. et al. Kronseder. Real-time observation of domain fluctuations in a two-dimensional magnetic model system. *Nature Communications*, 6, APR 2015.
- [30] L. Landau and E. Lifshitz. On the theory of the dispersion of magnetic permeability in ferromagnetic bodies. *Phys. Z. Sowjetunion*, 8(153):101–114, 1935.
- [31] Ivan Lemesh, Felix Buttner, and Geoffrey S. D. Beach. Accurate model of the stripe domain phase of perpendicularly magnetized multilayers. *Phys. Rev. B*, 95(17), MAY 17 2017.
- [32] T. N. G. Meier, M. Kronseder, and C. H. Back. Domain-width model for perpendicularly magnetized systems with dmi. *Phys. Rev. B*, 96(14), OCT 6 2017.

- [33] KW. et al Moon. Universal method for magnetic skyrmion bubble generation by controlling the stripe domain instability. *NPG Asia Materials*, 13(1), MAR 12 2021.
- [34] M. Morini and P. Sternberg. Cascade of minimizers for a nonlocal isoperimetric problem in thin domains. *SIAM J. Math. Anal.*, 46(3):2033–2051, 2014.
- [35] C. Muratov and T. Simon. A nonlocal isoperimetric problem with dipolar repulsion. *Comm. Math. Phys.*, 372(3):1059–1115, 2019.
- [36] F. Otto and T. Viehmann. Domain branching in uniaxial ferromagnets: asymptotic behavior of the energy. *Calc. Var. Part. Diff. Eq.*, 38:135–181, 2010.
- [37] A. et al. Wadas. Thickness-dependent magnetic domain structures of ultrathin co/au films studied by means of magnetic force microscopy in ultrahigh vacuum. *Appl. Phys. A-Mat. Sc. & Proc.*, 66(4):465–467, APR 1998.
- [38] Ran Wang, Ya-Xuan Shang, Rui Wu, Jin-Bo Yang, and Yang Ji. Evolution of magnetic domain structure in a YIG thin film. *Chinese Physics Letters*, 33(4):047502, apr 2016.
- [39] Daniel Zwillinger. *CRC standard mathematical tables and formulae*. CRC Press, Boca Raton, FL, second edition, 2012.